



**SLOVENSKI STANDARD**  
**oSIST prEN 16482:2022**  
**01-julij-2022**

---

**Livarstvo - Palice iz litega železa**

Founding - Continuous cast iron bars

Gießereiwesen - Gusseisen-Strangguss

Fonderie - Barres de fonte par coulée continue

**Ta slovenski standard je istoveten z: prEN 16482**

<https://standards.iteh.ai/catalog/standards/sist/24d27045-2785-4b4d-a3dc-4df3a172b3c7/osist-pren-16482-2022>

**ICS:**

77.140.80      Železni in jekleni ulitki      Iron and steel castings

**oSIST prEN 16482:2022**

**en,fr,de**



EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**DRAFT**  
**prEN 16482**

May 2022

ICS 77.080.10

Will supersede EN 16482:2014

English Version

## Founding - Continuous cast iron bars

Fonderie - Barres de fonte par coulée continue

Gießereiwesen - Gusseisen-Strangguss

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 190.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

**Warning** : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

<b>Contents</b>	<b>Page</b>
European foreword.....	3
Introduction .....	4
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions .....	6
4 Designation.....	6
5 Order information .....	7
6 Manufacture .....	7
7 Requirements.....	7
7.1 Characterizing properties.....	7
7.2 Tensile properties.....	7
7.3 Hardness properties .....	10
7.4 Impact energy.....	11
7.5 Graphite structure .....	12
7.6 Matrix structure.....	12
7.7 Straightness.....	12
7.8 Ultrasonic Testing.....	13
8 Sampling.....	13
8.1 General.....	13
8.2 Samples cut from a bar.....	13
9 Test methods .....	13
9.1 Tensile test .....	13
9.2 Hardness test.....	16
9.3 Graphite and matrix structure examination.....	16
9.4 Measurement of straightness .....	16
10 Retests.....	17
10.1 Need for retests.....	17
10.2 Test validity.....	17
10.3 Non-conforming test results .....	17
10.4 Heat treatment of samples and bars .....	17
11 Inspection documentation.....	17
Annex A (informative) Guidance values for hardness of spheroidal graphite cast iron bars .....	18
Annex B (informative) Dimensional allowances for continuous cast bars .....	19
Annex C (normative) Location of samples cut from a bar .....	21
Annex D (informative) Additional information on mechanical and physical properties of spheroidal graphite cast irons .....	22
Bibliography.....	25

## European foreword

This document (prEN 16482:2022) has been prepared by Technical Committee CEN/TC 190 “Foundry technology”, the secretariat of which is held by DIN.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 16482:2014.

The following modifications were implemented in this new version:

- new normative references;
- new reference to ASTM A536-84 (2009) Standard Specification for Ductile Iron Castings in the text and Bibliography;
- modification of Table 2 “Tensile properties of continuous cast spheroidal graphite cast iron bars”, where 2 Grades were modified to fulfill requirements also of ASTM A536-84 (2009): EN-GJS-400-18C;
- new Table 4 “Minimum impact energy values measured on V-notched test pieces machined from cast samples for ferritic grades of the ferritic to pearlitic group” in 7.4 (imported from EN 1563:2019);
- new Table 5 “Straightness of continuous cast bars” in 7.7;
- new subclause 7.8 “Ultrasonic Testing”;
- new Figure 1 “Dimensions of grey cast iron tensile test pieces”;
- new Figure 2 “Dimensions of spheroidal graphite cast iron tensile test pieces”;
- modification of Table A.1 “Guidance values for Brinell hardness”;
- modification of Table B.2 “Machining allowances for continuous cast iron bars”;
- modification of Table D.2 “Examples of mechanical properties measured on continuous cast iron bars with a diameter of 160 mm”.

## Introduction

The European Standards EN 1561:2011 and EN 1563:2018 classify grey cast irons and spheroidal graphite cast irons respectively, which are cast in sand moulds or moulds of comparable thermal behaviour.

This document classifies grey cast iron and spheroidal graphite cast iron bars, which are produced by the continuous casting process.

Due to the high cooling rate during solidification and further cooling, both graphite and matrix structure differ from those obtained by sand casting and consequently the mechanical properties in relation to section thickness [8], [9].

The mechanical properties of continuous cast iron bars are evaluated on machined test pieces prepared from samples cut from the bars.

However, for many applications, tensile strength or hardness are not the only interesting or determining properties. Other mechanical or physical properties can be decisive for the use of grey cast iron or spheroidal graphite cast iron, for example: thermal capacity, thermal diffusivity, damping capacity, thermo-cycle fatigue and toughness.

Additional technical data for grey cast irons is given in EN 1561:2011 and for spheroidal graphite cast irons in EN 1563:2018 and Annex D of this document.

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

[oSIST prEN 16482:2022](https://standards.iteh.ai/catalog/standards/sist/24d27045-2785-4b4d-a3dc-4df3a172b3c7/osist-pren-16482-2022)

<https://standards.iteh.ai/catalog/standards/sist/24d27045-2785-4b4d-a3dc-4df3a172b3c7/osist-pren-16482-2022>

## 1 Scope

This document defines the grades of grey cast iron and spheroidal graphite cast iron bars, which have been produced by the continuous casting process.

This document specifies the characterizing properties of grey cast iron bars by either:

- a) the tensile strength measured on machined test pieces prepared from samples cut from the bars, or
- b) the hardness measured on the bars.

If agreed by the manufacturer and the purchaser, the combination of both tensile strength from option a) and hardness from option b) can be specified.

This document specifies the characterizing properties of spheroidal graphite cast iron bars by the tensile strength measured on machined test pieces prepared from samples cut from the bars.

This document specifies 4 grades of grey cast iron and 14 grades of spheroidal graphite cast iron by a classification based on tensile strength and 4 grades of grey cast iron by a classification based on Brinell hardness.

This document specifies also the straightness of the bars.

This document does not cover technical delivery conditions for iron castings (see EN 1559-1:2011 and EN 1559-3:2011).

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10204:2004, *Metallic products - Types of inspection documents*

EN ISO 945-1:2019, *Microstructure of cast irons - Part 1: Graphite classification by visual analysis (ISO 945-1:2019)*

EN ISO 6506-1:2014, *Metallic materials - Brinell hardness test - Part 1: Test method (ISO 6506-1:2014)*

EN ISO 6892-1:2019, *Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1:2019)*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

**3.1**  
**grey cast iron**  
cast material, mainly iron and carbon based, carbon being present mainly in the form of flake (lamellar) graphite particles

Note 1 to entry: Grey cast iron is also known as flake graphite cast iron, and less commonly as lamellar graphite cast iron.

[SOURCE: EN 1561:2011, 3.1, 3.2]

**3.2**  
**spheroidal graphite cast iron**  
cast material, iron, carbon and silicon based, the carbon being present mainly in the form of spheroidal graphite particles

Note 1 to entry: Spheroidal graphite cast iron is also known as ductile iron, and less commonly as nodular iron.

[SOURCE: EN 1563:2018, 3.1]

**3.3**  
**ferritic to pearlitic cast irons**  
grey cast iron and spheroidal graphite cast iron with a matrix containing ferrite or pearlite or a combination of both

**3.4**  
**solid-solution strengthened ferritic spheroidal graphite cast iron**  
spheroidal graphite cast iron with a matrix mainly consisting of ferrite, solution strengthened mainly by silicon

**3.5**  
**graphite spheroidizing treatment**  
operation that brings the liquid iron into contact with a substance to produce graphite in the predominantly spheroidal (nodular) form during solidification

Note 1 to entry: This operation is often followed by a second one called inoculation.

[SOURCE: EN 1563:2018, 3.4]

**3.6**  
**sample**  
quantity of material cut from the continuous cast bar to represent the cast material

### 4 Designation

The material shall be designated in accordance with Table 1, Table 2, or Table 3.

NOTE The designation system is specified in EN 1560:2011 [3].



## 5 Order information

The following information shall be stated in the order:

- a) the number of this document;
- b) the designation of the material;
- c) the dimensions of the bar;
- d) any special requirements.

All requirements shall be agreed by the time of acceptance of the order, e.g. technical delivery conditions according to EN 1559-1:2011 and EN 1559-3:2011.

## 6 Manufacture

The methods of producing grey cast iron and spheroidal graphite cast iron continuous cast bars and their chemical compositions shall be left to the discretion of the manufacturer who shall ensure that the requirements of this document are met for the material grade specified in the order.

For the cast irons to be used in special applications, the chemical composition and the heat treatment may be the subject of an agreement between the manufacturer and the purchaser.

All agreements between the manufacturer and the purchaser shall be made by the time of the acceptance of the order.

## 7 Requirements

### 7.1 Characterizing properties

The order shall specify in an unambiguous manner whether the tensile strength measured on a test piece machined from samples cut from the continuous cast bars or the Brinell hardness measured on the bars is the characterizing property. If it does not do so, then the manufacturer shall characterize the material according to tensile strength.

### 7.2 Tensile properties

#### 7.2.1 General

The property values apply to grey cast iron and spheroidal graphite cast iron bars produced by the continuous casting process.

Tensile properties are dependant of the bar diameter as shown in Table 1 and Table 2.

For rectangular bars, the corresponding diameter  $D$  for the determination of the minimum tensile properties shall be calculated with Formula (1):

$$D = \frac{2 \times (H \times B)}{(H + B)} \quad (1)$$

where

$D$  is the corresponding bar diameter, in millimetres (mm);

$H$  is the height of the bar, in millimetres (mm);

$B$  is the width of the bar, in millimetres (mm).

## prEN 16482:2022 (E)

NOTE Tensile testing requires sound test pieces in order to guarantee pure uni-axial stress during the test.

For bar diameters > 400 mm, the minimum tensile properties to be obtained shall be agreed between the manufacturer and the purchaser by the time of acceptance of the order.

### 7.2.2 Test pieces machined from samples cut from the bar

The tensile properties, when measured in accordance with 9.1 using test pieces machined from samples cut from the bar, shall be in accordance with the requirements of Table 1 for grey cast irons or Table 2 for spheroidal graphite cast irons.

**Table 1 — Tensile properties of continuous cast grey cast iron bars**

Material designation		Bar diameter	Tensile strength	Matrix structure
Symbol	Number	$D$ mm	$R_m$ MPa min.	(for information only)
EN-GJL-150C	5.1102	$20 < D \leq 50$	110	ferritic, annealed
		$50 < D \leq 100$	100	
		$100 < D \leq 200$	90	
		$200 < D \leq 400$	80	
EN-GJL-200C	5.1202	$20 < D \leq 50$	155	ferritic-pearlitic
		$50 < D \leq 100$	140	
		$100 < D \leq 200$	125	
		$200 < D \leq 400$	115	
EN-GJL-250C	5.1203	$20 < D \leq 50$	195	pearlitic-ferritic
		$50 < D \leq 100$	180	
		$100 < D \leq 200$	165	
		$200 < D \leq 400$	155	
EN-GJL-300C	5.1308	$20 < D \leq 50$	220	predominantly pearlitic
		$50 < D \leq 100$	205	
		$100 < D \leq 200$	195	
		$200 < D \leq 400$	185	

Table 2 — Tensile properties of continuous cast spheroidal graphite cast iron bars

Material designation		Bar diameter $D$ mm	0,2 % proof strength $R_{p0,2}$ MPa min.	Tensile strength $R_m$ MPa min.	Elongation after fracture $A$ % min.	Matrix structure
EN-GJS-350-22C-LT	5.3120	$20 < D \leq 60$	220	350	22	ferritic
		$60 < D \leq 120$	210	330	18	
		$120 < D \leq 400$	200	320	15	
EN-GJS-350-22C-RT	5.3121	$20 < D \leq 60$	220	350	22	ferritic
		$60 < D \leq 120$	220	330	18	
		$120 < D \leq 400$	210	320	15	
EN-GJS-350-22C	5.3122	$20 < D \leq 60$	220	350	22	ferritic
		$60 < D \leq 120$	220	330	18	
		$120 < D \leq 400$	210	320	15	
EN-GJS-400-18C-LT	5.3123	$20 < D \leq 60$	240	400	18	ferritic
		$60 < D \leq 120$	230	380	15	
		$120 < D \leq 400$	220	360	12	
EN-GJS-400-18C-RT	5.3124	$20 < D \leq 60$	250	400	18	ferritic
		$60 < D \leq 120$	250	390	15	
		$120 < D \leq 400$	20	370	12	
EN-GJS-400-18C <sup>c</sup>	5.3125	$20 < D \leq 60$	280	400	18	ferritic
		$60 < D \leq 120$	280	400	18	
		$120 < D \leq 400$	260	390	16	
EN-GJS-400-15C <sup>a</sup>	5.3126	$20 < D \leq 60$	280	400	15	ferritic
		$60 < D \leq 120$	260	400	15	
		$120 < D \leq 400$	250	390	13	
EN-GJS-450-12C <sup>a,c</sup>	5.3128	$20 < D \leq 60$	310	450	12	predominantly ferritic
		$60 < D \leq 120$	to be agreed upon between			
		$120 < D \leq 400$	the manufacturer and purchaser			
EN-GJS-500-14C <sup>b</sup>	5.3129	$20 < D \leq 60$	400	500	14	ferritic
		$60 < D \leq 120$	390	480	12	
		$120 < D \leq 400$	360	470	10	