



Designation: ~~D2196-05~~ Designation: D2196 – 10

## Standard Test Methods for Rheological Properties of Non-Newtonian Materials by Rotational (Brookfield type) Viscometer<sup>1</sup>

This standard is issued under the fixed designation D2196; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 These test methods cover the determination of the apparent viscosity and the shear thinning and thixotropic properties of non-Newtonian materials in the shear rate range from 0.1 to 50 s<sup>-1</sup>.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

E1 [Specification for ASTM Liquid-in-Glass Thermometers](#)

### 3. Summary of Test Method

3.1 Test Method A consists of determining the apparent viscosity of coatings and related materials by measuring the torque on a spindle rotating at a constant speed in the material.

3.2 Test Methods B and C consist of determining the shear thinning and thixotropic (time-dependent) rheological properties of the materials.<sup>3</sup> The viscosities of these materials are determined at a series of prescribed speeds of a rotational-type viscometer. The agitation of the material immediately preceding the viscosity measurements is carefully controlled.

### 4. Significance and Use

4.1 Test Method A is used for determining the apparent viscosity at a given rotational speed, although viscosities at two or more speeds give better characterization of a non-Newtonian material than does a single viscosity measurement.

4.2 With Test Methods B and C, the extent of shear thinning is indicated by the drop in viscosity with increasing viscometer speed. The degree of thixotropy is indicated by comparison of viscosities at increasing and decreasing viscometer speeds (Test Method B), viscosity recovery (Test Method B), or viscosities before and after high shear (combination of Test Methods B and C). The high-shear treatment in Test Method C approximates shearing during paint application. The viscosity behavior measured after high shear is indicative of the characteristics of the paint soon after application.

### 5. Apparatus

5.1 Rotational-type viscometers having at least four speeds, such as:

5.1.1 *Brookfield Dial-Reading (Analog) Viscometer*, or equivalent having multiple rotational speeds with set of spindles; or

5.1.2 *Brookfield Digital Viscometer*, or equivalent having multiple rotational speeds, with set of spindles.

5.2 *Thermometer*—ASTM thermometer having a range from 20 to 70°C and conforming to the requirements for Thermometer 49C as prescribed in Specification E1—. In addition, temperature measuring devices such as non-mercury liquid-in-glass thermometers, thermocouples, or platinum resistance thermometers that provide equivalent or better accuracy and precision, that cover the temperature range for thermometer 49C, may be used.

<sup>1</sup> These test methods are under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and are the direct responsibility of Subcommittee D01.24 on Physical Properties of Liquid Paints and Paint Materials.

Current edition approved July 1, 2005-2010. Published August 2005-July 2010. Originally approved in 1963. Last previous edition approved in 1999-2005 as ~~D2196-99~~-D2196 – 05. DOI: 10.1520/D2196-105.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Pierce, P. E., "Measurement of Rheology of Thixotropic Organic Coatings and Resins with the Brookfield Viscometer," *Journal of Paint Technology*, Vol 43, No. 557, 1971, pp. 35-43.

5.3 Containers, round 0.5-L (1-pt) can, 85 mm (3<sup>3</sup>/<sub>8</sub> in.) in diameter, or 1-L (1-qt) can, 100 mm (4 in.) in diameter.

5.4 ~~Shaker, Shaker~~, or equivalent machine capable of vigorously shaking the test specimen.

## 6. Materials

6.1 ~~Standard Oils, calibrated in absolute viscosity, millipascal seconds.~~ Standard Oils, calibrated in absolute viscosity, millipascal seconds.

## 7. Calibration of Apparatus

7.1 Select at least two standard oils of viscosities differing by at least 0.5 Pa·s (5P) within the viscosity range of the material being measured and in the range of the viscometer. Condition the oils as closely as possible to 25.0°C (or other agreed-upon temperature) for 1 h in a 0.5-L (1-pt) can, 85 mm (3<sup>3</sup>/<sub>8</sub> in.) in diameter. Measure the viscosities of each oil as described in Test Method B (Section 13) taking readings only at increasing speeds (13.4). Make certain that the spindle is centered in the container prior to taking measurements.

NOTE 1—The Brookfield LV and RV series viscometers are equipped with a spindle guard leg. The spindle/speed multiplying factors (Table 1) are designed for use with the guard leg in place except for the following conditions: RV series when the factors are the same with or without the guard leg for spindles No. 3 through 7; or LV series when the factors are the same with or without the guard leg for spindles No. 3 and 4.

7.1.1 Calibration in a 0.5-L (1-pt) can is always possible with the LV series viscometer with the guard leg attached. Calibration of the RV series viscometer in the 1-pt can must be done with spindles No. 3 through 7 without the guard leg. If the No. 1 or No. 2 spindles are to be used, calibration is carried out in the 1-L (1-qt) can with the guard leg attached.

7.2 Combining the tolerance of the viscometer ( $\pm 1\%$ , equal to the spindle/speed factor) and the tolerance of the temperature control (typically  $\pm 0.5^\circ\text{C}$  at  $25^\circ\text{C}$ ) it is reasonable to assume that a viscometer is calibrated if the calculated viscosities are within  $\pm 5\%$  of the stated values (see Table 2 for examples of the considerable change in viscosity with temperature exhibited by standard oils). If measurements are not made at  $25^\circ\text{C}$ , then the stated viscosities should be corrected to the temperature at which they are measured. If the viscosities determined in 7.1 differ from the stated values of the viscosity standard by more than  $5\%$ , calculate new factors for each spindle/speed combination as follows:

$$f = Vs \quad (1)$$

where:

$f$  = new factor for converting scale reading to viscosity, mPa·s (cP),

$V$  = viscosity of standard oil, mPa·s, and

$s$  = scale reading of the viscometer.

7.3 Prepare a table of new factors similar to that furnished with the viscometer (Table 1) for the spindle/speed combinations worked out in 7.2. Spindle/speed factors vary inversely with speed.

## 8. Preparation of Specimen

8.1 Fill a 1-pt or 1-qt can with sample to within 25 mm (1 in.) of the top with the sample and bring it as close as possible to

**TABLE 1 Factors for Converting Brookfield Dial Readings to Millipascal Seconds (Centipoises)**

NOTE 1—M = 1000.

Speed, rpm	RV Series Factors Spindles						
	1	2	3	4	5	6	7
0.5	200	800	2000	4000	8000	20M	80M
1	100	400	1000	2000	4000	10M	40M
2	50	200	500	1000	2000	5M	20M
2.5	40	160	400	800	1600	4M	16M
4	25	100	250	500	1000	2.5M	10M
5	20	80	200	400	800	2M	8M
10	10	40	100	200	400	1M	4M
20	5	20	50	100	200	500	2M
50	2	8	20	40	80	200	800
100	1	4	10	20	40	100	400
Speed, rpm	LV Series Factors Spindles						
	1	2	3	4			
0.3	200	1000	4000	20M			
0.6	100	500	2000	10M			
1.5	40	200	800	4M			
3.0	20	100	400	2M			
6	10	50	200	1M			
12	5	25	100	500			
30	2	10	40	200			
60	1	5	20	100			

**TABLE 2 Viscosity Variation of Cannon Viscosity Standards  
About the 25°C Temperature Point**

Cannon Viscosity Standard	Viscosity at 25°C, mPa·s (cP)	Viscosity Change With + 1°C at 25°C, mPa·s (cP)
S-600	1 400	87.7 (6.26 %)
S-2000	4 900	332 (6.77 %)
S-8000	20 000	1462.3 (7.31 %)

a temperature of 25°C or other agreed-upon temperature prior to test.

8.2 Vigorously shake the specimen on the shaker or equivalent for 10 min, remove it from the shaker, and allow it to stand undisturbed for 60 min at 25°C prior to testing (Note 2). Start the test no later than 65 min after removing the can from the shaker. Do not transfer the specimen from the container in which it was shaken.

NOTE 2—Shake time may be reduced if necessary, or as agreed upon between the purchaser and manufacturer, but, in any case, should not be less than 3 min.

## TEST METHOD A—APPARENT VISCOSITY

### 9. Procedure

9.1 Make all measurements as close as possible to 25°C, or other agreed-upon temperature.

9.2 Place the instrument on the adjustable stand. Lower the viscometer to a level that will immerse the spindle to the proper depth. Level the instrument using the attached spirit level.

9.3 Tilt the selected spindle (Note 3), insert it into one side of the center of the surface of the material, and attach the spindle to the instrument as follows: Firmly hold the upper shaft coupling with thumb and forefinger; screw left-hand thread spindle coupling securely to the upper shaft coupling being very careful when connecting to avoid undue side pressure which might affect alignment. Avoid rotating the dial so that pointer touches the stops at either extreme of the scale.

NOTE 3—Select the spindle/speed combination that will give a minimum scale reading of 10 but preferably in the middle or upper portion of the scale. The speed and spindle to be used may differ from this by agreement between user and producer.

9.4 Lower the viscometer until the groove (immersion mark) on the shaft just touches the material. Adjust the viscometer level if necessary. Move the container slowly in a horizontal plane until the spindle is located in approximately the center of the container so that the test will be run in a region undisturbed by the lowering of the spindle.

9.5 *Dial-Reading Viscometer*—Turn on the viscometer. Adjust the viscometer to the rpm selected (Note 3) for the material under test. Allow the viscometer to run until the pointer has stabilized (Note 4). After the pointer has stabilized, depress the clutch and switch off the motor so that when it stops, the pointer will be in view (Note 5).

9.6 *Digital Viscometer*—Turn on the viscometer. Adjust the viscometer to the rpm selected for the material under test. Allow the viscometer to run until the digital reading has stabilized. The digital viscometer gives a direct reading in centipoises, mPa.

NOTE 4—In thixotropic paints, the pointer or digital reading does not always stabilize. On occasion it reaches a peak and then gradually declines as the structure is broken down. In these cases, the time of rotation or number of revolutions prior to reading the viscometer should be agreed to between user and manufacturer.

NOTE 5—Always release the clutch while the spindle is still immersed so that the pointer will float, rather than snap back to zero.

### 10. Calculation (Dial Reading Viscometer)

10.1 Calculate the apparent viscosity at each speed, as follows:

$$V = fs \tag{2}$$

where:

- $V$  = viscosity of sample in centipoises, mPa·s,
- $f$  = scale factor furnished with instrument (see Table 1), and
- $s$  = scale reading of viscometer.

### 11. Report

11.1 Report the following information:

- 11.1.1 The viscometer manufacturer, model and spindle,
- 11.1.2 The viscosity at the spindle/speed utilized,
- 11.1.3 The specimen temperature in degrees Celsius, and
- 11.1.4 The shake time and rest period, if other than specified.

### 12. Precision and Bias

12.1 *Precision*—See Section 23 for precision, including that for measurement at a single speed.