



**SLOVENSKI STANDARD**  
**oSIST prEN ISO 7142:2022**  
**01-maj-2022**

---

**Veziva za barve in lake - Epoksidne smole - Splošne metode preskušanja (ISO/DIS 7142:2022)**

Binders for paints and varnishes - Epoxy resins - General methods of test (ISO/DIS 7142:2022)

Bindemittel für Beschichtungsstoffe – Epoxidharze – Allgemeine Prüfverfahren (ISO/DIS 7142:2022)

Liants pour peintures et vernis - Résines époxydiques - Méthodes générales d'essai (ISO/DIS 7142:2022)

**Ta slovenski standard je istoveten z: prEN ISO 7142**

<https://standards.iteh.ai/catalog/standards/sist/751d2873-a86e-4d8b-a6d2-ea1f003ca5cc/osist-pr-en-iso-7142-2022>

**ICS:**

87.060.20      Veziva      Binders

**oSIST prEN ISO 7142:2022**      **en,fr,de**

**iTeh STANDARD  
PREVIEW  
(standards.iteh.ai)**

[oSIST prEN ISO 7142:2022](https://standards.iteh.ai/catalog/standards/sist/751d2873-a86e-4d8b-a6d2-ea1f003ca5cc/osist-pren-iso-7142-2022)

<https://standards.iteh.ai/catalog/standards/sist/751d2873-a86e-4d8b-a6d2-ea1f003ca5cc/osist-pren-iso-7142-2022>

# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 7142

ISO/TC 35

Secretariat: NEN

Voting begins on:  
2022-03-14Voting terminates on:  
2022-06-06

---

---

## Binders for paints and varnishes — Epoxy resins — General methods of test

*Liants pour peintures et vernis — Résines époxydiques — Méthodes générales d'essai*

ICS: 87.060.20

### iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 7142:2022](https://standards.iteh.ai/catalog/standards/sist/751d2873-a86e-4d8b-a6d2-ea1f003ca5cc/osist-pren-iso-7142-2022)<https://standards.iteh.ai/catalog/standards/sist/751d2873-a86e-4d8b-a6d2-ea1f003ca5cc/osist-pren-iso-7142-2022>

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

### ISO/CEN PARALLEL PROCESSING



Reference number  
ISO/DIS 7142:2022(E)

© ISO 2022

# iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 7142:2022](https://standards.iteh.ai/catalog/standards/sist/751d2873-a86e-4d8b-a6d2-ea1f003ca5cc/osist-pren-iso-7142-2022)

<https://standards.iteh.ai/catalog/standards/sist/751d2873-a86e-4d8b-a6d2-ea1f003ca5cc/osist-pren-iso-7142-2022>



## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

## Contents

Page

|  |          |
|--|----------|
| Foreword.....                                  | iv       |
| <b>1 Scope.....</b>                            | <b>1</b> |
| <b>2 Normative references.....</b>             | <b>1</b> |
| <b>3 Terms and definitions.....</b>            | <b>2</b> |
| <b>4 Sampling.....</b>                         | <b>2</b> |
| <b>5 Test methods.....</b>                     | <b>2</b> |
| <b>6 Test report.....</b>                      | <b>2</b> |
| <b>Annex A (normative) Hydroxyl value.....</b> | <b>4</b> |
| <b>Bibliography.....</b>                       | <b>7</b> |

# iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 7142:2022](https://standards.iteh.ai/catalog/standards/sist/751d2873-a86e-4d8b-a6d2-ea1f003ca5cc/osist-pren-iso-7142-2022)

<https://standards.iteh.ai/catalog/standards/sist/751d2873-a86e-4d8b-a6d2-ea1f003ca5cc/osist-pren-iso-7142-2022>

## ISO/DIS 7142:2022(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*.

This third edition cancels and replaces the second edition (ISO 7142:2007), which has been technically revised.

The main changes are as follows:  
<https://standards.iteh.ai/catalog/standards/sist/751d2873-a86e-4d8b-a6d2-ea1f003ca5cc/osist-pren-iso-7142-2022>

- the concentration of the phenolphthalein solution in [A.1.5](#) has been reduced to 0,5 g/l;
- the text has been editorially revised and the normative references have been updated.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Binders for paints and varnishes — Epoxy resins — General methods of test

## 1 Scope

This document specifies general methods of test for epoxy resins for use in paints, varnishes and similar products. It is also applicable to those solutions made from epoxy resins that are intended for use as binders for paints and varnishes.

The test methods to be applied to an individual epoxy resin shall be the subject of agreement between the interested parties.

The test methods described in this document are not intended for epoxy esters (see Note 1 to entry in [3.1](#)).

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 385, *Laboratory glassware — Burettes*

ISO 648, *Laboratory glassware — Single volume pipettes*

ISO 1523, *Determination of flash point — Closed cup equilibrium method*

ISO 3001, *Plastics — Epoxy compounds — Determination of epoxy equivalent*

ISO 3146, *Plastics — Determination of melting behaviour (melting temperature or melting range) of semicrystalline polymers by capillary tube and polarizing-microscope methods*

ISO 3219-2, *Rheology — Part 2: General principles of rotational and oscillatory rheometry*

ISO 3251, *Paints, varnishes and plastics — Determination of non-volatile-matter content*

ISO 3679, *Determination of flash no-flash and flash point — Rapid equilibrium closed cup method*

ISO 4615, *Plastics — Unsaturated polyesters and epoxide resins — Determination of total chlorine content*

ISO 4625-1, *Binders for paints and varnishes — Determination of softening point — Part 1: Ring-and-ball method*

ISO 4625-2, *Binders for paints and varnishes — Determination of softening point — Part 2: Cup-and-ball method*

ISO 4630, *Clear liquids — Estimation of colour by the Gardner colour scale*

ISO 6271, *Clear liquids — Estimation of colour by the platinum-cobalt colour scale*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

ISO 21627-2, *Plastics — Epoxy resins — Determination of chlorine content — Part 2: Easily saponifiable chlorine*

## ISO/DIS 7142:2022(E)

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

#### 3.1

##### epoxy resin

synthetic resin containing epoxy groups, generally prepared from epichlorohydrin and a bisphenol

Note 1 to entry: Epoxy esters obtained by reacting materials containing epoxy groups with fatty acids or oils which dry by oxidation are not covered by this document.

[SOURCE: ISO 4618:2014, 2.99 modified: Note 1 to entry has been added.]

### 4 Sampling

Take a representative sample of the product to be tested, as described in ISO 15528.

### 5 Test methods

The properties to be tested and correspondent test methods are listed in [Table 1](#).

**Table 1 — Properties and test methods**

| Property                        | Test method   |
|---------------------------------|---|
| Colour                          | ISO 4630 (Gardner colour scale) or ISO 6271 (Platinum-cobalt scale) |
| Viscosity <sup>a b</sup>        | ISO 3219-2 or other agreed methods                                  |
| Volatile or non-volatile matter | ISO 3251 <sup>c</sup>   |
| Flashpoint <sup>a</sup>         | ISO 1523 or ISO 3679  |
| Epoxy equivalent                | ISO 3001  |
| Hydroxyl value                  | <a href="#">Annex A</a>   |
| Total chlorine content          | ISO 4615  |
| Easily saponifiable chlorine    | ISO 21627-2   |
| Melting point                   | ISO 3146  |
| Softening point                 | ISO 4625-1 or ISO 4625-2  |

<sup>a</sup> For epoxy resin solutions, liquid resins and resins in test solutions only. Solid epoxy resins should be tested in a standard test solution of 40 % mass fraction in diethylene glycol mono-*n*-butylether. The solvent used and the concentration of the test solution should be indicated in the test report.

<sup>b</sup> If the flow-time is used for the characterization of the flow behaviour, it should be determined by the method specified in ISO 2431.

<sup>c</sup> Take a test portion of 5 g and heat it at 140 °C for 3 h without addition of solvent, as described in ISO 3251.

### 6 Test report

In the test report, at least the following information shall be provided:

- a) the type and identification of the product tested;
- b) a reference to this document, i.e. ISO 7142:—;
- c) the result of the tests, and the test methods used;



- d) any deviation, by agreement or otherwise, from the procedures specified;
- e) the dates of the tests.

**iTeh STANDARD  
PREVIEW  
(standards.iteh.ai)**

[oSIST prEN ISO 7142:2022](https://standards.iteh.ai/catalog/standards/sist/751d2873-a86e-4d8b-a6d2-ea1f003ca5cc/osist-pren-iso-7142-2022)  
<https://standards.iteh.ai/catalog/standards/sist/751d2873-a86e-4d8b-a6d2-ea1f003ca5cc/osist-pren-iso-7142-2022>

## Annex A (normative)

### Hydroxyl value

#### A.1 Reagents

During the analysis, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

**WARNING** — Take all necessary safety precautions when using the reagents [A.1.1](#) to [A.1.3](#).

##### A.1.1 Pyridine.

The pyridine shall be clear and shall not cause a significant colour during the blank test.

##### A.1.2 Pyridinium perchlorate.

Slowly add 144 g of 70 % (mass fraction) perchloric acid to 120 ml of pyridine, keeping the mixture cool. Recrystallize the precipitate twice in hot water and allow it to dry in air.

##### A.1.3 Acetic anhydride/pyridine mixture

Mix 12 g of 95 % (mass fraction) acetic anhydride with 88 g of pyridine.

Store the mixture in an airtight bottle and in the dark.

##### A.1.4 Potassium hydroxide, methanolic standard volumetric solution, $c(\text{KOH}) = 1 \text{ mol/l}$ .

##### A.1.5 Phenolphthalein, 5 g/l solution in 95 % (volume fraction) ethanol, methanol or 2-propanol.

#### A.2 Apparatus

Ordinary laboratory apparatus together with the following.

##### A.2.1 Conical flask, of capacity about 250 ml, fitted with a ground glass joint.

##### A.2.2 Reflux condenser, with ground glass joint, fitting on the conical flask ([A.2.1](#)).

##### A.2.3 Burette, of capacity 50 ml, complying with the requirements of ISO 385, for the potassium hydroxide solution ([A.1.4](#)).

##### A.2.4 Pipette, of capacity 25 ml, complying with the requirements of ISO 648.

##### A.2.5 Suitable heating device.