



SLOVENSKI STANDARD
SIST-TP CEN ISO/ASTM/TR 52906:2022

01-september-2022

Dodajalna izdelava - Neporušitveno preskušanje - Namerno vnašanje nepravilnosti v kovinske izdelke (ISO/ASTM TR 52906:2022)

Additive manufacturing - Non-destructive testing - Intentionally seeding flaws in metallic parts (ISO/ASTM TR 52906:2022)

Additive Fertigung - Zerstörungsfreie Prüfung und Bewertung - Bewusstes Einbringen von Fehlern in Bauteilen (ISO/ASTM TR 52906:2022)

Fabrication additive - Essais non destructifs - Implantation intentionnelle de défauts dans les pièces métalliques (ISO/ASTM TR 52906:2022)

Ta slovenski standard je istoveten z: CEN ISO/ASTM/TR 52906:2022

[SIST-TP CEN ISO/ASTM/TR 52906:2022](https://standards.sist.net/catalog/standards/sist/42933075-6769-493c-xadd-1837623078c/sist-tp-cen-iso-astm-tr-52906-2022)

ICS:

19.100	Neporušitveno preskušanje	Non-destructive testing
25.030	3D-tiskanje	Additive manufacturing

SIST-TP CEN ISO/ASTM/TR 52906:2022 en,fr,de

TECHNICAL REPORT
RAPPORT TECHNIQUE
TECHNISCHER BERICHT

**CEN ISO/ASTM/TR
52906**

May 2022

ICS

English Version

**Additive manufacturing - Non-destructive testing -
Intentionally seeding flaws in metallic parts
(ISO/ASTM/TR 52906:2022)**

Fabrication additive - Essais non destructifs -
Implantation intentionnelle de défauts dans les pièces
métalliques (ISO/ASTM/TR 52906:2022)

Additive Fertigung - Zerstörungsfreie Prüfung und
Bewertung - Bewusstes Einbringen von Fehlern in
Bauteilen (ISO/ASTM/TR 52906:2022)

This Technical Report was approved by CEN on 28 April 2022. It has been drawn up by the Technical Committee CEN/TC 438.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

<https://standards.iteh.ai>
Document Preview

[SIST-TP CEN ISO/ASTM/TR 52906:2022](https://standards.iteh.ai/catalog/standards/sist/42955045-6789-495c-9ad6-1b3765569be7/sist-tp-cen-iso-astm-tr-52906-2022)

<https://standards.iteh.ai/catalog/standards/sist/42955045-6789-495c-9ad6-1b3765569be7/sist-tp-cen-iso-astm-tr-52906-2022>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

CEN ISO/ASTM/TR 52906:2022 (E)

Contents	Page
European foreword.....	3

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST-TP CEN ISO/ASTM/TR 52906:2022](https://standards.iteh.ai/catalog/standards/sist/42955045-6789-495c-9ad6-1b3765569be7/sist-tp-cen-iso-astm-tr-52906-2022)

<https://standards.iteh.ai/catalog/standards/sist/42955045-6789-495c-9ad6-1b3765569be7/sist-tp-cen-iso-astm-tr-52906-2022>

European foreword

This document (CEN ISO/ASTM/TR 52906:2022) has been prepared by Technical Committee ISO/TC 261 "Additive manufacturing" in collaboration with Technical Committee CEN/TC 438 "Additive Manufacturing" the secretariat of which is held by AFNOR.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

Endorsement notice

The text of ISO/ASTM TR 52906:2022 has been approved by CEN as CEN ISO/ASTM/TR 52906:2022 without any modification.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST-TP CEN ISO/ASTM/TR 52906:2022](https://standards.iteh.ai/catalog/standards/sist/42955045-6789-495c-9ad6-1b3765569be7/sist-tp-cen-iso-astm-tr-52906-2022)

<https://standards.iteh.ai/catalog/standards/sist/42955045-6789-495c-9ad6-1b3765569be7/sist-tp-cen-iso-astm-tr-52906-2022>

TECHNICAL
REPORT

ISO/ASTM TR
52906

First edition
2022-05

Additive manufacturing — Non-destructive testing — Intentionally seeding flaws in metallic parts

Fabrication additive — Essais non destructifs — Implantation intentionnelle de défauts dans les pièces métalliques

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST-TP CEN ISO/ASTM/TR 52906:2022](https://standards.iteh.ai/catalog/standards/sist/42955045-6789-495c-9ad6-1b3765569be7/sist-tp-cen-iso-astm-tr-52906-2022)

<https://standards.iteh.ai/catalog/standards/sist/42955045-6789-495c-9ad6-1b3765569be7/sist-tp-cen-iso-astm-tr-52906-2022>



Reference number
ISO/ASTM TR 52906:2022(E)

© ISO/ASTM International 2022

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST-TP CEN ISO/ASTM/TR 52906:2022](https://standards.iteh.ai/catalog/standards/sist/42955045-6789-495c-9ad6-1b3765569be7/sist-tp-cen-iso-astm-tr-52906-2022)

<https://standards.iteh.ai/catalog/standards/sist/42955045-6789-495c-9ad6-1b3765569be7/sist-tp-cen-iso-astm-tr-52906-2022>



COPYRIGHT PROTECTED DOCUMENT

© ISO/ASTM International 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester. In the United States, such requests should be sent to ASTM International.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11

Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

ASTM International
100 Barr Harbor Drive, PO Box C700
West Conshohocken, PA 19428-2959, USA
Phone: +610 832 9634
Fax: +610 832 9635
Email: khooper@astm.org
Website: www.astm.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Abbreviated terms	2
5 Typical AM flaws	3
6 Procedure to produce replicas	7
7 Seeding approaches	7
7.1 General.....	7
7.2 CAD seeding.....	8
7.3 AM process manipulation replicas.....	10
7.3.1 General.....	10
7.3.2 Entrapped unsintered powder.....	11
7.3.3 Manual insertion of high-density inclusions.....	11
7.4 Post-production mechanical introduction of replicas.....	11
7.5 Significance and use for homogeneity.....	12
8 AM process manipulation for L-PBF and L-DED	14
8.1 General.....	14
8.2 AM machine parameter manipulation.....	14
8.3 Applicable flaw-seeding approaches as a function of desired flaw type.....	15
8.3.1 General.....	15
8.3.2 Porosity or voids (increased power density).....	15
8.3.3 Surface-connected flaws.....	15
8.4 Applicable flaw-seeding approach as a function of AM process.....	16
8.5 Applicable flaw-seeding approach as a function of AM material.....	17
8.5.1 General.....	17
8.5.2 High-density inclusions.....	18
9 Applicable flaw-seeding approach as a function of post processing machining	18
9.1 General.....	18
9.2 Mechanical machining.....	18
9.3 Electrode discharge machining replicas.....	18
9.4 Laser drilling replicas.....	18
Bibliography	20

ISO/ASTM TR 52906:2022(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents can be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by ISO/TC 261, *Additive manufacturing*, in cooperation with ASTM Committee F42, *Additive Manufacturing Technologies*, on the basis of a partnership agreement between ISO and ASTM International with the aim to create a common set of ISO/ASTM standards on additive manufacturing, and in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 438, *Additive manufacturing*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document provides information for intentionally seeding flaws in additively manufactured parts and complements ISO/ASTM TR 52905¹⁾.

The different AM building descriptions can be found readily in published standards (see ISO 17296-2) and scientific papers.

Jargon commonly used in the literature describing AM metal process defects includes “balling”, “fireworks”, “smoke” and often are not specific to the morphology of the defect and often result from widely differing mechanisms of formation.

When defining terms specific to AM metal flaws it may be useful to review some examples related to welding technology.

This document is for the creation of seeded replicas supports the user’s understanding not only for the characterization of actual flaws with respect to physical morphology but also for the materials and mechanisms of formation, location, and orientation. In addition, the fundamentals of the processes creating the replica (e.g. PBF or DED with regard to the heat sources electron beam (EB), laser beam (LB) or AP (arc processes) also need to be considered). The intentional seeding to produce flaw replicas can match the character of the actual flaw as closely as possible.

The reference photomicrographs or non-destructive testing images included in this document are in no way to be construed as specifications. These reference photomicrographs and non-destructive testing images are offered primarily to permit examples of “flaws” or replicate images thereof. They can be used for comparison of reports. Flaw seeding will be discussed without context to a specific part, location, or dimension. The material alloy will be provided as known. With some flaws the material alloy may not be as important, for example, a pore may reside in any number of alloys. It can be noted that there is currently no proven method for controlled and replicable seeding of intimate disbonds (sometimes known as “kissing bonds”) – where two surfaces are in intimate or close contact, but with compromised adhesion – in AM parts so this feature is, therefore, currently out of scope.

This document will not go into the fundamentals of each process but rather identify the parameters within each process that can lead to the intentional seeding of AM structures.

1) In preparation. Stage at the time of publication ISO/ASTM DTR 52905:2022.