

---

**Vlaknine - Vzorčenje za preskušanje (ISO/FDIS 7213:2021)**

Pulps - Sampling for testing (ISO/FDIS 7213:2021)

Pâtes - Échantillonnage pour essais (ISO/FDIS 7213:2021)

**Ta slovenski standard je istoveten z: prEN ISO 7213**

[oSIST prEN ISO 7213:2021](https://standards.iteh.ai/catalog/standards/sist/60ef078f-db7b-491a-b51c-f67d758c4615/osist-pren-iso-7213-2021)

<https://standards.iteh.ai/catalog/standards/sist/60ef078f-db7b-491a-b51c-f67d758c4615/osist-pren-iso-7213-2021>

**ICS:**

85.040

Vlaknine

Pulps

**oSIST prEN ISO 7213:2021**

**en,fr,de**

## **iTeh STANDARD PREVIEW (standards.iteh.ai)**

[oSIST prEN ISO 7213:2021](https://standards.iteh.ai/catalog/standards/sist/60ef078f-db7b-491a-b51c-f67d758c4615/osist-pren-iso-7213-2021)

<https://standards.iteh.ai/catalog/standards/sist/60ef078f-db7b-491a-b51c-f67d758c4615/osist-pren-iso-7213-2021>

FINAL  
DRAFT

INTERNATIONAL  
STANDARD

ISO/FDIS  
7213

ISO/TC 6

Secretariat: SCC

Voting begins on:  
**2021-08-17**

Voting terminates on:  
**2021-11-09**

## Pulps — Sampling for testing

*Pâtes — Échantillonnage pour essais*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[oSIST prEN ISO 7213:2021](https://standards.iteh.ai/catalog/standards/sist/60ef078f-db7b-491a-b51c-f67d758c4615/osist-pren-iso-7213-2021)

<https://standards.iteh.ai/catalog/standards/sist/60ef078f-db7b-491a-b51c-f67d758c4615/osist-pren-iso-7213-2021>

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

**ISO/CEN PARALLEL PROCESSING**



Reference number  
ISO/FDIS 7213:2021(E)

© ISO 2021

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 7213:2021](https://standards.iteh.ai/catalog/standards/sist/60ef078f-db7b-491a-b51c-f67d758c4615/osist-pren-iso-7213-2021)

<https://standards.iteh.ai/catalog/standards/sist/60ef078f-db7b-491a-b51c-f67d758c4615/osist-pren-iso-7213-2021>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword .....	iv
<b>1 Scope .....</b>	<b>1</b>
<b>2 Normative references .....</b>	<b>1</b>
<b>3 Terms and definitions .....</b>	<b>1</b>
<b>4 Principle .....</b>	<b>1</b>
<b>5 Sample bales (or rolls) .....</b>	<b>2</b>
<b>6 Procedure .....</b>	<b>2</b>
6.1 Pulps baled in sheet form .....	2
6.2 Pulps (such as flash-dried pulps baled in slabs) .....	3
6.3 Pulps in rolls .....	3
6.4 Pulp bales combined in units .....	3
<b>7 Sampling report .....</b>	<b>3</b>
<b>Bibliography .....</b>	<b>4</b>

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 7213:2021](https://standards.iteh.ai/catalog/standards/sist/60ef078f-db7b-491a-b51c-f67d758c4615/osist-pren-iso-7213-2021)

<https://standards.iteh.ai/catalog/standards/sist/60ef078f-db7b-491a-b51c-f67d758c4615/osist-pren-iso-7213-2021>

## ISO/FDIS 7213:2021(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*.

This second edition cancels and replaces the first edition (ISO 7213:1981), of which it constitutes a minor revision. The changes compared to the previous edition are as follows:

- updates to be consistent with ISO format requirements;
- minor editorial changes.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Pulps — Sampling for testing

## 1 Scope

This document specifies a method of obtaining, for test purposes, a gross sample representative of a certain lot of pulp. This document applies to all kinds of pulp delivered in bales or rolls. It is intended for use when sampling for all kinds of testing purposes except for the determination of saleable mass, in which case other International Standards apply such as ISO 801-1 and ISO 801-2.

If, however, the pulp is to be tested for saleable mass in addition to other properties, the gross sample obtained according to the appropriate International Standard for sampling saleable mass can also be used for the other pulp property tests.

## 2 Normative references

There are no normative references in this document.

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

### 3.1 lot

quantity of pulp of a single kind or grade, about which it is desired to make a judgement (usually to conform to agreed quality criteria)

Note 1 to entry: The number of bales or rolls comprising a lot may be indicated by the invoice or agreed upon by the contracting parties.

### 3.2 sample bale (or roll)

bale or roll that is selected for taking a specimen

### 3.3 specimen

quantity of pulp taken from a sample bale or roll

### 3.4 gross sample

combined specimens taken from a particular lot

## 4 Principle

Specimens of equal size are taken from a number of bales or rolls selected at random from the lot, and combined to form a gross sample.

NOTE The minimum number of bales to be sampled depends on the size of the lot.

## ISO/FDIS 7213:2021(E)

## 5 Sample bales (or rolls)

All the sample bales (or rolls) shall be selected at random to be representative of the lot. The sample bales shall be intact and as little damaged as possible.

To obtain a truly representative sample, the whole lot should be available for sampling. The minimum number of sample bales (or rolls) to be taken,  $n$ , is given in [Table 1](#). Where a whole lot is not available, the number of bales selected for sampling should be agreed upon between the interested parties. In the absence of any other agreement, the quantity of pulp available at the time of sampling shall be not less than half of the complete lot.

If the bales or rolls have identification numbers relating to several series, the sample bales (or rolls) shall be selected at random in proportion to the number of bales or rolls in each of these series, using the principle given in [Table 1](#).

The identification marks and numbers should be reported for future reference, if necessary.

**Table 1 — Number of sample bales (or rolls) to be taken**

Total number of bales (or rolls) in the lot $N$	Minimum number of sample bales (or rolls) $n$
Up to 100	10
101 - 200	15
201 - 300	18
301 - 400	20
401 - 500	23
501 - 600	25
601 - 700	27
701 - 800	29
801 - 900	30
901 - 1 000	32
Over 1 000	32

NOTE The table is based on the principle that  $n$  should not be less than the square root of  $N$ . However, this document does not require more than 32 bales (or rolls) to be sampled irrespective of the size of the lot.

## 6 Procedure

From each sample bale or roll, take one specimen. Record the identification numbers of all the bales or rolls sampled. All the specimens should contain about the same amount of dry fibre. This amount depends on which tests are to be performed. Normally 100 g per specimen is sufficient.

Combine the specimens to form the gross sample. Wrap it to protect it from contamination. Keep it away from sunlight, heat and moisture.

Obtain the specimens as suggested in [6.1](#), [6.2](#), [6.3](#) or [6.4](#) as appropriate. If the pulp is to be tested for trace metals, do not use metallic tools and discard any cut edges of pulp where metallic contamination may have occurred.

### 6.1 Pulps baled in sheet form

Open the sample bales and randomly select one sheet from each bale. Do not select from the five top or bottom sheets, and avoid taking material which is within 7 cm to 8 cm of the edge of the sheet. From each sheet selected, tear a specimen of appropriate size, and discard the rest.

To avoid opening bales, one of the following alternative methods may be used:

- a) The disc sampling procedure specified in ISO 801-2. Each specimen then consists of an equal number of test discs.
- b) Cut a rectangular area into the bale between the baling wires to a sufficient depth to obtain the appropriate size of specimen allowing for discarding the three outer sheets and for tearing off the cut edges.

## 6.2 Pulps (such as flash-dried pulps baled in slabs)

The specimen may consist of test discs cut, for example, as specified in ISO 801-2 or by pieces of pulp, broken out from the inside of a corner of a slab. The outer, exposed, portions of this material shall not be included.

## 6.3 Pulps in rolls

Remove the three outer layers from the roll and cut or tear a specimen of appropriate size, but excluding the edges of the roll.

## 6.4 Pulp bales combined in units

If a lot is delivered in combined units, consisting of a number of individual bales, the appropriate number of sample bales may be selected from the top and bottom bales in the units, to allow sampling by one of the alternative methods specified in 6.1, without the need to dismantle units.

## 7 Sampling report

If a sample report is prepared, it shall include the following particulars:

- a) all the information necessary for the complete identification of the lot;
- b) reference to this document;
- c) the date and place of sampling;
- d) the total quantity of the lot, number of bales if possible;
- e) the amount of pulp available for sampling;
- f) the number and identification (if it exists) of sample bales (or rolls);
- g) any unusual feature observed in the course of the sampling;
- h) any operations not specified in this document, or regarded as optional, which have possibly affected the sampling.

## Bibliography

- [1] ISO 801-1, *Pulps — Determination of saleable mass in lots — Part 1: Pulp baled in sheet form*
- [2] ISO 801-2, *Pulps — Determination of saleable mass in lots — Part 2: Pulps (such as flash-dried pulps) baled in slabs*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[oSIST prEN ISO 7213:2021](https://standards.iteh.ai/catalog/standards/sist/60ef078f-db7b-491a-b51c-f67d758c4615/osist-pren-iso-7213-2021)  
<https://standards.iteh.ai/catalog/standards/sist/60ef078f-db7b-491a-b51c-f67d758c4615/osist-pren-iso-7213-2021>