This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: D4552–92 (Reapproved 2004) Designation: D4552/D4552M – 10

Standard Practice for Classifying Hot-Mix Recycling Agents¹

This standard is issued under the fixed designation D4552/D4552M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1This practice covers a standardized method whereby petroleum product additives to be used in hot recycling of asphalt concrete can be identified. The products are classified by viscosity in centistokes measured at 140°F (60°C). This practice does not apply to emulsified materials.

1.2

<u>1.1 This practice covers a standardized method whereby petroleum product additives to be used in hot recycling of asphalt concrete can be identified. The products are classified by viscosity in mm²/s measured at 60°C [140°F]. This practice does not apply to emulsified materials.</u>

<u>1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.</u>

<u>1.3</u> This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

D70 Test Method for Density of Semi-Solid Bituminous Materials (Pycnometer Method)

D92 Test Method for Flash and Fire Points by Cleveland Open Cup Tester

D140 Practice for Sampling Bituminous Materials

D946 Specification for Penetration-Graded Asphalt Cement for Use in Pavement Construction

D1298 Test Method for Density, Relative Density (Specific Gravity), or API Gravity of Crude Petroleum and Liquid Petroleum Products by Hydrometer Method

D1754 Test Method for Effects of Heat and Air on Asphaltic Materials (Thin-Film Oven Test)

D2007 Test Method for Characteristic Groups in Rubber Extender and Processing Oils and Other Petroleum-Derived Oils by the Clay-Gel Absorption Chromatographic Method

D2170 Test Method for Kinematic Viscosity of Asphalts (Bitumens)

D2171 Test Method for Viscosity of Asphalts by Vacuum Capillary Viscometer

D2872 Test Method for Effect of Heat and Air on a Moving Film of Asphalt (Rolling Thin-Film Oven Test)

D3381 Specification for Viscosity-Graded Asphalt Cement for Use in Pavement Construction

3. Significance and Use

3.1 Recycling of deteriorated asphalt pavements is being used with increasing frequency for its economy and benefit of conserving raw materials. The objective of recycling is to reuse the two ingredients of asphalt concrete-aggregate and asphalt and to restore the desired properties to the mixture. Recycling is carried out hot or cold, depending on the condition of the deteriorated pavement, construction procedure, availability of equipment, and cost. This practice is for classifying recycling agents to be used in hot recycling.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

¹ This practice is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.40 on Asphalt Specifications.

Current edition approved July 1, 2004. Published July 2004. Originally approved in 1986. Last previous edition approved in 1999 as D4552-92 (1999). DOI: 10.1520/D4552-92R04.

Current edition approved June 15, 2010. Published July 2010. Originally approved in 1986. Last previous edition approved in 2004 as D4552–92 (2004). DOI: 10.1520/D4552_D4552L-04552M-10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.