



Designation: E690-98 (Reapproved 2004)^{ε1} Designation: E690 – 10

Standard Practice for In Situ Electromagnetic (Eddy-Current) Examination of Nonmagnetic Heat Exchanger Tubes¹

This standard is issued under the fixed designation E690; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

~~^{ε1}Note—Editorial changes made throughout in January 2004.~~

1. Scope*

1.1 This practice describes procedures to be followed during eddy-current examination (using an internal, probe-type, coil assembly) of nonmagnetic tubing that has been installed in a heat exchanger. The procedure recognizes both the unique problems of implementing an eddy-current examination of installed tubing, and the indigenous forms of tube-wall deterioration which may occur during this type of service. The document primarily addresses scheduled maintenance inspection of heat exchangers, but can also be used by manufacturers of heat exchangers, either to examine the condition of the tubes after installation, or to establish baseline data for evaluating subsequent performance of the product after exposure to various environmental conditions. The ultimate purpose is the detection and evaluation of particular types of tube integrity degradation which could result in in-service tube failures.

1.2 This practice does not establish acceptance criteria; they must be specified by the using parties.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E543 [Specification for Agencies Performing Nondestructive Testing](#)

E1316 [Terminology for Nondestructive Examinations](#)

2.2 *Other Documents:*

SNT-TC-1A Recommended Practice for Personnel Qualification and Certification in Nondestructive Testing³

ANSI/ASNT-CP-189 ASNT Standard for Qualification and Certification of Nondestructive Testing Personnel³

NAS-410 NAS Certification and Qualification of Nondestructive Personnel (Quality Assurance Committee)⁴

<https://standards.iteh.ai/catalog/standards/sist/615e0280-2612-4a44-ab14-d534bb318c7b/astm-e690-10>

3. Terminology

3.1 Standard terminology relating to electromagnetic examination may be found in Terminology E1316, Section C, Electromagnetic Testing.

4. Summary of Practice

4.1 The examination is performed by passing an eddy-current probe through each tube. These probes are energized with alternating currents at one or more frequencies. The electrical impedance of the probe is modified by the proximity of the tube, the tube dimensions, electrical conductivity, magnetic permeability, and metallurgical or mechanical discontinuities in the tube. During passage through the tube, changes in electromagnetic response caused by these variables in the tube produce electrical signals which are processed so as to produce an appropriate combination of visual displays, alarms, or temporary or permanent

¹ This practice is under the jurisdiction of ASTM Committee E07 on Nondestructive Testing and is the direct responsibility of Subcommittee E07.07 on Electromagnetic Methods.

Current edition approved January 1, 2004. Published February 2004. Originally approved in 1979. Last previous edition approved in 1998 as E690-98. DOI: 10.1520/E0690-98R04E01 on Electromagnetic Method.

Current edition approved June 1, 2010. Published July 2010. Originally approved in 1979. Last previous edition approved in 1998 as E690-98(2004)^{ε1}. DOI: 10.1520/E0690-10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from The American Society for Nondestructive Testing (ASNT), P.O. Box 28518, 1711 Arlingate Ln., Columbus, OH 43228-0518, <http://www.asnt.org>.

⁴ Available from Aerospace Industries Association of America, Inc., 1250 Eye Street, N.W., Washington, DC 20005.

^ε Available from Aerospace Industries Association of America, Inc. (AIA), 1000 Wilson Blvd., Suite 1700, Arlington, VA 22209-3928, <http://www.aia-aerospace.org>.

*A Summary of Changes section appears at the end of this standard.

records, or combination thereof, for subsequent analysis. ~~Note 1—The agency performing the testing or examination shall meet the requirements of Practice E543.~~

5. Significance and Use

5.1 Eddy-current examination is a nondestructive method of locating discontinuities in tubing made of materials that conduct electricity. Signals can be produced by discontinuities located either on the inner or outer surfaces of the tube, or by discontinuities totally contained within the tube wall. When using an internal probe, the density of eddy currents in the tube wall decreases very rapidly as the distance from the internal surface increases; thus the amplitude of the response to outer surface discontinuities decreases correspondingly.

5.2 Some indications obtained by this method may not be relevant to product quality. For example, an irrelevant signal may be caused by metallurgical or mechanical variations that are generated during manufacture but that are not detrimental to the end use of the product. Irrelevant indications can mask unacceptable discontinuities occurring in the same area. Relevant indications are those that result from nonacceptable discontinuities. Any indication above the reject level, which is believed to be irrelevant, shall be regarded as unacceptable until it is proven to be irrelevant. For tubing installed in heat exchangers, predictable sources of irrelevant indications are lands (short unfinned sections in finned tubing), dents, scratches, tool chatter marks, or variations in cold work. Rolling tubes into the supports may also cause irrelevant indications, as may the tube supports themselves. Eddy-current examination systems are generally not able to separate the indication generated by the end of the tube from indications of discontinuities adjacent to the ends of the tube (end effect). Therefore, this examination may not be valid at the boundaries of the tube sheets.

6. Basis of Application

6.1 The following criteria may be specified in the purchase specification, contractual agreement, or elsewhere, and may require agreement between the purchaser and the supplier.

- 6.1.1 Type of eddy-current system, and probe (coil assembly) configuration,
- 6.1.2 Location of heat exchanger, if applicable,
- 6.1.3 Size, material, and configuration of tubes to be examined,
- 6.1.4 Extent of examination, that is, length, tube sheet areas, straight length only, minimum radius of bends, etc.,
- 6.1.5 Time of examination, that is, the date and location of the intended examination, and the expected environmental conditions,
- 6.1.6 The source and type of material to be used for fabricating the reference standard,
- 6.1.7 The type(s), method of manufacture, location, dimensions, and number of artificial discontinuities to be placed on the reference standard,
- 6.1.8 Allowable tolerances for artificial discontinuities, and methods for verifying compliance,
- 6.1.9 Methods for determining the extent of end effect,
- 6.1.10 Maximum time interval between equipment reference checks,
- 6.1.11 Criteria to be used in interpreting and classifying observed indications,
- 6.1.12 Disposition of examination records and reference standard,
- 6.1.13 Contents of examination report, and
- 6.1.14 If specified in the contractual agreement, personnel performing examinations to this practice shall be qualified in accordance with a nationally recognized NDT personnel qualification practice or standard such as ANSI/ASNT-CP-189, SNT-TC-1A, MIL-STD-410E, NAS-410, ASNT-ACCP, or a similar document and certified by the certifying agency, as applicable. The practice or standard used and its applicable revision shall be identified in the contractual agreement between the using parties.

NOTE 21—MIL-STD-410 is canceled and has been replaced with NAS-410, however, it may be used with agreement between contracting parties.

6.1.15 If specified in the contractual agreement, NDT agencies shall be qualified and evaluated in accordance with Practice Specification E543. ~~The applicable edition of Specification E543.~~ ~~The applicable edition of Practice E543 shall be specified in the contractual agreement.~~

7. Apparatus

7.1 *Electronic Apparatus:*

7.1.1 The electronic apparatus shall be capable of energizing the probe coils with alternating currents of suitable frequencies, and shall be capable of sensing changes in the electromagnetic response of the probes. It is important to note that a differential coil probe system tends to maximize the response from abrupt changes along the tube length, while a single coil probe system usually responds to all changes.

7.1.2 Since many gradual changes are irrelevant, a differential coil system may permit higher gain than an absolute coil system, which enhances the response to small, short defects. Electrical signals produced in this manner may be processed so as to actuate an audio or visual readout, or both. When necessary, these signals may also be further processed to produce a permanent record. The apparatus should have some means of providing relative quantitative information based upon the amplitude or phase of the electrical signal, or both. This may take many forms, including calibrated sensitivity or attenuation controls, multiple alarm thresholds, or analog or digital readouts, or combination thereof.