



~~Designation: F1083-08~~ Designation: F1083 - 10

## Standard Specification for Pipe, Steel, Hot-Dipped Zinc-Coated (Galvanized) Welded, for Fence Structures<sup>1</sup>

This standard is issued under the fixed designation F1083; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

~~1.1 This specification covers hot-dipped galvanized welded steel pipe in NPS 1 (Note 1) to NPS 8, inclusive, with nominal (average) wall thickness as given in~~

1.1 This specification covers hot-dipped galvanized welded steel pipe in sizes ranging from 1.315–8.625 in. (33.4 – 219.1 mm) outside diameter (OD) inclusive, with nominal (average) wall thickness as given in Table 1 and Table 2. Pipe having other dimensions (Note 2) may be furnished provided such pipe complies with all other requirements of this specification. Pipe ordered under this specification is intended for use as a structural support for fencing in accordance with Specification F1043, Group 1A.

~~NOTE 1—The dimensionless designator NPS (nominal pipe size) has been substituted in this specification for such traditional terms as nominal diameter, size, and nominal size. 1—Outside diameter size is designated in that fence fittings are designed to securely fit on the outside of the pipe framework.~~

~~NOTE 2—A comprehensive listing of standardized pipe dimensions is contained in ANSI B 36.10.~~

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in ~~brackets~~parentheses are for information only.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

A53/A53M ~~Specification for Pipe, Steel, Black and Hot-Dipped, Zinc-Coated, Welded and Seamless~~

A90/A90M ~~Test Method for Weight [Mass] of Coating on Iron and Steel Articles with Zinc or Zinc-Alloy Coatings~~

A700 ~~Practices for Packaging, Marking, and Loading Methods for Steel Products for Shipment~~

B6 ~~Specification for Zinc~~

E8 ~~Test Methods for Tension Testing of Metallic Materials~~

E29 ~~Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications~~

F1043 ~~Specification for Strength and Protective Coatings on Steel Industrial Chain Link Fence Framework~~

#### 2.2 ANSI Standard:

B 36.10 ~~Welded and Seamless Wrought Steel Pipe~~<sup>3</sup>

### 3. Ordering Information

3.1 Orders for material under this specification shall include the following as required, to describe the desired material adequately:

3.1.1 Specification designation,

3.1.2 Quantity (feet, metres, or number of lengths),

~~3.1.3 Name of material (steel pipe);~~

3.1.3 Name of material (schedule 40 steel pipe or schedule 80 steel pipe),

3.1.4 Method of manufacture (electric-resistance welded or furnace welded),

3.1.5 Grade (Regular, Intermediate, or High Strength 83 000) *Intermediate Strength Grade available for sizes NPS 5 (125) 5.563 in. (141.3 mm) OD and larger. Regular and High Strength 83 000 Grades are available for all sizes.*

3.1.6 Type (Table 1 or Table 2),

<sup>1</sup> This specification is under the jurisdiction of Committee F14 on Fences and is the direct responsibility of Subcommittee F14.40 on Chain Link Fence and Wire Accessories.

Current edition approved Feb. 1, 2008; 2010. Published February 2008; July 2010. Originally approved in 1987. Last previous edition approved in 2006/2008 as F1083 – 068. DOI: 10.1520/F1083-108.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

**TABLE 1 Dimensions, Nominal Weights (Plain Ends) for Standard Weight Pipe (Schedule 40)**

NOTE 1—Pipe furnished in accordance with this table will be standard pipe. Nominal size designations are names, not dimensions, thus they are a unit-less term. The dimensionless designator NPS (nominal pipe size) is referenced in this specification as it is the historical designation for schedule 40 pipe. The fence framework application requires the framework fittings to fit securely on the outside of the pipe and therefore the OD, outside diameter, is the applicable dimension for this specification.

NOTE 2—The wall thickness is expressed in three decimal places, the fourth decimal place being carried forward or dropped, in accordance with Practice E29.

DNPS Designator	Trades Signatorze O.D. Metric	Outside Diameter		Wall Thickness		Weight	
		in.	{(mm)}	in.	{(mm)}	lb/ft	{(kg/m)}
1/8	[25]	1.315	{33.4}	0.133	{3.38}	1.68	{2.5}
1/4	1 3/8	1.315	{33.4}	0.133	{3.38}	1.68	{2.5}
1/4	[32]	1.660	{42.2}	0.140	{3.56}	2.27	{3.4}
1/4	1 5/8	1.660	{42.2}	0.140	{3.56}	2.27	{3.4}
1/2	[40]	1.900	{48.3}	0.145	{3.68}	2.72	{4.0}
1/2	1 7/8	1.900	{48.3}	0.145	{3.68}	2.72	{4.0}
2	[50]	2.375	{60.3}	0.154	{3.91}	3.65	{5.4}
2	2 3/8	2.375	{60.3}	0.154	{3.91}	3.65	{5.4}
2 1/2	[65]	2.875	{73.0}	0.203	{5.16}	5.80	{8.6}
2 1/2	2 7/8	2.875	{73.0}	0.203	{5.16}	5.80	{8.6}
3	[80]	3.500	{88.9}	0.216	{5.49}	7.58	{11.3}
3	3 1/2	3.500	{88.9}	0.216	{5.49}	7.58	{11.3}
3 1/2	[90]	4.000	{101.6}	0.226	{5.74}	9.12	{13.6}
3 1/2	4	4.000	{101.6}	0.226	{5.74}	9.12	{13.6}
4	[100]	4.500	{114.3}	0.237	{6.02}	10.80	{16.1}
4	4 1/2	4.500	{114.3}	0.237	{6.02}	10.80	{16.1}
5	[125] 5 1/8	5.563	{141.3}	0.258	{6.55}	14.63	{21.77}
5	5 1/8	5.563	{141.3}	0.258	{6.55}	14.63	{21.77}
6	[150]	6.625	{168.3}	0.280	{7.11}	18.99	{28.3}
6	6 3/8	6.625	{168.3}	0.280	{7.11}	18.99	{28.3}
8	[200]	8.625	{219.1}	0.322	{8.18}	28.58	{42.5}
8	8 5/8	8.625	{219.1}	0.322	{8.18}	28.58	{42.5}

**TABLE 2 Dimensions, Nominal Weights (Plain Ends) for Extra Strong Pipe (Schedule 80)**

NOTE 1—Pipe furnished in accordance with this table will be extra-strong pipe. Nominal size designations are names, not dimensions, thus they are a unit-less term. The dimensionless designator NPS (nominal pipe size) is referenced in this specification as it is the historical designation for schedule 80 pipe. The fence framework application requires the framework fittings to fit securely on the outside of the pipe and therefore the OD, outside diameter, is applicable dimension for this specification.

NOTE 2—The wall thickness is expressed in three decimal places, the fourth decimal place being carried forward or dropped, in accordance with Practice E29.

DNPS Designator	Trades Signatorze O.D. Metric	Outside Diameter		Wall Thickness		Weight	
		in.	{(mm)}	in.	{(mm)}	lb/ft	{(kg/m)}
1/8	[25]	1.315	{33.4}	0.179	{4.55}	2.17	{3.23}
1/4	1 3/8	1.315	{33.4}	0.179	{4.55}	2.17	{3.23}
1/4	[32]	1.660	{42.2}	0.191	{4.85}	3.00	{4.47}
1/4	1 5/8	1.660	{42.2}	0.191	{4.85}	3.00	{4.47}
1/2	[40]	1.900	{48.3}	0.200	{5.08}	3.63	{5.41}
1/2	1 7/8	1.900	{48.3}	0.200	{5.08}	3.63	{5.41}
2	[50]	2.375	{60.3}	0.218	{5.54}	5.03	{7.48}
2	2 3/8	2.375	{60.3}	0.218	{5.54}	5.03	{7.48}
2 1/2	[65]	2.875	{73.0}	0.276	{7.01}	7.67	{11.41}
2 1/2	2 7/8	2.875	{73.0}	0.276	{7.01}	7.67	{11.41}
3	[80]	3.500	{88.9}	0.300	{7.62}	10.26	{15.27}
3	3 1/2	3.500	{88.9}	0.300	{7.62}	10.26	{15.27}
3 1/2	[90]	4.000	{101.6}	0.318	{8.08}	12.52	{18.63}
3 1/2	4	4.000	{101.6}	0.318	{8.08}	12.52	{18.63}
4	[100]	4.500	{114.3}	0.337	{8.56}	15.00	{22.32}
4	4 1/2	4.500	{114.3}	0.337	{8.56}	15.00	{22.32}
5	[125] 5 1/8	5.563	{141.3}	0.375	{9.52}	20.80	{30.94}
5	5 1/8	5.563	{141.3}	0.375	{9.52}	20.80	{30.94}
6	[150]	6.625	{168.3}	0.432	{10.97}	28.60	{42.56}
6	6 3/8	6.625	{168.3}	0.432	{10.97}	28.60	{42.56}
8	[200]	8.625	{219.1}	0.500	{12.70}	43.43	{64.64}
8	8 5/8	8.625	{219.1}	0.500	{12.70}	43.43	{64.64}

3.1.7 Size (NPS designator and weight class; or outside diameter and nominal wall),  
 3.1.7 Size (outside diameter and weight per foot),