



SLOVENSKI STANDARD

oSIST prEN 15520:2023

01-marec-2023

Nadomešča:
SIST EN 15520:2007

Vročje brizganje - Priporočila za konstrukcijsko oblikovanje komponent s prevlekami, nanesenimi z vročim brizganjem

Thermal spraying - Recommendations for constructional design of components with thermally sprayed coatings

Thermisches Spritzen - Empfehlungen zum konstruktiven Gestalten von Bauteilen mit thermisch gespritzten Schichten

Projection thermique - Recommandations relatives à la conception des éléments de construction comportant un revêtement déposé par projection thermique

Ta slovenski standard je istoveten z: prEN 15520

ICS:

25.220.20 Površinska obdelava Surface treatment

oSIST prEN 15520:2023

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 15520

January 2023

ICS

Will supersede EN 15520:2007

English Version

Thermal spraying - Recommendations for constructional design of components with thermally sprayed coatings

Projection thermique - Recommandations relatives à la conception des éléments de construction comportant un revêtement déposé par projection thermique

Thermisches Spritzen - Empfehlungen zum konstruktiven Gestalten von Bauteilen mit thermisch gespritzten Schichten

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 240.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	3
Introduction	4
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions.....	5
4 Applications and specific properties of thermally sprayed coatings.....	5
5 Basic rules for design of components with thermal sprayed coatings.....	6
6 Design for preparation of components and work pieces for thermal spraying.....	7
7 Machining and post-treatment of thermal sprayed coatings.....	8
8 Instructions for design - Symbolic representation of the sprayed coating on drawings - Test instructions in the parts list.....	8
9 Examples for design suitable for spraying	8
9.1 Plane surfaces	8
9.2 Rotationally symmetrical parts.....	8
9.3 Special shape	9
Bibliography	17

[oSIST prEN 15520:2023](https://standards.iteh.ai/catalog/standards/sist/b2978766-a0fb-48e7-b0e7-55adc32b0db4/osist-pren-15520-2023)

<https://standards.iteh.ai/catalog/standards/sist/b2978766-a0fb-48e7-b0e7-55adc32b0db4/osist-pren-15520-2023>

European foreword

This document (prEN 15520:2023) has been prepared by Technical Committee CEN/TC 240 “Thermal spraying and thermally sprayed coatings”, the secretariat of which is held by DIN.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 15520:2007.

prEN 15520:2023 includes the following significant technical changes with respect to EN 15520:2007:

- normative references and bibliography updated;
- document editorially revised;
- figures revised and improved.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN 15520:2023](https://standards.iteh.ai/catalog/standards/sist/b2978766-a0fb-48e7-b0e7-55adc32b0db4/osist-pren-15520-2023)

<https://standards.iteh.ai/catalog/standards/sist/b2978766-a0fb-48e7-b0e7-55adc32b0db4/osist-pren-15520-2023>

prEN 15520:2023(E)

Introduction

Thermal spraying is applied to improve the surface properties of work pieces in order to increase the wear resistance, the electrical conductivity or the electrical resistance, to achieve corrosion resistance for the pertinent service conditions, to improve sliding behaviour or, to provide heat insulation. Recommendations for thermal spraying are contained in EN ISO 12671.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN 15520:2023](#)

<https://standards.iteh.ai/catalog/standards/sist/b2978766-a0fb-48e7-b0e7-55adc32b0db4/osist-pren-15520-2023>

1 Scope

This document applies for thermal sprayed coatings. It contains basic recommendations for the design of components, which have to be completely or partially coated. The recommendations apply for new manufacturing as well as for repair of worn components. The coating can be of metallic, metal-ceramic, oxide-ceramic materials or polymers.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 12671, *Thermal spraying - Thermally sprayed coatings - Symbolic representation on drawings (ISO 12671)*

EN 14665, *Thermal spraying - Thermally sprayed coatings - Symbolic representation on drawings*

3 Terms and definitions

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp/>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Applications and specific properties of thermally sprayed coatings

Due to their structure, thermal sprayed coatings possess properties which markedly distinguish them from bulk materials. An appropriate basic structural design and a suitable parent metal have to bear any mechanical loading. Usually, thermal sprayed coatings do not increase the strength of the parent work piece.

Some process related features and specific properties of thermal sprayed coatings are summarised in Table 1.

Table 1 — Process related features and specific properties of thermal sprayed coatings

Process related features	Specific properties of thermal sprayed coating
Components made of almost every material can be coated by thermal spraying.	Not every spraying procedure is appropriate for all applications.
Coatings with properties completely different from the parent material are possible.	—
Coatings can be sprayed with different spraying materials side by side, one upon another, or mixing into one another (graded coatings).	Usually the effect of the residual stress in the coating rises with increasing coating thickness.
Usually the heat input caused by spraying is so low, that it is possible to avoid structural transformation or deformation. The heat input by fusing self-fluxing alloys or diffusion annealing may cause structural transformation or deformation.	If the coating is not post heat treated the bond strength mainly depends on mechanical adhesive properties. If the coating is post heat treated the bond strength depends on diffusion and the coating is densified.
The ability to apply the spraying process is practically independent of the size of the component.	Some geometric dimensions e.g. internal bores with too small a diameter may limit the spray ability.
Components with complicated shapes can be coated, if appropriate spraying equipment is used.	Sprayed coatings are susceptible to edge loading, point and line loading and impact stresses.
Areas of a component, which shall be free of sprayed material can be protected, e. g. by masking.	—
The untreated surface of the coating provides a good basis for painting or sealing.	—
Several thermal spraying processes can be applied on site as well as in a workshop.	—
Coating properties e.g. porosity can be varied to suit particular applications.	Sprayed coatings are micro porous except for post heat treated self-fluxing alloy coatings.

5 Basic rules for design of components with thermal sprayed coatings

Without proper consideration of the constructional design for thermal sprayed coatings, it may not be possible to achieve the desired properties of the coating.

Designs which are suitable for thermal spraying will be suitable for pre-treatment, blasting and visual inspection.

Further design instructions for specific applications are contained in EN ISO 14921 and EN ISO 17834 and for the protection of steel structures against corrosion in EN ISO 12944-3, EN ISO 14713-1 and EN ISO 2063-1 and EN ISO 2063-2, which deal with the evaluation of coating material, processing and testing and give recommendations for coating thicknesses for several corrosive conditions.

The most important rules for the design are summarised in Table 2.

Table 2 — Basic rules and arguments

Basic rules	Arguments — Explanations
Sufficient accessibility of the area to be coated.	The procedure, spray gun with its electrical and/or gas connections, required spray distance and spray angle shall all be considered.
Area to be coated shall be visible and attainable.	Visible and within reach for the spray jet or tool moved by an operator or a manipulator.
Sharp edges are to be avoided.	Usually they cannot be coated, with a sufficient and uniform coating thickness. Coatings may be damaged on sharp edges. Sharp edges on holes and along cut edges shall be chamfered or rounded.
Small internal radii are to be avoided.	Turbulence of the spray jet, unfavourable angles of incidence, and irregular rebounding spray particles will occur which will lead to insufficient bond strength and density.
Sprayed coatings in narrow holes, slots or in blind holes are to be avoided.	Turbulence and spray particles which are insufficiently adherent to the wall may occur.
Dust inclusions when coating internal surfaces shall be minimised, see Figure 4.	Special care to remove dust and heat.
The spray jet should hit the surface at right-angles. The angle of incidence shall not be less than 45°.	Insufficient spray angles impair bond strength, efficiency, and coating structure. See Figures 4a) and 4b).
The risk of spalling of the coating has to be minimised.	The coating shall be continued around rounded or chamfered edges. See Figures 5a) and 5b).
The risk of damaging the coating has to be minimised.	A support edge or pocket (e. g. per Figure 9 detail X) may be employed.
Welds to be coated shall be free of splatters, undercuts and pores.	Smoothing of such irregularities shall be required.
Heat affected zone from thermally cut edges has to be minimised.	Remove the hardened sharp edge of the cut.

6 Design for preparation of components and work pieces for thermal spraying

When components or work pieces shall be only partially coated, the final machining to finished size of the whole component shall be carried out after spraying the coating. When manufacturing rotationally symmetrical components the blank should be pre-machined only in the area to be sprayed to the diameter appropriate for the coating thickness. One example is shown in Figure 8.

In case of thermal spraying of finish-machined parts or repair of parts by coating, areas which shall not be coated may be protected by appropriate measures (e. g. masking) for blasting and thermal spraying.

7 Machining and post-treatment of thermal sprayed coatings

The different properties of thermal sprayed coatings compared to bulk materials shall be considered in machining processes. Procedures for machining, thermal post-treatment, or sealing of sprayed coatings are indicated in EN ISO 14924 and in EN ISO 14920. Impairment of the parent metal by any thermal post-treatment shall be considered. For details see EN ISO 14920.

8 Instructions for design - Symbolic representation of the sprayed coating on drawings - Test instructions in the parts list

The symbolic representation of a sprayed coating on a drawing shall be according to EN 14665. If the symbolic representation does not cover the requirements for the coating, the coating specification shall be indicated in the pertinent parts list or by a note on the drawing.

The coating specification shall contain the type of coating, pre-treatments, test procedures, required values for e.g. tensile adhesive strength, hardness, etc. relevant for this component, and if applicable, the spraying procedure and post treatments.

An example is given in Clause 9 of this standard in Table 4 and Figure 9.

Instructions that define tests and the scope of tests shall be indicated in the parts list. Tests on component and tests on accompanying test specimens have to be indicated separately, see Figure 9 and Table 4.

If further tests like corrosion or wear tests are required, test procedures and required results have to be agreed between the contracting parties.

It is recommended to indicate the general supply conditions as per EN ISO 12670 in the pertinent parts list to specify requirements concerning quality management of the manufacturer and specific instructions for manufacturing and testing.

9 Examples for design suitable for spraying

9.1 Plane surfaces

Examples are shown in Figure 1. Further examples for coatings for protection against corrosion of welded structures are presented in EN ISO 12944-3.

9.2 Rotationally symmetrical parts

Restrictions of geometrical dimensions exist when coating inner surfaces. Specific conditions of the spray procedure such as spray distance and the size of spray spot have to be considered. Customary minimum dimensions for thermal spraying are contained in Table 3 (see also Figures 2 and 3). The actual dimensions depend on the procedure, equipment, and spray material. Examples of how to round or chamfer edges or carry out support edges or pockets are shown in Figure 5 and Figure 9.