This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.

Designation: E2236-05a Designation: E2236 - 10



Standard Test Methods for Measurement of Electrical Performance and Spectral **Response of Nonconcentrator Multijunction Photovoltaic** Cells and Modules¹

This standard is issued under the fixed designation E2236; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 These test methods provide special techniques needed to determine the electrical performance and spectral response of two-terminal, multijunction photovoltaic (PV) devices, both cell and modules.

1.2 These test methods are modifications and extensions of the procedures for single-junction devices defined by Test Methods E948, E1021, and E1036.

1.3 These test methods do not include temperature and irradiance corrections for spectral response and current-voltage (I-V) measurements. Procedures for such corrections are available in Test Methods E948, E1021, and E1036.

1.4These test methods apply only to nonconcentrator terrestrial multijunction photovoltaic cells and modules.

 $\frac{1.5}{1.5}$

1.4 These test methods may be applied to cells and modules intended for concentrator applications.

1.5 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard. 1.6 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

- 2.1 ASTM Standards:²

- E927 Specification for Solar Simulation for Photovoltaic Testing **Preview** E948 Test Method for Electrical Def E948 Test Method for Electrical Performance of Photovoltaic Cells Using Reference Cells Under Simulated Sunlight
- E973 Test Method for Determination of the Spectral Mismatch Parameter Between a Photovoltaic Device and a Photovoltaic **Reference Cell**
- E1021 Test Method for Spectral Responsivity Measurements of Photovoltaic Devices 57ea3699a1/astm-e2236-10
- E1036 Test Methods for Electrical Performance of Nonconcentrator Terrestrial Photovoltaic Modules and Arrays Using **Reference Cells**
- E1040 Specification for Physical Characteristics of Nonconcentrator Terrestrial Photovoltaic Reference Cells
- E1125 Test Method for Calibration of Primary Non-Concentrator Terrestrial Photovoltaic Reference Cells Using a Tabular Spectrum
- E1328 Terminology Relating to Photovoltaic Solar Energy Conversion
- E1362 Test Method for Calibration of Non-Concentrator Photovoltaic Secondary Reference Cells
- G138 Test Method for Calibration of a Spectroradiometer Using a Standard Source of Irradiance
- G173 Tables for Reference Solar Spectral Irradiances: Direct Normal and Hemispherical on 37 Tilted Surface

3. Terminology

3.1 Definitions—definitions of terms used in this standard may be found in Terminology E772 and in Terminology E1328.

3.2 Definitions of Terms Specific to This Standard:

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States

¹ These test methods are under the jurisdiction of ASTM Committee E44 on Solar, Geothermal and Other Alternative Energy Sources and is the direct responsibility of Subcommittee E44.09 on Photovoltaic Electric Power Conversion.

Current edition approved Sept.June 1, 2005.2010. Published October 2005.July 2010. Originally approved in 2002. Last previous edition approved in 2005 as E2236–05a. DOI: 10.1520/E2236-05A:10.1520/E2236-10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

E2236 – 10

3.2.1 multijunction device, n-a photovoltaic device composed of more than one photovoltaic junction stacked on top of each other and electrically connected in series.

3.2.2 component cells, n—the individual photovoltaic junctions of a multijunction device. 3.3 Symbols:

- = reference cell calibration constant under the reference spectrum, $A \cdot m^2 \cdot W^{-1}$ С
- E_o = total irradiance of reporting conditions, W·m⁻
- = source spectral irradiance, $W \cdot m^{-2} \cdot nm^{-1}$ or $W \cdot m^{-2} \cdot \mu m^{-1}$ $E_S(\lambda)$
- = reference spectral irradiance, $W \cdot m^{-2} \cdot nm^{-1}$ or $W \cdot m^{-2} \cdot \mu m^{-1}$ $E_R(\lambda)$
- FF = fill factor, dimensionless
- i = subscript index associated with an individual component cell
- I_o = current of test device under the reference spectrum, A
- Ι = current of test device under the source spectrum, A
- I_{sc} = short-circuit current, A
- = short-circuit current of reference cell under the source spectrum, A I_R
- = spectral mismatch parameter, dimensionless М
- = number of component cells in the multijunction device п
- P_{max} maximum power, W =

quantum efficiency, dimensionless $Q(\lambda)$ =

- $R(\lambda)$ = spectral response, $A \cdot W^{-1}$
- = test device spectral response, $A \cdot W^{-1}$ $R_T(\lambda)$
- $R_R(\lambda)$ = reference cell spectral response, $A \cdot W^{-1}$
- Т = temperature, °C
- V_{oc} = open-circuit voltage, V
- V_b = voltage applied by dc bias source, V
- Ź = current balance, dimensionless
- λ = wavelength, nm or μ m

4. Significance and Use

4.1 In a series-connected multijunction PV device, the incident total and spectral irradiance determines which component cell will generate the smallest photocurrent and thus limit the current through the entire series-connected device. This current-limiting behavior also affects the fill factor of the device. Because of this, special techniques are needed to measure the correct I-V characteristics of multijunction devices under the desired reporting conditions (see Test Methods E1036).

4.2 These test methods use a numerical parameter called the current balance which is a measure of how well the test conditions replicate the desired reporting conditions. When the current balance deviates from unity by more than 0.03, the uncertainty of the measurement may be increased.

4.3 The effects of current limiting in individual component cells can cause problems for I-V curve translations to different temperature and irradiance conditions, such as the translations recommended in Test Methods E1036. For example, if a different component cell becomes the limiting cell as the irradiance is varied, a discontinuity in the current versus irradiance characteristic may be observed. For this reason, it is recommended that I-V characteristics of multijunction devices be measured at temperature and irradiance conditions close to the desired reporting conditions.

4.4 Some multijunction devices have more than two terminals which allow electrical connections to each component cell. In these cases, the special techniques for spectral response measurements are not needed because the component cells can be measured individually. However, these I-V techniques are still needed if the device is intended to be operated as a two-terminal device.

4.5 Using these test methods, the spectral response is typically measured while the individual component cell under test is illuminated at levels that are less than E_{o} . Nonlinearity of the spectral response may cause the measured results to differ from the spectral response at the illumination levels of actual use conditions.

5. Summary of Test Methods

5.1 Spectral response measurements of the device under test are accomplished using light- and voltage-biasing techniques of each component cell, followed by determination of the spectral response according to Test Methods E1021.

5.2 If a spectrally adjustable solar simulator is available (see 6.1.1) the electrical performance measurements use an iterative process of adjusting the incident spectral irradiance until the operating conditions are close to the desired reporting conditions is used. This adjustment modifies a quantity known as the current balance. The I-V characteristics are then measured according to Test Methods E948 or E1036. Appendix X1 contains a derivation and discussion of current balance.

5.3 For the case of light sources where the spectral irradiance cannot be changed, such as outdoors or if a spectrally adjustable solar simulator is not available, the I-V characteristics are measured according to Test Methods E948 or E1036. However, the current balance in each component cell must also be determined and reported.