



Standard Specification for Aluminum-Alloy Extruded Structural Pipe and Tube¹

This standard is issued under the fixed designation B429/B429M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification covers aluminum-alloy extruded structural pipe and tube in those selected alloys shown in **Table 1** and tempers shown in **Table 2**, and in those standard sizes shown in **Tables 3-5**, as well as in other nonstandard sizes as agreed upon between the purchaser and supplier. Such pipe and tube is intended for use in structural applications such as highway and bridge rails, chain-link fence posts, handrails, sign structures, awning supports, lighting brackets, etc. Structural pipe and tube is not intended for fluid-carrying applications involving pressure.

NOTE 1—For drawn seamless tube used in pressure applications see Specifications **B210** and **B210M**, for seamless pipe and seamless extruded tube used in pressure applications see Specifications **B241/B241M**, and for drawn tube and pipe for general purpose applications see Specification **B483/B483M**.

1.2 Alloy and temper designations are in accordance with ANSI **H35.1/H35.1(M)**. The equivalent Unified Numbering System alloy designations are those of **Table 1** preceded by A9, for example, A96061 for alloy 6061 in accordance with Practice **E527**.

1.3 For acceptance criteria for inclusion of new aluminum and aluminum alloys in this specification, see **Annex A2**.

1.4 **Units**—The values stated in either inch-pound units or SI units are to be regarded separately as standard. SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the specification.

1.4.1 While this standard is a combined SI and inch-pound standard, standard pipe sizes are not applicable to SI units, therefore non-rationalized SI units (soft conversions) are shown for reader convenience. Rationalized [hard converted] SI units are shown in brackets while non-rationalized (soft converted) SI units are shown in parentheses.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the*

responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

- B210 Specification for Aluminum and Aluminum-Alloy Drawn Seamless Tubes**
B210M Specification for Aluminum and Aluminum-Alloy Drawn Seamless Tubes (Metric)
B241/B241M Specification for Aluminum and Aluminum-Alloy Seamless Pipe and Seamless Extruded Tube
B483/B483M Specification for Aluminum and Aluminum-Alloy Drawn Tube and Pipe for General Purpose Applications
B557 Test Methods for Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products
B557M Test Methods for Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products (Metric)
B660 Practices for Packaging/Packing of Aluminum and Magnesium Products
B666/B666M Practice for Identification Marking of Aluminum and Magnesium Products
B807/B807M Practice for Extrusion Press Solution Heat Treatment for Aluminum Alloys
B881 Terminology Relating to Aluminum- and Magnesium-Alloy Products
B918 Practice for Heat Treatment of Wrought Aluminum Alloys
B945 Practice for Aluminum Alloy Extrusions Press Cooled from an Elevated Temperature Shaping Process for Production of T1, T2, T5 and T10-Type Tempers
E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
E34 Test Methods for Chemical Analysis of Aluminum and Aluminum-Base Alloys
E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

¹ This specification is under the jurisdiction of ASTM Committee **B07** on Light Metals and Alloys and is the direct responsibility of Subcommittee **B07.03** on Aluminum Alloy Wrought Products.

Current edition approved June 15, 2010. Published July 2010. Originally approved in 1965. Last previous edition approved in 2006 as B429 – 06. DOI: 10.1520/B0429_B0429M-10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 Chemical Composition Limits^{A,B,C,D}

| Alloy Designation | Silicon | Iron | Copper | Manganese | Magnesium | Chromium | Zinc | Titanium | Other Elements ^E | | Aluminum |
|--------------------|----------|------|-----------|-----------|-----------|-----------|------|----------|-----------------------------|--------------------|-----------|
| | | | | | | | | | Each | Total ^F | |
| 6005 | 0.6-0.9 | 0.35 | 0.10 | 0.10 | 0.40-0.6 | 0.10 | 0.10 | 0.10 | 0.05 | 0.15 | Remainder |
| 6005A ^G | 0.50-0.9 | 0.35 | 0.30 | 0.50 | 0.40-0.7 | 0.30 | 0.20 | 0.10 | 0.05 | 0.15 | Remainder |
| 6061 | 0.40-0.8 | 0.7 | 0.15-0.40 | 0.15 | 0.8-1.2 | 0.04-0.35 | 0.25 | 0.15 | 0.05 | 0.15 | remainder |
| 6063 | 0.20-0.6 | 0.35 | 0.10 | 0.10 | 0.45 | 0.10 | 0.10 | 0.10 | 0.05 | 0.15 | remainder |
| 6082 | 0.7-1.3 | 0.50 | 0.10 | 0.40-1.0 | 0.6-1.2 | 0.25 | 0.20 | 0.10 | 0.05 | 0.15 | Remainder |
| 6105 | 0.6-1.0 | 0.35 | 0.10 | 0.15 | 0.45-0.8 | 0.10 | 0.10 | 0.10 | 0.05 | 0.15 | Remainder |

^A Limits are in percent maximum unless shown as a range.^B Analysis shall be made for the elements for which limits are shown in this table.^C To determine conformance to these limits, an observed value or a calculated value obtained from analysis shall be rounded-off to the nearest unit in the last right-hand place of the figures used in expressing the specified limit, in accordance with the rounding method of Practice E29.^D In case there is a discrepancy in the values listed in Table 1 with those listed in the International Alloy Designations and Chemical Composition Limits for Wrought Aluminum and Wrought Aluminum Alloys (commonly known as the "Teal Sheets"), the composition limits registered with The Aluminum Association and published in the "Teal Sheets" should be considered the controlling composition. The "Teal Sheets" are available at <http://www.aluminum.org/tealsheets>.^E Others includes all unlisted metallic elements. The producer may analyze samples for trace elements not specified in the specification. However, such analysis is not required and may not cover all metallic Others elements. Should any analysis by the producer or the purchaser establish that an Others element exceeds the limit of Each or that the aggregate of several Others elements exceeds the limit of Total, the material shall be considered nonconforming.^F Other Elements—Total shall be the sum of unspecified metallic elements 0.010 % or more, rounded to the second decimal before determining the sum.^G 0.12-0.50 Mn+Cr

E607 Test Method for Atomic Emission Spectrometric Analysis Aluminum Alloys by the Point to Plane Technique Nitrogen Atmosphere³

E716 Practices for Sampling and Sample Preparation of Aluminum and Aluminum Alloys for Determination of Chemical Composition by Spectrochemical Analysis

E1251 Test Method for Analysis of Aluminum and Aluminum Alloys by Spark Atomic Emission Spectrometry

2.2 ANSI Standards:

H35.1/H35.1(M) Alloy and Temper Designations Systems for Aluminum⁴

H35.2 Dimensional Tolerance for Aluminum Mill Products⁵

H35.2(M) Dimensional Tolerance for Aluminum Mill Products [Metric]⁴

2.3 Military Standard:

MIL-STD-129 Marking for Shipment and Storage⁵

2.4 Federal Standard:

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)⁵

2.5 EN Standards

CEN EN 14242 Aluminum and Aluminum Alloys, Chemical Analysis, Inductively Coupled Plasma Optical Emission Spectral Analysis⁶

3. Terminology

3.1 Definitions—Refer to Terminology B881 for definitions of product terms used in this specification.

3.2 Metric Sizes—Note that while this is a combined SI and Metric Units Specification, there are no standard equivalent metric designations for Pipe. Metric sizes are converted and shown only for user convenience.

³ Withdrawn. The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from Aluminum Association, Inc., 1525 Wilson Blvd., Suite 600, Arlington, VA 22209, <http://www.aluminum.org>.

⁵ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://dodssp.daps.dla.mil>.

⁶ Available from European Committee for Standardization (CEN), 36 rue de Stassart, B-1050, Brussels, Belgium, <http://www.cenorm.be>.

4. Ordering Information

4.1 Purchase orders (Orders) for material to this specification shall include the following information:

4.1.1 This specification designation (which includes the number, the year, and the revision letter, if applicable),

4.1.2 Quantity in pieces, pounds, or feet,

4.1.3 Size and schedule number for pipe; outside diameter and wall thickness for extruded tube (see Tables 3-5), and length in feet,

4.1.4 Alloy (Section 8) and temper (Section 9),

4.2 Additionally, orders for material to this specification shall include the following information when required by the purchaser:

4.2.1 Whether inspection or witness of inspection and tests by the purchaser's representative is required prior to material shipment (Section 13),

4.2.2 Whether certification of the material by the manufacturer is required (Section 15),

4.2.3 Whether marking for identification is required and whether marking in accordance with B666/B666M is required (Section 16),

4.2.4 Whether Practices B660 applies and, if so, the levels of preservation, packaging, and packing required (Section 17), and

4.2.5 Whether heat treatment in accordance with Practice B918 is required (10.3).

5. Materials and Manufacture

5.1 The pipe or tube may be produced by extrusion through a bridge/porthole-type die or by other methods at the option of the producer, provided that the resulting products comply with the requirements in this specification.

6. Special Characteristics

6.1 Unless otherwise specified, the pipe or tube shall be supplied with square-cut ends.

7. Responsibility for Quality Assurance

7.1 Responsibility for Inspection and Tests—Unless otherwise specified in the contract or purchase order, the producer is

TABLE 2 Tensile Property Limits^{A,B,C}

| Alloy-Temper | Specified Wall Thickness, in. [mm] | Tensile Strength, min, ksi [MPa] ^D | Yield Strength, min, ksi [MPa] ^D | Elongation, min, % | | |
|----------------------------|--|---|---|---------------------------------------|-----------------------|--|
| | | | | In 2 in. or 4 × Diameter ^E | In 50 mm ^F | In 5 × Diameter (5.65 √A) ^F |
| 6005-T1 | Up thru 0.500 [Up thru 12.5] | 25.0 [170] | 15 [105] | 16 | 16 | 14 |
| 6005-T5 | Up thru 0.124 [Up thru 3.20] 0.125-1.000 [3.20-25.0] | 38.0 [260] 38.0 [260] | 35.0 [240] 35.0 [240] | 8 10 | 8 10 | 9 |
| 6005A-T1 | Up thru 0.249 [Up thru 6.30] | 25.0 [170] | 14.5 [100] | 15 | 15 | ... |
| 6005A-T5 | Up thru 0.249 [Up thru 6.30] 0.250-0.999 [6.30-25.00] | 38.0 [260] 38.0 [260] | 31.0 [215] 31.0 [215] | 7 9 | 7 9 | 8 |
| 6005A-T61 | Up thru 0.249 [Up thru 6.30] 0.250-1.000 [6.30-25.00] | 38.0 [260] 38.0 [260] | 35.0 [240] 35.0 [240] | 8 10 | 8 10 | 9 |
| 6061-0 | All | 22.0 [150] max | 16.0 [110] max | 16 | 16 | |
| 6061-T1 | Up thru 0.625 | 26.0 [180] | 14.0 [95] | 16 | 16 | |
| 6061-T4, T4510, T4511 | All | 26.0 [180] | 16.0 [110] | 16 | 16 | 14 |
| 6061-T6, T62, T6510, T6511 | Up thru 0.249 [Up thru 6.30] 0.250 and over [over 6.30] | 38.0 [260] 38.0 [260] | 35.0 [240] 35.0 [240] | 8 10 | 8 10 | 9 |
| 6063-0 | All | 19 [130] max | ... | 18 | 18 | |
| 6063-T1 | Up thru 0.500 [Up thru 12.50] 0.501-1.000 [12.50- 25.00] | 17.0 [115] 16.0 [110] | 9.0 [60] 8.0 [55] | 12 12 | 12 12 | |
| 6063-T4, T42 | Up thru 0.500 [Up thru 12.50] 0.501-1.000 [over 12.50 thru 25.00] | 19.0 [130] 18.0 [125] | 10.0 [70] 9.0 [60] | 14 14 | 14 ... | 12 12 |
| 6063-T5 | Up thru 0.500 [Up thru 12.50] 0.501-1.000 [12.50- 25.00] | 22.0 [150] 21.0[145] | 16.0 [110] 15.0 [105] | 8 | 8 | |
| 6063-T52 | Up thru 1.000 [Up thru 25.00] | 22.0 [150] 30 [205] max | 16.0 [110]- 25.0 [170] max | 8 | 8 | |
| 6063-T6, T62 | Up thru 0.124 [Up thru 3.20] 0.125-1.000 [over 3.20 thru 25.00] | 30.0 [205] 30.0 [205] | 25.0 [170] 25.0 [170] | 8 10 | 8 10 | 9 |
| 6082-T6, T6511 | 0.200-1.000 [5.00-25.00] | 45.0 [310] | 38.0 [260] | 8 | 8 | 7 |
| 6105-T1 | Up thru 0.500 [Up thru 12.50] | 25.0 [170] | 15.0 [105] | 8 | 8 | 7 |
| 6105-T5 | Up thru 0.500 [Up thru 12.50] | 38.0 [260] | 35.0 [240] | 8 | 8 | 7 |

^A To determine conformance to this specification, each value for tensile strength and for yield strength shall be rounded-off to the nearest 0.1 ksi and each value for elongation to the nearest 0.5 percent, both in accordance with the rounding-off method of Practice E29.

^B Specimens shall be tested parallel to the direction of working.

^C The basis for establishment of mechanical property limits is shown in Annex A1.

^D For explanation of the SI unit MPa, see Appendix X1.

^E Elongation of full-section and cut-out sheet-type specimens is measured in 2 in., of cut-out round specimens, in 4 × specimen diameter.

^F Elongations in 50 mm apply for tube and pipe tested in full section and for sheet-type specimens machined from material up through 12.5 mm thickness having parallel surfaces. Elongation in 5D ($5.65\sqrt{A}$) where D and A are diameter and cross-sectional area of the specimen respectively, apply to round test specimens machined from thicknesses over 12.5 mm.

responsible for the performance of all inspection and test requirements specified herein. Except as otherwise specified in the contract or order, the producer may use his own or any other suitable facilities for the performance of the inspection and test requirements specified herein, unless disapproved by the purchaser at the time the order is placed. The purchaser shall have the right to perform any of the inspections and tests set forth in this specification where such inspections are deemed necessary to ensure that material conforms to prescribed requirements.

7.2 Lot Definition—An inspection lot shall consist of an identifiable quantity of material of the same mill form, alloy,

temper, and nominal dimensions traceable to a heat-treat lot or lots, and subjected to inspection at one time.

8. Chemical Composition

8.1 Limits—The material shall conform to the chemical composition limits specified in Table 1. Conformance shall be determined by the producer by taking samples in accordance with E716 when the ingots are poured, and analyzing those samples in accordance with E607, E1251, E34 or EN 14242. At least one sample shall be taken for each group of ingots poured simultaneously from the same source of molten metal. If the producer has determined the chemical composition during

TABLE 3 *Continued*

| Nominal Pipe Size Designation | ANSI Schedule No. ^B | Outside Diameter, in. | | | Inside Diameter, in. | | | Wall Thickness, in. | | | Weight, ^C lb/ft | |
|-------------------------------|--------------------------------|-----------------------|-------|-------|----------------------|-------|-------|---------------------|-------|-------|----------------------------|------|
| | | Nom. | Min. | Max. | Nom. | Nom. | Min. | Max. ^D | Nom. | Max. | Nom. | Max. |
| 6 | 5 | 6.625 | 6.594 | 6.687 | 6.407 | 0.109 | 0.095 | 0.123 | 2.624 | ... | | |
| | 10 | 6.625 | 6.594 | 6.687 | 6.357 | 0.134 | 0.117 | 0.151 | 3.213 | ... | | |
| | 40 | 6.625 | 6.559 | 6.691 | 6.065 | 0.280 | 0.245 | ... | 6.564 | 7.089 | | |
| | 80 | 6.625 | 6.559 | 6.691 | 5.761 | 0.432 | 0.378 | ... | 9.884 | 10.67 | | |
| | 120 | 6.625 | 6.559 | 6.691 | 5.501 | 0.562 | 0.492 | ... | 12.59 | 13.60 | | |
| | 160 | 6.625 | 6.559 | 6.691 | 5.187 | 0.719 | 0.629 | ... | 15.69 | 16.94 | | |
| 8 | 5 | 8.625 | 8.594 | 8.718 | 8.407 | 0.109 | 0.095 | 0.123 | 3.429 | ... | | |
| | 10 | 8.625 | 8.594 | 8.718 | 8.329 | 0.148 | 0.130 | 0.166 | 4.635 | ... | | |
| | 20 | 8.625 | 8.539 | 8.711 | 8.125 | 0.250 | 0.219 | ... | 7.735 | 8.354 | | |
| | 30 | 8.625 | 8.539 | 8.711 | 8.071 | 0.277 | 0.242 | ... | 8.543 | 9.227 | | |
| | 40 | 8.625 | 8.539 | 8.711 | 7.981 | 0.322 | 0.282 | ... | 9.878 | 10.67 | | |
| | 60 | 8.625 | 8.539 | 8.711 | 7.813 | 0.406 | 0.355 | ... | 12.33 | 13.31 | | |
| | 80 | 8.625 | 8.539 | 8.711 | 7.625 | 0.500 | 0.438 | ... | 15.01 | 16.21 | | |
| | 100 | 8.625 | 8.539 | 8.711 | 7.437 | 0.594 | 0.520 | ... | 17.62 | 19.03 | | |
| | 120 | 8.625 | 8.539 | 8.711 | 7.187 | 0.719 | 0.629 | ... | 21.00 | 22.68 | | |
| | 140 | 8.625 | 8.539 | 8.711 | 7.001 | 0.812 | 0.710 | ... | 23.44 | 25.31 | | |
| 10 | 160 | 8.625 | 8.539 | 8.711 | 6.813 | 0.906 | 0.793 | ... | 25.84 | 27.90 | | |

^A Soft Metric size conversions shown for reader convenience only. Metric sizes do not exist for standard schedule Pipe.

^B Schedule 40 is also designated as "standard pipe."

^C Based on the 6005A, 6061, 6082 alloy densities of 0.098 lb/in.³ (U.S. Customary) and 2.70 kg/m³, (Metric). For alloys 6063, 6005, and 6105 multiply by 0.99 and for alloy 3003 multiply by 1.011.

^D For Schedule 40, maximum wall thickness is controlled by weight tolerance.

[https://standards.niem.acatalog/standards/sis/22642c97-935c-4ab6-a816-4b6b3004f8fa/astm-b429-b429m-10](https://standards.niem.acatalog/standards/sis/22642c97-935c-4ab6-a816-4b6b3004f8fa ASTM B429/B429M-10)

pouring of the ingots, they shall not be required to sample and analyze the finished product.

8.2 Methods of Sampling—If it becomes necessary to analyze pipe or tube for conformance to chemical composition limits, the method used to sample pipe or tube for the determination of chemical composition shall be by agreement between the producer and the purchaser. Analysis shall be performed in accordance with E716, E607, E1251, E34 or EN 14242 (ICP method). The number of samples taken for determination of chemical composition shall be as follows:

8.2.1 When samples are taken from pipe or tube, a sample shall be taken to represent each 4000 lb [2000 kg] or fraction thereof of material in the shipment, except that not more than one sample shall be required per piece.

8.3 Other methods of analysis or in the case of dispute may be by agreement between the producer and the purchaser.

NOTE 2—It is standard practice in the United States aluminum industry to determine conformance to the chemical composition limits prior to further processing of ingots into wrought products. Due to the continuous nature of the process, it is not practical to keep a specific ingot analysis identified with a specific quantity of finished material.

NOTE 3—It is difficult to obtain a reliable analysis of each of the components of clad materials using material in its finished state. A

reasonably accurate determination of the core composition can be made if the cladding is substantially removed prior to analysis. The cladding composition is more difficult to determine because of the relatively thin layer and because of diffusion of core elements to the cladding. The correctness of cladding alloy used can usually be verified by a combination of metallographic examination and spectrochemical analysis of the surface at several widely separated points.

9. Tensile Properties

9.1 Limits—The material shall conform to the tensile property requirements specified in **Table 2**.

9.2 Number of Specimens:

9.2.1 For material having a nominal weight of less than 1 lb/linear ft [1.60 kg/linear m] one tension test specimen shall be taken for each 1000 lb [454 kg] or fraction thereof in the lot.

9.2.2 For material having a nominal weight of 1 lb or more/linear ft, one tension test specimen shall be taken for each 1000 ft [305 m] or fraction thereof in the lot.

9.2.3 Other procedures for selecting samples may be employed if agreed upon by the producer and the purchaser.

9.3 Test Specimens—Geometry of test specimens and the location in the product from which they are taken shall be as specified in Test Methods **B557** and **B557M**.


B429/B429M – 10
TABLE 4 Standard Structural Pipe Diameters, Wall Thicknesses, Weights,^A Metric SI Units

| Nominal Pipe Size Designation | ANSI Schedule No. ^B | Outside Diameter, mm | | Inside Diameter, mm | | Wall Thickness, mm | | Mass ^C Per Metre g | | |
|-------------------------------------|-----------------------------------|----------------------------|--------|---------------------------|-------|--------------------------|------|-------------------------------------|------|------|
| | | Nom. | Min. | Max. | Nom. | Nom. | Min. | Max. ^D | Nom. | |
| $\frac{1}{8}$ | 40 | 10.30 | 9.50 | 10.70 | 6.84 | 1.73 | 1.51 | ... | 0.13 | 0.14 |
| | 80 | 10.30 | 9.50 | 10.70 | 5.48 | 2.41 | 2.11 | ... | 0.16 | 0.17 |
| $\frac{1}{4}$ | 40 | 13.70 | 12.90 | 14.10 | 9.22 | 2.24 | 1.96 | ... | 0.22 | 0.24 |
| | 80 | 13.70 | 12.90 | 14.10 | 7.66 | 3.02 | 2.64 | ... | 0.27 | 0.29 |
| $\frac{3}{8}$ | 40 | 17.10 | 16.30 | 17.50 | 12.48 | 2.31 | 2.02 | ... | 0.29 | 0.31 |
| | 80 | 17.10 | 16.30 | 17.50 | 10.70 | 3.20 | 2.80 | ... | 0.38 | 0.41 |
| $\frac{1}{2}$ | 40 | 21.30 | 20.50 | 21.70 | 15.76 | 2.77 | 2.42 | ... | 0.44 | 0.48 |
| | 80 | 21.30 | 20.50 | 21.70 | 13.84 | 3.73 | 3.26 | ... | 0.56 | 0.60 |
| $\frac{3}{4}$ | 160 | 21.30 | 20.50 | 21.70 | 11.74 | 4.78 | 4.18 | ... | 0.67 | 0.72 |
| | 40 | 26.70 | 25.90 | 27.10 | 20.96 | 2.87 | 2.51 | ... | 0.58 | 0.63 |
| | 80 | 26.70 | 25.90 | 27.10 | 18.88 | 3.91 | 3.42 | ... | 0.76 | 0.82 |
| | 160 | 26.70 | 25.90 | 27.10 | 15.58 | 5.56 | 4.86 | ... | 1.00 | 1.08 |
| 1 | 40 | 33.40 | 32.60 | 33.80 | 26.64 | 3.38 | 2.96 | ... | 0.86 | 0.93 |
| | 80 | 33.40 | 32.60 | 33.80 | 24.30 | 4.55 | 3.98 | ... | 1.11 | 1.20 |
| | 160 | 33.40 | 32.60 | 33.80 | 20.70 | 6.35 | 5.56 | ... | 1.46 | 1.58 |
| $1\frac{1}{4}$ | 40 | 42.20 | 41.40 | 42.60 | 35.08 | 3.56 | 3.12 | ... | 1.17 | 1.26 |
| | 80 | 42.20 | 41.40 | 42.60 | 32.50 | 4.85 | 4.24 | ... | 1.54 | 1.66 |
| | 160 | 42.20 | 41.40 | 42.60 | 29.50 | 6.35 | 5.56 | ... | 1.93 | 2.08 |
| $1\frac{1}{2}$ | 40 | 48.30 | 47.50 | 48.70 | 40.94 | 3.68 | 3.22 | ... | 1.39 | 1.50 |
| | 80 | 48.30 | 47.50 | 48.70 | 38.14 | 5.08 | 4.44 | ... | 1.86 | 2.01 |
| | 160 | 48.30 | 47.50 | 48.70 | 34.02 | 7.14 | 6.25 | ... | 2.49 | 2.69 |
| 2 | 40 | 60.30 | 59.70 | 60.90 | 52.48 | 3.91 | 3.42 | ... | 1.87 | 2.02 |
| | 80 | 60.30 | 59.70 | 60.90 | 49.22 | 5.54 | 4.85 | ... | 2.57 | 2.78 |
| | 160 | 60.30 | 59.70 | 60.90 | 42.82 | 8.74 | 7.65 | ... | 3.82 | 4.13 |
| $2\frac{1}{2}$ | 40 | 73.00 | 72.30 | 73.70 | 62.68 | 5.16 | 4.52 | ... | 2.97 | 3.21 |
| | 80 | 73.00 | 72.30 | 73.70 | 58.98 | 7.01 | 6.13 | ... | 3.92 | 4.23 |
| | 160 | 73.00 | 72.30 | 73.70 | 53.94 | 9.53 | 8.34 | ... | 5.13 | 5.54 |
| 3 | 40 | 88.90 | 88.00 | 89.80 | 77.92 | 5.49 | 4.80 | ... | 3.88 | 4.19 |
| | 80 | 88.90 | 88.00 | 89.80 | 73.66 | 7.62 | 6.67 | ... | 5.25 | 5.67 |
| | 160 | 88.90 | 88.00 | 89.80 | 66.64 | 11.13 | 9.74 | ... | 7.34 | 7.93 |
| $3\frac{1}{2}$ | 40 | 101.60 | 100.60 | 102.60 | 90.12 | 5.74 | 5.02 | ... | 4.67 | 5.04 |
| | 80 | 101.60 | 100.60 | 102.60 | 85.44 | 8.08 | 7.07 | ... | 6.41 | 6.92 |

| Nominal Pipe Size Designation | ANSI Schedule No. ^B | Outside Diameter, mm | | Inside Diameter, mm | | Wall Thickness, mm | | Mass ^C Per Metre g | | |
|-------------------------------------|-----------------------------------|----------------------------|-------------------|---------------------------|--------|--------------------------|-------|-------------------------------------|-------|-------|
| | | Nom. | Min. ^E | Max. ^E | Nom. | Nom. | Min. | Max. ^D | Nom. | |
| 4 | 40 | 114.30 | 113.20 | 115.40 | 102.26 | 6.02 | 5.27 | ... | 5.53 | 5.97 |
| | 80 | 114.30 | 113.20 | 115.40 | 97.18 | 8.56 | 7.49 | ... | 7.68 | 8.29 |
| | 120 | 114.30 | 113.20 | 115.40 | 92.04 | 11.13 | 9.74 | ... | 9.74 | 10.53 |
| | 160 | 114.30 | 113.20 | 115.40 | 87.32 | 13.49 | 11.80 | ... | 11.54 | 12.45 |
| 5 | 40 | 141.30 | 139.90 | 142.70 | 128.20 | 6.55 | 5.73 | ... | 7.49 | 8.09 |
| | 80 | 141.30 | 139.90 | 142.70 | 122.24 | 9.53 | 8.34 | ... | 10.65 | 11.50 |
| | 120 | 141.30 | 139.90 | 142.70 | 115.90 | 12.70 | 11.11 | ... | 13.85 | 14.96 |
| | 160 | 141.30 | 139.90 | 142.70 | 109.54 | 15.88 | 13.90 | ... | 16.89 | 18.24 |
| 6 | 40 | 168.30 | 166.60 | 170.00 | 154.08 | 7.11 | 6.22 | ... | 9.72 | 10.50 |
| | 80 | 168.30 | 166.60 | 170.00 | 146.36 | 10.97 | 9.60 | ... | 14.64 | 15.81 |
| | 120 | 168.30 | 166.60 | 170.00 | 139.76 | 14.27 | 12.49 | ... | 18.64 | 20.13 |
| | 160 | 168.30 | 166.60 | 170.00 | 131.78 | 18.26 | 15.98 | ... | 23.24 | 25.10 |
| 8 | 20 | 219.10 | 216.90 | 221.30 | 206.40 | 6.35 | 5.56 | ... | 11.46 | 12.38 |
| | 30 | 219.10 | 216.90 | 221.30 | 205.02 | 7.04 | 6.16 | ... | 12.66 | 13.67 |
| | 40 | 219.10 | 216.90 | 221.30 | 202.74 | 8.18 | 7.16 | ... | 14.63 | 15.80 |
| | 60 | 219.10 | 216.90 | 221.30 | 198.48 | 10.31 | 9.02 | ... | 18.26 | 19.72 |
| | 80 | 219.10 | 216.90 | 221.30 | 193.70 | 12.70 | 11.11 | ... | 22.23 | 24.01 |
| | 100 | 219.10 | 216.90 | 221.30 | 188.92 | 15.09 | 13.20 | ... | 26.11 | 28.21 |
| | 120 | 219.10 | 216.90 | 221.30 | 182.58 | 18.26 | 15.98 | ... | 31.11 | 33.60 |
| | 140 | 219.10 | 216.90 | 221.30 | 177.86 | 20.62 | 18.04 | ... | 34.72 | 37.50 |
| | 160 | 219.10 | 216.90 | 221.30 | 173.08 | 23.01 | 20.13 | ... | 38.27 | 41.33 |