



Designation: ~~B429/B429M-06~~ Designation: B429/B429M - 10

Standard Specification for Aluminum-Alloy Extruded Structural Pipe and Tube¹

This standard is issued under the fixed designation B429/B429M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification covers aluminum-alloy extruded structural pipe and ~~extruded tube~~ in those selected alloys shown in Table 1 and tempers shown in Table 2, and in those standard sizes shown in ~~Tables 3 and 4~~ Tables 3-5, as well as in other nonstandard sizes as agreed upon between the purchaser and supplier. Such pipe and tube is intended for use in structural applications such as highway and bridge rails, chain-link fence posts, handrails, sign structures, awning supports, lighting brackets, etc. Structural pipe and tube is not intended for fluid-carrying applications involving pressure.

NOTE 1—For drawn seamless tube used in pressure applications see Specifications B210 and B210M, for seamless pipe and seamless extruded tube used in pressure applications see Specifications B241/B241M, and for drawn tube and pipe for general purpose applications see Specification B483/B483M.

1.2 Alloy and temper designations are in accordance with ANSI H35.1/H35.1(M). The equivalent Unified Numbering System alloy designations are those of Table 1 preceded by A9, for example, A96061 for alloy 6061 in accordance with Practice E527.

1.3 For acceptance criteria for inclusion of new aluminum and aluminum alloys in this specification, see Annex A2.

1.4 *Units*—The values stated in either inch-pound units or SI units are to be regarded separately as standard. SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the specification.

1.4.1 While this standard is a combined SI and inch-pound standard, standard pipe sizes are not applicable to SI units, therefore non-rationalized SI units (soft conversions) are shown for reader convenience. Rationalized [hard converted] SI units are shown in brackets while non-rationalized (soft converted) SI units are shown in parentheses.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 The following documents of the date of issue in effect on date of material procurement form a part of this specification to the extent referenced herein:

2-2

2.1 ASTM Standards:²

B210 Specification for Aluminum and Aluminum-Alloy Drawn Seamless Tubes

B210M Specification for Aluminum and Aluminum-Alloy Drawn Seamless Tubes (Metric)

B241/B241M Specification for Aluminum and Aluminum-Alloy Seamless Pipe and Seamless Extruded Tube

B483/B483M Specification for Aluminum and Aluminum-Alloy Drawn Tube and Pipe for General Purpose Applications

B557 Test Methods for Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products

B557M Test Methods for Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products (Metric)

B660 Practices for Packaging/Packing of Aluminum and Magnesium Products

B666/B666M Practice for Identification Marking of Aluminum and Magnesium Products

B807/B807M Practice for Extrusion Press Solution Heat Treatment for Aluminum Alloys

B881 Terminology Relating to Aluminum- and Magnesium-Alloy Products

B918 Practice for Heat Treatment of Wrought Aluminum Alloys

¹ This specification is under the jurisdiction of ASTM Committee B07 on Light Metals and Alloys and is the direct responsibility of Subcommittee B07.03 on Aluminum Alloy Wrought Products.

Current edition approved ~~March~~ June 15, 2006; ~~2010~~. Published ~~March 2006~~ July 2010. Originally approved in 1965. Last previous edition approved in ~~2002~~ 2006 as B429 - 026. DOI: 10.1520/B0429_B0429M-106.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Chemical Composition Limits^{A,B,C,D}

Alloy Designation	Silicon	Iron	Copper	Manganese	Magnesium	Chromium	Zinc	Titanium	Other Elements ^E		Aluminum
									Each	Total ^E	
6005	0.6-0.9	0.35	0.10	0.10	0.40-0.6	0.10	0.10	0.10	0.05	0.15	Remainder
6005A ^G	0.50-0.9	0.35	0.30	0.50	0.40-0.7	0.30	0.20	0.10	0.05	0.15	Remainder
6061	0.40-0.8	0.7	0.15-0.40	0.15	0.8-1.2	0.04-0.35	0.25	0.15	0.05	0.15	Remainder
6063	0.20-0.6	0.35	0.10	0.10	0.45-0.9	0.10	0.10	0.10	0.05	0.15	Remainder
6063	0.20-0.6	0.35	0.10	0.10	0.45	0.10	0.10	0.10	0.05	0.15	Remainder
6082	0.7-1.3	0.50	0.10	0.40-1.0	0.6-1.2	0.25	0.20	0.10	0.05	0.15	Remainder
6105	0.6-1.0	0.35	0.10	0.15	0.45-0.8	0.10	0.10	0.10	0.05	0.15	Remainder

^A Limits are in percent maximum unless shown as a range.

^B Analysis shall be made for the elements for which limits are shown in this table.

^C To determine conformance to these limits, an observed value or a calculated value obtained from analysis shall be rounded-off to the nearest unit in the last right-hand place of the figures used in expressing the specified limit, in accordance with the rounding method of Practice E29.

^D In case there is a discrepancy in the values listed in Table 1 with those listed in the International Alloy Designations and Chemical Composition Limits for Wrought Aluminum and Wrought Aluminum Alloys (commonly known as the "Teal Sheets", the composition limits registered with The Aluminum Association and published in the "Teal Sheets" should be considered the controlling composition. The "Teal Sheets" are available at <http://www.aluminum.org/tealsheets>.

^E *Others* includes all unlisted metallic elements. The producer may analyze samples for trace elements not specified in the specification. However, such analysis is not required and may not cover all metallic *Others* elements. Should any analysis by the producer or the purchaser establish that an *Others* element exceeds the limit of *Each* or that the aggregate of several *Others* elements exceeds the limit of *Total*, the material shall be considered nonconforming.

^E_F *Other Elements*—Total shall be the sum of unspecified metallic elements 0.010 % or more, rounded to the second decimal before determining the sum.

^G 0.12-0.50 Mn+Cr

[B945 Practice for Aluminum Alloy Extrusions Press Cooled from an Elevated Temperature Shaping Process for Production of T1, T2, T5 and T10 Type Tempers](#)

[E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#) [E34](#)

[E34 Test Methods for Chemical Analysis of Aluminum and Aluminum-Base Alloys](#) [E55 Practice for Sampling Wrought Nonferrous Metals and Alloys for Determination of Chemical Composition](#)

[E527 Practice for Numbering Metals and Alloys in the Unified Numbering System \(UNS\)](#) [E607](#)

[E607 Test Method for Atomic Emission Spectrometric Analysis Aluminum Alloys by the Point to Plane Technique Nitrogen Atmosphere](#) [E716](#)

[E716 Practices for Sampling Aluminum and Aluminum Alloys for Spectrochemical Analysis](#) [E1251](#)

[E1251 Test Method for Analysis of Aluminum and Aluminum Alloys by Atomic Emission Spectrometry](#)

2.3

2.2 *ANSI Standards:*

[H35.1/H35.1\(M\) Alloy and Temper Designations Systems for Aluminum](#)³ [H35.1\(M\) Alloy and Temper Designations Systems for Aluminum \[Metric\]](#)³

[H35.2 Dimensional Tolerance for Aluminum Mill Products](#)³ [H35.2\(M\) Dimensional Tolerance for Aluminum Mill Products \[Metric\]](#)³

[H35.2\(M\) Dimensional Tolerance for Aluminum Mill Products \[Metric\]](#)³

2.4

2.3 *Military Standard:*

[MIL-STD-129 Marking for Shipment and Storage](#)⁴

2.5

2.4 *Federal Standard:*

[Fed. Std. No. 123 Marking for Shipment \(Civil Agencies\)](#)⁴

2.5 *EN Standards*

[CEN EN 14242 Aluminum and Aluminum Alloys, Chemical Analysis, Inductively Coupled Plasma Optical Emission Spectral Analysis](#)⁵

3. Terminology

3.1 *Definitions*—Refer to Terminology B881 for definitions of product terms used in this specification.

3.2 *Metric Sizes*—Note that while this is a combined SI and Metric Units Specification, there are no standard equivalent metric designations for Pipe. Metric sizes are converted and shown only for user convenience.

4. Ordering Information

4.1 Purchase orders (Orders) for material to this specification shall include the following information:

² Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

³ Available from Aluminum Association, Inc., 1525 Wilson Blvd., Suite 600, Arlington, VA 22209, <http://www.aluminum.org>.

⁴ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://dodssp.daps.dla.mil>.

⁵ The Aluminum Association, 1525 Wilson Boulevard, Suite 600, Arlington, VA 22209.

⁵ Available from European Committee for Standardization (CEN), 36 rue de Stassart, B-1050, Brussels, Belgium, <http://www.cenorm.be>.

TABLE 2 Tensile Property Limits^{A,B,C}

Alloy-Temper	Specified Wall Thickness, in. [mm]	Tensile Strength, min, ksi [MPa] ^D	Yield Strength, min, ksi [MPa] ^D	Elongation, min, %		
				In 2 in. or 4 × Diameter ^E	In 50 mm ^F	In 5 × Diameter (5.65 √A) ^F
6005-T1	Up thru 0.500 [Up thru 12.5]	25.0 [170]	15 [105]	16	16	14
6005-T5	Up thru 0.124 [Up thru 3.20]	38.0 [260]	35.0 [240]	8	8	—
	0.125-1.000 [3.20-25.0]	38.0 [260]	35.0 [240]	10	10	9
6005A-T1	Up thru 0.249 [Up thru 6.30]	25.0 [170]	14.5 [100]	15	15	...
6005A-T5	Up thru 0.249 [Up thru 6.30]	38.0 [260]	31.0 [215]	7	7	...
	0.250-0.999 [6.30-25.00]	38.0 [260]	31.0 [215]	9	9	8
6005A-T61	Up thru 0.249 [Up thru 6.30]	38.0 [260]	35.0 [240]	8	8	...
	0.250-1.000 [6.30-25.00]	38.0 [260]	35.0 [240]	10	10	9
6061-0	All	22.0 [150] max	16.0 [110] max	16	16	—
6061-T1	Up thru 0.625	26.0 [180]	14.0 [95]	16	16	—
6061-T4, T4510, T4511	All	26.0 [180]	16.0 [110]	16	16	14
6061-T6, T62, T6510, T6511	Up thru 0.249 [thru 6.30]	38.0 [260]	35.0 [240]	8	8	...
	0.250 and over [over 6.30]	38.0 [260]	35.0 [240]	10	10	9
6061-T6, T62, T6510, T6511	Up thru 0.249 [Up thru 6.30]	38.0 [260]	35.0 [240]	8	8	...
	0.250 and over [over 6.30]	38.0 [260]	35.0 [240]	10	10	9
6063-0	All	19 [130] max	...	18	18	—
6063-T1	Up thru 0.500 [Up thru 12.50]	17.0 [115]	9.0 [60]	12	12	—
	0.501-1.000 [12.50- 25.00]	16.0 [110]	8.0 [55]	12	12	—
6063-T4, T42	Up thru 0.500 [thru 12.50]	19.0 [130]	10.0 [70]	14	14	12
	0.501-1.000 [over 12.50 thru 25.00]	18.0 [125]	9.0 [60]	14	14	12
6063-T4, T42	Up thru 0.500 [Up thru 12.50]	19.0 [130]	10.0 [70]	14	14	12
	0.501-1.000 [over 12.50 thru 25.00]	18.0 [125]	9.0 [60]	14	14	12
6063-T5	Up thru 0.500 [Up thru 12.50]	22.0 [150]	16.0 [110]	8	8	—
	0.501-1.000 [12.50- 25.00]	21.0 [145]	15.0 [105]	8	8	—
6063-T52	Up thru 1.000 [Up thru 25.00]	22.0 [150]	16.0 [110]- 25.0 [170] max	8	8	—
		30 [205] max				
6063-T6, T62	Up thru 0.124 [thru 3.20]	30.0 [205]	25.0 [170]	8	8	...
	0.125-1.000 [over 3.20 thru 25.00]	30.0 [205]	25.0 [170]	10	10	9
6063-T6, T62	Up thru 0.124 [Up thru 3.20]	30.0 [205]	25.0 [170]	8	8	...
	0.125-1.000 [over 3.20 thru 25.00]	30.0 [205]	25.0 [170]	10	10	9
6082-T6, T6511	0.200-1.000 [5.00-25.00]	45.0 [310]	38.0 [260]	8	8	7
6105-T1	Up thru 0.500 [Up thru 12.50]	25.0 [170]	15.0 [105]	16	16	14
6105-T5	Up thru 0.500 [Up thru 12.50]	38.0 [260]	35.0 [240]	8	8	7

^A To determine conformance to this specification, each value for tensile strength and for yield strength shall be rounded-off to the nearest 0.1 ksi and each value for elongation to the nearest 0.5 percent, both in accordance with the rounding-off method of Practice E29.

^B Specimens shall be tested parallel to the direction of working.

^C The basis for establishment of mechanical property limits is shown in Annex A1.

^D For explanation of the SI unit MPa, see Appendix X1.

^E Elongation of full-section and cut-out sheet-type specimens is measured in 2 in., of cut-out round specimens, in 4 × specimen diameter.

^F Elongations in 50 mm apply for tube and pipe tested in full section and for sheet-type specimens machined from material up through 12.5 mm thickness having parallel surfaces. Elongation in 5D (5.65 √A) where D and A are diameter and cross-sectional area of the specimen respectively, apply to round test specimens machined from thicknesses over 12.5 mm.

4.1.1 This specification designation (which includes the number, the year, and the revision letter, if applicable),

4.1.2 Quantity in pieces, pounds, or feet,

4.1.3 Size and schedule number for pipe; outside diameter and wall thickness for extruded tube (see Tables 3 and 4 Tables 3-5), and length in feet,

4.1.4 Alloy (Section 8) and temper (Section 9),

4.2 Additionally, orders for material to this specification shall include the following information when required by the purchaser:

4.2.1 Whether inspection or witness of inspection and tests by the purchaser's representative is required prior to material shipment (Section 13),

TABLE 3 Standard Structural Pipe Diameters, Wall Thicknesses, Weights^A

Nominal Pipe Size Designation	ANSI Schedule No. ^B	Outside Diameter, in.-(mm)			Inside Diameter, in.-(mm)			Wall Thickness, in.-(mm)			Weight, ^C lb/ft (Mass per Meter, g)	
		Nominal	Min.	Max.	Nominal	Nominal	Min.	Max. ^D	Nominal	Max.		
1/8	40	0.405	0.374	0.420	0.269	0.068	0.060	...	0.085	0.091		
	80	0.405	0.374	0.420	0.215	0.095	0.083	...	0.109	0.118		
1/4	40	0.540	0.509	0.555	0.364	0.088	0.077	...	0.147	0.159		
	80	0.540	0.509	0.555	0.302	0.119	0.104	...	0.185	0.200		
3/8	40	0.675	0.644	0.690	0.493	0.091	0.080	...	0.196	0.212		
	80	0.675	0.644	0.690	0.423	0.126	0.110	...	0.256	0.276		
1/2	40	0.840	0.809	0.855	0.622	0.109	0.095	...	0.294	(-0.48)		
	40	(21.30)	(20.50)	(21.7-0)	0.622 (15.76)	0.109 (2.77)	0.095 (2.42)	...	0.294 (0.44)	...		
1/2	5	0.840	0.809	0.855	0.710	0.065	0.053	0.077	0.186	...		
	10	0.840	0.809	0.855	0.674	0.083	0.071	0.095	0.232	...		
	40	0.840	0.809	0.855	0.622	0.109	0.095	...	0.294	0.318		
	80	0.840	0.809	0.855	0.546	0.147	0.129	...	0.376	0.406		
	160	0.840	0.809	0.855	0.464	0.188	0.164	...	0.453	0.489		
3/4	40	1.050	1.019	1.065	0.824	0.083	0.071	...	0.297	...		
	40	(26.70)	(25.90)	(27.10)	(22.4)	(2.11)	(1.80)	0.095	(7.54)	...		
3/4	40	1.050	1.019	1.065	0.824	0.113	0.099	(2.41)	0.391	0.422		
	40	(26.70)	(25.9	(27.10)	(2-0)	(2.87)	(2.5	...	(0.58)	(0.63)		
3/4	5	1.050	1.019	1.065	0.920	0.065	0.053	0.077	0.237	...		
	10	1.050	1.019	1.065	0.884	0.083	0.071	0.095	0.297	...		
	40	1.050	1.019	1.065	0.824	0.113	0.099	...	0.391	0.422		
	80	1.050	1.019	1.065	0.742	0.154	0.135	...	0.510	0.551		
	160	1.050	1.019	1.065	0.612	0.219	0.192	...	0.672	0.726		
1	40	1.315	1.284	1.330	1.097	0.109	0.095	...	0.486	...		
	40	(33.40)	(32.60)	(33.80)	(27.86)	(2.77)	(2.41)	0.123	(7.23)	...		
1	40	1.315	1.284	1.330	1.049	0.133	0.116	(3.12)	0.581	0.627		
	40	(33.40)	(32.60)	(33.80)	(26.64)	(3.38)	(2.95)	...	(0.86)	(0.93)		
1	5	1.315	1.284	1.330	1.185	0.065	0.053	0.077	0.300	...		
	10	1.315	1.284	1.330	1.097	0.109	0.095	0.123	0.486	...		
	40	1.315	1.284	1.330	1.049	0.133	0.116	...	0.581	0.627		
	80	1.315	1.284	1.330	0.957	0.179	0.157	...	0.751	0.811		
	160	1.315	1.284	1.330	0.815	0.250	0.219	...	0.984	1.062		
1 1/4	40	1.660	1.629	1.675	1.442	0.109	0.095	...	0.625	...		
	40	(42.16)	(41.38)	(42.55)	(36.6)	(2.77)	(2.41)	0.123	(9.29)	...		
1 1/4	40	1.660	1.629	1.675	1.380	0.140	0.122	(3.12)	0.786	0.849		
	40	(42.16)	(41.38)	(42.5	(35.05)	(3.56)	(3.1-0)	...	(1.17)	(1.26)		
1 1/4	5	1.660	1.629	1.675	1.530	0.065	0.053	0.077	0.383	...		
	10	1.660	1.629	1.675	1.442	0.109	0.095	0.123	0.625	...		
	40	1.660	1.629	1.675	1.380	0.140	0.122	...	0.786	0.849		
	80	1.660	1.629	1.675	1.278	0.191	0.167	...	1.037	1.120		
	160	1.660	1.629	1.675	1.160	0.250	0.219	...	1.302	1.407		
1 1/2	40	1.900	1.869	1.915	1.682	0.109	0.095	...	0.721	...		
	40	(48.26)	(47.47)	(48.64)	(42.7)	(2.77)	(2.41)	0.123	(1.07)	...		
1 1/2	40	1.900	1.869	1.915	1.610	0.145	0.127	(3.12)	0.940	1.015		
	40	(48.26)	(47.47)	(48.64)	(40.89)	(3.68)	(3.22)	...	(1.40)	(1.5-1)		
1 1/2	5	1.900	1.869	1.915	1.770	0.065	0.053	0.077	0.441	...		
	10	1.900	1.869	1.915	1.682	0.109	0.095	0.123	0.721	...		
	40	1.900	1.869	1.915	1.610	0.145	0.127	...	0.940	1.015		
	80	1.900	1.869	1.915	1.500	0.200	0.175	...	1.256	1.357		
	160	1.900	1.869	1.915	1.338	0.281	0.246	...	1.681	1.815		
2	40	2.375	2.344	2.406	2.157	0.109	0.095	...	0.913	...		
	40	(60.33)	(59.54)	(61.11)	(54.79)	(2.77)	(2.41)	0.123	(1.36)	...		
2	40	2.375	2.351	2.399	2.067	0.154	0.135	(3.12)	1.264	1.365		
	40	(60.33)	(59.7-2)	(60.93)	(52.50)	(3.91)	(3.43)	...	(1.88)	(2.00)		
2	5	2.375	2.344	2.406	2.245	0.065	0.053	0.077	0.555	...		
	10	2.375	2.344	2.406	2.157	0.109	0.095	0.123	0.913	...		
	40	2.375	2.351	2.399	2.067	0.154	0.135	...	1.264	1.365		
	80	2.375	2.351	2.399	1.939	0.218	0.191	...	1.737	1.876		
	160	2.375	2.351	2.399	1.687	0.344	0.301	...	2.581	2.788		

TABLE 3 *Continued*

Nominal Pipe Size Designation	ANSI Schedule No. ^B	Outside Diameter, in.-(mm)			Inside Diameter, in.-(mm)			Wall Thickness, in.-(mm)			Weight, ^C lb/ft (Mass per Meter, g)	
		Nominal ₁	Min. ₂	Max. ₃	Nominal ₄	Min. ₅	Max. ₆	Nominal ₇	Min. ₈	Max. ₉ ^D	Nominal ₁₀	Max. ₁₁
2½	10	2.875 (73.0)	2.844 (72.2)	2.906 (73.81)	2.635 (66.93)	0.120 (3.05)	0.105 (2.67)	0.135 (3.43)	1.221 (1.80)
	40	2.875 (73.0)	2.846 (72.29)	2.904 (73.76)	2.469 (62.71)	0.203 (5.16)	0.178 (4.52)	...	2.004 (2.96)	2.164 (3.22)
2½	5	2.875	2.844	2.906	2.709	0.083	0.071	0.095	0.856
	10	2.875	2.844	2.906	2.635	0.120	0.105	0.135	1.221
	40	2.875	2.846	2.904	2.469	0.203	0.178	...	2.004	2.164
	80	2.875	2.846	2.904	2.323	0.276	0.242	...	2.650	2.862
	160	2.875	2.846	2.904	2.125	0.375	0.328	...	3.464	3.741
3	10	3.500 (88.90)	3.469 (88.11)	3.531 (89.69)	3.260 (82.80)	0.120 (3.05)	0.105 (2.67)	0.135 (3.43)	1.498 (2.23)
	40	3.500 (88.90)	3.465 (88.00)	3.535 (89.79)	3.068 (77.9 2)	0.216 (5.49)	0.189 (4.8 0)	...	2.624 (3.90)	2.830 (4.21)
3	5	3.500	3.469	3.531	3.334	0.083	0.071	0.095	1.048
	10	3.500	3.469	3.531	3.260	0.120	0.105	0.135	1.498
	40	3.500	3.465	3.535	3.068	0.216	0.189	...	2.621	2.830
	80	3.500	3.465	3.535	2.900	0.300	0.262	...	3.547	3.830
	160	3.500	3.465	3.535	2.624	0.438	0.383	...	4.955	5.351
3½	40	4.000 (101.60)	3.960 (100.60)	4.040 (102.60)	3.548 (90.12)	0.226 (5.74)	0.198 (5.02)	...	3.151 (4.67)	3.403 (5.04)
	5	4.000	3.969	4.031	3.834	0.083	0.071	0.095	1.201
3½	10	4.000	3.969	4.031	3.760	0.120	0.105	0.135	1.720
	40	4.000	3.960	4.040	3.548	0.226	0.198	...	3.151	3.403
	80	4.000	3.960	4.040	3.364	0.318	0.278	...	4.326	4.672
	160	4.500	4.455	4.545	4.026 (102.26)	0.237 (6.02)	0.207 (5.27)	...	3.733 (5.53)	4.031 (5.598)	7.099 (8.409)	...
4	5	4.500	4.469	4.531	4.334	0.083	0.071	0.095	1.354
	10	4.500	4.469	4.531	4.260	0.120	0.105	0.135	1.942
	40	4.500	4.455	4.545	4.026	0.237	0.207	3.733	4.031
	80	4.500	4.455	4.545	3.826	0.337	0.295	...	5.183	5.598
	120	4.500	4.455	4.545	3.624	0.438	0.383	...	6.573	7.099
	160	4.500	4.455	4.545	3.438	0.531	0.465	...	7.786	8.409
5	5	5.563	5.532	5.625	5.345	0.109	0.095	0.123	2.196
	10	5.563	5.532	5.625	5.295	0.134	0.117	0.151	2.688
	40	5.563	5.507	5.619	5.047	0.258	0.226	...	5.057	5.461
	80	5.563	5.507	5.619	4.813	0.375	0.328	...	7.188	7.763
	120	5.563	5.507	5.619	4.563	0.500	0.438	...	9.353	10.10
	160	5.563	5.507	5.619	4.313	0.625	0.547	...	11.40	12.31
5	5	5.563	5.532	5.625	5.345	0.109	0.095	0.123	2.196
	10	5.563	5.532	5.625	5.295	0.134	0.117	0.151	2.688
	40	5.563	5.507	5.619	5.047	0.258	0.226	...	5.057	5.461
	80	5.563	5.507	5.619	4.813	0.375	0.328	...	7.188	7.763
	120	5.563	5.507	5.619	4.563	0.500	0.438	...	9.353	10.10
	160	5.563	5.507	5.619	4.313	0.625	0.547	...	11.40	12.31
6	5	6.625	6.594	6.687	6.407	0.109	0.095	0.123	2.624
	10	6.625	6.594	6.687	6.357	0.134	0.117	0.151	3.213
	40	6.625	6.559	6.691	6.065	0.280	0.245	...	6.564	7.089
	80	6.625	6.559	6.691	5.761	0.432	0.378	...	9.884	10.67
	120	6.625	6.559	6.691	5.501	0.562	0.492	...	12.59	13.60
	160	6.625	6.559	6.691	5.187	0.719	0.629	...	15.69	16.94
8	5	8.625	8.594	8.718	8.407	0.109	0.095	0.123	3.429
	10	8.625	8.594	8.718	8.329	0.148	0.130	0.166	4.635
	20	8.625	8.539	8.711	8.125	0.250	0.219	...	7.735	8.354
	30	8.625	8.539	8.711	8.071	0.277	0.242	...	8.543	9.227
	40	8.625	8.539	8.711	7.981	0.322	0.282	...	9.878	10.67
	60	8.625	8.539	8.711	7.813	0.406	0.355	...	12.33	13.31
	80	8.625	8.539	8.711	7.625	0.500	0.438	...	15.01	16.21
	100	8.625	8.539	8.711	7.437	0.594	0.520	...	17.62	19.03
	120	8.625	8.539	8.711	7.187	0.719	0.629	...	21.00	22.68
	140	8.625	8.539	8.711	7.001	0.812	0.710	...	23.44	25.31
	160	8.625	8.539	8.711	6.813	0.906	0.793	...	25.84	27.90

TABLE 3 *Continued*

Nominal Pipe Size Designation	ANSI Schedule No. ^B	Outside Diameter, in.-(mm)			Inside Diameter, in.-(mm)			Wall Thickness, in.-(mm)			Weight, ^C lb/ft (Mass per Meter, g)	
		Nominal	Min.	Max.	Nominal	Min.	Max. ^D	Nominal	Min.	Max.	Nominal	Max.
10	5	10.750	10.719	10.843	10.482	0.134	0.117	0.151	5.256
	10	10.750	10.719	10.843	10.420	0.165	0.144	0.186	6.453
	20	10.750	10.642	10.858	10.250	0.250	0.219	...	9.698	10.47
	30	10.750	10.642	10.858	10.136	0.307	0.269	...	11.84	12.79
	40	10.750	10.642	10.858	10.020	0.365	0.319	...	14.00	15.12
	60	10.750	10.642	10.858	9.750	0.500	0.438	...	18.93	20.45
	80	10.750	10.642	10.858	9.562	0.594	0.520	...	22.29	24.07
	100	10.750	10.642	10.858	9.312	0.719	0.629	...	26.65	28.78
12	5	12.750	12.719	12.843	12.438	0.156	0.136	0.176	7.258
	10	12.750	12.719	12.843	12.390	0.180	0.158	0.202	8.359
	20	12.750	12.622	12.878	12.250	0.250	0.219	...	11.55	12.47
	30	12.750	12.622	12.878	12.090	0.330	0.289	...	15.14	16.35
	40	12.750	12.622	12.878	11.938	0.406	0.355	...	18.52	20.00
	60	12.750	12.622	12.878	11.626	0.562	0.492	...	25.31	27.33
	80	12.750	12.622	12.878	11.374	0.688	0.602	...	30.66	33.11

^A Soft Metric size conversions shown for reader convenience only. Metric sizes do not exist for standard schedule Pipe.

^B Schedule 40 is also designated as "standard pipe."

^C Based on the 6005A, 6061, 6082 alloy densities of 0.098 lb/in.³ (U.S. Customary) and 2.70 kg/m³, (Metric). For alloys 6063, 6005, and 6105 multiply by 0.99 and for alloy 3003 multiply by 1.011.

^D For Schedule 40, maximum wall thickness is controlled by weight tolerance.

- 4.2.2 Whether certification of the material by the manufacturer is required (Section 15),
- 4.2.3 Whether marking for identification is required and whether marking in accordance with B666/B666M is required (Section 16),
- 4.2.4 Whether Practices B660 applies and, if so, the levels of preservation, packaging, and packing required (Section 17), and
- 4.2.5 Whether heat treatment in accordance with Practice B918 is required (10.210.3).

5. Materials and Manufacture

5.1 The pipe or tube may be produced by extrusion through a bridge/porthole-type die or by other methods at the option of the producer, provided that the resulting products comply with the requirements in this specification.

6. Special Characteristics

6.1 Unless otherwise specified, the pipe or tube shall be supplied with square-cut ends.

7. Responsibility for Quality Assurance

7.1 *Responsibility for Inspection and Tests*—Unless otherwise specified in the contract or purchase order, the producer is responsible for the performance of all inspection and test requirements specified herein. Except as otherwise specified in the contract or order, the producer may use his own or any other suitable facilities for the performance of the inspection and test requirements specified herein, unless disapproved by the purchaser at the time the order is placed. The purchaser shall have the right to perform any of the inspections and tests set forth in this specification where such inspections are deemed necessary to ensure that material conforms to prescribed requirements.

7.2 *Lot Definition*—An inspection lot shall consist of an identifiable quantity of material of the same mill form, alloy, temper, and nominal dimensions traceable to a heat-treat lot or lots, and subjected to inspection at one time.

8. Chemical Composition

8.1 *Limits:*

8.1.1 The material shall conform to the chemical composition limits prescribed in Table 1. The producer shall determine conformance by analyzing samples taken when the ingots are poured, or analyzing samples taken from the finished or semi-finished product. If the producer has determined the chemical composition of the material during the course of manufacture, he shall not be required to sample and analyze the finished product.

NOTE 2—It is standard practice in the North American aluminum industry to determine conformance to the chemical composition limits prior to further processing of ingots into wrought products. Due to the continuous nature of the process, it is not practical to keep a specific ingot analysis identified with a specific quantity of finished material. —The material shall conform to the chemical composition limits specified in Table 1. Conformance shall be determined by the producer by taking samples in accordance with E716 when the ingots are poured, and analyzing those samples in accordance with E607, E1251, E34 or EN 14242. At least one sample shall be taken for each group of ingots poured simultaneously from the same source of molten metal. If the producer has determined the chemical composition during pouring of the ingots, they shall not be required to sample and analyze the finished product.

8.2 *Number of Samples*—The number of samples taken for determination of chemical composition shall be as follows: