



~~Designation: D6261-98 (Reapproved 2003)~~ Designation: D6261 - 10

## Standard Specification for Extruded and Compression Molded Basic Shapes Made from Thermoplastic Polyester (TPES)<sup>1</sup>

This standard is issued under the fixed designation D6261; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### INTRODUCTION

This specification is intended to be a means of calling out mechanical grade plastic product used in the fabrication of end items or parts.

#### 1. Scope

1.1 This specification covers requirements and test methods for the material, dimensions, and workmanship, and the properties of extruded and compression molded plate, rod and tubular bar manufactured from thermoplastic polyester.

~~1.2 The properties included in this specification are those required for the compositions covered. Requirements necessary to identify particular characteristics important to specialized applications may be described by using the classification system given in Section~~

~~1.2 The properties included in this specification are those required for the compositions covered. Use the classification system given in Section 4 to describe requirements necessary to identify particular characteristics important to specialized applications.~~

1.3 This specification allows the use of recycled plastics<sup>2</sup> (see Section 4).

1.4 The values are stated in inch-pound units and are regarded as the standard in all property and dimensional tables. For reference purposes, SI units are also included in Table 1 and Table S-TPES only.

1.5 The following precautionary caveat pertains only to the test method portions sections of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

~~NOTE 1—There is no similar or equivalent ISO Standard.~~ 1—There is no known ISO equivalent to this specification.

#### 2. Referenced Documents

##### 2.1 ASTM Standards:<sup>3</sup>

D256 [Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics](#)

D618 [Practice for Conditioning Plastics for Testing](#)

D638 [Test Method for Tensile Properties of Plastics](#)

D790 [Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials](#)

D883 [Terminology Relating to Plastics](#)

D3892 [Practice for Packaging/Packing of Plastics](#)

D4507 [Specification for Thermoplastic Polyester \(TPES\) Unfilled and Reinforced Material](#)

D4000 [Classification System for Specifying Plastic Materials](#)

D5033 [Guide for Development of ASTM Standards Relating to Recycling and Use of Recycled Plastics](#)

D5927 [Classification System for Thermoplastic Polyester \(TPES\) Injection and Extrusion Materials Based on ISO Test Methods](#)

##### 2.2 ANSI Standard:

Z1.4-1993 [Sampling Procedures and Tables for Inspection by Attributes](#)<sup>4</sup>

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials. Current edition approved March 10, 2003. Published May 2003. Originally approved in 1998. Last previous edition approved in 1998 as D6261-98. DOI: 10.1520/D6261-98R03 on Plastics and is the direct responsibility of Subcommittee D20.20 on Plastic Products (Section D20.20.02).

Current edition approved June 1, 2010. Published August 2010. Originally approved in 1998. Last previous edition approved in 2003 as D6261-98(2003). DOI: 10.1520/D6261-10.

<sup>2</sup> As defined in Guide D5033.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>4</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

### 3. Terminology

#### 3.1 Definitions:

3.1.1 For definitions of other technical terms pertaining to plastics used in this specification, see Terminology D883 or Guide D5033.

#### 3.2 Definitions of Terms Specific to This Standard:

- 3.2.1 *plate, n*—flat stock ¼ in. (6.4 mm) or greater.
- 3.2.2 *recycled-plastic shape, n*—a product made from up to 100 % recycled plastic.
- 3.2.3 *rod, n*—an extruded solid cylindrical shape with a minimum diameter of ⅛ in. (3.2 mm).
- 3.2.4 *tubular bar, n*—an extruded annular shape with minimum inside diameter of ⅜ in. (9.6 mm) and minimum wall thickness of ⅓ in. (1.6 mm).

### 4. Classification and Material

4.1 Product shape and size as defined in the applicable purchase order.

4.2 This specification covers product extruded and compression molded as listed in Table S-TPES. Products included in the designations reference Specification D4507 or Specification D5927 callouts where applicable.

~~4.2.1~~ 4.2.1 Categorize the type of thermoplastic polyester shape product ~~may be categorized~~ by type, grade, and class depending on resin and filler compositions as defined in Table S-TPES.

~~4.2.2~~ 4.2.2 Use the following sections to categorize each type of thermoplastic polyester shape ~~may be categorized~~ into one of several grades as follows: grades:

4.2.2.1 *Grade 1—General Purpose*—Extruded or compression molded product made using only 100 % virgin thermoplastic polyester resin.

4.2.2.2 *Grade 2—Recycled*—Extruded or compression molded product made using any amount up to 100 % recycled thermoplastic polyester plastics.

4.3 The type, class and grade is further differentiated based on dimensional stability (elevated temperature excursion test), Table S-TPES, and dimensional requirements, Tables A and B.

#### 4.4 Property Tables:

4.4.1 Use Table S-TPES ~~may be used~~ to describe both extruded or compression molded products.

4.4.2 Use Table 1 ~~may also be used~~ to describe extruded or compression molded products not included in Table S-TPES via a cell callout that includes the applicable Table S-TPES thermoplastic polyester type and specific properties (Designations 1 through 7).

4.4.3 To facilitate the incorporation of future or special materials not covered by the Table S-TPES, the “as specified” category (00) for type, class and grade is shown in the table with the basic properties to be obtained from Table 1, as they apply.

4.4.4 *Reinforcements and Additive Materials*—A symbol (single-letter) will be used for the major reinforcement or combination, or both, along with two numbers that indicate the percentage of addition by mass with the tolerances as tabulated below. This must be included in all Table 1 callouts.

Symbol	Material	Tolerance (Based on the Total Mass)
C	Carbon and graphite fiber reinforced	± 2 %
G	Glass-reinforced < 15 % glass content > 15 % glass content	± 2 % ± 3 %
L	Lubricants (for example, PTFE, graphite and silicone)	by agreement between the supplier and the user
M	Mineral	± 2 %
R	Combinations of reinforcements or fillers, or both	± 3 % for the total reinforcement

4.5 *Callout Designation*—A one-line system shall be used to specify thermoplastic polyester materials covered by this specification. The system uses pre-defined cells to refer to specific aspects of this specification as illustrated below:

#### 4.5.1 Examples:

4.5.1.1 *Example 1*—Product made from general purpose PBT

CELL CALLOUT: S-TPES0111

S-TPES01	=	Product made from PBT in accordance with Table S-TPES
1	=	Unfilled class
1	=	General purpose grade product

4.5.1.2 *Example 2*—Product made from general purpose PET

CELL CALLOUT: S-TPES0211

S-TPES02	=	Product made from PET in accordance with Table S-TPES
1	=	Unfilled class
1	=	General purpose grade product

4.5.2 These two examples illustrate how a one-line, alpha-numeric sequence can identify the product composition, commercial parameters and physical characteristics of extruded or compression molded product. A space must be used as a separator between the specification number and the type designation. No separators are needed between type, class and grade. When special notes are to be included, such information ~~should~~shall be preceded by a comma. Special tolerances must be noted at time of order and are inserted after the grade in parentheses and preceded by a comma.

## 5. Ordering Information

5.1 All shapes covered by this specification shall be ordered using the proper callout designation (see 4.5).

## 6. Physical Property Requirements

6.1 The physical property values listed within this specification's tables are to be considered minimum specification values. Any requirement for specific test data for a given production lot ~~should~~shall be specified at the time of order. ~~Physical properties for products not yet included in Use Table S-TPES may be specified using Table 1-1 to specify physical properties for extruded or compression molded products not yet included in Table S-TPES.~~

## 7. Dimensional Requirements

7.1 The type, class and grade is differentiated based on dimensional stability (elevated temperature excursion test), as indicated in Table S-TPES.

7.2 Products shall be produced within commercial tolerances and with the lowest stress levels for machined parts as delineated in Tables A and B.

7.3 Tubular bar dimensions shall be supplied in the unfinished condition, unless otherwise specified at time of order, sufficient to finish to the nominal dimension ordered.

7.4 The maximum allowable camber or bow or both, shall be within the limits referenced in Tables A and B.

## 8. Workmanship, Finish and Appearance

8.1 *Appearance*—The resin material color is white to off-white. The product color shall be as published by the shapes manufacturer. They shall be uniform in color throughout the thickness. ~~Specific~~The specific colors and color matching shall only be as agreed to by order. Physical properties may be affected by other colors. It is possible that other colors will affect physical properties.

8.2 *Finish*—All products shall be free of blisters, wrinkles, cracks, gouges and defects that restrict commercial use of the product. Special surface finish shall be supplied only when specified in the purchase order or contract.

8.3 *Defects*—All products shall be free of voids, dirt, foreign material and embedded particles exceeding 1/32 in. (0.8 mm) maximum diameter as defined in 8.3.1.

8.3.1 The criteria for determining the internal cleanliness shall be external visual inspection. A maximum number of two internal defects per square foot of plate and one foot length of rod and tubular bar are allowed. Clusters of defects less than 1/32 in. (0.8 mm) diameter are to be counted as a single defect.

## 9. Sampling

9.1 Sampling shall be statistically adequate to satisfy the requirements of this specification as applicable (see ANSI Z1.4-1993).

9.2 For purposes of sampling, an inspection lot for examination and tests shall consist of all material of the same type, class, grade and nominal size submitted for inspection at one time.

## 10. Number of Tests

10.1 Routine lot inspection shall consist of all the criteria specified in the applicable product tables.

10.2 The criteria listed in these product tables and definitions are sufficient to establish conformity of the sheet, plate, rod or tubular bars to this specification. When the number of test specimens is not stated in the test method, ~~a single determination may be made; it is acceptable to make a single determination.~~ If more than single determinations and separate portions of the same sample are made, the results shall be averaged. The final result shall conform to the requirements prescribed in this specification.

## 11. Test Conditions

11.1 *Conditioning of Specimens*—The specification values and dimensions are based on conditioning techniques outlined in Procedure A of Practice D618.

11.2 *Standard Temperature*—The tests shall be conducted at the standard laboratory temperature of 73.4 ± 3.6°F (23 ± 2°C) and 50 ± 5 % relative humidity.