



Designation: ~~F1506-08~~ Designation: F1506 - 10

Standard Performance Specification for Flame Resistant Textile Materials for Wearing Apparel for Use by Electrical Workers Exposed to Momentary Electric Arc and Related Thermal Hazards¹

This standard is issued under the fixed designation F1506; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This performance specification covers the flame resistance of textile materials to be used for wearing apparel for use by electrical workers exposed to momentary electric arc and related thermal hazards.

NOTE 1—This performance specification does not cover coated fabrics commonly used in rainwear.

NOTE 2—At present, a bench scale arc test for laboratory use is not available. It is the intent of the committee to continue the search for an acceptable laboratory test based on either an electric arc exposure or an acceptable alternative, which will form the basis of a modification of this performance specification.

1.2 Materials used for basic protection levels are covered.

1.3 Protective properties relate to thermal exposure from momentary arc and associated exposure to open flame and radiant heat. (See Appendix X1.)

1.4 This performance specification covers wearing apparel design characteristics that relate specifically to protection from exposure to momentary electric arc and that relate to the utility of the wearing apparel.

NOTE 3—A number of other thermal test methods are under consideration and development and, when evaluated and proved effective by Committee F18, will be incorporated in either this performance specification or an appropriate alternative test method or specification.

1.5 *This standard should be used to evaluate and describe the properties of materials, products, or assemblies in response to heat and flame under controlled laboratory conditions. It should not be used to describe or appraise the fire hazard or fire risk of materials, products, or assemblies under actual fire conditions.*

1.5.1 The results of this evaluation may be used as elements of a fire-risk assessment that takes into account all of the factors that are pertinent to an assessment of the fire hazard of a particular end use.

1.6 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.7 The following precautionary caveat pertains only to the test methods portion, Section 7, of this performance specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D123 Terminology Relating to Textiles

D434 Test Method for Resistance to Slippage of Yarns in Woven Fabrics Using a Standard Seam

D1424 Test Method for Tearing Strength of Fabrics by Falling-Pendulum (Elmendorf-Type) Apparatus

D2262 Test Method for Tearing Strength of Woven Fabrics by the Tongue (Single Rip) Method (Constant-Rate-of-Traverse Tensile Testing Machine)³

D2724 Test Methods for Bonded, Fused, and Laminated Apparel Fabrics

D3786 Test Method for Bursting Strength of Textile Fabrics Diaphragm Bursting Strength Tester Method

¹ This performance specification is under the jurisdiction of ASTM Committee F18 on Electrical Protective Equipment for Workers and is the direct responsibility of Subcommittee F18.65 on Wearing Apparel.

Current edition approved May 1, 2008. Published June 2008. Originally approved in 1994. Last previous edition approved in 2002 as F1506-02a^{ε1}. DOI: 10.1520/F1506-08.

Current edition approved June 1, 2010. Published August 2010. Originally approved in 1994. Last previous edition approved in 2008 as F1506-08. DOI: 10.1520/F1506-10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D5034 Test Method for Breaking Strength and Elongation of Textile Fabrics (Grab Test)

D6413 Test Method for Flame Resistance of Textiles (Vertical Test)

F1449 Guide for Industrial Laundering of Flame, Thermal, and Arc Resistant Clothing

F1959/F1959M Test Method for Determining the Arc Rating of Materials for Clothing

2.2 AATCC Test Methods:³

Method 61 Colorfastness to Washing, Domestic and Laundering, Commercial: Accelerated

Method 132 Colorfastness to Dry-Cleaning

Method 135 Dimensional Changes Automatic Home Laundering of Woven and Knitted Fabrics

Method 158 Dimensional Changes on Drycleaning in Perchloroethylene: Machine Method

2.3 Federal Standard:⁴

Test Method 191A, 1534

3. Terminology

3.1 *Definitions*—For definitions of textile terms used in this performance specification, refer to Terminology D123.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *afterflame, n*—persistent flaming of a material after the ignition source has been removed.

3.2.1.1 *Discussion*—In arc testing, a visible flaming on or near a test specimen which persists after the arc exposure has ended. The afterflame ceases when flaming is no longer visible.

3.2.2 *afterflame time, n*—the length of time for which a material continues to flame after the ignition source has been removed.

3.2.2.1 *Discussion*—In arc testing, the length of time for which a specimen continues to exhibit a visible flaming as determined by a time display video recording of the specimen during arc testing.

3.2.3 *arc rating, n*—~~the maximum incident energy (E_T) resistance demonstrated by a material prior to breakopen or at the onset of a second-degree burn.~~—value attributed to materials that describes their performance to exposure to an electrical arc discharge.

3.2.3.1 *Discussion*—~~When the Arc Thermal Performance Value (ATPV) of the material cannot be determined due to breakopen, the arc rating is determined by measuring the Breakopen Threshold Energy (E_{BT}) according to Test Method F1959/F1959M. When the arc rating represents the Arc Thermal Performance Value, it is indicated as arc rating (ATPV); when representing the Breakopen Threshold Energy, it is indicated as arc rating (E_{BT}).~~ (should a material system exhibit a breakopen response below the ATPV value).

3.2.4 *arc thermal performance value (ATPV), n*—~~in arc testing, the incident energy on a fabric or material that results in sufficient heat transfer through the fabric or material to cause the onset of a second-degree burn based on the Stoll curve.~~, ~~the incident energy on a material or a multilayer system of materials that results in a 50 % probability that sufficient heat transfer through the tested specimen is predicted to cause the onset of a second-degree skin burn injury based on the Stoll⁵ curve, cal/cm².~~

3.2.5 *basic protection level*—the level of protection provided by flame-resistant materials that do not continue to burn after exposure to and removal of a source of ignition (see 7.6).

3.2.6 *basic protection level wearing apparel*—clothing intended for continuous wear for work activities in designated locations in which exposure to momentary electric arc and related radiant heat and open-flame sources is possible.

3.2.7 *breakopen threshold energy (E_{BT}), n*—~~in electric arc testing, the average of the five highest E_T values that did not cause specimen breakopen and did not cause sensor temperature rise to exceed the Stoll curve.~~—the incident energy on a material or material system that results in a 50 % probability of breakopen.

3.2.7.1 *Discussion*—This is the value in J/cm²(cal/cm²) determined by use of logistic regression analysis representing the energy at which breakopen of the layer occurred.

3.2.8 *design test, n*—for arc and flame resistant textile materials, one made on a sample treated as representative of an industrial product; these tests will not generally be repeated in quantity production.

3.2.8.1 *Discussion*—Perform the design test only when a new or modified textile material, that is, fabric, is used to manufacture apparel. A modification in the fabric could be, but is not limited to, any of the following: the supplier, composition, weave type, weight, or dyeing and finishing process.

3.2.9 *findings*—miscellaneous fabrics in garments such as zipper tapes, linings, pockets, waistbands, and facings.

3.2.10 *momentary electric arc*—a discharge of electricity through a gaseous media, normally characterized by a voltage drop in the immediate vicinity of the electrodes, approximately equal to the ionization potential of the gaseous media.

3.2.11 *radiant heat*—heat communicated by energy propagated through space and transmitted by electromagnetic waves.

³ Withdrawn.

³ AATCC Technical Manual, available from American Association of Textile Chemists and Colorists, PO Box 12215, Research Triangle Park, NC 27709-2215.

⁴ AATCC Technical Manual, available from American Association of Textile Chemists and Colorists, PO Box 12215, Research Triangle Park, NC 27709-2215.

⁴ Available from Standardization Documents Order Desk, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

⁶ Available from Standardization Documents Order Desk, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

⁵ Derived from: Stoll, A. M., and Chianta, M. A., "Method and Rating System for Evaluations of Thermal Protection," *Aerospace Medicine*, Vol 40, 1969, pp. 1232-1238 and Stoll, A. M., and Chianta, M. A., "Heat Transfer through Fabrics as Related to Thermal Injury," *Transactions—New York Academy of Sciences*, Vol 33(7), Nov. 1971, pp. 649-670.

3.2.12 *thermal hazard*—the heat energy sufficient to cause burn injury to human tissue subjected to a momentary electric arc.

3.2.13 *user*—the employer or entity purchasing the equipment to be utilized by workers for their protection; in the absence of such an employer or entity, the individual purchasing and utilizing the protective equipment.

4. Significance and Use

4.1 This performance specification provides performance properties for textile materials used in wearing apparel that represent initial minimum requirements for basic protection levels.

4.1.1 The performance properties have been selected based on materials in use and take into consideration durability requirements for specific apparel.

4.2 Work practices vary from user to user depending upon many factors. These may include, but are not limited to, operating system voltages, construction design, work procedure or techniques, and weather conditions. Therefore, except for the restrictions set forth in this performance specification because of design limitations, the use and maintenance of this equipment is beyond the scope of this performance specification.

4.2.1 It is common practice and the responsibility of the user of this type of protective equipment to prepare complete instructions and regulations to govern in detail the correct and safe use of such equipment.

5. Materials and Manufacture

5.1 Material tests shall be performed on textile materials as they are delivered to the clothing manufacturer.

5.1.1 Material tests may be performed on samples taken from finished garments.

5.2 Lot size for the initial (without laundering) flammability test shall be 4572 m (5000 yd) of manufactured fabric or the manufactured yardage, whichever is less. One sample of 1.0 m shall be taken from each lot.

5.3 Lot size for all other tests except design tests shall be 45 720 m (50 000 yd) or at least every three months, whichever is more frequent. One sample of 4.0 m shall be taken from each lot.

5.4 Design tests shall be run on the original and when changes are made to flame resistant textile materials, for example, fiber type, yarn type, weaving style, fabric weight, dyeing, or finishing procedure.

6. Requirements

6.1 Thread, findings, and closures used in garment construction shall not contribute to the severity of injuries to the wearer in the event of a momentary electric arc and related thermal exposure.

6.1.1 Sewing thread utilized in the construction of garments shall be made of an inherently flame-resistant fiber and shall not melt when tested at a temperature of 260°C (500°F) in accordance with Federal Test Method Standard 191A, 1534. ~~Note 4—If~~

6.1.2 When fasteners or closures, for example, zippers, snaps, or buttons, or a combination thereof, are used in a manner in which they are in contact with the skin, they can increase heat transfer and burn injury due to heat conduction or melting onto the skin. Fasteners or closures that are used in this manner should shall be covered with a layer of fabric material between the fastener or closure and the skin. The fabric material used for this purpose shall meet the requirements of this performance specification.

6.2 The properties of materials for basic protection level wearing apparel shall conform to the specifications in Table 1 ~~and~~, Table 2, ~~when evaluated in accordance with Section~~ and Table 3 when evaluated in accordance with Section 7.

NOTE 54—Physical characteristic tests and values in Section 7 and Table 1 and Table 2 are based on experience from woven and knit fabrics currently in use and may not be applicable to other fabric types.

NOTE 65—Characteristics (for example, clothing ensembles, design, and laundry maintenance) of protective garments for basic protection level wearing apparel should be guided by the information contained in Appendix X1.

6.3 Garments shall be labeled with the following information:

6.3.1 Tracking identification code system,

6.3.2 Meets requirements of Performance Specification F1506,

6.3.3 Manufacturer's name,

6.3.4 Size and other associated standard labeling,

6.3.5 Care instructions and fiber content, and

6.3.6 Arc rating (ATPV) or arc rating (E_{BT}).

6.3.6.1 When garments are made with a different number of fabric layers in different areas of the garment, the arc rating for each area shall be designated. Pockets, trim, closures, seams, labels, and heraldry shall not be considered as extra layers.

7. Test Methods

7.1 *Breaking Load*—Determine the breaking load in accordance with Test Methods D5034 (Grab test G: CRT or CRE).

7.2 *Tear Resistance*—Determine the tear resistance in accordance with Test Method D1424.

7.2.1 As an option for selected materials, Test Method D2262 may be employed. This option may be exercised upon agreement between the buyer and the seller. However, correlation between this test method and Test Method D1424 is not expected.

7.3 *Seam Slippage*—Determine the seam slippage in accordance with Test Method D434.

7.4 *Colorfastness*: