



Designation: ~~C937-02~~ Designation: C937 - 10

Standard Specification for Grout Fluidifier for Preplaced-Aggregate Concrete¹

This standard is issued under the fixed designation C937; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

- 1.1 This specification covers fluidifier for grout used for preplaced-aggregate (PA) concrete.
- 1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information purposes only.
- 1.3 The following precautionary caveat pertains only to the test method portion, Section 89, of this standard: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- C33 Specification for Concrete Aggregates
- C125 Terminology Relating to Concrete and Concrete Aggregates
- C150 Specification for Portland Cement
- C219 Terminology Relating to Hydraulic Cement
- C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
- C637 Specification for Aggregates for Radiation-Shielding Concrete
- C938 Practice for Proportioning Grout Mixtures for Preplaced-Aggregate Concrete
- C939 Test Method for Flow of Grout for Preplaced-Aggregate Concrete (Flow Cone Method)
- C940 Test Method for Expansion and Bleeding of Freshly Mixed Grouts for Preplaced-Aggregate Concrete in the Laboratory
- C941 Test Method for Water Retentivity of Grout Mixtures for Preplaced-Aggregate Concrete in the Laboratory
- C942 Test Method for Compressive Strength of Grouts for Preplaced-Aggregate Concrete in the Laboratory
- ~~C943 Practice for Making Test Cylinders and Prisms for Determining Strength and Density of Preplaced-Aggregate Concrete in the Laboratory~~
- C953 Test Method for Time of Setting of Grouts for Preplaced-Aggregate Concrete in the Laboratory

3. Ordering Information

~~3.1 The purchaser shall specify the material desired as “grout fluidifier for preplaced-aggregate concrete.” The material shall meet the requirements of this specification. Terminology~~

3.1 Definitions:

3.1.1 For definitions of terms used in this test method, refer to Terminologies C125 and C219.

4. Ordering Information

4.1 The purchaser shall specify the material desired as “grout fluidifier for preplaced-aggregate concrete.” The material shall meet the requirements of this specification.

5. Materials

~~4.1 Grout~~ 5.1 Grout ingredients shall conform to the following requirements:

5.1.1 Portland cement shall meet the requirements of Specification C150 for the type to be used.

¹ This specification is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C9.41 on Concrete for Radiation Shielding.

~~Current edition approved Dec. 10, 2002. Published February 2003. Originally approved in 1980. Last previous edition approved in 1997 as C937-97. DOI: 10.1520/C0937-02 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.41 on Hydraulic Cement Grouts.~~

Current edition approved June 15, 2010. Published July 2010. Originally approved in 1980. Last previous edition approved in 2002 as C937-02. DOI: 10.1520/C0937-10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Expansion Limits

Alkali Content of Cement, % Expressed as Na ₂ O	Expansion Limits, %
0.80 or more	7 to 14
0.40 to 0.79	5 to 12
0.39 or less	3 to 9

45.1.2 Pozzolan shall meet the requirements of Specification C618.

45.1.3 Fine aggregate shall meet the requirements of Specification C33 except that grading shall conform to Specification C637, Table number 2, Grading 1 for Fine Aggregate.

5:

6. *Physical Requirements* Physical Requirements

5.1The6.1 The fluidifier, when tested in grout as specified herein, shall conform to the following requirements:

Reduction in mixing water, min, % of control (Test Method C941)	3
Expansion, 3 h after mixing, (Test Method C940)	See Table 1
Bleeding, 3 h after mixing, (Test Method C940), max, %	2
Increase in water retentivity (Test Method C941), min, % of control	60
Initial setting time, min, h (Test Method C953)	4
Final setting time, max, h (Test Method C953)	24
Compressive strength at 7 days and 28 days, (Test Method C942), min, % of control	90

6. Composition

6.1The fluidifier shall be composed of materials that will yield a product having the properties stipulated under Physical Requirements when tested in accordance with this specification.

7. Composition

7.1 The fluidifier shall be composed of materials that will yield a product having the properties stipulated under Physical Requirements when tested in accordance with this specification.

8. Sampling

7.1The8.1 The test sample of fluidifier shall have a mass of at least 225 g (½ lb) and shall be representative of the material supplied. When feasible, the test sample shall be composited from grab samples taken from not fewer than four packages selected at random.

8:

9. Test Method

8.1

9.1 *Summary of Method*—Physical properties of grout containing fluidifier are determined and compared with corresponding properties of grout made without fluidifier.

8.2

9.2 *Significance and Use*—The effects of adding fluidifier to a standard grout mixture are determined in order to evaluate its ability to reduce mixing water, prevent early stiffening, hold solid constituents in suspension, produce controlled expansion prior to initial setting, and maintain or increase compressive strength.

8.3

9.3 *Procedure:*

89.3.1 Have all grout materials including mixing water at $23.0 \pm 2.0^\circ\text{C}$ ($73.5 \pm 3.5^\circ\text{F}$) at the start of the test.

89.3.2 Maintain the laboratory and curing room at $23.0 \pm 2.0^\circ\text{C}$ ($73.5 \pm 3.5^\circ\text{F}$) at all times during testing.

8.3.39.3.3 *Grout Preparation:*

89.3.3.1 Proportion two grout mixtures, one a control mixture without and one a test mixture with the grout fluidifier under consideration, each containing equal parts, by weight, of cementitious material and fine aggregate, with sufficient water to produce a grout efflux time by Test Method C939 of 21 ± 2 s. The cementitious material shall consist of two parts portland cement to one part of pozzolan, by weight.

89.3.3.2 The test mixture shall contain grout fluidifier equal to 1% of the combined weight of portland cement plus pozzolan; unless otherwise recommended by the manufacturer. The control mixture shall contain no fluidifier.