

SLOVENSKI STANDARD
oSIST prEN ISO 683-17:2022
01-junij-2022

Toplotno obdelana jekla, legirana in avtomatna jekla - 17. del: Jekla za kroglične in valjčne ležaje (ISO/DIS 683-17:2022)

Heat-treated steels, alloy steels and free-cutting steels - Part 17: Ball and roller bearing steels (ISO/DIS 683-17:2022)

Für eine Wärmebehandlung bestimmte Stähle, legierte Stähle und Automatenstähle - Teil 17: Wälzlagerstähle (ISO/DIS 683-17:2022)

Aciers pour traitement thermique, aciers alliés et aciers pour décolletage - Partie 17: Aciers pour roulements (ISO/DIS 683-17:2022)

Ta slovenski standard je istoveten z: prEN ISO 683-17

<https://standards.iteh.ai/catalog/standards/sist/92db0187-91ed-459e-b557-4b52fe03dc28/osist-pren-iso-683-17-2022>

ICS:

21.100.20	Kotalni ležaji	Rolling bearings
77.140.10	Jekla za toplotno obdelavo	Heat-treatable steels
77.140.20	Visokokakovostna jekla	Stainless steels

oSIST prEN ISO 683-17:2022

en,fr,de

**iTeh STANDARD
PREVIEW
(standards.iteh.ai)**

[oSIST prEN ISO 683-17:2022](https://standards.iteh.ai/catalog/standards/sist/92db0187-91ed-459e-b557-4b52fe03dc28/osist-pren-iso-683-17-2022)

<https://standards.iteh.ai/catalog/standards/sist/92db0187-91ed-459e-b557-4b52fe03dc28/osist-pren-iso-683-17-2022>

DRAFT INTERNATIONAL STANDARD

ISO/DIS 683-17

ISO/TC 17/SC 4

Secretariat: DIN

Voting begins on:
2022-04-26

Voting terminates on:
2022-07-19

Heat-treatable steels, alloy steels and free-cutting steels — Part 17: Ball and roller bearing steels

Partie 17: Aciers pour roulements

ICS: 21.100.20; 77.140.10

**iTeh STANDARD
PREVIEW
(standards.iteh.ai)**

[oSIST prEN ISO 683-17:2022
https://standards.iteh.ai/catalog/standards/sist/92db0187-
91ed-459e-b557-4b52fe03dc28/osist-pren-iso-683-17-
2022](https://standards.iteh.ai/catalog/standards/sist/92db0187-91ed-459e-b557-4b52fe03dc28/osist-pren-iso-683-17-2022)

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 683-17:2022(E)

© ISO 2022

**iTeh STANDARD
PREVIEW
(standards.iteh.ai)**

[oSIST prEN ISO 683-17:2022](https://standards.iteh.ai/catalog/standards/sist/92db0187-91ed-459e-b557-4b52fe03dc28/osist-pren-iso-683-17-2022)

<https://standards.iteh.ai/catalog/standards/sist/92db0187-91ed-459e-b557-4b52fe03dc28/osist-pren-iso-683-17-2022>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	2
4 Classification and designation.....	2
4.1 Classification.....	2
4.2 Designation.....	2
5 Information to be supplied by the purchaser.....	2
5.1 Mandatory information.....	2
5.2 Options/Supplementary or special requirements.....	3
6 Manufacturing process.....	3
6.1 General.....	3
6.2 Deoxidation, vacuum degassing and hydrogen removal.....	3
6.3 Heat treatment and surface condition at delivery.....	3
6.3.1 Heat-treatment condition.....	3
6.3.2 Particular surface conditions.....	4
6.3.3 Traceability of the cast.....	4
7 Requirements.....	4
7.1 General.....	4
7.2 Chemical composition.....	4
7.3 Hardenability.....	4
7.4 Hardness.....	4
7.5 Microstructure.....	4
7.5.1 Austenitic grain size of case-hardening and induction-hardening bearing steels.....	4
7.5.2 Spheroidization and distribution of carbides.....	4
7.5.3 Structure of case-hardening steels in the condition +FP.....	5
7.6 Non-metallic inclusions.....	5
7.6.1 Microscopic inclusions.....	5
7.6.2 Macroscopic inclusions.....	5
7.7 Internal soundness.....	5
7.8 Surface quality.....	5
7.9 Shape, dimensions and tolerances.....	5
8 Inspection.....	6
8.1 Testing procedures and types of inspection documents.....	6
8.2 Frequency of testing.....	6
8.3 Specific inspection and testing.....	6
8.3.1 Verification of the hardenability and hardness.....	6
8.3.2 Inspection of the surface quality.....	6
8.3.3 Dimensional inspection.....	6
9 Test methods.....	6
9.1 Chemical analysis.....	6
9.2 Hardness and hardenability tests.....	7
9.2.1 Hardness.....	7
9.2.2 Verification of hardenability.....	7
9.2.3 Retests.....	7
10 Marking.....	7
Annex A (normative) Supplementary or special requirements.....	21
Annex B (informative) Designations of the steels given in Tables 3, 5 and 6 and of comparable grades covered in various designation systems.....	24

**iTeh STANDARD
PREVIEW
(standards.iteh.ai)**

oSIST prEN ISO 683-17:2022
<https://standards.iteh.ai/catalog/standards/sist/92db0187-91ed-459e-b557-4b52fe03dc28/osist-pren-iso-683-17-2022>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee [for Project Committee] ISO/TC 17, Steel, Subcommittee SC 4, Heat treatable and alloy steels.

This fourth edition cancels and replaces the third edition (ISO 683-17:2014), which has been technically revised.

The main changes compared to the previous edition are as follows:

- Requirements for Ca and Ti content have been added for through-hardening bearing steels;
- Requirements for O content have been added for through-hardening and induction-hardening bearing steels;
- Option for H content for premium bearing steels has been added for through-hardening, case-hardening and induction-hardening bearing steels;
- Option for verification of microscopic inclusions in Table A.1 for through-hardening bearing steels has been revised.

A list of all parts in the ISO 683 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

**iTeh STANDARD
PREVIEW
(standards.iteh.ai)**

[oSIST prEN ISO 683-17:2022](https://standards.iteh.ai/catalog/standards/sist/92db0187-91ed-459e-b557-4b52fe03dc28/osist-pren-iso-683-17-2022)

<https://standards.iteh.ai/catalog/standards/sist/92db0187-91ed-459e-b557-4b52fe03dc28/osist-pren-iso-683-17-2022>

Heat-treatable steels, alloy steels and free-cutting steels —

Part 17: Ball and roller bearing steels

1 Scope

This part of ISO 683 specifies the technical delivery requirements for five groups of wrought ball and roller bearing steels as listed in [Table 3](#), namely

- through-hardening bearing steels (steels with about 1 % C and 1 % to 2 % Cr),
- case-hardening bearing steels,
- induction-hardening bearing steels (unalloyed and alloyed),
- stainless bearing steels, and
- high-temperature bearing steels.

This part of ISO 683 applies to the products and heat-treatment conditions given in [Table 1](#) and the surface conditions given in [Table 2](#).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 377, *Steel and steel products — Location and preparation of samples and test pieces for mechanical testing*

ISO 404, *Steel and steel products — General technical delivery requirements*

ISO 642, *Steel — Hardenability test by end quenching (Jominy test)*

ISO 643, *Steels — Micrographic determination of the apparent grain size*

ISO 3763, *Wrought steels — Macroscopic methods for assessing the content of non-metallic inclusions*

ISO 3887, *Steels — Determination of the depth of decarburization*

ISO 4948-1, *Steels — Classification — Part 1: Classification of steels into unalloyed and alloy steels based on chemical composition*

ISO 4948-2, *Steels — Classification — Part 2: Classification of unalloyed and alloy steels according to main quality classes and main property or application characteristics*

ISO/TS 4949, *Steel names based on letter symbols*

ISO 4967, *Steel — Determination of content of non-metallic inclusions — Micrographic method using standard diagrams*

ISO 4969, *Steel — Etching method for macroscopic examination*

ISO/DIS 683-17:2022(E)

ISO 5949, *Tool steels and bearing steels — Micrographic method for assessing the distribution of carbides using reference photomicrographs*

ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method*

ISO 6508-1, *Metallic materials — Rockwell hardness test — Part 1: Test method*

ISO 6929, *Steel products — Vocabulary*

ISO 9443, *Surface quality classes for hot-rolled bars and wire rod*

ISO/TR 9769, *Steel and iron — Review of available methods of analysis*

ISO 10474, *Steel and steel products — Inspection documents*

ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 6929 and the following apply.

3.1 ball and roller bearing steels
steels for rings and/or rolling bodies which use balls and rollers to maintain the separation between the moving parts of the bearing

4 Classification and designation

4.1 Classification

The classification of the relevant steel grades is allocated in accordance with ISO 4948-1 and ISO 4948-2. All steel grades covered by this part of ISO 683 are special steels.

4.2 Designation

For the steel grades covered by this part of ISO 683, the steel names given in the relevant tables are allocated in accordance with ISO/TS 4949.

5 Information to be supplied by the purchaser

5.1 Mandatory information

The manufacturer shall obtain the following information from the purchaser at the time of enquiry and order:

- a) the quantity to be delivered;
- b) the designation of the products form (billets, bars, rod, wire, tubes, rings, discs, etc.);
- c) either the reference to the dimensional standard and the dimensions and tolerances selected from it (see 7.6) or the designation of any other document covering the dimensions and tolerances required for the product;
- d) a reference to this part of ISO 683, i. e. ISO 683-17;
- e) the designation of the steel grade (see Table 3);
- f) the symbol for the heat-treatment condition on delivery (see 6.3.1 and Table 1);

- g) usually designation for an inspection certificate [3.1](#) or, if required, an inspection certificate 3.2 in accordance with ISO 10474.

5.2 Options/Supplementary or special requirements

A number of options are specified in this part of ISO 683 and listed below. If the purchaser does not indicate the wish to implement any of these options, the products will be supplied in accordance with the basic specifications of this part of ISO 683 (see [5.1](#)).

- a) If another surface condition than 'hot-worked' or a special surface quality is required, the surface condition (see [Table 2](#)), and the surface quality (see [7.5](#)).
- b) Any requirement concerning the hardenability (+H) (see 7.1.3 and [Table 5](#)) and the verification of hardenability and if agreed the information about calculation of the hardenability (see [9.2.2](#)).
- c) Any supplementary requirement that shall be complied with, the symbol and, where necessary, the details of this supplementary requirement (see [Annex A](#)).

EXAMPLE 50 hot-rolled round bars according to ISO 1035-1 with nominal diameter of 50,0 mm, nominal length of 8 000 mm and with tolerance class S on diameter of $\pm 0,40$ mm and tolerance class L2 on length of +100/0 mm in accordance with ISO 1035-4 and with hot-worked surface made of steel grade ISO 683-17, 100Cr6 (see [Table 3](#)) in annealed condition to achieve spheroidized carbides (+AC), with an inspection certificate [3.1](#) in accordance with ISO 10474:

50 round bars ISO 1035-1/-4 - 50,0 S x 8 000 L2

steel grade ISO 683-17 - 100Cr6+AC

inspection certificate ISO 10474 - 3.1

ITeH STANDARD
PREVIEW
(standards.iteh.ai)

6 Manufacturing process

[oSIST prEN ISO 683-17:2022](#)

6.1 General <https://standards.iteh.ai/catalog/standards/sist/92db0187-91ed-459e-b557-4b52fe03dc28/osist-pren-iso-683-17-2022>

With the restrictions given by the requirements in [6.2](#) and [6.3](#) the manufacturing process of the steel and of the products is left to the discretions of the manufacturer.

If requested, the purchaser shall be informed about the steel making process used.

Remelting of the steel may be agreed upon at the time of enquiry and order.

6.2 Deoxidation, vacuum degassing and hydrogen removal

All steels shall be deoxidized.

Vacuum degassing and hydrogen removal treatment for premium applications is at the discretion of the manufacturer.

6.3 Heat treatment and surface condition at delivery

6.3.1 Heat-treatment condition

The products shall be delivered in one of the heat-treatment conditions given in [Table 1](#), lines 2 to 10, as agreed at the time of enquiry and order. If there is no agreement, the products shall be delivered in the untreated condition.

ISO/DIS 683-17:2022(E)

6.3.2 Particular surface conditions

If agreed upon at the time of enquiry and order, the products shall be delivered in one of the particular surface conditions given in [Table 2](#), lines 3 to 9.

6.3.3 Traceability of the cast

Each product shall be traceable to the cast, see [Clause 10](#).

7 Requirements

7.1 General

[Table 1](#) gives a survey of combinations of usual heat-treatment conditions at delivery, product forms and requirements according to [Tables 3](#) to [6](#) (chemical composition, hardenability, maximum hardness, hardness range).

In addition to this part of ISO 683, the general technical delivery requirements of ISO 404 are applicable.

7.2 Chemical composition

The chemical composition determined by cast analysis shall comply with the values in [Table 3](#).

Permissible deviations between the limiting values for cast analysis and the values for product analysis are given in [Table 4](#).

The product analysis shall be carried out when specified at the time of the enquiry and order (see [9.1](#) and [A.2](#)).

7.3 Hardenability

Where the steel is not ordered according to hardenability requirements, i.e. where the steel type designations of [Table 3](#) and not the designations given in [Table 5](#) are applied, the requirements for hardness specified in [Table 6](#) (see also [Table 1](#), column 9) apply, as appropriate, for the particular heat-treatment condition. In this case, the values of hardenability given in [Table 5](#) are for guidance purposes only.

Where the steel is ordered to hardenability requirements by using the designations given in [Table 5](#) the values of hardenability given in [Table 5](#) apply in addition to the requirements cited in [Table 1](#), column 9 (see footnote b to [Table 3](#)).

7.4 Hardness

The hardness in the usual conditions of delivery is given in [Table 6](#).

7.5 Microstructure

7.5.1 Austenitic grain size of case-hardening and induction-hardening bearing steels

Case-hardening steels and induction-hardening steels shall have a fine grain size of 5 or finer (see ISO 643). For verification of the grain size, see [A.3](#).

7.5.2 Spheroidization and distribution of carbides

7.5.2.1 For deliveries in treatment conditions +AC and +AC+C, the carbides of the through-hardening steels shall be spheroidized and the carbides of the stainless and high-temperature bearing steels