
**Cardiovascular implants and
extracorporeal systems —
Cardiovascular absorbable implants**

*Implants cardiovasculaires et systèmes extracorporels — Implants
cardiovasculaires absorbables*

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO/TS 17137:2019

<https://standards.iteh.ai/catalog/standards/iso/f6889736-66e8-4ed6-8f11-d505d591ea15/iso-ts-17137-2019>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO/TS 17137:2019

<https://standards.iteh.ai/catalog/standards/iso/f6889736-66e8-4ed6-8f11-d505d591ea15/iso-ts-17137-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	v
Introduction.....	vi
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	2
4 Device design, fabrication, packaging, and use considerations.....	2
4.1 Classification.....	2
4.2 Intended clinical performance.....	3
4.3 Intended clinical use.....	3
4.4 Materials.....	3
4.5 Packaging, labelling, and sterilization.....	4
4.5.1 Packaging.....	4
4.5.2 Labelling.....	4
4.5.3 Sterilization.....	5
4.6 Product shelf-life considerations.....	6
4.6.1 General information.....	6
4.6.2 Real-time aging.....	7
4.6.3 Accelerated aging.....	7
4.7 Risk management.....	7
4.7.1 General.....	7
4.7.2 Failure modes.....	7
4.7.3 Risk mitigation.....	8
4.7.4 Specific aspects for absorbable implants.....	8
5 Design evaluation.....	8
5.1 Evaluation overview and general considerations.....	8
5.1.1 Overview.....	8
5.1.2 General considerations.....	10
5.1.3 Summary of <i>in vitro</i> evaluation steps.....	11
5.2 <i>in vitro</i> procedural evaluation.....	12
5.2.1 Conditioning of test samples.....	12
5.2.2 Assessment of delivery and placement.....	12
5.2.3 Assessment of initial function post-deployment.....	13
5.3 <i>in vitro</i> degradation evaluation.....	13
5.3.1 General.....	13
5.3.2 Sample conditioning.....	14
5.3.3 Mechanical evaluation.....	14
5.3.4 Cyclic fatigue durability evaluation.....	15
5.3.5 Physical/chemical degradation evaluation.....	15
5.3.6 Imaging compatibility evaluation.....	17
5.4 Biological evaluation.....	17
5.4.1 General considerations.....	17
5.4.2 Sterilization considerations.....	18
5.4.3 Drug-device combination product considerations.....	18
5.5 <i>in vitro-in vivo</i> correlation.....	19
5.6 <i>in vivo</i> pre-clinical evaluation.....	19
5.6.1 Purpose.....	19
5.6.2 Specific objectives.....	20
5.6.3 Protocol.....	20
5.6.4 Data collection.....	22
5.6.5 Test report and additional information.....	22
5.7 Clinical evaluation.....	22
5.7.1 Purpose.....	22

5.7.2	Specific objectives.....	23
5.7.3	Clinical investigation plan.....	23
5.7.4	Data collection	23
5.7.5	Final report.....	24
5.7.6	Post market surveillance.....	24
Annex A (informative) Explanation on nomenclature of absorb, degrade and related terms		25
Bibliography		26

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO/TS 17137:2019](https://standards.iteh.ai/catalog/standards/iso/f6889736-66e8-4ed6-8f11-d505d591ea15/iso-ts-17137-2019)

<https://standards.iteh.ai/catalog/standards/iso/f6889736-66e8-4ed6-8f11-d505d591ea15/iso-ts-17137-2019>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 150, *Implants for surgery*, Subcommittee SC 2, *Cardiovascular implants and extracorporeal systems*.

This second edition cancels and replaces the first edition (ISO/TS 17137:2014), which has been technically revised.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Absorbable cardiovascular implants are medical devices with various clinical indications for use in the human cardiovascular blood system. An absorbable cardiovascular implant, or at least a portion thereof, is designed to intentionally degrade over time into degradation products that are absorbed by the body through metabolism, assimilation, and/or excretion (elimination). Such implants can be either surgically or interventionally introduced to the site of treatment.

This document outlines requirements for intended performance, design attributes, materials, design evaluation, manufacturing, sterilization, packaging, and information supplied by the manufacturer. This document should be considered as a supplement to ISO 14630, which specifies general requirements for the performance of non-active surgical implants. This document should also be considered as a supplement to relevant device-specific standards such as the ISO 25539 series specifying requirements for endovascular devices, which do not address degradation and other time dependent aspects of absorbable implants and coatings. Additionally, this document should be considered in conjunction with ISO 14155, which specifies proper practices in clinical investigations.

This document is not comprehensive with respect to the pharmacological evaluation of cardiovascular absorbable implants. More detailed safety and performance requirements for pharmacological agents included in the absorbable cardiovascular implant are described in ISO 12417-1.

Only issues related to degradation and absorption combined with the cardiovascular implant are covered by this document. Due to the variations in the design of implants covered by this document and in some cases due to the relatively recent development of some of these implants (e.g. absorbable stents), acceptable standardized *in vitro* tests and clinical results are not always available. As further scientific and clinical data become available, appropriate revision of this document will be necessary.

NOTE For issues related to the common mechanical function of the cardiovascular implant, the reader might find it useful to consider a number of other international standards (see Bibliography).

ISO/TS 17137:2019

<https://standards.iteh.ai/catalog/standards/iso/f6889736-66e8-4ed6-8f11-d505d591ea15/iso-ts-17137-2019>

Cardiovascular implants and extracorporeal systems — Cardiovascular absorbable implants

1 Scope

This document outlines design evaluation guidelines for absorbable cardiovascular implants used to treat vessels and/or the vascular space within the circulatory system, including the heart and all vasculature. This document is meant to supplement device-specific standards by providing guidelines specific for absorbable implants and/or components

This document is applicable to implants in direct contact with the cardiovascular system, where the intended action is upon the circulatory system. This document does not address the specific evaluation of issues associated with viable tissues, viable cells, and/or implants with non-viable biological materials and their derivatives. Additionally, procedures and devices used prior to and following the introduction of the absorbable cardiovascular implant (e.g. balloon angioplasty devices) are excluded from the scope of This document if they do not affect the absorption aspects of the implant. A cardiovascular absorbable implant may incorporate substance(s) which, if used separately, can be considered to be a medicinal product (drug product) but the action of the medicinal substance is ancillary to that of the implant and supports the primary mode of action of the implant.

NOTE 1 Some aspects of absorbable components of cardiovascular device-drug combination products (e.g. coatings) in their connection with drug-related aspects of the device are addressed in ISO 12417-1.

NOTE 2 An explanation of the nomenclature of absorb, degrade and related terms can be found in [Annex A](#) of this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5840 (all parts), *Cardiovascular implants — Cardiac valve prostheses*

ISO 10993 (all parts), *Biological evaluation of medical devices*

ISO 11135, *Sterilization of health-care products — Ethylene oxide — Requirements for the development, validation and routine control of a sterilization process for medical devices*

ISO 11137 (all parts), *Sterilization of health care products — Radiation*

ISO 11607-1, *Packaging for terminally sterilized medical devices — Part 1: Requirements for materials, sterile barrier systems and packaging systems*

ISO 12417-1, *Cardiovascular implants and extracorporeal systems — Vascular device-drug combination products — Part 1: General requirements*

ISO 14155, *Clinical investigation of medical devices for human subjects — Good clinical practice*

ISO 14630, *Non-active surgical implants — General requirements*

ISO 14937, *Sterilization of health care products — General requirements for characterization of a sterilizing agent and the development, validation and routine control of a sterilization process for medical devices*

ISO 14971, *Medical devices — Application of risk management to medical devices*

ISO 17665-1, *Sterilization of health care products — Moist heat — Part 1: Requirements for the development, validation and routine control of a sterilization process for medical devices*

ISO 25539 (all parts), *Cardiovascular implants — Endovascular devices*

ISO/TR 37137, *Cardiovascular biological evaluation of medical devices — Guidance for absorbable implants*

ASTM F640, *Standard Test Methods for Determining Radiopacity for Medical Use*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

absorb

absorption

<biomaterials> action of a non-endogenous (foreign) material or substance or its degradation products passing through or being assimilated by cells and/or tissue over time

3.2

degradation product

intermediate or final result from the physical, metabolic, and/or chemical decomposition of a material or substance

3.3

degrade

physically, metabolically, and/or chemically decompose a material or substance

3.4

leachable

substance that can be released from a medical device or material during clinical use

Note 1 to entry: In absorbable devices, leachables can be substances released from the as-manufactured product or substances generated and released as a consequence of its degradation (i.e degradation products).

4 Device design, fabrication, packaging, and use considerations

4.1 Classification

A cardiovascular absorbable implant is a product that accomplishes its intended clinical use and performance through primarily physical and/or mechanical means over a defined time period. An absorbable cardiovascular implant may also incorporate a medicinal substance. A cardiovascular absorbable implant accomplishes its intended clinical use and is then fully or partially absorbed by the body over a finite period of time. The implant's temporary nature is provided by its ability to degrade and the resulting degradation products' ability to be metabolized, assimilated, and/or excreted (eliminated) over time.

The manufacturer shall determine the acceptability of the product for clinical use at all stages of the product life cycle.

4.2 Intended clinical performance

The intended performance of an absorbable implant shall be described and documented by addressing at least the following, with particular regard to patient's safety:

- a) intended purpose(s);
- b) functional lifetime – duration of intended mechanical function;
- c) *in vivo* longevity – approximate time to full absorption of the absorbable components; absence of histological (physical) presence in tissue.

4.3 Intended clinical use

The intended clinical use shall, if applicable, be preferentially identified as one or more of the following:

- a) abdominal aorta;
- b) arterio-venous shunt for vascular access;
- c) carotid artery;
- d) coronary artery;
- e) coronary heart chambers;
- f) femoral artery;
- g) iliac artery;
- h) popliteal artery;
- i) intra-cerebral artery;
- j) renal artery;
- k) thoracic aorta;
- l) thoraco-abdominal aorta;
- m) tibial artery;
- n) heart valve;
- o) venous valve;
- p) other heart, arterial, or venous anatomy to be specified as appropriate.

4.4 Materials

The requirements of ISO 14630:2012, Clause 6, shall apply.

Additional testing appropriate to specific material types (e.g. metals, polymers, drugs) shall be performed to determine material acceptability for use in the design. For example, guidance for assessing absorbable polymeric implants can be found in ASTM F2902, with ASTM F3160 useful for absorbable metal materials testing. In a more specific example, absorbable materials dependent on shape memory properties should be subjected to testing that assesses transformation properties. For drug-eluting absorbable implants, drug identity testing shall be performed, including the identification of impurities and degradants. Electro-chemical potentials of differing metals (stents, guidewires, other accessory devices) might require additional types of testing.

4.5 Packaging, labelling, and sterilization

4.5.1 Packaging

4.5.1.1 General

The requirements of ISO 11607-1 and ISO 14630:2012, Clause 10 shall apply.

Each device shall be packaged in a unit container with a sterile barrier, or a combination of unit container and an outer container. The unit container (within its outer container if applicable) may be packaged in a shipping container during transit and storage.

The device packaging configuration should be designed to protect the implant during normal conditions of handling, storage and transport such that device specifications are maintained. The sterile barrier shall be maintained throughout its designated shelf-life to permit the contents to be presented for use in an aseptic manner.

4.5.1.2 Considerations for absorbable product

For absorbable products, non-standard packaging attributes may be needed to mitigate or eliminate the effects of environmental factors in order to maintain the physical, chemical and/or mechanical specifications of the implant. Where the absorbable product is susceptible to hydrolytic or corrosive degradation, consideration should be given toward the control and/or removal of moisture from the package interior (e.g. through the use of moisture resistant packaging materials and/or desiccants). In addition, absorbable products may also be susceptible to physical, chemical, and/or mechanical degradation under extreme temperature conditions. For example, storage of polymeric products or components at temperatures that approach or exceed a glass transition temperature could adversely affect the physical and chemical state of the implant. Therefore, storage conditions should specify the acceptable temperature range and limit the duration of packaged product exposure to elevated thermal conditions.

4.5.2 Labelling

ISO/TS 17137:2019

<https://standards.iteh.ai/catalog/standards/iso/f6889736-66e8-4ed6-8f11-d505d591ea15/iso-ts-17137-2019>

4.5.2.1 Label(s)

Each device shall be accompanied by one or more labels, one on each of the containers.

The requirements of ISO 14630:2012, Clause 11, shall apply, with the following information to be supplied as part of the label(s):

- a) name or trade name of the device;
- b) expiration date (indication of shelf-life) and the recommended storage conditions;
- c) description and/or list of the package contents;
- d) size and device type, if applicable;
- e) dimensions applicable for clinical use;
- f) sterilization method and the notification "STERILE", if applicable;
- g) a warning against the use of the device if the package's sterile barrier is damaged;
- h) a written and/or "Do not resterilize" symbol warning against re-sterilizing and/or reusing the device, if applicable;
- i) reference to consult Instructions for Use for user information;
- j) chemical nature of any storage medium in the unit container, with appropriate hazard warning.

4.5.2.2 Instructions for use (IFU)

The requirements of ISO 14630:2012, Clause 11, shall apply together with the following information to be included:

- a) name or trade name of the device;
- b) recommendations for storage; the actual modelled storage range determined to be acceptable for the packaged device, taking into consideration the absorbable properties of the implant or components thereof;
- c) statement that the device can or cannot be re-sterilized, including the statements “STERILE”, “DO NOT RESTERILIZE” in prominent form, if applicable;
- d) the statement “SINGLE USE ONLY” in prominent form;
- e) description and/or list of the package contents;
- f) available models and sizes applicable for intended clinical use;
- g) identification and description of the absorbable device or components thereof;
- h) location of the absorbable part of the device, if only a portion of the implant is absorbable;
- i) a general description of the principle of degradation along with both the expected time frame for loss of mechanical function and absorption of the implant;
- j) intended use/indications for use;
- k) contraindications, warnings and precautions;
- l) the potential for interaction of the absorbable material with other materials used in the handling, preparation and implantation of the implant, considering direct contact and the effect of procedural fluids;
- m) potential adverse events, including known adverse events associated with implant (or portion thereof) degradation and/or *in vivo* absorption process;
- n) recommended methods for the aseptic presentation and preparation of the implant considering the potential for interaction of the absorbable material with the environment or materials used;
- o) recommended methods for preparation of the implantation site if applicable;
- p) recommendations for visualization if applicable;
- q) if the implant is metallic, electrically conductive, or contains metallic or electrically conductive components, MRI safety information shall be provided, including any potential impact that an accompanying radio frequency (RF)-induced temperature rise may have on the absorbable properties of the implant or components thereof. Provided information may also include a post-implantation time period after which safety MRI precautions are no longer relevant or needed;
- r) date of or reference relating to the publication of the text, indicating if the text has been revised.

4.5.3 Sterilization

4.5.3.1 General

The sterilization requirements of ISO 14630 shall apply.

The entirety of the device and packaging shall be compatible with the chosen sterilization method. The following provides a list of typical sterilization methods and a brief description of their applicability to absorbable implants or components thereof.