



Designation: A822/A822M – 04(Reapproved 2010)

Standard Specification for Seamless Cold-Drawn Carbon Steel Tubing for Hydraulic System Service¹

This standard is issued under the fixed designation A822/A822M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers nominal wall thickness, seamless, cold-drawn carbon steel tubing intended for use in hydraulic systems and in other similar applications where forming operations require tight radius bending and flaring.

1.2 Tubing sizes and thicknesses usually furnished to this specification are $\frac{1}{8}$ to $3\frac{1}{2}$ in. [3.2 to 88.9 mm] in outside diameter and 0.035 to 0.134 in. [0.9 to 3.4 mm] inclusive, in nominal wall thickness. Tubing having other dimensions may be furnished, provided such tubing complies with all other requirements of this specification.

1.3 Mechanical property requirements do not apply to tubing smaller than $\frac{1}{8}$ in. [3.2 mm] in inside diameter or 0.015 in. [0.4 mm] in thickness.

1.4 Optional supplementary requirements are provided and, when desired, shall be so stated in the order.

1.5 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

2. Referenced Documents

2.1 ASTM Standards:²

A450/A450M Specification for General Requirements for Carbon and Low Alloy Steel Tubes

A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.09 on Carbon Steel Tubular Products.

Current edition approved April 1, 2010. Published August 2010. Originally approved in 1984. Last previous edition approved in 2004 as A822/A822M-04. DOI: 10.1520/A0822_A0822M-04R10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *lot*—for tension and hardness test requirements—the term “lot” applies to all tubes, prior to cutting, of the same nominal diameter and wall thickness which are produced from the same heat of steel. When final heat treatment is in a batch-type furnace, a lot shall include only those tubes of the same size and the same heat which are heat treated in the same furnace charge. When the final heat treatment is in a continuous furnace, a lot shall include all tubes of the same size and heat, heat treated in the same furnace at the same temperature, time at heat, and furnace speed.

4. Ordering Information

4.1 Orders for material to this specification should include the following, as required, to describe the desired material adequately:

4.1.1 Quantity (feet, metres, or number of lengths),

4.1.2 Name of material (seamless tubing),

4.1.3 Manufacture (cold-drawn),

4.1.4 Tube size (outside diameter and nominal wall thickness),

4.1.5 Length (specific or random),

4.1.6 Test report required (see Certified Test Report section in Specification A450/A450M),

4.1.7 Specification designation, and

4.1.8 End use of material.

5. General Requirements

5.1 Material furnished under this specification shall conform to the applicable requirements of the latest edition of Specification A450/A450M, unless otherwise provided herein.

6. Manufacture

6.1 Tubes shall be made by the seamless process and shall be cold drawn to size.

7. Heat Treatment

7.1 Tubes shall be heated after the final cold working operation to a temperature of at least 1200 °F [650 °C].