



Designation: D6926 – 10

# Standard Practice for Preparation of Bituminous Specimens Using Marshall Apparatus<sup>1</sup>

This standard is issued under the fixed designation D6926; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This practice covers preparation and compaction of 102 mm (4 in.) diameter by nominal 64 mm (2.5 in.) high cylindrical bituminous paving mixture specimens by means of the original manual Marshall method and subsequent variations of the method (Test Method D6927). This practice is intended for use with laboratory and plant produced bituminous mixtures with aggregate up to 25 mm (1 in.) maximum size and for recompaction of asphalt pavement samples.

1.2 There are three types of Marshall compaction apparatus in use. The following types of hammer arrangements are included in this practice:

1.2.1 Manually held hammer handle attached to a flat compaction foot through a spring loaded swivel and is hand operated (original standard developed by the Corps of Engineers).

1.2.2 Hammer handle restrained laterally (fixed) but not vertically attached to a flat compaction foot through a spring loaded swivel and is either mechanically or hand operated. There may or may not be a constant surcharge on top of the hammer handle. Mechanical hammers are available that operate at (1) nominal 55 blows per minute and (2) equal to or greater than 75 blows per minute.

1.2.3 Hammer handle restrained laterally (fixed) with constant surcharge on top of hammer, a slanted compaction foot, rotating mold base, and is mechanically operated.

1.3 Although the mass and height of mass drop for each apparatus are the same, density achieved in compacted specimens with the same number of blows will be different. It is up to the user to establish the specific required number of blows to be used for compaction of the specimen in relation to the field.

1.4 *Units*—The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.20 on Mechanical Tests of Bituminous Mixtures.

Current edition approved June 15, 2010. Published September 2010. Originally approved in 2004. Last previous edition approved in 2004 as D6926–04 DOI: 10.1520/D6926-10.

1.5 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

- D2493 Standard Viscosity-Temperature Chart for Asphalts
- D3666 Specification for Minimum Requirements for Agencies Testing and Inspecting Road and Paving Materials
- D6927 Test Method for Marshall Stability and Flow of Asphalt Mixtures
- E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

## 3. Significance and Use

3.1 Compacted bituminous mixture specimens molded by this procedure are used for various physical tests such as stability, flow, indirect tensile strength, fatigue, creep, and modulus. Density and voids analysis are also conducted on specimens for mixture design and evaluation of field compaction.


NOTE 1—Uncompacted mixtures are used for determination of theoretical maximum specific gravity.

## 4. Apparatus

4.1 *Specimen Mold Assembly*—Mold cylinders, base plates, and extension collars shall conform to the details shown in Fig. 1.

4.2 *Specimen Extractor*—The specimen extractor shall have a steel disk that will enter the mold without binding and not be less than 3.95 in. (100 mm) in diameter and ½ in. (12.5 mm) thick. The steel disk is used for extracting compacted specimens from molds with the use of the mold collar. Any suitable extraction device such as a hydraulic jack apparatus or a lever arm device may be used, provided the specimens are not deformed during the extraction process.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.



|   | in.            | (mm)             |
|---|----------------|------------------|
| A | 4.100 to 4.150 | (104.1 to 105.4) |
| B | 4.295 to 3.439 | (109.1 to 110.2) |
| C | 4.490 to 4.560 | (114.0 to 115.8) |
| D | 4.211 to 4.320 | (107.0 to 109.7) |
| E | 3.990 to 4.005 | (101.3 to 101.7) |
| F | 4.720 to 4.780 | (119.9 to 121.4) |
| G | 3.980 to 3.990 | (101.1 to 101.3) |
| H | 2.730 to 2.770 | (69.3 to 70.4)   |
| J | 0.235 to 0.285 | (7.0 to 7.2)     |
| K | 0.235 to 0.265 | (6.1 to 6.7)     |
| L | 3.420 to 3.460 | (86.9 to 87.9)   |
| M | 0.120 to 0.190 | (3.0 to 4.8)     |
| N | 0.485 to 0.585 | (12.3 to 14.9)   |

FIG. 1 Compaction Mold

4.3 Compaction Hammers:

4.3.1 Compaction Hammers with a Manually Held (Type 1) or Fixed (Type 2) Handle, either mechanically or hand operated as generally shown in Fig. 2, shall have a flat, circular compaction foot with spring loaded swivel and a 10 ± 0.02 lb (4.54 ± 0.01 kg) sliding mass with a free fall of 18 ± 0.06 in. (457.2 ± 1.5 mm) (see Fig. 2 for hammer tolerances). A typical mechanical hammer is shown in Fig. 3.


NOTE 2—Manual compaction hammers should be equipped with a finger safety guard.

4.3.2 Compaction Hammers with a Fixed Hammer Handle, surcharge on top of handle, constantly rotating base, and mechanically operated (Type 3) shall have a slanted, circular tamping face and a 10 ± 0.02 lb (4.54 ± 0.01 kg) sliding weight with a free fall of 18 ± 0.06 in. (457.2 ± 1.5 mm) (see

Fig. 2 for hammer and tamping face bevel angle and tolerances, respectively). A rotating mechanism is incorporated in the base. The base rotation rate and hammer blow rate shall be 18 to 30 rpm and 64 ± 4 blows per minute, respectively.

NOTE 3—Type 3 Marshall hammer apparatus are available in versions with more than one hammer. Multiple hammer operation will affect specimen density and is not recommended. Best comparative results will be obtained by compacting all specimens with the same hammer and with no other hammers operating.

4.4 Compaction Pedestal—The compaction pedestal shall consist of a nominal 8 by 8 in. (203.2 by 203.2 mm) wooden post approximately 18 in. (457 mm) long capped with a steel plate approximately 12 by 12 in. (304.8 by 304.8 mm) and 1 in. (25.4 mm) thick. The wooden post shall be oak, yellow pine, or other wood having an average dry density of 42 to 48



|     | Description                             |                    |                     |
|-----|---|--------------------|---------------------|
| O-P | Drop Distance                           | 456.57 - 457.84 mm | (17.975 -18.025 in) |
| Q   | Guide Bushing                           | -                  | -                   |
| R   | Guide Rod Minimum Diameter              | 15.875 mm          | (.625 in)           |
| S   | Face Diameter Hardened Impact Resistant | 100.08 - 100.58 mm | (3.950 - 3.960 in)  |
| T   | Foot Thickness                          | 11.43 - 13.97 mm   | (0.450 - 0.550 in)  |
| U   | Weight Face Diameter                    | 49.78 - 51.82 mm   | (1.960 - 2.040 in)  |
| W   | Weight Mass                             | 4.527 - 4.545 kg   | (9.98 - 10.02 lb)   |
| X   | Spring                                  | -                  | -                   |
| Z   | Finger Guard                            | 75 mm              | (2.95 in)           |

FIG. 2 Manual Compaction Hammer

lb/ft<sup>3</sup> (670 to 770 kg/m<sup>3</sup>). The wooden post shall be secured by bolts through four angle brackets to a solid concrete slab. The