
General practices for the repair of water-leakage cracks in concrete structures

*Pratiques générales pour la répartition des fissures dues à l'eau dans
les structures en béton*

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO/TR 16475:2020](https://standards.iteh.ai/catalog/standards/iso/0887a2ac-27e7-427f-9f96-d369f1f36f1a/iso-tr-16475-2020)

<https://standards.iteh.ai/catalog/standards/iso/0887a2ac-27e7-427f-9f96-d369f1f36f1a/iso-tr-16475-2020>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO/TR 16475:2020

<https://standards.iteh.ai/catalog/standards/iso/0887a2ac-27e7-427f-9f96-d369f1f36f1a/iso-tr-16475-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	2
3 Terms and definitions	2
4 Conditions of water-leakage cracks	2
4.1 Types of water-leakage cracks	2
4.2 Environmental degradation factors that cause water-leakage cracks	3
4.2.1 General	3
4.2.2 Chemical conditions	4
4.2.3 Physical (mechanical) conditions	4
5 Expected performance for repair materials	5
5.1 General	5
5.2 Expected performance for chemical conditions	5
5.2.1 Thermal stability	5
5.2.2 Chemical resistance	5
5.3 Expected performance for physical (mechanical) conditions	5
5.3.1 Water (wash out) resistance	5
5.3.2 Adhesion on wet substrate surface	5
5.3.3 Watertightness	6
5.3.4 Response to the substrate movement	6
6 Grout materials for repair	6
6.1 General	6
6.2 Acrylic grouts (water-based acrylic gel grout)	7
6.3 Cementitious grouts (water-based mixture of cement grout)	7
6.4 Epoxy resin grout	8
6.5 Polyurethane grouts	8
6.6 Synthetic rubber polymer gel grout	8
6.7 Other materials	8
7 Appropriate repair material selection procedure	9
7.1 Selection process of repair materials (injection grouts)	9
7.2 Test for performance requirements	9
7.2.1 General	9
7.2.2 Test for thermal stability	10
7.2.3 Test for chemical resistance	10
7.2.4 Test for water flow (wash out) resistance	10
7.2.5 Test for adhesion on wet substrate surface	10
7.2.6 Test for watertightness	11
7.2.7 Test for response to the substrate movement	11
8 Execution of different types of repair methods	11
8.1 General	11
8.2 Grouting injection methods	11
8.3 Injection method for reforming a waterproofing layer	12
9 Performance assessments of repaired structures	13
9.1 Inspection of repairs	13
9.2 Evaluation of repairs	13
10 Data collection (reference material)	14
Bibliography	15

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 71, *Concrete, reinforced concrete and pre-stressed concrete*, Subcommittee SC 7, *Maintenance and repair of concrete structures*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

<https://standards.iteh.ai/catalog/standards/iso/0887a2ac-27e7-427f-9f96-d369f1f36f1a/iso-tr-16475-2020>

Introduction

This document is intended to provide an informative outline of practice for the repair of water-leakage cracks of concrete structures. There are two types of cracks that can form in a concrete structure; dry cracks and water-leakage (wet) cracks. Cracks normally form when the structural element is subject to phenomena such as dry-shrinkage and formation of joints. In the typical above grade sections of the concrete structure, dry cracks are more easily controlled and repaired with a well-defined maintenance method. When cracks are formed by the effect of hydrostatic pressure and the interface of the crack is subject to constant wetness, these cracks are designated as water-leakage cracks. The ingress of water through cracks often leads to increase of humidity in the building interior and this can result in a drastically accelerated degradation of durability for the concrete structure. In extreme cases, the presence of water can generate harmful effects that cause health problems to the users, rendering the building completely uninhabitable.

In the current state, it is difficult to secure a proper repair method of water-leakage cracks because of insufficient knowledge and understanding of the degradation factors (i.e. environmental conditions, the influences of various human activities, etc.), at an institutional level. There are already a number of repair techniques and application methods that are commonly used in application, but the required conditions for properly repairing and sealing the water-leakage cracks have often been proven to be difficult. Even in some cases where the repair procedures have been followed through properly with skilled workmanship, the performance level of the repair method may be insufficient and lead to reopening of the leakage crack. This can in turn lead to increase in maintenance and labour costs and decrease in the property value of the building structures.

Past records of remedial actions for cracks and damage in concrete structures have shown varying degrees of results; some have shown failure, some have had minor success and, in some cases, an adequate solution was implemented. However, the cases of successful repair methods cannot serve as a universal model for all cases of cracks and leakage due to the diversity of environmental degradation factors existing in the construction field. In this regard, a standardized practice for selecting appropriate leakage repair materials and methods in construction sites can be used. It is highly anticipated that a newly proposed awareness and understanding of these issues will prevent further unnecessary increase in maintenance costs, expenditures and results in improved durability performance of concrete structures.

General practices for the repair of water-leakage cracks in concrete structures

1 Scope

This document provides a guideline for the selection of a proper grout material to repair water leakage through cracks and other deformities in concrete structures. The factors relevant to the quality control of maintenance and repair of water-leakage cracks are as the following;

- a) conditions of water-leakage cracks;
- b) performance requirements for repair materials;
- c) different types of repair materials (grouts);
- d) procedures followed to select the appropriate repair materials;
- e) execution of different types of repair methods;
- f) performance assessments of applied materials and methods;
- g) data collection.

This document does not include any details on the repair of dry cracks and the causes of cracks. The details on dry crack repair are covered in ISO 16311-4.

A flow chart for maintenance of water-leakage cracks is shown in [Figure 1](#).




Figure 1 — Flow chart for maintenance of water-leakage chart

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 16311-2, *Maintenance and repair of concrete structures — Part 2: Assessment of existing concrete structures*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 16311-2 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1
water-leakage crack
gap or split in a concrete substrate accompanied by intermittent or continuous contact of water present across the interface of the gap/split surface

3.2
leakage
amount or flowing state of liquid(water) that is entering into the interior of the concrete structure by means of a crack, hole, joint or other structural fault

3.3
thermal stability
ability to withstand long time exposure to elevated temperature

[SOURCE: IEC 60050:2010, 212-12-32] [ISO/TR 16475:2020](https://standards.iteh.ai/catalog/standards/iso/0887a2ac-27e7-427f-9f96-d369f1f36f1a/iso-tr-16475-2020)
<https://standards.iteh.ai/catalog/standards/iso/0887a2ac-27e7-427f-9f96-d369f1f36f1a/iso-tr-16475-2020>

3.4
washout resistance
property of the water-leakage crack (3.1) repair material related to the ability to withstand quantitative and qualitative loss of materials produced by the pressure and flow velocity of water

3.5
watertightness
repair material's waterproofing performance in consideration to its impermeability, adhesion strength to the concrete substrate surface and cohesive strength, while being subject to the influence of hydrostatic pressure

4 Conditions of water-leakage cracks

4.1 Types of water-leakage cracks

Leakage type and degree, and crack size (width) classification can be difficult as there are variances in leakage crack control methods with different repair material and methods. Leakage types can be classified as damp, seepage and flow, but specific amount of water leakage for the corresponding leakage types also varies. Optimal grout injection method and material selection through evaluation and testing can be applied for the respective classification of cracks (fine, medium and large cracks) in relation to different leakage types and degrees (damp, seepage and flow). In this document, a leakage type and degree classification system from ICRI 340.1-2006 is provided. The reference also provides an information on the possible crack size classification (crack width) that corresponds to the leakage types and degrees. This information is provided in [Table 1](#).

Table 1 — Classification of cracks in relation to repair of water-leakage (example)

Type of crack	Patterns of leakage
Non-moving crack	—
Fine cracks ≤ 2 mm ($\leq 1/13$ in) Medium cracks > 2 mm to 6 mm ($> 1/13$ in to $1/4$ in) Large cracks > 6 mm to 20 mm ($> 1/4$ in to $10/13$ in)	Damp surface
	Light seepage <1 l/min (<1/4 gal/min)
	Medium seepage >1 l/min to 5 l/min (>1/4 gal/min to 1 1/4 gal/min)
	Heavy seepage >5 l/min to 10 l/min (>1 1/4 gal/min to 2 1/2 gal/min)
	Light flow >10 l/min to 15 l/min (>2 1/2 gal/min to 4 gal/min)
	Medium flow >15 l/min to 25 l/min (>4 gal/min to 6 1/2 gal/min)
	Heavy flow >25 l/min (>6 1/2 gal/min)
NOTE 1 Each and every crack width in the left column corresponds to the leakage amount conditions specified in the right-side column.	
NOTE 2 Leakage types and degrees, and crack sizes (width) can differ in national standards.	

4.2 Environmental degradation factors that cause water-leakage cracks

4.2.1 General

Unlike dry cracks, water-leakage cracks are often caused by exposure to certain environmental-related (chemical and physical) degradation factors that are caused by nature. These factors are: temperature and humidity in the atmosphere and concrete surface, water pressure, flow velocity, chemical reactions of the water and various forms of mechanical loads (e.g. vibration caused by passing vehicles). When in the presence of one or more these environmental factors in a concrete structure, structural degradation accelerates and negatively affects performance level of repair (see [Figure 2](#)).




Figure 2 — Environmental conditions and required performance for water-leakage crack repairs

Water-leakage cracks are constantly subject to a variety of environmental degradation factors. In order to establish a proper response to degradation factors that exist in the surrounding environment, it is important to select the appropriate repair materials and methods.

Based on the types of environmental factors found in the concrete structure surroundings, the types of possible defects such as material adhesion failure, waterproofing layer delamination or material cracking can be estimated. Potential sources of degradation can be clearly identified and repair materials with the required performance level that can respond to these degradation factors is selected accordingly. Finally, the installation process can be observed and evaluated to determine that the repair material can maintain a long-term quality performance while subject to constant exposure to the given environmental degradation condition.

[Figure 2](#) categorizes the environmental degradation factors into the relevant categories and outlines the required material properties.

4.2.2 Chemical conditions

Chemical factors that affect the performance of repair materials in water-leakage cracks include temperature changes and ambient conditions of the water-leakage cracks and the chemical composition of the water (e.g. underground water, salt water, sewage water and acid rain). These factors affect thermal stability, resistance to chemical attack, watertightness and the adhesion performance of repair material on the concrete substrate surface.

4.2.3 Physical (mechanical) conditions

The physical (mechanical) factors that affect the performance of repair materials in water-leakage cracks include the movement of the concrete substrate joints or cracks, shrinkage and expansion of concrete due to temperature change, structural settlement, surrounding loads caused by passing of vehicles and hydrostatic pressure.