



Designation: C125 – 10a

Standard Terminology Relating to Concrete and Concrete Aggregates¹

This standard is issued under the fixed designation C125; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This standard is a compilation of general terminology related to hydraulic cement concrete, concrete aggregates, and other materials used in or with hydraulic cement concrete.

1.2 Other terminology under the jurisdiction of Committee C09 is included in two specialized standards. Terms relating to constituents of concrete aggregates are defined in Descriptive Nomenclature C294. Terms relating to constituents of aggregates for radiation-shielding concrete are defined in Descriptive Nomenclature C638.

1.3 Related terminology for hydraulic cement is included in Terminology C219. Additionally, the American Concrete Institute has an electronic document, *ACI Concrete Terminology*,² which is updated periodically. While this ACI Terminology is a useful resource, it shall not be referenced directly in ASTM standards because it is not a consensus document. The use of individual ACI or other definitions in ASTM standards shall be in accordance with *Form and Style*, Section E5.9, *Attributions*.

1.4 When a term is used in an ASTM standard for which Committee C09 is responsible, it is included herein only if used in more than one Committee C09 standard.

1.5 Definitions that are adopted from those published by other ASTM committees or other standards organizations are identified with the ASTM designation (for example, Terminology C219) or with the abbreviation of the name of the other organization.

1.6 A definition in this standard is a statement of the meaning of a word or word group expressed in a single sentence with additional information included in notes or discussion.

NOTE 1—The subcommittee responsible for this standard will review definitions on a five-year basis to determine if the definition is still appropriate as stated. Revisions will be made when determined necessary. The year shown in parentheses at the end of a definition indicates the year the definition or revision to the definition was approved. A letter R and a

¹ This terminology is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.91 on Terminology.

Current edition approved Aug. 1, 2010. Published September 2010. Originally approved in 1936. Last previous edition approved in 2010 as C125–10. DOI: 10.1520/C0125-10a.

² Available from American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, <http://www.terminology.concrete.org>.

year indicate when the definition was reviewed. No date indicates the term has not yet been reviewed.

2. Referenced Documents

2.1 ASTM Standards:³

- C143/C143M Test Method for Slump of Hydraulic-Cement Concrete
- C219 Terminology Relating to Hydraulic Cement
- C294 Descriptive Nomenclature for Constituents of Concrete Aggregates
- C403/C403M Test Method for Time of Setting of Concrete Mixtures by Penetration Resistance
- C494/C494M Specification for Chemical Admixtures for Concrete
- C511 Specification for Mixing Rooms, Moist Cabinets, Moist Rooms, and Water Storage Tanks Used in the Testing of Hydraulic Cements and Concretes
- C638 Descriptive Nomenclature of Constituents of Aggregates for Radiation-Shielding Concrete
- C939 Test Method for Flow of Grout for Preplaced-Aggregate Concrete (Flow Cone Method)
- C1074 Practice for Estimating Concrete Strength by the Maturity Method
- C1240 Specification for Silica Fume Used in Cementitious Mixtures
- C1437 Test Method for Flow of Hydraulic Cement Mortar
- C1610/C1610M Test Method for Static Segregation of Self-Consolidating Concrete Using Column Technique
- C1611/C1611M Test Method for Slump Flow of Self-Consolidating Concrete

3. Terms and Their Definitions

absorption, n —the process by which a liquid is drawn into and tends to fill permeable pores in a porous solid body; also, the increase in mass of a porous solid body resulting from the penetration of a liquid into its permeable pores. (R 2008)

DISCUSSION—In the case of concrete and concrete aggregates, unless otherwise stated, the liquid involved is water, the increase in mass is

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

that which does not include water adhering to the outside surface, the increase in mass is expressed as a percentage of the dry mass of the body and the body is considered to be “dry” when it has been treated by an appropriate process to remove uncombined water, such as drying to constant mass at a temperature between 100 and 110°C.

admixture, *n*—a material other than water, aggregates, hydraulic cementitious material, and fiber reinforcement that is used as an ingredient of a cementitious mixture to modify its freshly mixed, setting, or hardened properties and that is added to the batch before or during its mixing. (R 2008)

accelerating admixture, *n*—admixture that accelerates the setting and early strength development of concrete. (C494/C494M)

air-entraining admixture, *n*—admixture that causes the development of a system of microscopic air bubbles in concrete or mortar during mixing.

chemical admixture, *n*—a nonpozzolanic admixture in the form of a liquid, suspension, or water-soluble solid.

mineral admixture, *n*—deprecated term.

DISCUSSION—This term has been used to refer to different types of water insoluble, finely divided materials such as pozzolanic materials, cementitious materials, and aggregate. These materials are not similar, and it is not useful to group them under a single term. The name of the specific material should be used, for example, use “pozzolan,” “slag cement,” or “finely divided aggregate,” as is appropriate.

retarding admixture, *n*—admixture that retards the setting of concrete. (C494/C494M)

water-reducing admixture, *n*—admixture that either increases the slump of freshly mixed mortar or concrete without increasing the water content or that maintains the slump with a reduced amount of water due to factors other than air entrainment.

water-reducing admixture, high-range, *n*—a water-reducing admixture capable of producing at least 12 % reduction of water content when tested in accordance with Specification C494/C494M and meeting the other relevant requirements of Specification C494/C494M.

aggregate, *n*—granular material, such as sand, gravel, crushed stone, or iron blast-furnace slag, used with a cementing medium to form hydraulic-cement concrete or mortar. (R 2008)

coarse aggregate, *n*—(1) aggregate predominantly retained on the 4.75-mm (No. 4) sieve; or (2) that portion of an aggregate retained on the 4.75-mm (No. 4) sieve.

DISCUSSION—The definitions are alternatives to be applied under differing circumstances. Definition (1) is applied to an entire aggregate either in a natural condition or after processing. Definition (2) is applied to a portion of an aggregate. Requirements for properties and grading should be stated in the specification.

fine aggregate, *n*—(1) aggregate passing the 9.5-mm (3/8-in.) sieve and almost entirely passing the 4.75-mm (No. 4) sieve and predominantly retained on the 75- μ m (No. 200) sieve; or (2) that portion of an aggregate passing the 4.75-mm (No. 4) sieve and retained on the 75- μ m (No. 200) sieve.

DISCUSSION—The definitions are alternatives to be applied under differing circumstances. Definition (1) is applied to an entire aggregate

either in a natural condition or after processing. Definition (2) is applied to a portion of an aggregate. Requirements for properties and grading should be stated in the specifications.

heavyweight aggregate, *n*—see *high-density aggregate*.

high-density aggregate, *n*—aggregate with relative density greater than 3.3, such as: barite, magnetite, limonite, ilmenite, iron, or steel.

lightweight aggregate, *n*—see *low-density aggregate*.

low-density aggregate, *n*—aggregate with bulk density less than 1120 kg/m³ (70 lb/ft³), such as: pumice, scoria, volcanic cinders, tuff, and diatomite; expanded or sintered clay, shale, slate, diatomaceous shale, perlite, vermiculite, or slag; and end products of coal or coke combustion.

normal-density aggregate, *n*—aggregate that is neither high nor low density.

DISCUSSION—This term refers to aggregate with relative density typically ranging between 2.4 and 3.0, or with bulk density typically ranging between 1120 kg/m³ (70 lb/ft³) and 1920 kg/m³ (120 lb/ft³).

normalweight aggregate, *n*—see *normal-density aggregate*.

air content, *n*—the volume of air voids in cement paste, mortar, or concrete, exclusive of pore space in aggregate particles, usually expressed as a percentage of total volume of the paste, mortar, or concrete. (R 2008)

air-cooled blast-furnace slag—see **blast-furnace slag, air-cooled**.

air void—see **void, air**.

blast-furnace slag, *n*—the nonmetallic product, consisting essentially of silicates and aluminosilicates of calcium and other bases, that is developed in a molten condition simultaneously with iron in a blast furnace. (R 2008)

blast-furnace slag, air-cooled, *n*—the material resulting from solidification of molten blast-furnace slag under atmospheric conditions; subsequent cooling may be accelerated by application of water to the solidified surface. (R 2008)

blast-furnace slag, granulated, *n*—the glassy, granular material formed when molten blast-furnace slag is rapidly chilled, as by immersion in water. (R 2008)

bleeding, *n*—the autogenous flow of mixing water within, or its emergence from, newly placed concrete or mortar caused by the settlement of the solid materials within the mass, also called water gain. (R 2008)

bulk density, *n*—of *aggregate*, the mass of a unit volume of bulk aggregate material (the unit volume includes the volume of the individual particles and the volume of the voids between the particles). (R 2008)

DISCUSSION—This term replaces the deprecated term **unit weight**—of *aggregate*.

bulk specific gravity, *n*—the ratio of the mass of a volume of a material (including the permeable and impermeable voids in the material, but excluding the voids between particles of the material) at a stated temperature to the mass of an equal volume of distilled water at a stated temperature. (R 2008)

bulk specific gravity (saturated surface dry), *n*—the ratio of the mass of a volume of a material including the mass of water within the pores in the material (but excluding the

voids between particles) at a stated temperature, to the mass of an equal volume of distilled water at a stated temperature. (R 2008)

cellular concrete—see **concrete, cellular**.

cement, hydraulic, *n*—a cement that sets and hardens by chemical reaction with water and is capable of doing so under water. (R 2008)

cement, slag, *n*—granulated blast-furnace slag that has been ground to cement fineness, with or without additions, and that is a hydraulic cement.

cementitious material (hydraulic), *n*—an inorganic material or a mixture of inorganic materials that sets and develops strength by chemical reaction with water by formation of hydrates and is capable of doing so under water. (R 2008)

cementitious mixture, *n*—a mixture (mortar, concrete, or grout) containing hydraulic cement. (R 2008)

compound, curing, *n*—a liquid that, when applied to the surface of newly-placed concrete, forms a membrane that impedes the evaporation of water and, in the case of white pigmented compounds, reflects heat. (2010)

concrete, *n*—a composite material that consists essentially of a binding medium within which are embedded particles or fragments of aggregate; in hydraulic-cement concrete, the binder is formed from a mixture of hydraulic cement and water. (R 2008)

concrete, cellular, *n*—a lightweight hydraulic-cement concrete having a homogeneous void or cell structure attained using gas-forming chemicals or foaming agents. (R 2008)

concrete, fresh, *n*—concrete which possesses enough of its original workability so that it can be placed and consolidated by the intended methods. (R 2008)

concrete, hardened, *n*—concrete that has developed sufficient strength to serve some defined purpose or resist a stipulated loading without failure. (R 2008)

concrete, roller-compacted, RCC, *n*—concrete compacted while fresh by a roller, often a vibratory roller. (R 2008)

concrete, self-consolidating, SCC, *n*—concrete that can flow around reinforcement and consolidate under its own weight without additional effort and without exceeding specified limits of segregation. (2010)

DISCUSSION—Project specifications shall indicate the acceptable segregation based upon a specified test method. Test Method **C1610/C1610M** provides a procedure for determining the degree of aggregate segregation under static conditions and the Appendix of Test Method **C1611/C1611M** describes a non-mandatory technique for assessing the degree of segregation under flowing conditions.

consistency, *n*—of a fresh cementitious mixture, the relative mobility or ability to flow. (2010)

DISCUSSION—This characteristic of fresh cementitious mixtures is difficult to quantify and empirical test methods have been adopted to provide indicators of consistency. For example, the slump test described in Test Method **C143/C143M** is used for concrete, the flow table method described in Test Method **C1437** is used for mortar, and the flow cone method described in Test Method **C939** is used for grout.

consolidation, *n*—of cementitious mixtures, the process of increasing the density of a fresh cementitious mixture in a form, mold, or container by reducing the volume of voids. (2009)

DISCUSSION—Except for **self-consolidating concrete**, consolidation is accomplished by inputting mechanical energy, typically by rodding, tamping, tapping, vibration, or some combination of these actions. Specific apparatus and methods for consolidation are defined in the relevant C09 Standards.

crushed gravel—see **gravel, crushed**.

crushed stone—see **stone, crushed**.

curing, *n*—action taken to maintain moisture and temperature conditions in a freshly-placed cementitious mixture to allow hydraulic cement hydration and (if applicable) pozzolanic reactions to occur so that the potential properties of the mixture may develop. (2010)

curing compound—see **compound, curing**.

D-cracking, *n*—in concrete, a series of cracks near to and roughly parallel to features such as joints, edges, and structural cracks.

density, *n*—mass per unit volume (preferred over deprecated term **unit weight**).

elongated piece (of aggregate), *n*—a particle of aggregate for which the ratio of the length to width of its circumscribing rectangular prism is greater than a specified value (see also **flat piece (of aggregate)**).

entrained air—see **void, air**.

entrapped air—see **void, air**.

expanded blast-furnace slag, *n*—the lightweight cellular material obtained by controlled processing of molten blast-furnace slag with water or water and other agents, such as steam or compressed air or both.

fibers, *n*—slender filaments, which may be discrete or in the form of bundles, networks, or strands of natural or manufactured materials, which can be distributed uniformly throughout a fresh cementitious mixture.

fineness modulus, *n*—of aggregate, a factor obtained by adding the percentages of material in the sample that is coarser than each of the following sieves (cumulative percentages retained), and dividing the sum by 100: 150- μ m (No. 100), 300- μ m (No. 50), 600- μ m (No. 30), 1.18-mm (No. 16), 2.36-mm (No. 8), 4.75-mm (No. 4), 9.5-mm ($\frac{3}{8}$ -in.), 19.0-mm ($\frac{3}{4}$ -in.), 37.5-mm (1½-in.), 75-mm (3-in.), 150-mm (6-in.).

flat piece (of aggregate), *n*—a particle of aggregate for which the ratio of the width to thickness of its circumscribing rectangular prism is greater than a specified value (see also **elongated piece (of aggregate)**).

fly ash, *n*—the finely divided residue that results from the combustion of ground or powdered coal and that is transported by flue gases from the combustion zone to the particle removal system.

fog room, *n*—a moist room in which the humidity is controlled by atomization of water. (see Specification **C511**)

fresh concrete—see **concrete, fresh**.

granulated blast-furnace slag—see **blast-furnace slag, granulated**.

gravel, *n*—coarse aggregate resulting from natural disintegration and abrasion of rock or processing of weakly bound conglomerate.