



SLOVENSKI STANDARD SIST EN ISO 11337:2023

01-april-2023

Polimerni materiali - Poliamidi - Določanje ϵ -kaprolaktama in ω -laurolaktama s plinsko kromatografijo (ISO 11337:2023)

Plastics - Polyamides - Determination of ϵ -caprolactam and ω -laurolactam by gas chromatography (ISO 11337:2023)

Kunststoffe - Polyamide - Gaschromatographische Bestimmung von ϵ -Caprolactam und ω -Laurolactam (ISO 11337:2023)

Plastiques - Polyamides - Détermination du ϵ -caprolactame et du ω -laurolactame par chromatographie en phase gazeuse (ISO 11337:2023)

Ta slovenski standard je istoveten z: **EN ISO 11337:2023**

ICS:

83.080.20 Plastomeri Thermoplastic materials

SIST EN ISO 11337:2023 **en,fr,de**

EUROPEAN STANDARD

EN ISO 11337

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2023

ICS 83.080.20

Supersedes EN ISO 11337:2010

English Version

Plastics - Polyamides - Determination of ϵ -caprolactam and ζ -lauro lactam by gas chromatography (ISO 11337:2023)

Plastiques - Polyamides - Détermination du ϵ -caprolactame et du ζ -lauro lactame par chromatographie en phase gazeuse (ISO 11337:2023)

Kunststoffe - Polyamide - Gaschromatographische Bestimmung von ϵ -Caprolactam und ζ -Lauro lactam (ISO 11337:2023)

This European Standard was approved by CEN on 6 January 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 11337:2023](https://standards.iteh.ai/catalog/standards/sist/644b22d4-714e-403e-966e-f0ac11fc6f35/sist-en-iso-11337-2023)

<https://standards.iteh.ai/catalog/standards/sist/644b22d4-714e-403e-966e-f0ac11fc6f35/sist-en-iso-11337-2023>

European foreword

This document (EN ISO 11337:2023) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2023, and conflicting national standards shall be withdrawn at the latest by August 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 11337:2010.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

(standards.iteh.ai)

Endorsement notice

SIST EN ISO 11337:2023

The text of ISO 11337:2023 has been approved by CEN as EN ISO 11337:2023 without any modification.

INTERNATIONAL
STANDARD

ISO
11337

Third edition
2023-01

**Plastics — Polyamides —
Determination of ϵ -caprolactam and
 ω -lauro lactam by gas chromatography**

*Plastiques — Polyamides — Détermination du ϵ -caprolactame et du
 ω -lauro lactame par chromatographie en phase gazeuse*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 11337:2023

<https://standards.iteh.ai/catalog/standards/sist/644b22d4-714e-403e-966e-f0ac11fc6f35/sist-en-iso-11337-2023>



Reference number
ISO 11337:2023(E)

© ISO 2023

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 11337:2023

<https://standards.iteh.ai/catalog/standards/sist/644b22d4-714e-403e-966e-f0ac11fc6f35/sist-en-iso-11337-2023>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Method A: Extraction method.....	1
4.1 Principle.....	1
4.2 Reagents.....	1
4.3 Apparatus and materials.....	2
4.4 Preparation of test sample.....	3
4.5 Procedure.....	4
4.5.1 Test portion.....	4
4.5.2 Extraction.....	4
4.5.3 Preparation of internal-standard solution.....	4
4.5.4 Preparation of sample solution.....	4
4.5.5 Preparation of calibration solution.....	4
4.5.6 Gas-chromatographic analysis of sample and calibration solutions.....	4
4.5.7 Evaluation of gas chromatographic peaks.....	5
4.6 Expression of results.....	5
4.7 Precision.....	5
4.8 Test report.....	6
5 Method B: Dissolution method.....	6
5.1 Principle.....	6
5.2 Reagents.....	6
5.3 Apparatus.....	7
5.4 Preparation of internal-standard solutions.....	8
5.4.1 General.....	8
5.4.2 Internal standard for unextracted polyamide 6.....	8
5.4.3 Internal standard for extracted polyamide 6.....	8
5.4.4 Internal standard for polyamide 12.....	8
5.4.5 Preparation of calibration solutions.....	9
5.4.6 Calibration.....	10
5.5 Procedure.....	10
5.5.1 Preparation and injection of sample solution.....	10
5.5.2 Evaluation of gas-chromatographic peaks.....	10
5.5.3 Solvent recovery.....	10
5.6 Expression of results.....	11
5.7 Precision.....	11
5.8 Test report.....	11

ISO 11337:2023(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 11337:2010), which has been technically revised.

The main changes are as follows:

- isopropanol has been added as suitable internal standard for method A;
- the use of packed and capillary columns has been indicated specifically;
- the specification of suitable detectors has been opened.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Plastics — Polyamides — Determination of ϵ -caprolactam and ω -lauro lactam by gas chromatography

SAFETY STATEMENT — Persons using this document should be familiar with normal laboratory practice, if applicable. This document does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

1 Scope

This document specifies a method for determining ϵ -caprolactam and ω -lauro lactam in polyamides by gas chromatography. It is applicable particularly to the determination of ϵ -caprolactam in polyamide 6 and ω -lauro lactam in polyamide 12.

Two variants of the basic method are specified.

- Method A is an extraction method with boiling methanol, and the extract is injected into a gas chromatograph.
- Method B is a method using a solvent, and the solution is injected into a gas chromatograph.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendment) applies.

<https://standards.iteh.ai/catalog/standards/sist/644b22d4-714e-403e-966e-f0ac11fc6f35/sist-en-iso-11337-2023>

ISO 472, *Plastics — Vocabulary*

ISO 565, *Test sieves — Metal wire cloth, perforated metal plate and electroformed sheet — Nominal sizes of openings*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 472 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Method A: Extraction method

4.1 Principle

A test portion is extracted with boiling methanol and a small volume of the extract is injected into a gas chromatograph equipped with a suitable detector to separate and detect the volatile components. The extract contains 1-dodecanol as an internal standard.

4.2 Reagents

During the analysis, use only reagents of recognized analytical grade.