



SLOVENSKI STANDARD
oSIST prEN ISO 11337:2022
01-september-2022

Polimerni materiali - Poliamidi - Določanje e-kaprolaktama in w-lauroolaktama s plinsko kromatografijo (ISO/DIS 11337:2022)

Plastics - Polyamides - Determination of e-caprolactam and w-lauroolactam by gas chromatography (ISO/DIS 11337:2022)

Kunststoffe - Polyamide - Gaschromatographische Bestimmung von ε-Caprolactam und ω-Lauroolactam (ISO/DIS 11337:2022)

Plastiques - Polyamides - Détermination du e-caprolactame et du w-lauroolactame par chromatographie en phase gazeuse (ISO/DIS 11337:2022)

Ta slovenski standard je istoveten z: prEN ISO 11337

ICS:

83.080.20 Plastomeri Thermoplastic materials

oSIST prEN ISO 11337:2022 **en,fr,de**

DRAFT INTERNATIONAL STANDARD

ISO/DIS 11337

ISO/TC 61/SC 9

Secretariat: KATS

Voting begins on:
2022-06-09Voting terminates on:
2022-09-01

Plastics — Polyamides — Determination of e-caprolactam and w-lauro lactam by gas chromatography

Plastiques — Polyamides — Détermination du e-caprolactame et du w-lauro lactame par chromatographie en phase gazeuse

ICS: 83.080.20

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 11337:2022](https://standards.iteh.ai/catalog/standards/sist/644b22d4-714e-403e-966e-f0ac11fc6f35/osist-pren-iso-11337-2022)

<https://standards.iteh.ai/catalog/standards/sist/644b22d4-714e-403e-966e-f0ac11fc6f35/osist-pren-iso-11337-2022>

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 11337:2022(E)

© ISO 2022

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 11337:2022](https://standards.iteh.ai/catalog/standards/sist/644b22d4-714e-403e-966e-f0ac11fc6f35/osist-pren-iso-11337-2022)

<https://standards.iteh.ai/catalog/standards/sist/644b22d4-714e-403e-966e-f0ac11fc6f35/osist-pren-iso-11337-2022>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Method A: Extraction method.....	1
4.1 Principle.....	1
4.2 Reagents.....	2
4.3 Apparatus and materials.....	2
4.4 Preparation of test sample.....	3
4.5 Procedure.....	4
4.5.1 Test portion.....	4
4.5.2 Extraction.....	4
4.5.3 Preparation of internal-standard solution.....	4
4.5.4 Preparation of sample solution.....	4
4.5.5 Preparation of calibration solution.....	4
4.5.6 Gas-chromatographic analysis of sample and calibration solutions.....	4
4.5.7 Evaluation of gas chromatographic peaks.....	5
4.6 Expression of results.....	5
4.7 Precision.....	5
4.8 Test report.....	6
5 Method B: Dissolution method.....	6
5.1 Principle.....	6
5.2 Reagents.....	6
5.3 Apparatus.....	7
5.4 Preparation of internal-standard solutions.....	8
5.4.1 General.....	8
5.4.2 Internal standard for unextracted polyamide 6.....	8
5.4.3 Internal standard for extracted polyamide 6.....	8
5.4.4 Internal standard for polyamide 12.....	8
5.4.5 Preparation of calibration solutions.....	8
5.4.6 Calibration.....	9
5.5 Procedure.....	10
5.5.1 Preparation and injection of sample solution.....	10
5.5.2 Evaluation of gas-chromatographic peaks.....	10
5.5.3 Solvent recovery.....	10
5.6 Expression of results.....	10
5.7 Precision.....	11
5.8 Test report.....	11

ISO/DIS 11337:2022(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 11337 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*.

This second edition cancels and replaces the first edition (ISO 11337:2004), which has been technically revised. It also incorporates the Technical Corrigendum ISO 11337:2004/Cor.1:2007.

ITEH STANDARD REVIEW
(standards.iteh.ai)

[oSIST prEN ISO 11337:2022](https://standards.iteh.ai/catalog/standards/sist/644b22d4-714e-403e-966e-f0ac11fc6f35/osist-pren-iso-11337-2022)

<https://standards.iteh.ai/catalog/standards/sist/644b22d4-714e-403e-966e-f0ac11fc6f35/osist-pren-iso-11337-2022>

Plastics — Polyamides — Determination of ϵ -caprolactam and ω -lauro lactam by gas chromatography

SAFETY STATEMENT — Persons using this document should be familiar with normal laboratory practice, if applicable. This document does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any regulatory requirements.

1 Scope

This document specifies a method for determining ϵ -caprolactam and ω -lauro lactam in polyamides by gas chromatography. It is applicable particularly to the determination of ϵ -caprolactam in polyamide 6 and ω -lauro lactam in polyamide 12.

Two variants of the basic method are specified:

- Method A is an extraction method with boiling methanol, and the extract is injected into a gas chromatograph.
- Method B is a method using a solvent, and the solution is injected into a gas chromatograph.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendment) applies.

ISO 472, *Plastics — Vocabulary*

ISO 565, *Test sieves — Metal wire cloth, perforated metal plate and electroformed sheet — Nominal sizes of openings*

3 Terms and definitions

For the purposes for this document, the terms and definitions given in ISO 472 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org>

4 Method A: Extraction method

4.1 Principle

A test portion is extracted with boiling methanol and a small volume of the extract injected into a gas chromatograph equipped with a suitable detector to separate and detect the volatile components. The extract contains 1-dodecanol as an internal standard.

ISO/DIS 11337:2022(E)

4.2 Reagents

During the analysis, use only reagents of recognized analytical grade.

4.2.1 Solvent such as methanol.

4.2.2 Internal standard such as 1-dodecanol or isopropanol.

4.2.3 ϵ -Caprolactam.

4.3 Apparatus and materials

Ordinary laboratory apparatus, plus the following:

4.3.1 **Mill**, for reducing the sample to the required grain size.

A mill in which the sample is ground at a low temperature is preferred. Large pieces can be reduced in size with a pair of scissors before they are fed to the mill.

4.3.2 **Two sieves**, with aperture sizes of 710 μm and 500 μm respectively, complying with the requirements of ISO 565.

4.3.3 **Extraction apparatus**, that will accommodate an extraction crucible or porous ceramic thimble containing the test portion.

The apparatus shall be of such a design that the crucible or thimble is heated by the rising methanol vapour or the apparatus shall be constructed of an extraction flask with a Soxhlet-type reflux condenser.

Examples of suitable extraction apparatus designed along these lines are

EXAMPLE 1

- 250 ml extraction flask;
- extraction chamber to accommodate the extraction crucible so that it is enveloped on all sides by the rising methanol vapour and the condensed methanol drips through it continuously;
- glass triangle to support the crucible;
- reflux condenser;
- sintered-glass filter crucible, pore size 40 μm to 50 μm , capacity 30 ml;
- porcelain filter-plate of slightly smaller diameter than the crucible, with holes of diameter 0,4 mm.

EXAMPLE 2

- 250 ml extraction flask;
- jacketed Soxhlet extractor;
- reflux condenser;
- sintered-glass filter crucible, pore size 40 μm to 50 μm , capacity 30 ml, or a porous ceramic thimble of similar capacity (the dimensions shall be such that the crucible or thimble can be satisfactorily accommodated in the Soxhlet apparatus);
- porcelain filter-plate of slightly smaller diameter than the crucible or thimble, as appropriate, with holes of diameter 0,4 mm.

4.3.4 Suitable heating device for extraction apparatus.

4.3.5 Analytical balance, accurate to 0, 2 mg.

4.3.6 Liquid nitrogen or **solid carbon dioxide**, if necessary.

4.3.7 Gas chromatograph, with suitable detector.

a) Column

The following columns are suitable:

- a glass column (3 mm \varnothing × 1,6 m), packed with acid-washed Chromosorb® W¹⁾ of particle diameter 0,149 mm to 0,177 mm (80 mesh to 100 mesh) coated with 10 % (by mass) poly(ethylene glycol) 20M;
- a megabore Carbowax^{TM1)} column (0,53 mm \varnothing × 15 m) of corresponding separation efficiency.

The method of packing is not specified but shall be such as to obtain satisfactory separation efficiency.

Other column dimensions may be used as long as a sufficient separation efficiency is achieved.

A capillary column may also be used.

Suggested operating conditions for using a glass column and a FID detector are shown in [Table 1](#).

Table 1 — Operating conditions for gas chromatograph

Item	Value
Column temperature	200 °C
Injector temperature	250 °C
Detector temperature	250 °C
Carrier gas	Helium or nitrogen
Carrier gas flow rate	20 ml/min

Other types of columns and/or detectors may require different operating temperatures and types and flow rates of carrier and makeup gas.

b) Detector

Use a suitable detector with adequate selection of operating temperature and type and flow rate of carrier and makeup gas so that:

- the sensitivity is high;
- the relationship between response and concentration is linear over the whole measurement range;
- small changes in flow rate produce only insignificant effects on response and sensitivity.

4.3.8 Microsyringes, with capacities from 1 μ l to 10 μ l.

4.4 Preparation of test sample

Take a representative sample of the polymer and grind it in the mill ([4.3.1](#)). Grind the material in small portions to prevent undue heat development (i.e. to avoid the temperature rising above about 40 °C), letting the mill cool down in between portions. Solid carbon dioxide or liquid nitrogen ([4.3.6](#)) may be

1) Examples of suitable products available commercially. This information is given for the convenience of users of this International Standard and does not constitute an endorsement by ISO of these products.

ISO/DIS 11337:2022(E)

ground together with the polymer to prevent heat build-up. With a large mill having a greater heat capacity, these precautions may not be required. Collect the fraction that passes through a sieve with mesh aperture 710 μm (4.3.2), but not through the one with mesh aperture 500 μm .

4.5 Procedure

4.5.1 Test portion

Weigh, to the nearest 0,001 g, $(5 \pm 0,5)$ g (mass m_0) of the test sample into the filter crucible or porous thimble (4.3.3). With low-concentration samples, it is preferable to increase the mass of the test portion so that it contains approximately 0,01 g to 0,05 g of ϵ -caprolactam.

NOTE Polyamides can contain a small amount of water, forming part of the mass of the test portion (m_0). This water is not allowed for in the calculation of the methanol-extractable matter content since its effect is small compared the variance of the determination.

4.5.2 Extraction

Cover the test portion (see 4.5.1) with the filter-plate, pour about 50 ml of methanol (4.2.1) into the extraction flask, place the crucible or thimble containing the test portion in the extraction chamber and fit the condenser to the chamber. Heat the solvent in the flask to boiling. When the apparatus described in 4.3.3, Example 1, is used, adjust the rate of reflux to 1 to 2 drops per second and ensure that the drops fall into the crucible. When a Soxhlet extractor as described in 4.3.3, Example 2, is used, adjust the heating so that there are five to eight siphonings per hour.

Extract for a period of $3 \text{ h} \pm 5 \text{ min}$ and then allow the extractor to cool to ambient temperature, overnight if necessary.

Detach the extraction flask with its contents and analyse by gas chromatography, using the procedure specified in 4.5.3 to 4.5.7.

4.5.3 Preparation of internal-standard solution

Weigh out, to the nearest 0,2 mg, $(2 \pm 0,2)$ g of 1-dodecanol (4.2.2) and transfer it to a 1 l volumetric flask. Dissolve in methanol and make up to the mark with the same solvent.

While 1-dodecanol is the preferred internal standard, it is also possible to use isopropanol.

4.5.4 Preparation of sample solution

Transfer the extract obtained in 4.5.2 to a 100 ml volumetric flask and add 10 ml of the internal-standard solution prepared in 4.5.3. Rinse the extraction flask with small amounts of methanol, add the rinsings to the volumetric flask and make up to the mark with methanol.

4.5.5 Preparation of calibration solution

Weigh, to the nearest 0,2 mg, $(0,05 \pm 0,005)$ g of ϵ -caprolactam (4.2.3) and transfer to a 100 ml volumetric flask. Add 10 ml of the internal-standard solution prepared in 4.5.3. Dissolve in methanol and make up to the mark with the same solvent.

4.5.6 Gas-chromatographic analysis of sample and calibration solutions

Inject a suitable volume between 1 μl and 10 μl (depending on the sensitivity of the detector used) of the sample solution prepared in 4.5.4 or the calibration solution prepared in 4.5.5.

When using a capillary column, it is recommended to limit the injection volume to 5 μl to avoid overloading the column.