



**SLOVENSKI STANDARD**  
**oSIST prEN ISO 4892-1:2023**  
**01-december-2023**

---

**Polimerni materiali - Metode izpostavljanja laboratorijskim virom svetlobe - 1. del:  
Splošna navodila (ISO/DIS 4892-1:2023)**

Plastics - Methods of exposure to laboratory light sources - Part 1: General guidance  
(ISO/DIS 4892-1:2023)

Kunststoffe - Künstliches Bestrahlen oder Bewittern in Geräten - Teil 1: Allgemeine  
Anleitung (ISO/DIS 4892-1:2023)

Plastiques - Méthodes d'exposition à des sources lumineuses de laboratoire - Partie 1:  
Lignes directrices générales (ISO/DIS 4892-1:2023)

**Ta slovenski standard je istoveten z: prEN ISO 4892-1**

[oSIST prEN ISO 4892-1:2023](https://standards.slovenski-standard.si/standards/sist/83780/01/0101-1000-019a-03723a-10102/osist-pr-en-iso-4892-1-2023)

**ICS:**

83.080.01	Polimerni materiali na splošno	Plastics in general
-----------	-----------------------------------	---------------------

**oSIST prEN ISO 4892-1:2023**

**en,fr,de**



# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 4892-1

ISO/TC 61/SC 6

Secretariat: DIN

Voting begins on:  
2023-10-03Voting terminates on:  
2023-12-26

---

---

## Plastics — Methods of exposure to laboratory light sources —

### Part 1: General guidance

*Plastiques — Méthodes d'exposition à des sources lumineuses de laboratoire —  
Partie 1: Lignes directrices générales*

ICS: 83.080.01

iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

[oSIST prEN ISO 4892-1:2023](https://standards.iteh.ai/catalog/standards/sist/89fbd04d-9181-46c0-819a-89725a4fd4c2/osist-pren-iso-4892-1-2023)

<https://standards.iteh.ai/catalog/standards/sist/89fbd04d-9181-46c0-819a-89725a4fd4c2/osist-pren-iso-4892-1-2023>

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

**ISO/CEN PARALLEL PROCESSING**



Reference number  
ISO/DIS 4892-1:2023(E)

© ISO 2023

iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

[oSIST prEN ISO 4892-1:2023](https://standards.iteh.ai/catalog/standards/sist/89fbd04d-9181-46c0-819a-89725a4fd4c2/osist-pren-iso-4892-1-2023)

<https://standards.iteh.ai/catalog/standards/sist/89fbd04d-9181-46c0-819a-89725a4fd4c2/osist-pren-iso-4892-1-2023>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>vi</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>2</b>
<b>4 Principle</b> .....	<b>4</b>
4.1 General.....	4
4.2 Significance.....	4
4.3 Use of accelerated tests with laboratory light sources.....	5
<b>5 Requirements for laboratory exposure devices</b> .....	<b>6</b>
5.1 Irradiance.....	6
5.2 Temperature.....	7
5.3 Humidity and wetting.....	10
5.4 Other requirements for the exposure device.....	11
<b>6 Test specimens</b> .....	<b>12</b>
6.1 Form, shape and preparation.....	12
6.2 Number of test specimens.....	13
6.3 Storage and conditioning.....	13
<b>7 Test conditions and procedure</b> .....	<b>13</b>
7.1 Set points for exposure conditions.....	13
7.2 Property measurements on test specimens.....	14
7.3 Sampling for intermediate and final evaluation.....	15
<b>8 Periods of exposure and evaluation of test results</b> .....	<b>15</b>
8.1 General.....	15
8.2 Use of control materials.....	15
8.3 Use of results in specifications.....	15
<b>9 Test report</b> .....	<b>16</b>
<b>Annex A (normative) Procedures for measuring the irradiance uniformity in the specimen exposure area</b> .....	<b>18</b>
<b>Annex B (informative) Factors that decrease the degree of correlation between artificial accelerated weathering or artificial accelerated irradiation exposures and actual-use exposures</b> .....	<b>21</b>
<b>Annex C (informative) Solar spectral irradiance standards</b> .....	<b>24</b>
<b>Bibliography</b> .....	<b>27</b>

## ISO/DIS 4892-1:2023(E)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at [www.iso.org/patents](http://www.iso.org/patents). ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 6, *Ageing, chemical and environmental resistance*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 4892-1:2016), which has been technically revised.

The main changes are as follows:

- definition of [3.2](#) and [3.5](#) clarified and Notes to entry added;
- definition and Notes to entry of [3.3](#) and [3.4](#) clarified;
- new terms and definitions and Notes to entry added for black-panel thermometer, black-standard thermometer, white-panel thermometer, and white-standard thermometer ([3.7](#) – [3.10](#));
- reference to ISO/TR 18486 added under [4.2.4](#);
- calibration requirements clarified in [5.1.7](#), [5.2.8](#), [5.2.9](#), [5.3.6](#);
- requirements regarding black-panel thermometer, black-standard thermometer, white-panel thermometer, and white-standard thermometer in [5.2](#) and [Table 2](#) clarified;
- reference to ISO 23741 added in [5.3.1](#);
- new [Subclause 7.3](#) “Sampling for intermediate and final evaluation” added;
- requirements for the test report updated;

- reference to CIE 85 in Annex C updated to CIE 241;
- editorial changes.

A list of all parts in the ISO 4892 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## iTeh Standards (<https://standards.iteh.ai>) Document Preview

[oSIST prEN ISO 4892-1:2023](https://standards.iteh.ai/catalog/standards/sist/89fbd04d-9181-46c0-819a-89725a4fd4c2/osist-pren-iso-4892-1-2023)

<https://standards.iteh.ai/catalog/standards/sist/89fbd04d-9181-46c0-819a-89725a4fd4c2/osist-pren-iso-4892-1-2023>

## ISO/DIS 4892-1:2023(E)

### Introduction

Plastics are often used outdoors or in indoor locations where they are exposed to solar radiation or to solar radiation behind glass for long periods. It is therefore very important to determine the effects of solar radiation, heat, moisture and other climatic stresses on the colour and other properties of plastics. Outdoor exposures to solar radiation and to solar radiation filtered by window glass are described in ISO 877 (all parts)<sup>[1]</sup>. However, it is often necessary to determine more rapidly the effects of radiation, heat and moisture on the physical, chemical and optical properties of plastics with artificial accelerated weathering or artificial accelerated irradiation exposures that use specific laboratory light sources. Exposures in these laboratory devices are conducted under more controlled conditions than found in natural environments and are intended to accelerate eventual polymer degradation and product failures.

Relating results from accelerated weathering or artificial accelerated irradiation exposures to those obtained in actual-use conditions is difficult because of variability in both types of exposure and because laboratory tests never reproduce exactly all the exposure stresses experienced by plastics exposed in actual-use conditions. No single laboratory exposure test can be specified as a total simulation of actual-use exposures.

The relative durability of materials in actual-use exposures can be very different depending on the location of the exposure because of differences in UV radiation, time of wetness, temperature, pollutants and other factors. Therefore, even if results from specific accelerated weathering or artificial accelerated irradiation exposures are found to be useful for comparing the relative durability of materials exposed in a particular outdoor location or in particular actual-use conditions, it cannot be assumed that they will be useful for determining the relative durability of materials exposed in a different outdoor location or in different actual-use conditions.

iteh Standards  
(<https://standards.iteh.ai>)  
Document Preview

[oSIST prEN ISO 4892-1:2023](https://standards.iteh.ai/catalog/standards/sist/89fbd04d-9181-46c0-819a-89725a4fd4c2/osist-pren-iso-4892-1-2023)

<https://standards.iteh.ai/catalog/standards/sist/89fbd04d-9181-46c0-819a-89725a4fd4c2/osist-pren-iso-4892-1-2023>



# Plastics — Methods of exposure to laboratory light sources —

## Part 1: General guidance

### 1 Scope

This document provides information and general guidance relevant to the selection and operation of the methods of exposure described in detail in subsequent parts of the ISO 4892 series. It also describes general performance requirements for devices used for exposing plastics to laboratory light sources. Information regarding performance requirements is for producers of artificial accelerated weathering or artificial accelerated irradiation devices.

**NOTE** In this document, the term “light source” refers to radiation sources that emit UV radiation, visible radiation, infrared radiation or any combination of these types of radiation.

This document also provides information on the interpretation of data from artificial accelerated weathering or artificial accelerated irradiation exposures. More specific information about methods for determining the change in the properties of plastics after exposure and reporting these results is given in ISO 4582.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 293, *Plastics — Compression moulding of test specimens of thermoplastic materials*

ISO 294-1, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 1: General principles, and moulding of multipurpose and bar test specimens*

ISO 294-2, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 2: Small tensile bars*

ISO 294-3, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 3: Small plates*

ISO 295, *Plastics — Compression moulding of test specimens of thermosetting materials*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO 3167, *Plastics — Multipurpose test specimens*

ISO 4582, *Plastics — Determination of changes in colour and variations in properties after exposure to glass-filtered solar radiation, natural weathering or laboratory radiation sources*

ISO 4892-2, *Plastics — Methods of exposure to laboratory light sources — Part 2: Xenon-arc lamps*

ISO 4892-3, *Plastics — Methods of exposure to laboratory light sources — Part 3: Fluorescent UV lamps*

## ISO/DIS 4892-1:2023(E)

ISO 4892-4, *Plastics — Methods of exposure to laboratory light sources — Part 4: Open-flame carbon-arc lamps*

ISO 9370, *Plastics — Instrumental determination of radiant exposure in weathering tests — General guidance and basic test method*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

NOTE Definitions of other terms that are related to weathering tests are found in Reference [2].

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

#### 3.1

##### **control**

<weathering testing> material which is of similar composition and construction to the test material and which is exposed at the same time for comparison with the test material

Note 1 to entry: An example of the use of a control material would be when a formulation different from one currently being used is being evaluated. In that case, the control would be the plastic made with the original formulation.

#### 3.2

##### **file specimen**

portion of the material to be tested which is stored under conditions likely to cause minimal material degradation

Note 1 to entry: These are typically dark, dry and temperate conditions.

Note 2 to entry: The file specimen is used for comparison between the exposed and unexposed states.

#### 3.3

##### **artificial accelerated weathering**

exposure of a material in a laboratory device intended to simulate outdoor ageing faster by radiation, temperature, and moisture, typically including liquid water

Note 1 to entry: These exposures are typically using a laboratory light source intended to simulate outdoor conditions in an attempt to produce more rapidly the same changes that occur when the material is used in an outdoor environment.

Note 2 to entry: The conditions can be cyclic and intensified compared with those encountered in outdoor exposure.

Note 3 to entry: The device can include means for control and/or monitoring of the light source and other weathering parameters. It may also include exposure to special conditions, such as acid spray to simulate the effect of air pollution.

#### 3.4

##### **artificial accelerated irradiation**

exposure of a material to a light source in a laboratory device intended to simulate ageing faster by radiation, temperature, and moisture, typically only in the form of relative humidity, but without liquid water

Note 1 to entry: These exposures are typically using a laboratory light source intended to simulate window-glass-filtered solar radiation or radiation from interior lighting sources in an attempt to produce more rapidly the same changes that occur when the material is used in an indoor environment.

Note 2 to entry: These exposures are commonly referred to as fading or lightfastness tests.

### 3.5

#### **weathering reference material**

material of known weathering performance

Note 1 to entry: Weathering reference materials are used for weathering and irradiation testing.

### 3.6

#### **reference specimen**

portion of the weathering reference material that is to be exposed

### 3.7

#### **black-panel thermometer**

##### **BPT**

flat, black metal plate which is exposed to radiation, with a temperature sensor attached to the front centre of the exposed surface

Note 1 to entry: The intention is to mimic the thermal conditions of a coated black metal panel. The measured temperature depends on heat fluxes by short and long wavelength radiation and convection on the front side and the rear side of the panel.

Note 2 to entry: The BPT provides a measure for the reference surface temperature of irradiated surfaces. The BPT will typically show lower temperatures than the black-standard thermometer under the same conditions.

Note 3 to entry: Black-panel thermometers are sometimes referred to as uninsulated black-panel thermometers.

### 3.8

#### **black-standard thermometer**

##### **BST**

flat, black metal plate which is exposed to radiation, with a thermal insulation on the backside and the temperature sensor is attached to the rear centre of the exposed plate and between metal plate and insulation

Note 1 to entry: The intention is to mimic the thermal conditions of a common black polymer specimen. The measured temperature depends on heat fluxes by short and long wavelength radiation and convection on the frontside of the panel only.

Note 2 to entry: The BST will show one of the highest temperatures in the specimen plane.

Note 3 to entry: Black-standard thermometers are sometimes referred to as insulated black-panel thermometers.

### 3.9

#### **white-panel thermometer**

##### **WPT**

white metal plate which is exposed to radiation, with a temperature sensor attached to the front centre of the exposed surface

Note 1 to entry: The intention is to mimic the thermal conditions of a coated white metal panel. The measured temperature depends on heat fluxes by short and long wavelength radiation and convection on the front side and the rear side of the panel.

Note 2 to entry: The WPT provides a measure for the reference surface temperature of irradiated surfaces. The WPT will typically show lower temperatures than the white-standard thermometer.