
Metallic powders — Determination of envelope-specific surface area from measurements of the permeability to air of a powder bed under steady-state flow conditions

Poudres métalliques — Détermination de la surface spécifique d'enveloppe à partir de mesures de la perméabilité à l'air d'un lit de poudre dans des conditions d'écoulement permanent

(<https://standards.iteh.ai>)
Document Preview

[ISO 10070:2019](https://standards.iteh.ai/catalog/standards/iso/c301abf6-dc02-418d-885d-07ca4432118f/iso-10070-2019)

<https://standards.iteh.ai/catalog/standards/iso/c301abf6-dc02-418d-885d-07ca4432118f/iso-10070-2019>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 10070:2019

<https://standards.iteh.ai/catalog/standards/iso/c301abf6-dc02-418d-885d-07ca4432118f/iso-10070-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols	3
5 General principles	4
5.1 Permeability.....	4
5.2 Carman-Arnell and Kozeny-Carman formulae.....	4
5.3 General.....	5
5.4 Envelope density.....	5
6 Procedure	6
6.1 Preparation of test portion.....	6
6.2 Preparation of packed powder bed.....	6
6.3 Determination.....	6
7 Expression of results	6
8 Test report	7
Annex A (informative) Examples of methods of determining the permeability to air of a powder bed	8
Annex B (informative) Preliminary treatment of powder for de-agglomeration	17
Bibliography	18

ISO 10070:2019

<https://standards.iteh.ai/catalog/standards/iso/c301abf6-dc02-418d-885d-07ca4432118f/iso-10070-2019>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 119, *Powder metallurgy*, Subcommittee SC 2, *Sampling and testing methods for powders (including powders for hardmetals)*.

This second edition cancels and replaces the first edition (ISO 10070:1991), which has been technically revised.

The main changes compared to the previous edition are as follows:

- introduction of an automated test device based on the Gooden and Smith method, including procedure and calibration.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The measurement of the permeability of a packed powder bed to a laminar gas flow is the basis of this document. The determination can be made either at constant pressure drop (steady-state flow) or at variable pressure drop (constant volume). This document deals only with determinations made under steady-state flow conditions.

The permeability measured is influenced by the porosity of the powder bed. For a given particle shape, the values of permeability and porosity can be used to calculate a specific surface area of the powder by means of different formulae.

The surface area so calculated includes only those walls of the pores in the powder bed which are swept by the gas flow. It does not take into account closed or blind pores. It is known as the envelope-specific surface area. It can be very different from the total surface area of particles as measured, for instance, by gas adsorption methods.

A single equation is used in the standard methods described in this document. It entails certain limitations with respect to the type of powder (particle shape) and the porosity of the powder bed for which the method is applicable. Consequently, this is not an absolute method, and the value obtained depends upon the procedure used and the assumptions made.

The specific surface area determined can be converted into a mean equivalent spherical diameter (see [Clause 3](#)).

iTeh Standards (<https://standards.iteh.ai>) Document Preview

[ISO 10070:2019](#)

<https://standards.iteh.ai/catalog/standards/iso/c301abf6-dc02-418d-885d-07ca4432118f/iso-10070-2019>

Metallic powders — Determination of envelope-specific surface area from measurements of the permeability to air of a powder bed under steady-state flow conditions

1 Scope

This document specifies a method of measuring the air permeability and the porosity of a packed bed of metal powder, and of deriving therefrom the value of the envelope-specific surface area. The permeability is determined under steady-state flow conditions, using a laminar flow of air at a pressure near atmospheric. This document does not include the measurement of permeability by a constant volume method.

Several different methods have been proposed for this determination, and several test devices are available commercially. They give similar, reproducible results, provided that the general instructions given in this document are respected, and the test parameters are identical.

This document does not specify a particular commercial test device and corresponding test procedure. However, for the convenience of the user, an informative annex has been included (see [Annex A](#)) which is intended to give some practical information on three specific methods:

- the Lea and Nurse method, involving a test device which can be built in a laboratory (see [A.1](#));
- the Zhang Ruifu method, using a similar test device (see [A.2](#));
- the Gooden and Smith method, involving a test device which can be built in a laboratory but for which a commercial test device also exists. (Two types of commercial test device exist; one of these is no longer available for purchase, but is still being used, see [A.3](#).)

These methods are given as examples only. Other test devices available in various countries are acceptable within the scope of this document.

This testing method is applicable to all metallic powders, including powders for hardmetals, up to 1 000 μm in diameter, but it is generally used for particles having diameters between 0,2 μm and 75,0 μm . It is not intended to be used for powders composed of particles whose shape is far from equiaxial, i.e. flakes or fibres, unless specifically agreed upon between the parties concerned.

This testing method is not applicable to mixtures of different metallic powders or powders containing binders or lubricant.

If the powder contains agglomerates, the measured surface area can be affected by the degree of agglomeration. If the powder is subjected to a de-agglomeration treatment (see [Annex B](#)), the method used is to be agreed upon between the parties concerned.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3954, *Powders for powder metallurgical purposes — Sampling*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 envelope density

mass of a powder bed divided by its *envelope volume* (3.3)

Note 1 to entry: The envelope density may be less than the solid density when particles contain pores that do not contribute to the gas flow through the powder bed.

3.2 envelope-specific surface area

specific surface area of a powder as determined by gas permeametry

3.3 envelope volume

volume occupied by the particles in a powder bed, excluding the volume of the *interstices* (3.5)

Note 1 to entry: In permeametry, the envelope volume comprises the volume of the solid matter plus the volume of all the pores which do not contribute to gas flow (closed pores, blind pores, micropores, surface micropores, surface roughness, etc.). Since this volume cannot be measured by any known method, it is taken, for the purposes of this document, as being equal to the effective volume, as determined by pyknometry.

3.4 equivalent sphere diameter

diameter of theoretical non-porous spherical particles of identical size, with which the same method of permeametry as that used for the powder under examination would give the same *volume-specific surface area* (3.9)

3.5 interstices

spaces between particles in a powder bed, through which the air flows

<https://standards.iteh.ai/catalog/standards/iso/c301abf6-dc02-418d-885d-07ca4432118f/iso-10070-2019>

3.6 mass-specific surface area

surface area of a powder divided by its mass

Note 1 to entry: This area depends on the type of method used for its determination.

3.7 permeability

ability of a porous material to allow a fluid to flow through it

Note 1 to entry: to entry In this document, the fluid used is dry air.

3.8 permeable porosity

volume of *interstices* (3.5) divided by the volume of the powder bed

3.9 volume-specific surface area

surface area of a powder divided by its effective volume (i.e. by its envelope volume)

4 Symbols

Table 1 — Symbols used in the text

Symbol	Meaning	Unit	Observations
Powder bed			
A	Cross-sectional area	m^2	Area of whole cross-section of powder bed perpendicular to flow direction: $A = \frac{\pi d^2}{4}$
d	Diameter of measuring cell	m	
L	Thickness (or height)	m	
m	Mass of powder	kg	
ρ_e	Envelope density	kg/m^3	
ρ	Solid density	kg/m^3	
ε_p	Permeable porosity		$\varepsilon_p = 1 - \frac{m}{AL\rho_e}$
ε	Total porosity		$\varepsilon = 1 - \frac{m}{AL\rho}$
Gas flow			
q	Volume flow rate	m^3/s	Converted to standard conditions (STP - 0 °C, 1 atm)
p	Mean gas pressure	N/m^2	
Δp	Pressure drop	N/m^2	
η	Viscosity of gas	Ns/m^2	
T	Temperature of gas	K	
M	Molar mass of gas	kg/mol	$M = 0,029 \text{ kg/mol}$ for air
R	Molar gas constant	$\frac{J}{mol K}$	$R = 8,31 \frac{J}{mol K}$
Calculation			
K	Kozeny-Carman factor		For the purposes of this document, $K = 5,0$
δK_0	Compound constant		For the purposes of this document, the generally accepted value of 2,25 is used
S_w	Mass-specific surface area	m^2/kg	
S_K	Kozeny term	m^{-1}	Formula (3)
S_m	Slip flow term	m^{-1}	Formula (4)
S_V	Volume-specific surface area	m^{-1}	$S_V = \rho_e S_w$
Φ	Permeability	m^2	
D	Equivalent sphere diameter	m	$D = \frac{6}{S_V} = \frac{6}{\rho_e S_w}$

5 General principles

5.1 Permeability

Basically, permeametry is the experimental determination of the permeability, Φ , of a powder bed, the porosity of which is known.

The permeability is determined by measuring the volume flow rate, q , and the drop-in pressure, Δp , of a dry gas (generally air) continuously traversing the powder bed under laminar flow conditions.

The permeability is then calculated from Darcy's law, as shown in [Formula \(1\)](#):

$$\Phi = \frac{q\eta L}{A \Delta p} \quad (1)$$

5.2 Carman-Arnell and Kozeny-Carman formulae

The Carman-Arnell formula, as shown in [Formula \(2\)](#), relates specific surface area to the porosity and permeability of a packed bed of powder and takes into account both the viscous flow and the slip flow. This formula can be written as:

$$\Phi = \frac{\varepsilon_p}{K\eta} \left[\frac{\varepsilon_p^2}{S_V^2 (1-\varepsilon_p)^2} + \frac{8}{3} \sqrt{\frac{2RT}{\pi M}} \times \frac{\delta K_0 \eta \varepsilon_p}{p S_V (1-\varepsilon_p)} \right] \quad (2)$$

The solution of [Formula \(2\)](#), which is quadratic in S_V can be simplified by calculating the value of two terms, the Kozeny term S_K and the slip flow term S_m , and then combining them to give S_V .

The Kozeny term S_K is given by [Formula \(3\)](#):

$$S_K = \sqrt{\frac{A \Delta p \varepsilon_p^3}{K (1-\varepsilon_p)^2 L \eta q}} \quad (3)$$

The Kozeny term is identical to the Kozeny-Carman formula for S_V and gives the contribution to the surface area of the powder due to streamline flow.

The slip flow term S_m is given by [Formula \(4\)](#)

$$S_m = \frac{A \Delta p}{KLq} \times \frac{8}{3} \sqrt{\frac{2RT}{\pi M}} \times \frac{\delta K_0 \varepsilon_p^2}{p (1-\varepsilon_p)} \quad (4)$$

or, in the case of air, [Formula \(5\)](#):

$$S_m = 81 \times S_K^2 \frac{(1-\varepsilon_p) \eta}{p \varepsilon_p} \sqrt{T} \quad (5)$$

S_V is then given by [Formula \(6\)](#):

$$S_V = \frac{S_m}{2} + \sqrt{\frac{S_m^2}{4} + S_K^2} \quad (6)$$