



# SLOVENSKI STANDARD SIST-TP CWA 17896:2022

01-september-2022

---

**Preskusna metoda za ovrednotenje adhezijskih lastnosti kompozitnih spojev iz polimerov, ojačenih z vlakni**

Test method for the evaluation of the adhesive properties of fibre reinforced polymer composite joints

Prüfverfahren zur Bewertung der Hafteigenschaften von faserverstärkten Polymerverbundverbindungen

<https://standards.iteh.ai/catalog/standards/sist/d927f3c8-52ad-4871-9cda-10b1b2001/sist-tp-cwa-17896-2022>

**Ta slovenski standard je istoveten z: CWA 17896:2022**

---

**ICS:**

83.120	Ojačani polimeri	Reinforced plastics
83.180	Lepila	Adhesives

**SIST-TP CWA 17896:2022**

**en,fr,de**



**CEN****CWA 17896****WORKSHOP**

June 2022

**AGREEMENT**

ICS 83.120; 83.180

English version

## Test method for the evaluation of the adhesive properties of fibre reinforced polymer composite joints

This CEN Workshop Agreement has been drafted and approved by a Workshop of representatives of interested parties, the constitution of which is indicated in the foreword of this Workshop Agreement.

The formal process followed by the Workshop in the development of this Workshop Agreement has been endorsed by the National Members of CEN but neither the National Members of CEN nor the CEN-CENELEC Management Centre can be held accountable for the technical content of this CEN Workshop Agreement or possible conflicts with standards or legislation.

This CEN Workshop Agreement can in no way be held as being an official standard developed by CEN and its Members.

This CEN Workshop Agreement is publicly available as a reference document from the CEN Members National Standard Bodies.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

<b>Contents</b>	<b>Page</b>
Foreword .....	3
Introduction .....	5
1 Scope .....	6
2 Normative references .....	6
3 Terms, definitions, symbols and abbreviated terms .....	6
3.1 Terms and definitions .....	6
3.2 Symbols and abbreviated terms .....	7
4 Significance and Use .....	8
5 Lap Strap Geometry .....	8
5.1 Sampling .....	8
5.2 Laminate Configuration .....	8
5.3 Specimen Dimensions .....	8
5.4 Specimen preparation .....	9
5.4.1 Surface preparation .....	9
5.4.2 Joint procedure of the measured bonding area .....	9
5.5 Conditioning .....	10
5.6 Repairable or self-healing composites .....	10
6 Mechanical testing .....	11
6.1 Testing machine .....	11
6.2 Grips .....	11
6.3 Placement of the specimen .....	11
6.4 Testing process .....	12
7 Non-destructive evaluation (NDE) .....	12
8 Calculation .....	13
8.1 Maximum strength (MPa) .....	13
8.2 Strain .....	14
8.3 Stiffness .....	14
8.4 Knockdown effect .....	15
8.5 Repair efficiency .....	15
9 Test report .....	15
Bibliography .....	17

## Foreword

This CEN Workshop Agreement (CWA 17896:2022) has been developed in accordance with the CEN-CENELEC Guide 29 “CEN/CENELEC Workshop Agreements – A rapid prototyping to standardization” and with the relevant provisions of CEN/CENELEC Internal Regulations - Part 2. It was approved by a Workshop of representatives of interested parties on 2022-04-06, the constitution of which was supported by CEN following the public call for participation made on 2021-07-26. However, this CEN Workshop Agreement does not necessarily include all relevant stakeholders.

The final text of this CEN Workshop Agreement was provided to CEN for publication on 2022-05-20.

Results incorporated in this CWA received funding from the European Union’s Horizon 2020 research and innovation programme under grant agreement No 769274 (AIRPOXY project).

The following organizations and individuals developed and approved this CEN Workshop Agreement:

- Nerea Markaide – Chairperson, FUNDACIÓN CIDETEC (Spain)
- Esther Bermejo – Secretary, UNE (Spain)
- Alkiviadis Paipetis – CWA Leader, University of Ioannina (Greece)
- Georgios Foteinidis, University of Ioannina (Greece)
- Kyriaki Tsirka, University of Ioannina (Greece)
- Maria Kosarli, University of Ioannina (Greece)
- Nektaria-Marianthi Barkoula, University of Ioannina (Greece)
- Conor Kelly, ÉireComposites Teoroanta (Ireland)
- Alain Leroy, COEXPAIR S.A. (Belgium)
- Juan Pedro Berro Ramirez, Altair Engineering France (France)
- Alaitz Ruiz de Luzuriaga, FUNDACIÓN CIDETEC (Spain)
- Stefan Weidmann, Leibniz-Institut für Verbundwerkstoffe GmbH-IVW (Germany)
- Stephan Becker, Leibniz-Institut für Verbundwerkstoffe GmbH-IVW (Germany)
- M<sup>a</sup> Eugenia Rodríguez, FUNDACIÓ EURECAT (Spain)
- Vincent Gayraud, FUNDACIÓ EURECAT (Spain)
- Diego Calderón, IDEC – Ingeniería y Desarrollos en Composites, S.L. (Spain)
- Rakel Gonzalez, IDEC – Ingeniería y Desarrollos en Composites, S.L. (Spain)
- Guillaume Messin, IPC-Centre Technique Industriel de la Plasturgie et des Composites (France)
- Mathieu Lions, IPC-Centre Technique Industriel de la Plasturgie et des Composites (France)

**CWA 17896:2022 (E)**

- Rafael Luterbacher, GMA Group (Germany)
- Dimitrios Bekas, MEGA PLAST Industrial-Exporting S.A. (Greece)
- Markus Wolfahrt, Polymer Competence Center Leoben (Austria)
- Robert Perrin, DGA Aeronautical Systems (France)
- Pierre Barbier, Hexcel Composites (France)
- Daniel Ng, ASD-STAN Aerospace

Attention is drawn to the possibility that some elements of this document may be subject to patent rights. CEN-CENELEC policy on patent rights is described in CEN-CENELEC Guide 8 “Guidelines for Implementation of the Common IPR Policy on Patent”. CEN shall not be held responsible for identifying any or all such patent rights.

Although the Workshop parties have made every effort to ensure the reliability and accuracy of technical and non-technical descriptions, the Workshop is not able to guarantee, explicitly or implicitly, the correctness of this document. Anyone who applies this CEN Workshop Agreement shall be aware that neither the Workshop, nor CEN, can be held liable for damages or losses of any kind whatsoever. The use of this CEN Workshop Agreement does not relieve users of their responsibility for their own actions, and they apply this document at their own risk. The CEN Workshop Agreement should not be construed as legal advice authoritatively endorsed by CEN/CENELEC.

(standards.iteh.ai)

SIST-TP CWA 17896:2022

<https://standards.iteh.ai/catalog/standards/sist/d927f3c8-52ad-4871-9cda-d65b1c2ba094/sist-tp-cwa-17896-2022>

## Introduction

Advanced fibre reinforced polymer composites, due to their lightweight, are used in aeronautics, aerospace, automotive, and naval activities (e.g., aircraft fuselage, wind turbines, gears, chassis, etc.). Skin-stiffened or “stringer run-outs” structures are used mostly in aerospace and are very sensitive to local damages. Usually, the stringer tends to debond from the skin, and then the delamination may further propagate in the skin. The mechanical characterization of these specimens is both time-consuming and material intensive.

This document describes a modified test method used in a European project to characterize delamination at the tip of the flange and to understand ‘stringer run-out’ experienced in the manufacture of composite large panel, typically greater than 0,5 m in any in-plane direction. The method employed a simplified joint configuration via a lap-strap geometry. The results of the work showed that the simplified lap-strap specimens showed the same damage mechanisms as the stringer run-out.

Firstly, the lap debonds from the strap and then the delamination may further propagate interplay in the strap. It should be mentioned that failure in the lap -strap geometry is manifested in a mixed-mode. At the early stages of the test, the adhesive layer between lap and strap fails in mode II, followed by mode I failure at higher stress levels. This test method could also be used to evaluate the healing or repair efficiency at self-healing or repairable composites or their knockdown effect (see 5.6).

Non-destructive Evaluation (NDE) techniques, for example Acoustic Emission, can be optionally applied to the Lap Strap specimen with the mechanical testing. NDE techniques include Electrical Resistance Change Method (ERCM) and Acoustic Emission (AE). These techniques could provide information about the failure of the geometry and, additionally, information about the damage that was induced before failure. They are strongly suggested in cases of poor mechanical properties of the adhesive.

[SIST-TP CWA 17896:2022](https://standards.iteh.ai/catalog/standards/sist/d927f3c8-52ad-4871-9cda-d65b1c2ba094/sist-tp-cwa-17896-2022)

<https://standards.iteh.ai/catalog/standards/sist/d927f3c8-52ad-4871-9cda-d65b1c2ba094/sist-tp-cwa-17896-2022>

## CWA 17896:2022 (E)

## 1 Scope

This document provides a test method for the determination of the adhesive properties in joints of continuous fibre reinforced polymer matrix composite structures using the Lap Strap specimen.

The evaluation includes the optional concurrent use of the non-destructive technique of the Electrical Resistance Change Method (ERCM) and/or Acoustic Emission (AE) for the monitoring of the debonding of the lap from the strap optionally. The ERCM NDE technique has a limited application only on carbon fibre composites due to the inherent electrical conductivity of the carbon fibres.

This test applies to composites manufactured with continuous carbon fibres (woven or unidirectional) and thermoset or thermoplastic matrices, with quasi-isotropic lamination. This methodology can be used on repairable or self-healing composites in order to estimate the repair or healing efficiency respectively.

Safety aspects about manufacturing and mechanical testing of the composites are excluded.

## 2 Normative references

There are no normative references in this document.

## 3 Terms, definitions, symbols and abbreviated terms

### 3.1 Terms and definitions

For the purposes of this document, the following terms, definitions, symbols and abbreviated terms apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

#### 3.1.1

##### **non-destructive evaluation**

##### **NDE**

process or procedure for determining the quality or characteristics of a material, part or assembly without permanently altering the subject or its properties

[SOURCE: ISO 21648:2008, 2.1.29]

#### 3.1.2

##### **on-line monitoring**

any inspection activity carried out concurrent with the mechanical testing

#### 3.1.3

##### **knockdown effect**

the change of the initial mechanical properties of a composite material after the incorporation of a self-healing or a self-repairing system

#### 3.1.4

##### **balanced laminate**

continuous fibre-reinforced laminate that each  $+\theta^\circ$  (angle) lamina is balanced by a  $-\theta^\circ$  (angle) lamina in regard to a reference axis



**3.1.5****symmetric laminate**

continuous fibre-reinforced laminate that each ply above the mid-plane is identically the same in terms of position and orientation with one below the mid-plane

**3.2 Symbols and abbreviated terms**

AE	Acoustic Emission
b	measured specimen width
E	apparent stiffness
ERCM	Electrical Resistance Change Method
$F^{max}$	value of the load at the drop-off point
g	measured grip-to-grip distance
h	measured lap thickness
l	extension
NDE	Non-Destructive Evaluation
$R_0$	Initial value of the resistance
$\Delta R$	The final value of the resistance minus the initial value of the resistance
$\varepsilon$	lap strap strain
$\theta^\circ$	angle
$\sigma_{max}^{Initial}$	lap strap strength from a initial composite
$\sigma_{max}^{Modified}$	lap strap strength from a modified composite
$\sigma_{max}$	lap strap strength at the drop off point
$\sigma_{max}^{Reference}$	lap strap strength from a reference composite
$\sigma_{max}^{Repaired}$	lap strap strength from a repaired composite

## CWA 17896:2022 (E)

## 4 Significance and Use

The most common failure mode of stiffened composite panels is the debonding between the skin and the stringer. The proposed test method provides the mechanical strength of the lap strap specimen that simulates the mechanical and failure behaviour of a stiffened panel and reduces consumption of the materials and manufacturing time. The geometry described is a simplified joint configuration that reduces consumption of the materials and manufacturing time, while simultaneously indicating similar damage mechanisms as the stringer run-out configuration. The results from this test method can provide information about the damage mechanisms of such composite structures made from the specific materials. Furthermore, for repairable or self-healing structures, it may establish quantitatively the knockdown effect between the conventional and repairable composites. Therefore, it should offer quantitatively knowledge about the values before and after repair in order to assess the repair efficiency of these structures.

## 5 Lap Strap Geometry

### 5.1 Sampling

At least five specimens should be tested per test condition. The use of fewer specimens should be avoided. For statistically significant data, the procedures outlined in ASTM E122 should be followed. The number of specimens shall be reported.

### 5.2 Laminate Configuration

Multidirectional quasi-isotropic laminates shall be tested which should be both balanced and symmetric with respect to the span direction of the specimen. The lamination sequence should be  $[45/0/-45/90]_N$  if a unidirectional tape used or  $[(+45/-45)/(0/90)]_N$  if a woven fabric is used, where N is a whole number. The thickness of both the lap and the strap should be between 2 mm to 5 mm. The thickness and the lamination sequence of the lap, the strap and the endtab have to be the same. The variation in thickness for the individual parts of the lap strap specimen shall not exceed 0,1 mm. The panels may be manufactured by hand or wet lay-up method or tow-placement and moulded by (hot) press, vacuum bag, autoclave, or resin transfer moulding. The panels should be free of voids or should be calculated according to ASTM D2734. The volume content should be reported in accordance with ASTM D3171.

### 5.3 Specimen Dimensions

The typical configuration for the lap strap specimens is shown in Figure 1. The dimensions of the individual parts of the specimen shall be the following:

Lap length & width = 100 mm & 20 mm

Strap length & width = 200 mm & 20 mm

Endtab length & width = 50 mm & 20 mm

Measure the width and the thickness of each part to the nearest 0,05 mm at the midpoint and from either end. The average values of the measurements should be recorded and reported.

## 5.4 Specimen preparation

### 5.4.1 General

The specimen preparation is important for this geometry. The parts of the specimens should be cut from the same laminate or should be moulded to the desired final dimensions. Edges should be flat and parallel without any fluctuations at the surface. A method that produces sharp cut edges should be used as cutting method.

### 5.4.2 Surface preparation

The bonding surface of each part may be rough by lightly grinding or scrubbed with sandpaper and then they should be cleaned with a volatile solvent such as acetone or ethanol in order to remove the residuals. The surface preparation process should be performed according to ASTM D2093 or EN 13887:2003 or ISO 17212:2012 and shall not affect the composite properties.

### 5.4.3 Joint procedure of the measured bonding area

The adhesive (film, resin, etc.), as defined in ASTM D907 and ASTM D4800, should be applied in accordance with the manufacturer's guidelines between the lap and the strap (measured bonding area). In case of a two-part adhesive, the mixture shall be prepared according to the supplier's directions. The curing of the adhesive shall be performed according to supplier recommendations and conditioning should be done according to ASTM D618. The thickness of the adhesive bonding may be varied, with a minimum thickness of 0,2 mm to 0,4 mm. The control of the thickness can be achieved using the minimum number of metal beads that are needed. A maximum pressure of about 3 bar is acceptable. Final specimens should be allowed to cool down to room temperature for at least 3 h if an elevated temperature is used for the curing. If the curing is performed at room temperature, allow full-cure time plus 20 % prior to the testing. If no additional adhesive may be used and the welding process is followed, the initial thickness of the lap and the strap should be remained. After the bonding process of the lap to the strap, the end tab can be secondary bonded.

<https://standards.iteh.ai/catalog/standards/sist/d927f3c8-52ad-4871-9cda-d65b1c2ba094/sist-tp-cwa-17896-2022>