



SLOVENSKI STANDARD
oSIST prEN ISO 6506-2:2023

01-december-2023

Kovinski materiali - Preskus trdote po Brinellu - 2. del: Preverjanje in umerjanje naprav za preskušanje (ISO/DIS 6506-2:2023)

Metallic materials - Brinell hardness test - Part 2: Verification and calibration of testing machines (ISO/DIS 6506-2:2023)

Metallische Werkstoffe - Härteprüfung nach Brinell - Teil 2: Überprüfung und Kalibrierung der Prüfmaschinen (ISO/DIS 6506-2:2023)

Matériaux métalliques - Essai de dureté Brinell - Partie 2: Vérification et étalonnage des machines d'essai (ISO/DIS 6506-2:2023)

Ta slovenski standard je istoveten z: prEN ISO 6506-2

[oSIST prEN ISO 6506-2:2023](https://standards.slovenski-standard.si/standards/sist/02297317-0200-1a11-9100-2000/00145a/0sist-prEN-ISO-6506-2-2023)

<https://standards.slovenski-standard.si/standards/sist/02297317-0200-1a11-9100-2000/00145a/0sist-prEN-ISO-6506-2-2023>

ICS:

77.040.10 Mehansko preskušanje kovin Mechanical testing of metals

oSIST prEN ISO 6506-2:2023

en

DRAFT INTERNATIONAL STANDARD

ISO/DIS 6506-2

ISO/TC 164/SC 3

Secretariat: DIN

Voting begins on:
2023-10-23Voting terminates on:
2024-01-15

Metallic materials — Brinell hardness test —

Part 2: Verification and calibration of testing machines

*Matériaux métalliques — Essai de dureté Brinell —**Partie 2: Vérification et étalonnage des machines d'essai*

ICS: 77.040.10

iTeh Standards (<https://standards.iteh.ai>) Document Preview

[oSIST prEN ISO 6506-2:2023](https://standards.iteh.ai/catalog/standards/sist/d2297314-82d8-4a4f-9108-20ee90fa1d3a/osist-pren-iso-6506-2-2023)<https://standards.iteh.ai/catalog/standards/sist/d2297314-82d8-4a4f-9108-20ee90fa1d3a/osist-pren-iso-6506-2-2023>

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 6506-2:2023(E)

© ISO 2023

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[oSIST prEN ISO 6506-2:2023](https://standards.iteh.ai/catalog/standards/sist/d2297314-82d8-4a4f-9108-20ee90fa1d3a/osist-pren-iso-6506-2-2023)

<https://standards.iteh.ai/catalog/standards/sist/d2297314-82d8-4a4f-9108-20ee90fa1d3a/osist-pren-iso-6506-2-2023>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 General conditions.....	1
5 Direct verification.....	2
5.1 General.....	2
5.2 Verification of the test forces.....	2
5.3 Measurement and verification of the properties of the indenter ball.....	3
5.4 Calibration of the indentation diameter measuring system.....	3
5.5 Verification of the testing cycle.....	4
6 Indirect verification.....	4
7 Intervals between verifications.....	6
8 Verification report/calibration certificate.....	6
Annex A (informative) Uncertainty of measurement of the verification results of the hardness testing machine.....	8
Annex B (normative) Verification of hardness testing machines that are incapable of meeting the specified force/time profile.....	15
Bibliography.....	16

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[oSIST prEN ISO 6506-2:2023](https://standards.itih.ai/catalog/standards/sist/d2297314-82d8-4a4f-9108-20ee90fa1d3a/osist-pren-iso-6506-2-2023)

<https://standards.itih.ai/catalog/standards/sist/d2297314-82d8-4a4f-9108-20ee90fa1d3a/osist-pren-iso-6506-2-2023>

ISO/DIS 6506-2:2023(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 3, *Hardness testing*.

This fourth edition cancels and replaces the third edition (ISO 6506-2:2017), which has been technically revised.

The main changes compared to the previous edition are as follows:

At least the following:

- “error” has been replaced by “bias” in [Table 3](#);
- the requirement for indirect verification has been amended in [Clause 7](#);
- editorial changes have been introduced.

A list of all parts in the ISO 6506 series can be found on the ISO website.

Metallic materials — Brinell hardness test —

Part 2: Verification and calibration of testing machines

1 Scope

This document specifies methods of direct and indirect verification of testing machines used for determining Brinell hardness in accordance with ISO 6506-1 and also specifies when these two types of verification shall be performed.

The direct verification involves checking that individual machine performance parameters fall within specified limits whereas the indirect verification utilizes hardness measurements of reference blocks, calibrated in accordance with ISO 6506-3, to check the machine's overall performance.

If a testing machine is also to be used for other methods of hardness testing, it has to be verified independently for each method.

2 Normative references

This document is applicable to both fixed location and portable hardness testing machines. This document is applicable to both fixed location and portable hardness testing machines including machines that are incapable of satisfying the specified force-time profile, for which a prescribed modified procedure for the direct verification of force and testing cycle is provided.

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 376, *Metallic materials — Calibration of force-proving instruments used for the verification of uniaxial testing machines*

ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method*

ISO 6506-3, *Metallic materials — Brinell hardness test — Part 3: Calibration of reference blocks*

ISO 6507-1, *Metallic materials — Vickers hardness test — Part 1: Test method*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

4 General conditions

Before a Brinell hardness testing machine is verified, the machine shall be checked to ensure that it is properly set up in accordance with the manufacturer's instructions.

ISO/DIS 6506-2:2023(E)

Especially, it should be checked that:

- a) the mount holding the ball-holder slides correctly in its guide;
- b) every ball-holder with a ball used during the calibration is firmly held in the mount;
- c) the test force is applied and removed without shock, vibration, or overrun and in such a manner that the readings are not influenced; and
- d) if the indentation diameter measuring system is integrated into the machine,
 - the change from removing the test force to measuring mode does not affect the diameter measurements,
 - the illumination is suitable for making the diameter measurements, and — the centre of the indentation is in the centre of the field of view, if necessary.

5 Direct verification

5.1 General

5.1.1 Direct verification should be carried out at a temperature of (23 ± 5) °C. If the verification is made outside this temperature range, this shall be reported in the verification report.

5.1.2 The instruments used for verification shall be traceable to the SI with the exception of hardness, which shall be traceable to National Standards.

5.1.3 Direct verification involves:

- a) verification of the test forces;
- b) verification of the diameter, hardness, and density of the indenter ball;
- c) calibration of the indentation diameter measuring system; and
- d) verification of the testing cycle.

For each of the above items, direct verification also includes assessment of the results against the specified tolerances.

5.2 Verification of the test forces

5.2.1 All test forces for which the machine shall be used, shall be verified. If it can be demonstrated that the indenter position does not affect the applied force, this shall be done in at least one position of the indenter, otherwise it shall be done at not less than three positions of the indenter, uniformly spaced throughout its range of movement during testing. The test forces that have been verified shall be listed on the verification report.

5.2.2 Three measurements shall be made for each force at each position of the indenter, subject to [5.2.1](#) above. Immediately before each measurement is taken, the indenter shall be moved in the same direction as during testing.

5.2.3 The force shall be measured by one of the following two methods:

- by means of a force-proving instrument in accordance with ISO 376 Class 1 or better;
- by balancing against a force, accurate to $\pm 0,2$ %, applied by means of calibrated masses or another method with the same accuracy.

5.2.4 Each measurement of a force shall be within $\pm 1,0$ % of the nominal test force [see [Formula \(A.2\)](#)].

5.3 Measurement and verification of the properties of the indenter ball

5.3.1 The indenter consists of a ball and an indenter holder. The verification applies only to the ball.

5.3.2 For the purpose of verifying the size and the hardness of the balls, a minimum of two balls, selected at random from a batch, shall be tested. Each sampled ball shall be verified for size and hardness and then discarded.

5.3.3 The balls shall be polished and free from surface defects.

5.3.4 The user shall either measure the balls to ensure that they meet the following requirements or shall obtain balls from a supplier certifying that the following conditions are met.

5.3.4.1 The diameter shall be determined by taking the mean value of not less than three single values of diameter measured at different positions on the ball. No single value shall differ from the nominal diameter by more than the tolerance given in [Table 1](#).

Table 1 — Tolerances for the different ball diameters

Ball diameter mm	Tolerance mm
10	$\pm 0,005$
5	$\pm 0,004$
2,5	$\pm 0,003$
1	$\pm 0,003$

5.3.4.2 The characteristics of the tungsten carbide composite balls shall be as follows.

a) Hardness: The hardness shall be not less than 1 500 HV, when determined in accordance with ISO 6507-1. The tungsten carbide composite ball can be tested directly on its spherical surface or by sectioning the ball and testing on the ball interior.

b) Density: $\rho = (14,8 \pm 0,2) \text{ g/cm}^3$.

The density can be determined from the sampled balls, prior to hardness testing, or from the whole batch. The following chemical composition is recommended:

- tungsten carbide (WC): balance;
- total other carbides: 2,0 %;
- cobalt (Co): 5,0 % to 7,0 %.

5.4 Calibration of the indentation diameter measuring system

5.4.1 For systems where the indentation diameter is measured directly, the scale of the system shall be graduated to permit estimation of the diameter to within 0,5 %. The indentation diameter measuring system shall be calibrated for every objective lens and for each incorporated line scale, in two perpendicular measurement axes (if applicable), by measurements made on a standard scale at a minimum of four intervals, arranged centrally in the field of view, for each working range. For each measurement, the magnitude of the difference between the measured and reference values shall not be greater than $\pm 0,5$ % [see [Formula \(A.4\)](#)].

ISO/DIS 6506-2:2023(E)

5.4.2 For systems where the indentation diameter is calculated from a measurement of projected area, the system shall be calibrated for every objective lens by measurements of a range of at least four standard circular reference images covering the range of areas measured. The maximum error shall not exceed ± 1 % of the area.

5.4.3 All systems shall also be verified by making measurements of certified reference indentations, such as those on hardness reference blocks calibrated in accordance with ISO 6506-3. For each ball size, at least four indentations, covering the working range of diameters, shall be measured by each objective lens. During these measurements, the type of illumination shall be uniform and shall remain unchanged. The mean value of the measured diameters shall not differ from the certified mean diameter of the reference indentation by more than $\pm 0,5$ %.

5.5 Verification of the testing cycle

5.5.1 The testing cycle is to be verified by the testing machine manufacturer at the time of manufacture and when the testing machine undergoes repair which might have affected the testing cycle. Verification of the testing cycle at other times is as specified in [Table 4](#).

5.5.2 The testing cycle shall be verified to conform with the testing cycle defined in clause 7.6, ISO 6506-1, taking into account any uncertainty associated with the timing measurements.

5.5.3 For machines that are incapable of satisfying the specified force-time profile, the direct verification of force and testing cycle shall be modified by the use of [Annex B](#).

6 Indirect verification

6.1 Indirect verification should be carried out at a temperature of (23 ± 5) °C by means of reference blocks calibrated in accordance with ISO 6506-3. If the verification is made outside of this temperature range, this shall be reported in the verification report.

The test and bottom surfaces of the reference blocks and the surfaces of indenters shall not contain any additives or corrosion products.

6.2 The testing machine shall be verified for each test force and for each size of ball used. For each test force, at least two reference blocks shall be selected from the hardness ranges specified in [Table 2](#) (for $0,102 \times F/D^2 = 30$) and [Table 3](#) (for other force-diameter indices).

The two reference blocks shall be taken from different hardness ranges, if possible.

6.3 If this indirect verification is not the one immediately following a direct verification, the reference indentation on each reference block shall be measured, with the same type of illumination that was used during the machine's previous direct verification. For each indentation, the difference between the mean measured value and the certified mean diameter shall not exceed 0,5 %. If preferred, this check can instead be made on a similarly sized indentation in a separate reference block.

6.4 On each reference block, five indentations shall be uniformly distributed over the test surface and measured. The test shall be made in accordance with ISO 6506-1.

6.5 For each reference block, let $d_1, d_2, d_3, d_4,$ and d_5 be the mean values of the measured diameters of the indentations, arranged in increasing order of magnitude, and \bar{d} is calculated using [Formula \(1\)](#):

$$\bar{d} = \frac{d_1 + d_2 + d_3 + d_4 + d_5}{5} \quad (1)$$