



SLOVENSKI STANDARD SIST EN ISO 11357-1:2023

01-maj-2023

Polimerni materiali - Diferenčna dinamična kalorimetrija (DSC) - 1. del: Splošna načela (ISO 11357-1:2023)

Plastics - Differential scanning calorimetry (DSC) - Part 1: General principles (ISO 11357-1:2023)

Kunststoffe - Dynamische Differenzkalorimetrie (DSC) - Teil 1: Allgemeine Grundlagen (ISO 11357-1:2023)

Plastiques - Analyse calorimétrique différentielle (DSC) - Partie 1: Principes généraux (ISO 11357-1:2023)

Ta slovenski standard je istoveten z: EN ISO 11357-1:2023

ICS:

17.200.10	Toplota. Kalorimetrija	Heat. Calorimetry
83.080.01	Polimerni materiali na splošno	Plastics in general

SIST EN ISO 11357-1:2023

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 11357-1

March 2023

ICS 83.080.01

Supersedes EN ISO 11357-1:2016

English Version

Plastics - Differential scanning calorimetry (DSC) - Part 1: General principles (ISO 11357-1:2023)

Plastiques - Analyse calorimétrique différentielle (DSC)
- Partie 1: Principes généraux (ISO 11357-1:2023)

Kunststoffe - Dynamische Differenzkalorimetrie (DSC)
- Teil 1: Allgemeine Grundlagen (ISO 11357-1:2023)

This European Standard was approved by CEN on 25 February 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

[SIST EN ISO 11357-1:2023](https://standards.iteh.ai/catalog/standards/sist/a0036832-76df-45df-a881-df3d69d1405a/sist-en-iso-11357-1-2023)

<https://standards.iteh.ai/catalog/standards/sist/a0036832-76df-45df-a881-df3d69d1405a/sist-en-iso-11357-1-2023>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 11357-1:2023

<https://standards.iteh.ai/catalog/standards/sist/a0036832-76df-45df-a881-df3d69d1405a/sist-en-iso-11357-1-2023>

European foreword

This document (EN ISO 11357-1:2023) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2023, and conflicting national standards shall be withdrawn at the latest by September 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 11357-1:2016.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

(standards.iteh.ai)

Endorsement notice

SIST EN ISO 11357-1:2023

The text of ISO 11357-1:2023 has been approved by CEN as EN ISO 11357-1:2023 without any modification.

INTERNATIONAL
STANDARD

ISO
11357-1

Fourth edition
2023-02

**Plastics — Differential scanning
calorimetry (DSC) —**

**Part 1:
General principles**

Plastiques — Analyse calorimétrique différentielle (DSC) —

Partie 1: Principes généraux

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 11357-1:2023

<https://standards.iteh.ai/catalog/standards/sist/a0036832-76df-45df-a881-df3d69d1405a/sist-en-iso-11357-1-2023>



Reference number
ISO 11357-1:2023(E)

© ISO 2023

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 11357-1:2023

<https://standards.iteh.ai/catalog/standards/sist/a0036832-76df-45df-a881-df3d69d1405a/sist-en-iso-11357-1-2023>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Basic principles	8
4.1 General.....	8
4.2 Heat-flux DSC.....	8
4.3 Power-compensation DSC.....	8
5 Apparatus and materials	9
6 Specimen	10
7 Test conditions and specimen conditioning	11
7.1 Test conditions.....	11
7.2 Conditioning of specimens.....	11
8 Calibration	11
8.1 General.....	11
8.2 Calibration materials.....	12
8.3 Temperature calibration.....	12
8.3.1 General.....	12
8.3.2 Procedure.....	12
8.3.3 Accuracy of calibration.....	13
8.4 Heat calibration.....	13
8.4.1 General.....	13
8.4.2 Procedure.....	14
8.4.3 Accuracy of calibration.....	14
8.5 Heat flow rate calibration.....	14
8.5.1 General.....	14
8.5.2 Procedure.....	15
9 Procedure	17
9.1 Setting up the apparatus.....	17
9.1.1 Switching on.....	17
9.1.2 Purge gas.....	17
9.1.3 Experimental conditions.....	17
9.1.4 Baseline determination.....	17
9.2 Loading the specimen into the crucible.....	17
9.2.1 General.....	17
9.2.2 Selection of crucibles.....	17
9.2.3 Weighing the specimen crucible.....	18
9.2.4 Loading the specimen.....	18
9.2.5 Determination of the mass of the specimen.....	18
9.3 Insertion of crucibles into the instrument.....	18
9.4 Performing measurements.....	18
9.4.1 General.....	18
9.4.2 Scanning mode.....	18
9.4.3 Isothermal mode.....	19
9.5 Post-run checks.....	20
9.5.1 Check for loss in mass.....	20
9.5.2 Inspection of specimens.....	20
9.5.3 Checking of crucibles and crucible holder.....	20
10 Test report	20

ISO 11357-1:2023(E)

Annex A (normative) Extended, high-precision, temperature calibration^[12]	22
Annex B (normative) Extended, high-precision, heat calibration	24
Annex C (informative) Recommended calibration materials	26
Annex D (informative) Interaction of calibration materials with different crucible materials	30
Annex E (informative) General recommendations	32
Bibliography	34

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 11357-1:2023](https://standards.iteh.ai/catalog/standards/sist/a0036832-76df-45df-a881-df3d69d1405a/sist-en-iso-11357-1-2023)

<https://standards.iteh.ai/catalog/standards/sist/a0036832-76df-45df-a881-df3d69d1405a/sist-en-iso-11357-1-2023>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 11357-1:2016), which has been technically revised.

The main changes compared to the previous edition are as follows:

- the examples of materials given for temperature and enthalpy calibration have been updated;
- the data of sapphire to be used for calibration of heat flow rate have been updated.

A list of all parts in the ISO 11357 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

ISO 11357-1:2023(E)**Introduction**

The ISO 11357 series describes thermoanalytical DSC test methods which can be used for quality assurance purposes, for routine checks of raw materials and finished products, or for the determination of comparable data needed for data sheets or databases. The procedures given in ISO 11357 apply as long as product standards or standards describing special atmospheres for conditioning of specimens do not specify otherwise.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 11357-1:2023](https://standards.iteh.ai/catalog/standards/sist/a0036832-76df-45df-a881-df3d69d1405a/sist-en-iso-11357-1-2023)

<https://standards.iteh.ai/catalog/standards/sist/a0036832-76df-45df-a881-df3d69d1405a/sist-en-iso-11357-1-2023>

Plastics — Differential scanning calorimetry (DSC) —

Part 1: General principles

SAFETY STATEMENT — Persons using this document should be familiar with normal laboratory practice, if applicable. This document does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to determine applicable regulatory requirements.

1 Scope

The ISO 11357 series specifies several differential scanning calorimetry (DSC) methods for the thermal analysis of polymers and polymer blends, such as

- thermoplastics (polymers, moulding compounds and other moulding materials, with or without fillers, fibres or reinforcements),
- thermosets (uncured or cured materials, with or without fillers, fibres or reinforcements), and
- elastomers (with or without fillers, fibres or reinforcements).

The ISO 11357 series is applicable for the observation and measurement of various properties of, and phenomena associated with, the above-mentioned materials, such as

- physical transitions (glass transition, phase transitions such as melting and crystallization, polymorphic transitions, etc.),
- chemical reactions (polymerization, crosslinking and curing of elastomers and thermosets, etc.),
- the stability to oxidation, and
- the heat capacity.

This document specifies a number of general aspects of differential scanning calorimetry, such as the principle and the apparatus, sampling, calibration and general aspects of the procedure and test report common to all parts.

Details on performing specific methods are given in subsequent parts of the ISO 11357 series (see Foreword).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 472, *Plastics — Vocabulary*

ISO 80000-5, *Quantities and units — Part 5: Thermodynamics*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 472, ISO 80000-5 and the following apply.