INTERNATIONAL STANDARD



Second edition 2018-07

Plastics — Determination of viscosity using a falling-ball viscometer —

Part 1: Inclined-tube method

Plastiques — Détermination de la viscosité au moyen d'un **iTeh ST** Partie 1: Méthode du tube incliné (standards.iteh.ai)

<u>ISO 12058-1:2018</u> https://standards.iteh.ai/catalog/standards/sist/f3d1ac16-eeda-4d4d-8ef6-6d16e3558c78/iso-12058-1-2018



Reference number ISO 12058-1:2018(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 12058-1:2018</u> https://standards.iteh.ai/catalog/standards/sist/f3d1ac16-eeda-4d4d-8ef6-6d16e3558c78/iso-12058-1-2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Fax: +41 22 749 09 47 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Page

Contents

Forew	/ord	iv				
1	Scope	1				
2	Normative reference					
3	Terms and definitions					
4	Principle	1				
5	Measurand and units	1				
6	Measurement range and temperature range	2				
7	Apparatus 7.1 Falling-ball viscometer 7.2 Thermometer 7.3 Timer 7.4 Thermostat	2 2 4 4				
8	Sampling	4				
9	Procedure					
10	Expression of results					
11	Precision	5				
12	Test report ITeh STANDARD PREVIEW	6				
Biblio	graphy (standards.iteh.ai)	7				

<u>ISO 12058-1:2018</u> https://standards.iteh.ai/catalog/standards/sist/f3d1ac16-eeda-4d4d-8ef6-6d16e3558c78/iso-12058-1-2018

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*. https://standards.iteh.ai/catalog/standards/sist/f3d1ac16-eeda-4d4d-8ef6-

This second edition cancels and replaces the first edition (1SO 12058-1:1997), of which it constitutes a minor revision to update normative references, to change the units of temperature ranges to Kelvin and to convert footnotes into Notes.

A list of all parts in the ISO 12058 series can be found on the ISO website.

Plastics — Determination of viscosity using a falling-ball viscometer —

Part 1: Inclined-tube method

1 Scope

This document specifies the general principles of a method, using an inclined-tube falling-ball viscometer, for determining the viscosity of polymers and resins in the liquid emulsified or dispersed state. It is intended for application to liquids over a viscosity measurement range of 0,6 mPa·s to 250 000 mPa·s (temperature range -20 °C to +120 °C) for which the shear stress and shear rate are proportional, i.e. the viscosity is independent of the shear rate. This ideal behaviour is commonly known as Newtonian behaviour. If a liquid differs significantly from this behaviour, different results can be obtained with the different balls of a falling-ball viscometer or from viscometers with different geometries, such as capillary and rotational viscometers.

2 Normative reference STANDARD PREVIEW

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2811-1, Paints and varnishes it Determination of density 16-Part 1 Pycnometer method 6d16e3558c78/iso-12058-1-2018

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <u>http://www.electropedia.org/</u>
- ISO Online browsing platform: available at http://www.iso.org/obp

4 Principle

The viscosity of a liquid is determined by observing the motion of a solid sphere under the influence of gravity in an inclined cylindrical tube filled with the liquid.

5 Measurand and units

Dynamic viscosity, expressed in millipascal seconds (mPa s).

ISO 12058-1:2018(E)

6 Measurement range and temperature range

Viscosity-measurement range: 0,6 mPa·s to 250 000 mPa·s

Minimum falling time for ball: 60 s for ball No. 1 50 s for balls 2 to 4 30 s for balls 5 and 6 Temperature range: -20 °C to +120 °C

7 Apparatus

7.1 Falling-ball viscometer

See <u>Figure 1</u>.

The apparatus consists of an inclined measurement tube (falling-ball tube) filled with the liquid under test and made of thermally aged, calibrated, precision borosilicate-glass tubing with a coefficient of linear expansion of $(3,3 \times 10^{-6})$ K⁻¹, plus six balls of diameter 15,81 mm to 11,0 mm (see <u>Table 1</u>), each of balls 1 to 4 having the same coefficient of expansion as the tube itself. To minimize errors, the measurement tube and balls shall be free of flaws.

NOTE 1 The determination of viscosity using an inclined-tube failing-ball viscometer can be carried out using equipment supplied by a number of manufacturers. One example of such an instrument is the Hoeppler viscometer as described in DIN 53015:1978[I] **Lancards.iten.al**)

641663558678/iso 12058 1 2018							
Ball No.	Material	Density , ρ ₁ (typical)	Diameter	Out-of-round- ness	Constant K (typical)	Dynamic viscosity measurement range (typical)	
		g/cm ³	mm	mm	mPa·s·cm ³ /(g s)	mPa∙s	
1	Borosilicate glass	2,4	15,81 ± 0,01	±0,000 5	0,007	0,6 to 10	
2	Borosilicate glass	2,4	15,60 ± 0,05	±0,000 5	0,09	7 to 130	
3	Nickel-iron	8,1	15,60 ± 0,05	±0,001	0,09	30 to 700	
4	Nickel-iron	8,1	15,2 ± 0,1	±0,001	0,7	200 to 4 800	
5	Nickel-iron or steel	7,7 to 8,1	14,0 ± 0,5	±0,001	7	1 500 to 45 000	
6	Steel	7,7 to 7,8	11 ± 1	±0,002	35	>7 500	

$Table 1 - Balls for use in falling-ball viscometer: having a measurement tube with an inside \\ https://stadiameter.iof:15;94:mm:±i0;01:mm-eeda-4d4d-8ef6-$

For a given ball, the calibration constant *K* of the apparatus depends on the internal diameter of the tube. The values given in <u>Table 1</u> apply to a tube 15,94 mm \pm 0,01 mm in diameter.

The measurement tube has two circular marks defining the measurement distance to within 100 mm \pm 1 mm. The tube is surrounded by a tubular glass jacket for temperature control and fixed to a stand in such a manner that the axis of the tube is inclined at 10° \pm 1° to the vertical for measurement purposes.

NOTE 2 Apparatus with an inclination other than 10° is not suitable for use with this document.

ISO 12058-1:2018(E)

Dimensions in millimetres



Key 1

2

3

4

5

The measurement tube and the glass jacket can be inverted by rotating them together about their mounting point on the stand in order to return the ball to the starting position. The ends of the measurement tube are closed with two plugs, one of which contains a capillary joined to a hollow space. This type of closure prevents unacceptable pressure variations occurring, as well as the entry of air due to temperature fluctuations. The liquid under test is completely surrounded by the jacket and plugs, thus preventing evaporation or the formation of a surface skin. The stand is equipped with a spirit level and feet with levelling screws. A removable thermometer is fitted (see <u>7.2</u>).

Each viscometer shall have a test certificate, issued by the manufacturer or by a third party, stating the individual apparatus constants. The viscometer shall be recalibrated whenever a new measurement tube or a new ball is used or when considerable demands are placed on the viscometer (e.g. a series of measurements on aggressive liquids).

7.2 Thermometer

The special thermometer used in the apparatus is placed in the liquid in the thermal jacket. It shall have a scale graduated at intervals of not more than 0,1 °C. It shall be calibrated totally immersed, and shall be capable of measuring the temperature to \pm 0,03 K. The thermometer reading shall be corrected as indicated in the calibration certificate. The thermometer shall be protected against radiant heat during the measurement.

7.3 Timer

The time taken by the ball to travel the distance between the two circular marks shall be measured using one of the following. **Teh STANDARD PREVIEW**

7.3.1 Stopwatch, having a scale interval not greater than 0,1 s. The stop watch shall be compared from time to time with a standard clock accurate to within 15 s in 24 h. It is advisable to use calibrated stopwatches.

https://standards.iteh.ai/catalog/standards/sist/f3d1ac16-eeda-4d4d-8ef6-

7.3.2 Electronic timer, based on frequency counting or comprising synchronous clocks. The frequency used shall be constant to within 10^{-4} of its normal value.

7.3.3 Automatic timer, with the same accuracy as the stopwatch (7.3.1).

7.4 Thermostat

The temperature in the jacket shall be maintained constant, by means of a thermostat, to within at least $\pm 0,03$ K over the temperature range from 10 °C to 80 °C and to within $\pm 0,05$ K at temperatures outside this range. Only fluorescent tubes, which radiate little heat, shall be used to illuminate the apparatus.

8 Sampling

Sampling shall be carried out in accordance with the specification or standard for the liquid under test.

9 Procedure

Ensure that all parts of the apparatus coming into contact with the liquid under test are clean and dry.

NOTE 1 Usually the tube is cleaned by rinsing it with a suitable solvent.

Pour the liquid under test into the measurement tube and introduce the ball. Then place the plug with the capillary in the upper end of the measurement tube and screw tight. The ball shall not have any bubbles adhering to it. Maintain the liquid under test at the specified test temperature for at least 15 min.

NOTE 2 If highly viscous liquids are measured or if the measurement temperature differs by more than about 20 °C from room temperature, equilibration can require significantly longer than 15 min.

Before each series of measurements, roll the ball along the length of the tube once in order to ensure thorough mixing of the liquid. Then measure the time the ball takes to travel between the two circular marks (see <u>Figure 1</u>).

Repeat the measurement at least three times.

If the density of the liquid under test is not known, determine it in accordance with ISO 2811-1.

10 Expression of results

Calculate the dynamic viscosity, η , expressed in millipascal seconds, using the following formula:

 $\eta = K(\rho_1 - \rho_2)t$

where

- *K* is the calibration constant of the instrument (see <u>Table 1</u> and <u>7.1</u>);
- ρ_1 is the density, in grams per cubic centimetre, of the ball (see <u>Table 1</u>);
- ρ_2 is the density, in grams per cubic centimetre, of the liquid under test;
- *t* is the time, in seconds, for the ball to travel the distance between the two marks.

(standards.iteh.ai)

Take as the result the average, rounded to three significant figures, of the determinations carried out.

11 Precision

To assess the reliability of results, the following principles are used.

https://standards.iteh.ai/catalog/standards/sist/f3d1ac16-eeda-4d4d-8ef6-

Repeatability (same operator, same apparatus, same procedure)

If two results are obtained under repeatability conditions, both results may be regarded as acceptable and in accordance with this document if they differ from their mean value by not more than the appropriate limit given in Table 2.

Reproducibility (different operators, different apparatus, but same procedure)

If a result is obtained under reproducibility conditions in each of two different laboratories, both results may be regarded as acceptable and in accordance with this document if they do not differ from their mean value by more than the appropriate limit given in <u>Table 2</u>.

Ball No	Repeatability limit	Reproducibility limit				
Ball NO.	%	%				
1	1,0	2				
2 to 4	0,5	1				
5	0,7	1,5				
6	1,5	3				
NOTE The values given were established following tests performed in Germany using DIN 53015:1978[1].						

Table 2 — Repeatability and reproducibility limits