## INTERNATIONAL STANDARD



Second edition 2019-04

# Plastics — Determination of dynamic mechanical properties —

Part 9:

# Tensile vibration — Sonic-pulse propagation method

iTeh ST Plastiques – Détermination des propriétés mécaniques dynamiques – (standards iteh ai) Partie 9: Vibration en traction – Méthode de propagation de signaux acoustiques ISO 6721-9:2019 https://standards.iteh.ai/catalog/standards/sist/5808ec34-caeb-42bc-a5fa-6d62162d277c/iso-6721-9-2019



Reference number ISO 6721-9:2019(E)

## iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 6721-9:2019</u> https://standards.iteh.ai/catalog/standards/sist/5808ec34-caeb-42bc-a5fa-6d62162d277c/iso-6721-9-2019



### **COPYRIGHT PROTECTED DOCUMENT**

#### © ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Fax: +41 22 749 09 47 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

## Contents

Page

Forew	vord	iv	
1	Scope	1	
2	Normative references	1	
3	Terms and definitions		
4	Principle	2	
5	Test device5.1Apparatus5.2Transducers5.3Transducer drive unit5.4Pulse arrival time measuring equipment5.5Temperature measurement and control equipment	2 2 2 2 3 3	
6	Test specimens     6.1   General     6.2   Shape and dimensions     6.3   Preparation	3 3 3	
7	Number of specimens		
8	Conditioning	3	
9	Procedure   iTeh STANDARD PREVIEW     9.1   Test atmosphere     9.2   Mounting the specimeanclards.iteh.ai     9.3   Performing the test     9.4   Varying the temperature	3 3 3 3 4	
10	Calculation and/expression of results     10.1   Symbols   6d62162d277c/iso-6721-9-2019     10.2   Calculation of the longitudinal wave velocity     10.3   Calculation of the tensile storage modulus, E'     10.4   Significant figures	5 5 5 5 5	
11	Precision		
12	Test report	5	
Anne	Annex A (informative) Precision		
Biblic	Bibliography		

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="https://www.iso.org/directives">www.iso.org/directives</a>).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see <a href="https://www.iso.org/patents">www.iso.org/patents</a>).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see <u>www.iso</u> .org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*.

https://standards.iteh.ai/catalog/standards/sist/5808ec34-caeb-42bc-a5fa-

This second edition cancels and replaces the first edition (ISO-6721-9:1997), which has been technically revised. It also incorporates the Amendment ISO 6721-9:1997/Amd.1:2007. The main changes compared to the previous edition are as follows:

- the document has been revised editorially;
- normative references have been changed to undated.

A list of all parts in the ISO 6721 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <u>www.iso.org/members.html</u>.

# Plastics — Determination of dynamic mechanical properties —

## Part 9: Tensile vibration — Sonic-pulse propagation method

### 1 Scope

This document describes a pulse propagation method for determining the storage component of the complex tensile modulus E' of polymers at discrete frequencies typically in the range 3 kHz to 10 kHz. The method is suitable for measuring materials with storage moduli in the range 0,01 GPa to 200 GPa and with loss factors below 0,1 at around 10 kHz. With materials having a higher loss, significant errors in velocity measurement are introduced through decay of amplitude.

The method allows measurements to be made on thin films or fine fibres and long specimens, typically tapes of  $300 \text{ mm} \times 5 \text{ mm} \times 0.1 \text{ mm}$  or fibres of  $300 \text{ mm} \times 0.1 \text{ mm}$  (diameter).

This method may not be suitable for cellular plastics, composite plastics and multilayer products.

## iTeh STANDARD PREVIEW

# 2 Normative references (standards.iteh.ai)

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1183-1, Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method

ISO 1183-2, Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method

ISO 1183-3, Plastics — Methods for determining the density of non-cellular plastics — Part 3: Gas pyknometer method

ISO 6721-1, Plastics — Determination of dynamic mechanical properties — Part 1: General principles

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 6721-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <a href="https://www.iso.org/obp">https://www.iso.org/obp</a>
- IEC Electropedia: available at <a href="http://www.electropedia.org/">http://www.electropedia.org/</a>

#### 3.1

#### longitudinal sonic pulse

single sonic pulse where the deformations coincide with the direction of propagation of the pulse

#### Principle 4

Measurements are made of the velocity of a single longitudinal sonic wave in a longitudinal thin specimen. The velocity of the longitudinal sonic wave is determined by measuring the transit time of a sonic pulse between two transducers attached to the specimen over a frequency range from 3 kHz to 10 kHz. A longitudinal sonic pulse is transmitted along the length of the specimen. The velocity is independent on the specimen geometry, if the sonic velocity is measured in a long, thin specimen. The tensile storage modulus is calculated from the product of specimen density and the square of sonic velocity.

#### **Test device** 5

#### 5.1 Apparatus

The requirements for the apparatus shall enable measurement of the velocity of a longitudinal sonic pulse in a specimen.

Figure 1 shows schematically an example for measuring pulse velocity in a test specimen between the transmitting and receiving transducers.



#### Figure 1 — Schematic diagram of suitable apparatus for measuring sonic pulse velocity between a transmitting and a receiving transducer

#### Transducers 5.2

Two piezoelectric transducers having a resonant frequency in the range from about 3 kHz to 10 kHz shall be mounted on the frame so that the direction of the vibration of each transducer accurately coincides with the direction to the position of the other transducer. A mechanical pulse having longitudinal displacement in the test specimen is generated by the transmitting transducer. A pulse propagated through a test specimen is detected by the receiving transducer. One transducer shall be movable so that the distance between them can be varied from about 50 mm to 500 mm, and accurately measured to  $\pm 0.5$  % of the distance between the transducers.

#### 5.3 **Transducer drive unit**

This unit shall provide a suitable pulse voltage for the transmitting transducer to produce a sonic pulse.

1

2

3

4

5

6

#### 5.4 Pulse arrival time measuring equipment

This instrument shall be capable of measuring the time interval between two pulses, one from transducer drive unit and the other from receiving transducer to an accuracy of  $\pm$  0,5 µs.

NOTE The time interval will depend upon the distance between the transmitting and receiving transducers and the sonic wave velocity in the material.

#### 5.5 Temperature measurement and control equipment

According to ISO 6721-1.

#### 6 Test specimens

#### 6.1 General

The test specimens shall be in accordance with ISO 6721-1.

#### 6.2 Shape and dimensions

Test specimens in the form of a thin film or fibre are suitable. The dimensions are not critical, however, specimens 200 mm to 500 mm in length, 1 mm to 10 mm in width, and 0,1 mm to 1 mm in thickness or diameter are suitable.

iTeh STANDARD PREVIEW

(standards.iteh.ai)

#### 6.3 Preparation

According to ISO 6721-1.

 ISO 6721-9:2019
7 Number of specimens 6d62162d277c/iso-6721-9-2019

According to ISO 6721-1.

#### 8 Conditioning

According to ISO 6721-1.

#### 9 Procedure

#### 9.1 Test atmosphere

According to ISO 6721-1.

#### 9.2 Mounting the specimen

Place a test specimen in the apparatus so that the received pulse has a suitable amplitude to determine its arrival time. Poor contact between the test specimen and the transducers makes the pulse energy inadequate for determining the sonic pulse propagation time.

For not rigid specimens, apply a small tension to the specimen to make it tight, but not stretched.

#### 9.3 Performing the test

**9.3.1** Position the transducers so that the longitudinal sonic pulse will be transmitted through the test specimen. The separation distance between them is determined so that the sonic pulse arrival time shall

be at least 100  $\mu$ s for good accuracy (See Note). Measure the separation distance of the transducers, *L* (m) to an accuracy of ± 0,5 %.

NOTE Since most plastic materials will have a pulse velocity between 1 and  $2,5 \times 10^3 \text{ m} \cdot \text{s}^{-1}$ , the minimum separation distance will generally be 0,1 m to 0,25 m.

**9.3.2** Apply a sonic pulse to the specimen, and measure the arrival time  $t_A$  (s) to an accuracy of ± 0,5 µs.

**9.3.3** Repeat the measurements described in <u>9.3.1</u> and <u>9.3.2</u> for the same specimen at least three different separation distances between the transducers. In order to get good accuracy, the values of the distance should be selected so as to be distributed uniformly within the whole range of the distance suitable for determining the arrival time (See Figure 2).



#### Figure 2 — Example of linear regression of distance and arrival time

**9.3.4** Measure the density of the test specimen,  $\rho$  (kg·m<sup>-3</sup>) at the same temperature as that the pulse arrival time is measured to an accuracy of ± 0,5 % using one of the procedures described in ISO 1183-1 or ISO 1183-2 or ISO 1183-3.

#### 9.4 Varying the temperature

According to ISO 6721-1.

Key

tA

L

### 10 Calculation and expression of results

#### **10.1 Symbols**

<i>E</i> ' (Pa)	tensile storage modulus
<i>L</i> (m)	transducer separation distance
<i>L<sub>i</sub></i> (m)	transducer separation distance for <i>i</i> th measurement
$t_{\rm A}$ (s)	observed pulse arrival time
t <sub>Ai</sub> (s)	observed pulse arrival time corresponding to $L_i$
<i>v</i> <sub>L</sub> (m·s <sup>−1</sup> )	longitudinal wave velocity in the test specimen
ρ (kg·m⁻³)	density of the test specimen

#### 10.2 Calculation of the longitudinal wave velocity

The wave velocity,  $v_L$  is given by the slope,  $\Delta L/\Delta t_A$  of the plots of  $L_i$  vs.  $t_{Ai}$ . The value of the slope shall be obtained from at least three measurements at different distance of the transducer separation, analysing the data with linear regression (See Figure 2).

$$v_{\rm L} = \Delta L / \Delta t_{\rm A}$$
 iTeh STANDARD PREVIEW (1)

#### (standards.iteh.ai) 10.3 Calculation of the tensile storage modulus, E

The tensile storage modulus, *E*' is calculated using Formula (2).

 $E' = \rho v_{\rm I}^2$ 

https://standards.iteh.ai/catalog/standards/sist/5808ec34-ca 6d62162d277c/iso-6721-9-2019

10.4 Significant figures

Calculate the wave velocity,  $v_{\rm L}$  and the tensile storage modulus, E' to three significant figures.

### **11 Precision**

The precision of this test method is not known because interlaboratory data are not available due to the difficulty in finding laboratories with test equipment capable of operating at the same frequency. It is recognized that the properties of thermoplastics are time-dependent, and the pulse propagation time and hence the dynamic modulus depend closely on the frequency of the sonic pulse used. For information purposes, however, the within-laboratory standard deviation has been determined using data from one laboratory which tested four different materials (see <u>Annex A</u>).

### **12 Test report**

The test report shall contain the following information:

- a) a reference to this document, i.e. ISO 6721-9;
- b) all details necessary for complete identification of the material tested, including type, source, manufacturer's code number, form and previous history where these are known;
- c) for films or sheets, their thickness and, if applicable, the direction of the major axes of the test specimens in relation to some feature of the films or sheets;

(2)