

---

---

**Plastics — Determination of the  
ultimate anaerobic biodegradation  
of plastic materials in controlled  
slurry digestion systems — Method by  
measurement of biogas production**

*Plastiques — Évaluation de la biodégradabilité anaérobie ultime  
des matériaux plastiques dans des systèmes de digestion de boue  
contrôlés — Méthode par mesurage de la production de biogaz*

(<https://standards.iteh.ai>)  
Document Preview

[ISO 13975:2019](https://standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/iso/238935ab-420b-4caf-bba3-23c161056258/iso-13975-2019>



iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

[ISO 13975:2019](https://standards.iteh.ai/catalog/standards/iso/238935ab-420b-4caf-bba3-23c161056258/iso-13975-2019)

<https://standards.iteh.ai/catalog/standards/iso/238935ab-420b-4caf-bba3-23c161056258/iso-13975-2019>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword.....	iv
Introduction.....	v
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>1</b>
<b>4 Principle.....</b>	<b>3</b>
<b>5 Test and reference materials.....</b>	<b>3</b>
<b>6 Apparatus.....</b>	<b>3</b>
<b>7 Procedure.....</b>	<b>4</b>
7.1 General.....	4
7.2 Preparation of inoculum.....	4
7.3 Start-up of the test.....	5
7.4 Measurement of biogas produced (see <a href="#">Annex A</a> ).....	5
7.5 Test duration.....	5
7.6 Measurement of dissolved inorganic carbon (see <a href="#">Annex B</a> ).....	5
<b>8 Calculation and expression of results.....</b>	<b>5</b>
8.1 Amount of biogas produced.....	5
8.2 Amount of dissolved inorganic carbon.....	6
8.3 Calculation of percentage biodegradation.....	6
<b>9 Expression and interpretation of results.....</b>	<b>7</b>
<b>10 Validity of results.....</b>	<b>7</b>
<b>11 Test report.....</b>	<b>7</b>
<b>Annex A (informative) Examples of test systems.....</b>	<b>8</b>
<b>Annex B (informative) Example of apparatus for measurement of biogas dissolved in slurry.....</b>	<b>10</b>
<b>Annex C (informative) Example of a biodegradation curve.....</b>	<b>11</b>
<b>Annex D (informative) Table of water vapour pressures at various temperatures.....</b>	<b>12</b>
<b>Bibliography.....</b>	<b>13</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 14, *Environmental aspects*.

This second edition cancels and replaces the first edition (ISO 13975:2012), which has been technically revised. The main changes compared to the previous edition are as follows:

- at least following numbers of test vessels have been provided;
  - three test vessels for the test mixture;
  - three vessels for blank controls;
  - three vessels for checking inoculum activity using a reference material;
- the Clausius-Clapeyron equation has been collected (see [Formula D.1](#)).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

Biological recycling (biorecycling), together with mechanical recycling and chemical recycling, is a viable option for the recovery of plastic waste. This document specifies a method of evaluating the anaerobic biodegradability of such waste in a controlled anaerobic slurry system. This is a representative anaerobic digestion test method and system for biodegradable plastic waste.

The production of a biogas is observed under anaerobic conditions suitable for the growth of thermophilic or mesophilic microorganisms. The biogas is collected in a bag under atmospheric pressure, and the biogas volume is measured with a syringe or a gas burette. The biodegradability of the test material is evaluated from the sum of the amount of carbon dioxide dissolved in the supernatant and the cumulative quantity of evolved biogas. This document describes a biodegradation test method for plastic materials in a controlled anaerobic slurry system. It differs from ISO 15985 which uses high-solids anaerobic digestion conditions, and ISO 14853 which uses an aqueous system in an anaerobic environment.

iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

[ISO 13975:2019](https://standards.iteh.ai/catalog/standards/iso/238935ab-420b-4caf-bba3-23c161056258/iso-13975-2019)

<https://standards.iteh.ai/catalog/standards/iso/238935ab-420b-4caf-bba3-23c161056258/iso-13975-2019>



# Plastics — Determination of the ultimate anaerobic biodegradation of plastic materials in controlled slurry digestion systems — Method by measurement of biogas production

**WARNING** — Sewage sludge and other organic waste might contain potentially pathogenic organisms. Therefore, appropriate precautions should be taken when handling such materials. Digestion of organic materials produces flammable gases that present fire and explosion risks. These gases also contain toxic chemicals, including hydrogen sulfide and ammonia, in substantial concentrations. Appropriate safety measures, such as the use of a draft chamber, gas masks and/or well-ventilated laboratory facilities, should be taken. Toxic test chemicals and chemicals whose properties are not known should be handled with care and in accordance with safety instructions. Care should be taken when transporting and storing quantities of organic matter undergoing digestion.

## 1 Scope

This document specifies a method of evaluating the ultimate anaerobic biodegradability of plastic materials in a controlled anaerobic slurry digestion system with a solids concentration not exceeding 15 %, which is often found for the treatment of sewage sludge, livestock faeces or garbage. The test method is designed to yield a percentage and rate of conversion of the organic carbon in the test materials to carbon dioxide and methane produced as biogas.

The method applies to the following materials, provided they have a known carbon content:

- natural and/or synthetic polymers, copolymers or mixtures;
- plastic materials that contain additives such as plasticizers, colorants, or other compounds;
- water-soluble polymers.

It does not apply to materials which exhibit inhibitory effects on the test microorganisms at the concentration chosen for the test.

**NOTE** Inhibitory effects can be determined by an inhibition test (e.g. ISO 13641-1 or ISO 13641-2).

## 2 Normative references

There are no normative references in this document.

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 3.1

#### **ultimate anaerobic biodegradation**

breakdown of an organic compound by microorganisms in the absence of oxygen into carbon dioxide, methane, water and mineral salts of any other elements present (mineralization) plus new biomass

**3.2**  
**digested sludge**

mixture of the settled sewage and activated sludge which has been incubated in a mesophilic or thermophilic anaerobic digester to reduce the biomass and odour and to improve the dewaterability of the sludge

Note 1 to entry: Digested sludge contains an association of anaerobic fermentative and methanogenic microorganisms producing carbon dioxide and methane.

**3.3**  
**slurry**

watery mixture of insoluble matter

Note 1 to entry: The suspended-solids concentration of a slurry might be as high as around 15 %, but slurry is fluid and pumpable.

**3.4**  
**dissolved inorganic carbon**  
**DIC**

carbon dioxide dissolved in water or transformed into carbonic acid, hydrogen carbonate ion and carbonate ion

**3.5**  
**total dry solids**

amount of solids obtained by taking a known volume of test material or inoculum and drying at about 105 °C to constant mass

**3.6**  
**volatile solids**

amount of solids obtained by subtracting the residue of a known volume of test material or inoculum after incineration at about 550 °C from the *total dry solids* (3.5) of the same test portion

Note 1 to entry: The volatile-solids content is an indication of the amount of organic matter present.

**3.7**  
**theoretical amount of evolved biogas**  
**ThBiogas**

maximum theoretical amount of biogas (CH<sub>4</sub> + CO<sub>2</sub>) which will evolve after complete biodegradation of an organic compound under anaerobic conditions

Note 1 to entry: ThBiogas is calculated from the molecular formula and expressed as litres of biogas evolved per gram of test material under the standard conditions.

**3.8**  
**lag phase**

time from the start of an anaerobic digestion test until adaptation and/or selection of the degrading microorganisms is achieved and the degree of biodegradation of a chemical compound or organic matter has increased to about 10 % of the *maximum level of biodegradation* (3.11)

Note 1 to entry: It is measured in days.

**3.9**  
**biodegradation phase**

time from the end of the *lag phase* (3.8) of a test until about 90 % of the *maximum level of biodegradation* (3.11) has been reached

Note 1 to entry: It is measured in days.



**3.10****plateau phase**

time from the end of the *biodegradation phase* (3.9) until the end of the test

Note 1 to entry: It is measured in days.

**3.11****maximum level of biodegradation**

degree of biodegradation of a chemical compound or organic matter in a test, above which no further biodegradation takes place during the test

Note 1 to entry: It is measured in percent.

**4 Principle**

This test method is designed to determine the biodegradability of plastic materials under anaerobic conditions in a slurry system. The methanogenic inoculum is obtained from an anaerobic digester operating on sewage sludge or, alternatively, on organic waste such as livestock faeces or garbage. The test material mixed with the inoculum is anaerobically incubated in a test vessel at a pre-selected temperature for a period normally of 60 days. The test period may be shortened or extended until a plateau phase is reached, but the total period shall not exceed 90 days. The digestion temperature shall be  $(55 \pm 5)$  °C in order to simulate thermophilic anaerobic digestion. Alternatively, the digestion temperature may be set at  $(35 \pm 3)$  °C in order to simulate mesophilic anaerobic digestion.

The volume of the gases produced in the test vessel, carbon dioxide (CO<sub>2</sub>) and methane (CH<sub>4</sub>), is measured. A considerable amount of CO<sub>2</sub> will also be dissolved in the digested sludge or dissociated to hydrogen carbonate ion and carbonate ion under the conditions of the test. This dissolved inorganic carbon (DIC) is measured at the end of the test. The amount of biogas produced is calculated from the volume of biogas collected and the amount of DIC formed in excess of blank values.

The percentage biodegradation is calculated as the ratio of the sum of the net increase of produced biogas and DIC to the theoretical amount of evolved biogas (ThBiogas). The biodegradation curve can be followed by making intermediate measurements of biogas production.

<https://standards.iteh.ai/catalog/standards/iso/238935ab-420b-4caf-bba3-23c161056258/iso-13975-2019>

**5 Test and reference materials**

**5.1 Test material**, the test material is normally added directly as solids to give a concentration of volatile solids in the range of 7 g/l to 10 g/l. The test material should preferably be used in powder form or as film.

**5.2 Reference material**, thin-layer chromatography (TLC) grade microcrystalline cellulose with a particle size < 20 µm, for use as the reference material in the positive control.

**6 Apparatus**

Ensure that all glassware is thoroughly cleaned and, in particular, free from organic or toxic matter. The usual laboratory equipment are required, including the following.

**6.1 Digestion vessel.**

Use conical or other suitable glass flasks with gastight connectors and gas-impermeable tubing. A minimum volume of 1,5 l is recommended in view of the requirements of 7.3.

**6.2 Gas volume measurement system.**

Use a gas-sampling bag to collect the biogas evolved. A gastight syringe or a gas burette should preferably be used to measure the volume of the gas in the bag. The water in contact with the gas shall

be at a pH < 2 to avoid CO<sub>2</sub> loss through dissolution in the water. All the connectors and tubing shall be gastight and gas-impermeable.

### 6.3 Dissolved inorganic carbon measurement system.

Use a suitable carbon analyser for the direct detection of dissolved inorganic carbon in the supernatant in the digestion vessels.

For example, measure the amount of CO<sub>2</sub> evolved by adding an excess quantity of diluted phosphoric acid (see [Annex B](#)).

### 6.4 Apparatus for gas analysis (optional).

Use a gas chromatograph, or other apparatus, equipped with a suitable detector and column(s) for measuring the methane and carbon dioxide concentration in the evolved gases.

6.5 **Analytical apparatus** (optional), for determining volatile fatty acids, as well as total Kjeldahl nitrogen, ammonia nitrogen, dry solids (at 105 °C) and volatile solids (at 550 °C).

## 7 Procedure

### 7.1 General

Take all necessary precautions, as far as practically possible, to prevent the digested sludge from being exposed to air (oxygen), e.g. purge the digestion vessels with inert gas.

### 7.2 Preparation of inoculum

Collect digested sludge from a digester at a sewage treatment plant treating predominantly domestic sewage. Alternatively, digested sludge from a digester treating livestock faeces or garbage may be used. In either case, make sure that the digested sludge is collected from an active digester. Filter the digested sludge with a 2-mm-opening sieve. Use wide-necked bottles made of high-density polyethylene or a similar gas-impermeable but expandable material. Glass bottles are not recommended for safety reasons. Fill the bottles to within 1 cm of the top and seal tightly. After transport to the laboratory, use the digested sludge directly from the bottles or place it in a laboratory-scale digester. Release excess biogas to prevent the inside pressure from building up.

Alternatively, use a laboratory-grown anaerobic sludge as a source of the inoculum.

The final concentration of the total dry solids in the digested sludge in the test vessels shall not exceed 150 g/l. The pH of the digested sludge shall be between 7,5 and 8,5.

Consider pre-incubation of the digested sludge to reduce background gas production and to decrease the influence of the blanks. It has been shown that pre-incubation for about 5 days gives an adequate decrease in biogas production by the blank without an unacceptable extension of either the lag phase or the biodegradation phase during the test.

If a thermophilic digested sludge is prepared from a mesophilic digested sludge, the digested sludge can be adapted by raising the cultivation temperature, in steps, from 35 °C to 55 °C in about one month. Growth of thermophilic methanogens can be confirmed by an increase in the ratio of methane in the biogas.

An inoculum may be pre-conditioned, but normally no pre-exposed inoculum should be used, especially in the case of standard tests simulating biodegradation behaviour in natural environments. Depending on the purpose of the test, a pre-exposed inoculum may also be used, provided this is clearly stated in the test report.

If required, add any nutrient to the digested sludge during pre-incubation (see ISO 14853 for micronutrients). Indicate in the test report that pre-incubation was carried out.