

DRAFT INTERNATIONAL STANDARD

ISO/DIS 17088

ISO/TC 61/SC 14

Secretariat: DIN

Voting begins on:
2020-02-12

Voting terminates on:
2020-05-06

Plastics — Organic recycling — Specifications for compostable plastics

Spécifications pour les plastiques compostables

ICS: 83.080.01

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/f6c8f7de-bf7c-4341-8dd8-b2eef7e53bed/iso-dis-17088>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.



Reference number
ISO/DIS 17088:2020(E)

© ISO 2020

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/f6c8f7de-bf7c-4341-8dd8-b2eef7e53bed/iso-dis-17088>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	vi
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	2
4 General.....	4
5 Basic requirements.....	5
6 Detailed requirements.....	5
6.1 General.....	5
6.2 Disintegration during composting.....	6
6.2.1 Variation in permitted thickness.....	6
6.3 Ultimate biodegradation.....	6
6.4 No adverse effects of compost on terrestrial organisms.....	8
6.4.1 General.....	8
6.4.2 Ecotoxicity test scheme.....	8
6.4.3 Plant growth test.....	8
6.4.4 Acute earthworm toxicity test.....	9
6.4.5 Chronic earthworm toxicity test.....	9
6.4.6 Nitrification inhibition test with soil microorganisms.....	9
6.5 Control of constituents.....	9
6.5.1 General.....	9
6.5.2 Regulated metals and other elements.....	9
6.5.3 Per- and poly-fluorinated substances (PFCs).....	10
6.5.4 Other hazardous substances.....	10
6.5.5 Volatile solids.....	10
7 Declaration of results.....	10
8 Test report.....	10
Annex A (informative) Examples of maximum concentrations of regulated metals and other elements.....	12
Annex B (normative) Maximum concentrations of per- and poly-fluorinated substances and other hazardous substances.....	13
Annex C (normative) Determination of ecotoxic effects on higher plants.....	15
Annex D (normative) Determination of acute ecotoxic effects to earthworm.....	17
Annex E (normative) Determination of chronic ecotoxic effects to earthworm.....	19
Annex F (normative) Determination of nitrification activity of soil microorganisms.....	21
Bibliography.....	23

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 14, *Environmental aspects*.

This third edition cancels and replaces the second edition (ISO 17088:2012), which has been technically revised.

The main changes compared to the previous edition are as follows:

- in [Clause 3](#), new terms and definitions have been added: organic recycling, anaerobic digestion, per- and poly-fluorinated substance, well-managed composting process, industrial composting, organic constituents, home composting;
- in [Clause 3](#), the term and definition for catalyst has been deleted;
- in [Clause 6](#), *Detailed requirements*, 6.1.4 on catalysts has been deleted;
- new [subclause 6.2.1](#) on variation in permitted thickness has been added;
- in the subclauses of [6.3](#), requirements regarding biodegradability of constituents have been revised;
- in [6.3.1.1](#), *Laboratory test methods*, additional laboratory test methods for biodegradation testing have been added: ISO 14851, ISO 14852, ISO 17556;
- new [subclause 6.3.2](#) on anaerobic biodegradation has been added;
- [6.4.2](#), *Ecotoxicity testing scheme* has been extended covering ecotoxicity tests with representative species from three tropical levels;
- In [6.5](#), *Control of constituents*, new requirements regarding control of constituents with respect to per- and poly-fluorinated substances (PFCs) and hazardous substances (as specified in [Annex B](#)) have been included;
- list of regulated metals regarding EU + EFTA countries has been revised;

- normative [Annex B](#) *Maximum concentrations of per- and poly-fluorinated substances and other hazardous substances*, [Annex C](#) *Determination of ecotoxic effects on higher plants*, [Annex D](#) *Determination of acute ecotoxic effects to earthworm*, [Annex E](#) *Determination of chronic ecotoxic effects to earthworm* and [Annex F](#) *Determination of nitrification activity of soil microorganisms* have been added.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Full standard:
<https://standards.iteh.ai/catalog/standards/sist/f6c8f7de-bf7c-4341-8dd8-b2ee7e53bed/iso-dis-17088>

Introduction

Management of solid wastes is a problem of growing interest around the world. Cities, towns and countries are attempting to divert more materials from disposal (landfills and incineration without energy recovery) by performing different recovery options in order to transform waste into usable products. Plastics recovery technologies include material recovery (mechanical recycling, chemical or feedstock recycling, and biological or organic recycling) and the recovery of energy in the form of usable heat under controlled combustion conditions.

This document can be applied to correctly identify plastics, and products made from plastics, which can be recovered by organic recycling, i.e. will disintegrate and biodegrade satisfactorily together with biowaste producing compost as an outcome, in composting or in anaerobic digestion followed by composting, and will not leave any persistent or hazardous residues.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/f6c8f7de-bf7c-4341-8dd8-b2ee7e53bed/iso-dis-17088>

Plastics — Organic recycling — Specifications for compostable plastics

WARNING — Sewage, activated sludge, soil and compost might contain potentially pathogenic organisms. Therefore appropriate precautions should be taken when handling them. Toxic test, compounds and those whose properties are unknown should be handled with care. The handling of these materials in the context of the application of this International Standard might be further controlled by national and/or regional legislation.

1 Scope

This document specifies procedures and requirements for plastics, and products made from plastics, that are suitable for recovery through organic recycling. The four following aspects are addressed:

- a) disintegration during composting;
- b) ultimate aerobic biodegradation;
- c) no adverse effects of compost on terrestrial organisms;
- d) control of constituents.

These four characteristics are suitable to assess the effects on the industrial composting process and facility.

This specification is intended to be used as the basis for systems of labelling and claims for plastics materials and products.

This document does not provide information on requirements for the biodegradability of plastics which end up in the environment as litter. It is also not applicable to biological treatment undertaken in small installations by householders.

NOTE 1 The recovery of compostable plastics through composting can be carried out under the conditions found in well-managed industrial composting processes, where the temperature, water content, aerobic conditions, carbon/nitrogen ratio and processing conditions are optimized. Such conditions are generally obtained in industrial and municipal composting plants. Under these conditions, compostable plastics will disintegrate and biodegrade at rates comparable to yard trimmings, kraft paper bags and food scraps.

NOTE 2 “Organically recoverable”, “compostable”, “compostable in municipal and industrial composting facilities” or “biodegradable during composting” are expressions considered to be equivalent to organically recyclable for the purposes of this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 472, *Plastics — Vocabulary*

ISO 14855-1, *Determination of the ultimate aerobic biodegradability of plastic materials under controlled composting conditions — Method by analysis of evolved carbon dioxide — Part 1: General method*

ISO 14855-2, *Determination of the ultimate aerobic biodegradability of plastic materials under controlled composting conditions — Method by analysis of evolved carbon dioxide — Part 2: Gravimetric measurement of carbon dioxide evolved in a laboratory-scale test*

ISO 14851, *Determination of the ultimate aerobic biodegradability of plastic materials in an aqueous medium — Method by measuring the oxygen demand in a closed respirometer*

ISO 14852, *Determination of the ultimate aerobic biodegradability of plastic materials in an aqueous medium — Method by analysis of evolved carbon dioxide*

ISO 17556, *Plastics — Determination of the ultimate aerobic biodegradability of plastic materials in soil by measuring the oxygen demand in a respirometer or the amount of carbon dioxide evolved*

ISO 16929, *Plastics — Determination of the degree of disintegration of plastic materials under defined composting conditions in a pilot-scale test*

ISO 20200, *Plastics — Determination of the degree of disintegration of plastic materials under simulated composting conditions in a laboratory-scale test*

ISO 15685, *Soil quality — Determination of potential nitrification and inhibition of nitrification — Rapid test by ammonium oxidation*

ISO 11268-1, *Soil quality — Effects of pollutants on earthworms — Part 1: Determination of acute toxicity to Eisenia fetida/Eisenia andrei*

ISO 11268-2, *Soil quality — Effects of pollutants on earthworms — Part 2: Determination of effects on reproduction of Eisenia fetida/Eisenia andrei*

ISO 11269-2, *Soil quality — Determination of the effects of pollutants on soil flora — Part 2: Effects of contaminated soil on the emergence and early growth of higher plants*

OECD 2006), Test No. 208: *Terrestrial Plant Test: Seedling Emergence and Seedling Growth Test*, OECD Guidelines for the Testing of Chemicals, Section 2, OECD Publishing, Paris,

ISO 12846, *Water quality — Determination of mercury — Method using atomic absorption spectrometry (AAS) with and without enrichment*

EN 14582, *Characterization of waste — Halogen and sulfur content — Oxygen combustion in closed systems and determination methods*

ISO 17294-2, *Water quality — Application of inductively coupled plasma mass spectrometry (ICP-MS) — Part 2: Determination of selected elements including uranium isotopes*

3 Terms and definitions

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1 compost

organic soil conditioner obtained by biodegradation of a mixture consisting principally of vegetable residues, occasionally with other organic material and having a limited mineral content

[SOURCE: ISO 472:2013, 2.1735]

3.2**compostable plastic**

plastic that undergoes degradation by biological processes during composting to yield CO₂, water, inorganic compounds and biomass at a rate consistent with other known compostable materials and leave no visible, distinguishable or toxic residue

Note 1 to entry: Synonym of toxic: hazardous.

3.3**composting**

aerobic process designed to produce compost starting from biodegradable waste

Note 1 to entry: Composting is classified into industrial composting, home composting and worm composting.

3.4**disintegration**

physical breakdown of a material into very small fragments

3.5**filler**

relatively inert solid material added to a plastic to modify its strength, permanence, working properties or other qualities, or to lower costs

3.6**organic recycling**

aerobic (composting) or anaerobic (digestion) treatment of plastics waste under controlled conditions using micro-organisms to produce, in the presence of oxygen, stabilized organic residues (compost), carbon dioxide and water or, in the absence of oxygen, stabilized organic residues (compost), methane and carbon dioxide

Note 1 to entry: The term “biological recycling” is used synonymously.

Note 2 to entry: Modified from ISO 15270:2008.

3.7**theoretical amount of evolved carbon dioxide****ThCO₂**

maximum theoretical amount of carbon dioxide evolved after completely oxidizing a chemical compound, calculated from the molecular formula and expressed as milligrams of carbon dioxide evolved per milligram or gram of test compound

3.8**total dry solids**

amount of solids obtained by taking a known volume of test material or compost and drying at about 105 °C to constant mass

3.9**ultimate aerobic biodegradation**

breakdown of an organic compound by microorganisms in the presence of oxygen into carbon dioxide, water and mineral salts of any other elements present (mineralization) plus new biomass

3.10**volatile solids**

amount of solids obtained by subtracting the residue of a known volume of test material or compost after incineration at about 550 °C from the total dry solids of the same sample

Note 1 to entry: The volatile-solids content is an indication of the amount of organic matter present.

**3.11
anaerobic digestion**

process of controlled decomposition of biodegradable materials under managed conditions where free oxygen is absent, at temperatures suitable for naturally occurring mesophilic or thermophilic anaerobic and facultative bacteria species, that convert the inputs to a methane rich biogas and digestate

Note 1 to entry: In a second phase, the digestate is typically stabilised by means of a composting (aerobic) process.

**3.12
per- and poly-fluorinated substance
PFC**

organofluorine substance containing only carbon-fluorine bonds and carbon-carbon bonds but also other heteroatoms

**3.13
well-managed composting process**

composting process performed under controlled conditions where the temperature, water content, aerobic conditions, carbon/ nitrogen ratio and other conditions are optimized

**3.14
industrial composting**

composting process performed under controlled conditions on industrial scale with the aim of producing compost for the market

Note 1 to entry: In some regions industrial composting is referred to as professional composting

**3.15
organic constituent**

chemical constituent that contains carbon covalently linked to other carbon atoms and to other elements, most commonly hydrogen, oxygen or nitrogen

Note 1 to entry: Inorganic carbonates, carbides, cyanides and simple oxides such as carbon monoxide and carbon dioxide are not considered as organic constituent.

Note 2 to entry: Allotropes of carbon, such as diamond, graphite, carbon black, fullerenes, and carbon nanotubes are also not considered as organic constituent.

**3.16
home composting**

practise performed by a private individual with the aim of producing compost for his own use

4 General

4.1 The purpose of this document is to establish requirements for plastics materials and plastics products that can be recovered by means of organic recycling in well-managed composting facilities where the typical conditions of composting can be consistently obtained (i.e. a long thermophilic phase, aerobic conditions, sufficient water content, a suitable carbon/nitrogen ratio, etc.).

4.2 The following characteristics are determined:

- a) the ultimate level of aerobic biodegradation of the test material;
- b) the degree of disintegration obtained;
- c) any negative effects on the finished compost;
- d) the maximum concentration of regulated metals and other elements and per- and poly-fluorinated substances (PFCs) (determined as fluorine) in the test material.

In addition, the use of other hazardous substances as specified in [Annex B](#) in the test material is assessed.

5 Basic requirements

5.1 In order to comply with this document, plastics products and materials shall demonstrate each of the characteristics found in [5.1.1](#) to [5.1.4](#), as quantified in [clause 6](#).

5.1.1 Disintegration during composting

The plastics product or material shall disintegrate during composting as quantified in [6.2](#).

NOTE Special attention should be given to the visual aspects of compost. Visual contamination of compost as evidenced by reduction of aesthetic acceptability should not be significantly increased by any post composting residues of the introduced plastics product or material.

5.1.2 Ultimate aerobic biodegradation

The ultimate level of aerobic biodegradation shall be established by testing under controlled conditions as quantified in [6.3](#).

5.1.3 No adverse effect of compost on terrestrial organisms

The composting of plastics products or materials shall have no adverse effects on terrestrial organisms as quantified in [6.4](#).

Ecotoxic effects on terrestrial organisms shall be determined by comparing compost produced with or without the addition of a plastics product or a material.

5.1.4 Control of constituents

The plastics product or material under investigation shall be identified and characterized prior to testing including

- determination of the presence of regulated metals and other elements;
- determination of the presence of per- and poly-fluorinated substances (PFCs) (determined as fluorine);
- evaluation of the presence of other hazardous substances as specified in [Annex B](#);
- determination of volatile solids

as quantified in [6.5](#), taking legal compliance into consideration.

6 Detailed requirements

6.1 General

6.1.1 In order to be identified as compostable, products and materials shall meet the requirements of [6.2](#), [6.3](#), [6.4](#) and [6.5](#), using appropriate laboratory tests representative of the conditions found in industrial composting facilities.

6.1.2 Test samples shall not be subjected to conditions or procedures designed to accelerate disintegration or biodegradation prior to testing as described in [6.2](#) or [6.3](#).