



**Designation: D117 – 10**

# Standard Guide for Sampling, Test Methods, and Specifications for Electrical Insulating Oils of Petroleum Origin<sup>1</sup>

This standard is issued under the fixed designation D117; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

## 1. Scope

1.1 This guide describes methods of testing and specifications for electrical insulating oils of petroleum origin intended for use in electrical cables, transformers, oil circuit breakers, and other electrical apparatus where the oils are used as insulating, or heat transfer media, or both.

1.2 The purpose of this guide is to outline the applicability of the available test methods. Where more than one is available for measuring a given property, their relative advantages are described, along with an indication of laboratory convenience, precision, (95 % confidence limits), and applicability to specific types of electrical insulating oils.

1.3 This guide is classified into the following categories: Sampling Practices, Physical Tests, Electrical Tests, Chemical Tests, and Specifications. Within each test category, the test methods are listed alphabetically by property measured. A list of standards follows:

Category	Section	ASTM Method
<i>Sampling:</i>	3	D923, D2759, D3305
<i>Physical Tests:</i>		
Aniline Point	4	D611
Coefficient of Thermal Expansion	5	D1903
Color	6	D1500
Examination: Visual Infrared	7	D1524, D2144
Flash and Fire Point	8	D92
Interfacial Tension	9	D971, D2285
Pour Point of Petroleum Products	10	D97
Particle Count in Mineral Insulating Oil	11	D6786
Refractive Index	12	D1218, D1807
Relative Density (Specific Gravity)	13	D287, D1217, D1298, D1481

Category	Section	ASTM Method
Specific Heat	14	D2766
Thermal Conductivity	15	D2717
Turbidity	16	D6181
Viscosity	17	D88, D445, D2161
<i>Electrical Tests:</i>		
Dielectric Breakdown Voltage	18	D877, D1816, D3300
Dissipation Factor and Relative Permittivity (Dielectric Constant)	19	D924
Gassing Characteristic Under Thermal Stress	20	D7150
Gassing Tendency	21	D2300
Resistivity	22	D1169
Stability Under Electrical Discharge	23	D6180
<i>Chemical Tests:</i>		
Acidity, Approximate	24	D1534
Carbon-Type Composition	25	D2140
Compatibility with Construction Material	26	D3455
Copper Content	27	D3635
Elements by Inductively Coupled Plasma (ICP-AES)	28	D7151
Furanic Compounds in Electrical Insulating Liquids	29	D5837
Gas Analysis	30	D3612
Gas Content	31	D831, D1827, D2945
Inorganic Chlorides and Sulfates	32	D878
Neutralization (Acid and Base) Numbers	33	D664, D974
Oxidation Inhibitor Content	34	D2668, D4768
Oxidation Stability	35	D1934, D2112, D2440
Polychlorinated Biphenyl Content	36	D4059
Relative Content of Dissolved Decay	37	D6802
Sediment and Soluble Sludge	38	D1698
Sulfur, Corrosive	39	D1275
Water Content	40	D1533
<i>Specification:</i>		
Mineral Insulating Oil for Electrical Apparatus	41	D3487
High Firepoint Electrical Insulating Oils	42	D5222

<sup>1</sup> This guide is under the jurisdiction of ASTM Committee D27 on Electrical Insulating Liquids and Gases and is the direct responsibility of Subcommittee D27.01 on Mineral.

Current edition approved Sept. 15, 2010. Published October 2010. Originally published as D117 – 21 T. Last previous edition approved in 2002 as D117 – 02. DOI: 10.1520/D0117-10.

1.4 The values stated in SI units are to be regarded as standard. The values stated in parentheses are provided for information only.

1.5 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

**D88** Test Method for Saybolt Viscosity

**D92** Test Method for Flash and Fire Points by Cleveland Open Cup Tester

**D97** Test Method for Pour Point of Petroleum Products

**D287** Test Method for API Gravity of Crude Petroleum and Petroleum Products (Hydrometer Method)

**D445** Test Method for Kinematic Viscosity of Transparent and Opaque Liquids (and Calculation of Dynamic Viscosity)

**D611** Test Methods for Aniline Point and Mixed Aniline Point of Petroleum Products and Hydrocarbon Solvents

**D664** Test Method for Acid Number of Petroleum Products by Potentiometric Titration

**D831** Test Method for Gas Content of Cable and Capacitor Oils

**D877** Test Method for Dielectric Breakdown Voltage of Insulating Liquids Using Disk Electrodes

**D878** Test Method for Inorganic Chlorides and Sulfates in Insulating Oils

**D923** Practices for Sampling Electrical Insulating Liquids

**D924** Test Method for Dissipation Factor (or Power Factor) and Relative Permittivity (Dielectric Constant) of Electrical Insulating Liquids

**D971** Test Method for Interfacial Tension of Oil Against Water by the Ring Method

**D974** Test Method for Acid and Base Number by Color-Indicator Titration

**D1169** Test Method for Specific Resistance (Resistivity) of Electrical Insulating Liquids

**D1217** Test Method for Density and Relative Density (Specific Gravity) of Liquids by Bingham Pycnometer

**D1218** Test Method for Refractive Index and Refractive Dispersion of Hydrocarbon Liquids

**D1250** Guide for Use of the Petroleum Measurement Tables

**D1275** Test Method for Corrosive Sulfur in Electrical Insulating Oils

**D1298** Test Method for Density, Relative Density, or API Gravity of Crude Petroleum and Liquid Petroleum Products by Hydrometer Method

**D1481** Test Method for Density and Relative Density (Specific Gravity) of Viscous Materials by Lipkin Bicapillary Pycnometer

**D1500** Test Method for ASTM Color of Petroleum Products (ASTM Color Scale)

**D1524** Test Method for Visual Examination of Used Electrical Insulating Oils of Petroleum Origin in the Field

**D1533** Test Method for Water in Insulating Liquids by Coulometric Karl Fischer Titration

**D1534** Test Method for Approximate Acidity in Electrical Insulating Liquids by Color-Indicator Titration

**D1698** Test Method for Sediments and Soluble Sludge in Service-Aged Insulating Oils

**D1807** Test Methods for Refractive Index and Specific Optical Dispersion of Electrical Insulating Liquids

**D1816** Test Method for Dielectric Breakdown Voltage of Insulating Liquids Using VDE Electrodes

**D1827** Test Method for Gas Content (Nonacidic) of Insulating Liquids by Displacement with Carbon Dioxide (Withdrawn 2009)<sup>3</sup>

**D1903** Practice for Determining the Coefficient of Thermal Expansion of Electrical Insulating Liquids of Petroleum Origin, and Askarels

**D1934** Test Method for Oxidative Aging of Electrical Insulating Petroleum Oils by Open-Beaker Method

**D2112** Test Method for Oxidation Stability of Inhibited Mineral Insulating Oil by Pressure Vessel

**D2140** Practice for Calculating Carbon-Type Composition of Insulating Oils of Petroleum Origin

**D2144** Practices for Examination of Electrical Insulating Oils by Infrared Absorption

**D2161** Practice for Conversion of Kinematic Viscosity to Saybolt Universal Viscosity or to Saybolt Furol Viscosity

**D2285** Test Method for Interfacial Tension of Electrical Insulating Oils of Petroleum Origin Against Water by the Drop-Weight Method (Withdrawn 2008)<sup>3</sup>

**D2300** Test Method for Gassing of Electrical Insulating Liquids Under Electrical Stress and Ionization (Modified Pirelli Method)

**D2440** Test Method for Oxidation Stability of Mineral Insulating Oil

**D2668** Test Method for 2,6-*di-tert*-Butyl- *p*-Cresol and 2,6-*di-tert*-Butyl Phenol in Electrical Insulating Oil by Infrared Absorption

**D2717** Test Method for Thermal Conductivity of Liquids

**D2759** Practice for Sampling Gas from a Transformer Under Positive Pressure

**D2766** Test Method for Specific Heat of Liquids and Solids

**D2945** Test Method for Gas Content of Insulating Oils (Withdrawn 2012)<sup>3</sup>

**D3300** Test Method for Dielectric Breakdown Voltage of Insulating Oils of Petroleum Origin Under Impulse Conditions

**D3305** Practice for Sampling Small Gas Volume in a Transformer

**D3455** Test Methods for Compatibility of Construction Material with Electrical Insulating Oil of Petroleum Origin

**D3487** Specification for Mineral Insulating Oil Used in Electrical Apparatus

**D3612** Test Method for Analysis of Gases Dissolved in Electrical Insulating Oil by Gas Chromatography

**D3635** Test Method for Dissolved Copper In Electrical

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

- Insulating Oil By Atomic Absorption Spectrophotometry  
**D4052** Test Method for Density, Relative Density, and API Gravity of Liquids by Digital Density Meter  
**D4059** Test Method for Analysis of Polychlorinated Biphenyls in Insulating Liquids by Gas Chromatography  
**D4768** Test Method for Analysis of 2,6-Ditertiary-Butyl Para-Cresol and 2,6-Ditertiary-Butyl Phenol in Insulating Liquids by Gas Chromatography  
**D5185** Test Method for Multielement Determination of Used and Unused Lubricating Oils and Base Oils by Inductively Coupled Plasma Atomic Emission Spectrometry (ICP-AES)  
**D5222** Specification for High Fire-Point Mineral Electrical Insulating Oils  
**D5837** Test Method for Furanic Compounds in Electrical Insulating Liquids by High-Performance Liquid Chromatography (HPLC)  
**D6180** Test Method for Stability of Insulating Oils of Petroleum Origin Under Electrical Discharge  
**D6181** Test Method for Measurement of Turbidity in Mineral Insulating Oil of Petroleum Origin (Withdrawn 2012)<sup>3</sup>  
**D6786** Test Method for Particle Count in Mineral Insulating Oil Using Automatic Optical Particle Counters  
**D6802** Test Method for Determination of the Relative Content Of Dissolved Decay Products in Mineral Insulating Oils by Spectrophotometry  
**D7150** Test Method for the Determination of Gassing Characteristics of Insulating Liquids Under Thermal Stress at Low Temperature  
**D7151** Test Method for Determination of Elements in Insulating Oils by Inductively Coupled Plasma Atomic Emission Spectrometry (ICP-AES)

## SAMPLING

### 3. Sampling

3.1 Accurate sampling, whether of the complete contents or only parts thereof, is extremely important from the standpoint of evaluation of the quality of the product sampled. Obviously, careless sampling procedure or contamination in the sampling equipment will result in a sample that is not truly representative. This generally leads to erroneous conclusions concerning quality and incurs loss of the time, effort, and expense involved in securing, transporting, and testing the sample.

3.2 Sample the insulating oil in accordance with Practices **D923**, **D2759** and **D3305** as appropriate.

## PHYSICAL PROPERTIES

### 4. Aniline Point

4.1 *Scope*—This test method covers the determination of the aniline point of petroleum products, provided that the aniline point is below the bubble point and above the solidification point of the aniline-sample mixture.

4.2 *Summary of Test Method:*

4.2.1 *Test Method D611*—Equal volumes of aniline and test specimen or aniline and test specimen plus *n*-heptane are

placed in a tube and mixed mechanically. The mixture is heated at a controlled rate until the two phases become miscible. The mixture is then cooled at a controlled rate, and the temperature at which the two phases separate is recorded as the aniline point.

4.3 *Significance and Use*—The aniline point of an insulating oil indicates the solvency of the oil for some materials that are in contact with the oil. A higher aniline point implies a lower aromaticity and a lower degree of solvency for some materials.

### 5. Coefficient of Thermal Expansion

5.1 *Scope*—This test method covers the determination of the coefficient of thermal expansion of electrical insulating liquids of petroleum origin.

5.2 *Definition:*

5.2.1 *coefficient of thermal expansion*—the change in volume per unit volume per degree change in temperature. It is commonly stated as the average coefficient over a given temperature range.

5.3 *Summary of Test Method*—The specific gravity of insulating oils is determined at two temperatures below 90°C and separated by not less than 5°C nor more than 14°C. Test methods used may be **D287**, **D1217**, **D1298**, or **D1481**. The calculation of average coefficient of thermal expansion over this temperature range is given in Test Method **D1903**.

5.4 *Significance and Use*—A knowledge of the coefficient of expansion of a liquid is essential to compute the required size of a container to accommodate a volume of liquid over the full temperature range to which it will be subjected. It is also used to compute the volume of void space that would exist in an inelastic device filled with the liquid after the liquid has cooled to a lower temperature.

### 6. Color

6.1 *Scope*—This test method covers the visual determination of color of a wide variety of liquid petroleum products, including mineral insulating oils.

6.2 *Summary of Test Method:*

6.2.1 *Test Method D1500*—The test specimen is placed in a glass sample jar (an ordinary 125-mL test specimen bottle is satisfactory for routine tests). The color of the sample by transmitted light is compared with a series of tinted glass standards. The glass standard matching the sample is selected, or if an exact match is not possible, the next darker glass is selected. The results are reported numerically on a scale of 0.5 to 8.0.

6.3 *Significance*—A low color number is an essential requirement for inspection of assembled apparatus in a tank. An increase in the color number during service is an indicator of deterioration or contamination of the insulating oil.

### 7. Examination

7.1 *Scope:*

7.1.1 Both visual examination and qualitative infrared absorption are described in this section. The test methods are:

7.1.2 *Test Method D1524*—This is a visual examination of mineral insulating oils that have been used in transformers, oil

circuit breakers, or other electrical apparatus as insulating or cooling media, or both. This test is intended for use in the field.

7.1.3 *Test Method D2144*—The infrared absorption from 2.5 to 25  $\mu\text{m}$  (4000 to 667  $\text{cm}^{-1}$ ) is recorded as a means of (a) establishing continuity by comparison with the spectra of previous shipments by the same supplier, (b) for the detection of some types of contaminants, (c) for the identification of oils in storage or service. This test method is not intended for the determination of the various constituents of an oil.

## 7.2 Summary of Test Methods:

7.2.1 *Test Method D1524*—Estimate the color of the oil by use of an oil comparator, matching the oil test specimen with tinted glass color standards. Note the presence of cloudiness, particles of insulation, metal corrosion products, or other undesirable suspended materials in the oil.

7.2.2 *Test Methods D2144*—The infrared spectrum is recorded from 2.5 to 25  $\mu\text{m}$  (4000 to 667  $\text{cm}^{-1}$ ) either as the absorption spectrum itself, or as the differential between the test specimen and reference oil. The spectra are compared with reference spectra to establish the identity of the oil.

## 7.3 Significance and Use:

7.3.1 *Test Method D1524*—The observation of the color and condition of the oil in a field inspection permits a determination of whether the sample should be sent to a central laboratory for full evaluation.

7.3.2 *Test Methods D2144*—The infrared spectrum of an electrical insulating oil indicates the general chemical composition of the sample. Because of the complex mixture of compounds present in insulating oils, the spectrum is not sharply defined and may not be suitable for quantitative estimation of components. The identity of the oil can be quickly established as being the same or different from previous samples by comparison with the reference spectra.

## 8. Flash and Fire Point

### 8.1 Scope:

8.1.1 This test method covers the determination of flash and fire points of all petroleum products except fuel oils and those having an open cup flash below 79°C (175°F).

8.1.2 This test method should be used solely to measure and describe the properties of materials in response to heat and flame under controlled laboratory conditions and should not be used for the description, appraisal, or regulation of the fire hazard of materials under actual fire conditions.

### 8.2 Definitions:

8.2.1 *flash point*—the temperature at which vapors above the oil surface first ignite when a small test flame is passed across the surface under specified conditions.

8.2.2 *fire point*—the temperature at which oil first ignites and burns for at least 5 s when a small test flame is passed across the surface under specified conditions.

8.3 *Summary of Test Method*—Fill the test cup to the specified level with the test specimen. Heat the sample initially at 14 to 17°C/min (25 to 30°F/min) until the temperature is 56°C (100°F) below the expected flash point. Reduce the rate of temperature change to 5 to 6°C/min (9 to 11°F/min) and apply the test flame every 2°C (or 5°F) until a flash occurs.

Continue heating and testing every 2°C (or 5°F) until the oil continues to burn for at least 5 s. The procedure is described in Test Method D92.

8.4 *Significance and Use*—The flash point and fire point tests give an indication of the flammability of an oil. They may also be used to provide a qualitative indication of contamination with more flammable materials. In the latter context, the flash point test is more sensitive.

## 9. Interfacial Tension

9.1 *Scope*—These test methods cover the measurement, under nonequilibrium conditions, of the interfacial tension of insulating oils against water. These test methods have been shown by experience to give a reliable indication of the presence of hydrophilic compounds.

### 9.2 Definition:

9.2.1 *interfacial tension*—the molecular attractive force between unlike molecules at an interface. It is usually expressed in dynes per centimetre or millinewtons per metre.

### 9.3 Summary of Test Methods:

9.3.1 *Test Method D971*—Interfacial tension is determined by measuring the force necessary to detach a platinum wire upward from the oil-water interface. To calculate the interfacial tension, the force so measured is corrected by an empirically determined factor which depends upon the force applied, the densities of both oil and water, and the dimensions of the ring. The measurement is completed within 1 min of the formation of the interface.

9.3.2 *Test Method D2285*—Interfacial tension is determined by measuring the volume of a drop of water that the oil will support. The larger the drop of water, the higher the interfacial tension of the oil. The instrument used to measure the volume of the drops of water is calibrated to read approximately in dynes per centimeter interfacial tension. For better accuracy, the reading can be corrected by a factor that depends on the density of the oil. The drop is allowed to age for 30 s and to fall between 45 and 60 s after formation.

9.4 *Significance and Use*—Interfacial tension measurements on electrical insulating oils provide a sensitive means of detecting small amounts of soluble polar contaminants and products of oxidation. A high value for new mineral insulating oil indicates the absence of undesirable polar contaminants. The test is frequently applied to service-aged oils as an indication of the degree of deterioration.

## 10. Pour Point

10.1 *Scope*—The pour point is applicable to any petroleum oil.

### 10.2 Definition:

10.2.1 *pour point*—the lowest temperature, expressed as a multiple of 3°C at which the oil is observed to flow when cooled and examined under prescribed conditions.

10.3 *Summary of Test Method*—After preliminary heating, the test specimen is cooled at a specified rate and examined at

intervals of 3°C for flow characteristics. The lowest temperature at which movement of the oil is observed within 5 s is reported as the pour point. The procedure is described in Test Method **D97**.

#### 10.4 *Significance and Use:*

10.4.1 The pour point of an insulating oil gives an indication of the temperature below which it may not be possible to pour or remove the oil from its container.

10.4.2 In connection with oil for use in cable systems, the pour point may be useful to indicate the point at which no free movement will take place in the cable or to indicate the temperature at which partial separation of wax may occur.

10.4.3 The pour point of a transformer oil is important as an index of the lowest temperature to which the material may be cooled without seriously limiting the degree of circulation of the oil. Some materials are sensitive to temperature cycling or prolonged storage at low temperatures, and their pour points may not adequately predict their low temperature flow properties.

### 11. Particle Count in Mineral Insulating Oil Using Automatic Opticle Particle Counters

11.1 *Scope*—This test method covers the determination of particle concentration and particle size distribution in mineral insulating oil. It is suitable for testing oils having a viscosity of 6 to 20 cSt at 40°C. The test method is specific to liquid automatic particle analyzers that use the light extinction principle.

#### 11.2 *Summary of Test Method:*

11.2.1 Samples are taken in particle-clean bottles that are suitable for particle analysis. The sample bottle is agitated to redistribute particles in the oil, then the oil is placed in an automatic particle counter, where the number of particles and their size distribution are determined by the light extinction principle.

11.2.2 As particles pass through the sensing zone of the instrument, the quantity of light reaching the detector is obscured. This signal is translated to an equivalent projected area diameter based on calibration with a NIST-traceable fluid (ISO Medium Test Dust suspension).

#### 11.3 *Significance and Use:*

11.3.1 Particles in insulating oil can have a detrimental effect on the dielectric properties of the fluid, depending on the size, concentration, and nature of the particles. The source of these particles can be external contaminants, oil degradation byproducts, or internal materials such as metals, carbon, or cellulose fibers.

11.3.2 Particle counts provide a general degree of contamination level and may be useful in assessing the condition of specific types of electrical equipment. Particle counts can also be used to determine filtering effectiveness when processing oil.

11.3.3 If more specific knowledge of the nature of the particles is needed, other tests such as metals analysis or fiber identification and counting must be performed.

### 12. Refractive Index and Specific Optical Dispersion

#### 12.1 *Scope:*

12.1.1 *Test Method D1218*—Describes a precision method for determining refractive index accurate to 0.00006 and refractive dispersion accurate to 0.00012. The liquid must be transparent, no darker than ASTM 4.0 color (see Test Method **D1500**) and have a refractive index between 1.33 and 1.50. The specific optical dispersion is calculated by dividing the refractive dispersion value by the specific gravity of the liquid.

12.1.2 *Test Method D1807*—Describes a routine method for measuring refractive index accurate to three units in the fourth decimal place, measuring refractive dispersion, and calculating specific optical dispersion accurate to three units in the fourth decimal place. The oils must be transparent and light colored.

#### 12.2 *Definitions:*

12.2.1 *refractive index*—the ratio of the velocity of light in air to its velocity in the substance under test.

12.2.2 *specific optical dispersion*—the difference between the refractive indexes of light of two different wave lengths, both indexes measured at the same temperature, the difference being divided by the specific gravity also measured at the test temperature. For convenience, the specific dispersion value is multiplied by 10<sup>4</sup>.

#### 12.3 *Summary of Test Method:*

12.3.1 The two methods differ in the accuracy of the refractometer used. After adjusting the instrument temperature to 25°C, apply the test specimen to the refracting prism, read the refractive index, and read the compensator dial reading. From the correlation tables supplied with the instrument obtain the refractive dispersion. Calculate the specific optical dispersion by dividing refractive dispersion by the specific gravity of the oil.

#### 12.4 *Significance and Use:*

12.4.1 *Refractive Index* of an insulating liquid varies with its composition and with the nature and amount of contaminants held in solution. Where the refractive index of an insulating liquid when new is known, determinations made on the same liquid after periods of service may form a basis for estimating any change in composition or the degree of contamination acquired through solution.

12.4.2 *Specific Optical Dispersion* serves as a quick index to the amount of unsaturated compounds present in an oil. As the dispersion values for paraffinic and naphthenic compounds are nearly the same and are essentially independent of molecular weight and structural differences, values above a minimum of about 97 bear a direct relationship to the amount of aromatic compounds present in insulating oil.

### 13. Relative Density (Specific Gravity)

#### 13.1 *Scope:*

13.1.1 The methods used to measure relative density (specific gravity) may use a hydrometer, pycnometer, or an oscillating tube.

13.1.1.1 *Test Method D287*—Uses an API hydrometer and is limited to liquids having a Reid vapor pressure of 180 kPa (26 psi) or less.

13.1.1.2 *Test Method D1217*—Covers the use of a pycnometer to measure the relative density (specific gravity) of petroleum fractions.

13.1.1.3 *Test Method D1298*—Covers the use of a hydrometer to measure relative density (specific gravity) directly or the measurement of API gravity followed by conversion to relative density (specific gravity). This test method is limited to liquids having a Reid vapor pressure of 179 kPa (26 psi) or less. This test method is most suitable for use with mobile transparent liquids, although it can also be used with viscous oils if sufficient care is taken in the measurement.

13.1.1.4 *Test Method D1481*—Covers the determination of the densities of oils more viscous than 15 cSt at 20°C. The liquid should not have a vapor pressure greater than 13 kPa (100 mm Hg) at the test temperature. To measure the density of less viscous liquids more accurately than permitted by the hydrometer method, Test Method **D1217** is available.

13.1.1.5 *Test Method D4052*—Covers the measurement of relative density (specific gravity) by the measurement of change in oscillation frequency of a vibrating glass tube filled with test liquid.

### 13.2 Definition:

13.2.1 *relative density (specific gravity)*—the ratio of the mass (weighed in vacuum) of a given volume of liquid at 15.6°C (60°F) to the mass of an equal volume of pure water at the same temperature. When reporting results, explicitly state the reference temperature, for example, specific gravity 15.6/15.6°C.

### 13.3 Summary of Test Method:

13.3.1 API gravity may be measured at the oil temperature using a hydrometer (Test Methods **D287** or **D1298**) and converting to 15.6°C using Guide **D1250**.

13.3.2 Relative density (specific gravity) may be measured at the oil temperature using a hydrometer (Test Method **D1298**) and converted to 15.6°C using Guide **D1250**.

13.3.3 *Test Method D1481*—The liquid is drawn into the bicapillary pycnometer through the removable siphon arm and adjusted to volume at the temperature of test. After equilibration at the test temperature, liquid levels are read; and the pycnometer is removed from the thermostated bath, cooled to room temperature, and weighed. Density or relative density (specific gravity), as desired, is then calculated from the volume at the test temperature, and the weight of the sample. The effect of air buoyancy is included in the calculation.

### 13.4 Significance and Use:

13.4.1 Electrical insulating oils are usually sold on the basis of volume delivered at 15.6°C (60°F). Delivery is often made on the basis of net weight of product in drums, and the specific gravities often are measured at temperatures other than 15.6°C. The values of relative density (specific gravity) at 15.6°C must be known to calculate the volume at 15.6°C of the oil delivered.

13.4.2 The relative density (specific gravity) of a mineral insulating oil influences the heat transfer rates and may be pertinent in determining suitability for use in specific applications. In certain cold climates, ice may form in de-energized transformers exposed to temperatures below 0°C, and the maximum specific gravity of the oil used in such equipment should be at a value that will ensure that ice will not float in the oil at any temperature the oil might attain.

13.4.3 When making additions of insulating liquid to apparatus in service, a difference in relative density (specific gravity) may indicate a tendency of the two bodies of liquid to remain in separate layers rather than mixing into a homogeneous single body of liquid. Such conditions have caused serious overheating of self-cooled apparatus. Suitable precautions should be taken to ensure mixing.

## 14. Specific Heat

14.1 *Scope*—This test method covers determination of the specific heat of electrical insulating liquids of petroleum origin.

### 14.2 Definition:

14.2.1 *specific heat (or heat capacity) of a substance*—a thermodynamic property that is a measure of the amount of energy required to produce a given temperature change within a unit quantity of that substance. The standard unit of heat capacity is Joules/Kg°C at some defined temperature; specific heat is dimensionless as it is the ratio of the substance's heat capacity relative to that of water.

14.3 *Summary of Test Method*—The specific heat is determined by Test Method **D2766**. The measurement is made by heating a test specimen at a known and fixed rate. Once dynamic heating equilibrium is obtained, the heat flow is recorded as a function of temperature. The heat flow normalized to specimen mass and heating rate is directly proportional to the specimen's specific heat capacity.

14.4 *Significance and Use*—A knowledge of the specific heat is helpful in designing adequate heat transfer properties for electrical apparatus. A higher specific heat value indicates a more efficient heat transfer medium.

## 15. Thermal Conductivity

15.1 *Scope*—This test method covers the determination of the thermal conductivity of electrical insulating liquids of petroleum origin.

### 15.2 Definition:

15.2.1 *thermal conductivity*—the ability of a substance to transfer energy as heat in the absence of mass transport phenomena. The standard unit of thermal conductivity is as follows:

$$W/(mK) \text{ (Cal/cm s } ^\circ\text{C)}$$

15.3 *Summary of Test Method*—The thermal conductivity is determined by Test Method **D2717**. This test method measures the temperature gradient produced across the liquid by a known amount of energy introduced into the test cell by an electrically heated platinum element.

15.4 *Significance and Use*—A knowledge of thermal conductivity is helpful in designing adequate heat transfer properties for electrical apparatus. A high value indicates a good heat transfer efficiency property for the liquid.

## 16. Turbidity

16.1 *Scope*—This test method determines the amount of suspended particulate matter in electrical insulating oil of petroleum origin.

### 16.2 Definition: