



SLOVENSKI STANDARD
oSIST prEN ISO 3262-3:2022
01-december-2022

Polnila za barve - Specifikacije in metode preskušanja - 3. del: Pobelitev (ISO/DIS 3262-3:2022)

Extenders for paints - Specifications and methods of test - Part 3: Blanc fixe (ISO/DIS 3262-3:2022)

Füllstoffe - Anforderungen und Prüfverfahren - Teil3: Blanc fixe (ISO/DIS 3262-3:2022)

Matières de charge pour peintures - Spécifications et méthodes d'essai - Partie 3: Blanc fixe (ISO/DIS 3262-3:2022)

<https://standards.iteh.ai/catalog/standards/sist/791eebe5-9650-4e61-ae2a-1e20c0000000/sist-pr-en-iso-3262-3-2022>

Ta slovenski standard je istoveten z: prEN ISO 3262-3

ICS:

87.060.10 Pigmenti in polnila Pigments and extenders

oSIST prEN ISO 3262-3:2022

en,fr,de

DRAFT INTERNATIONAL STANDARD

ISO/DIS 3262-3

ISO/TC 256

Secretariat: DIN

Voting begins on:
2022-09-20Voting terminates on:
2022-12-13

Extenders — Specifications and methods of test —

Part 3: Blanc fixe

*Matières de charge — Spécifications et méthodes d'essai —**Partie 3: Blanc fixe*

ICS: 87.060.10

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 3262-3:2022](https://standards.iteh.ai/catalog/standards/sist/791eebe5-9650-4e61-ae2a-4eabd27a2c4b/osist-pren-iso-3262-3-2022)<https://standards.iteh.ai/catalog/standards/sist/791eebe5-9650-4e61-ae2a-4eabd27a2c4b/osist-pren-iso-3262-3-2022>

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 3262-3:2022(E)

© ISO 2022

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 3262-3:2022](https://standards.iteh.ai/catalog/standards/sist/791eebe5-9650-4e61-ae2a-4eabd27a2c4b/osist-pren-iso-3262-3-2022)

<https://standards.iteh.ai/catalog/standards/sist/791eebe5-9650-4e61-ae2a-4eabd27a2c4b/osist-pren-iso-3262-3-2022>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Requirements and test methods	2
5 Sampling	2
6 Determination of BaSO₄ content (gravimetric)	2
6.1 General.....	2
6.2 Reagents.....	3
6.3 Apparatus.....	3
6.4 Procedure.....	3
6.5 Expression of results.....	4
7 Determination of BaSO₄ content (X-ray fluorescent analysis)	5
7.1 General.....	5
7.2 Reagents.....	5
7.3 Apparatus.....	5
7.4 Procedure.....	5
7.5 Expression of results.....	5
8 Test report	5
Bibliography	6

Web STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 3262-3:2022](https://standards.iteh.ai/catalog/standards/sist/791eebe5-9650-4e61-ae2a-4eabd27a2c4b/osist-pren-iso-3262-3-2022)

<https://standards.iteh.ai/catalog/standards/sist/791eebe5-9650-4e61-ae2a-4eabd27a2c4b/osist-pren-iso-3262-3-2022>

ISO/DIS 3262-3:2022(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 256, *Pigments, dyestuffs and extenders*.

This second edition cancels and replaces the first edition (ISO 3262-3:1998), which has been technically revised.

The main changes are as follows:

- the title has been changed to "Extenders";
- additional method for BaSO₄ content added (X-ray fluorescent analysis);
- gravimetric method for BaSO₄ content simplified;
- ammonium carbamate solution replaces sodium carbonate solution in gravimetric method;
- the normative references have been updated and the text has been editorially revised.

A list of all parts in the ISO 3262 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Extenders — Specifications and methods of test —

Part 3: Blanc fixe

1 Scope

This document specifies requirements and corresponding methods of test for blanc fixe.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 787-2, *General methods of test for pigments and extenders — Part 2: Determination of matter volatile at 105 °C*

ISO 787-3, *General methods of test for pigments and extenders — Part 3: Determination of matter soluble in water — Hot extraction method*

ISO 787-5, *General methods of test for pigments and extenders — Part 5: Determination of oil absorption value*

ISO 787-7, *General methods of test for pigments and extenders — Part 7: Determination of residue on sieve — Water method — Manual procedure*

ISO 787-9, *General methods of test for pigments and extenders — Part 9: Determination of pH value of an aqueous suspension*

ISO 787-14, *General methods of test for pigments and extenders — Part 14: Determination of resistivity of aqueous extract*

ISO 3262-1, *Extenders — Specifications and methods of test — Part 1: Introduction and general test methods*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 4793, *Laboratory sintered (fritted) filters — Porosity grading, classification and designation*

ISO 12677, *Chemical analysis of refractory products by X-ray fluorescence (XRF) — Fused cast-bead method*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

ISO 18451-1, *Pigments, dyestuffs and extenders — Terminology — Part 1: General terms*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 18451-1 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

ISO/DIS 3262-3:2022(E)

— IEC Electropedia: available at <https://www.electropedia.org/>

3.1

blanc fixe

synthetic (as opposed to naturally occurring) barium sulfate, produced by a precipitation process

4 Requirements and test methods

For blanc fixe complying with this part of ISO 3262, the essential requirements are specified in [Table 1](#) and the conditional requirements are listed in [Table 2](#).

Table 1 — Essential requirements

Characteristic	Unit	Requirement	Test method
BaSO ₄ content, min.	% mass fraction	95	See Clause 6 or Clause 7 ^a
Residue on 45 µm sieve, max.	% mass fraction	0,2	ISO 787-7 ^b
Matter volatile at 105 °C, max.	% mass fraction	0,5 ^c	ISO 787-2 ^d
Loss on ignition, max.	% mass fraction	3 ^b	ISO 3262-1
Matter soluble in water, max.	% mass fraction	0,5	ISO 787-3
pH value of aqueous suspension		6 to 10	ISO 787-9

^a Both methods (gravimetric or X-ray fluorescent analysis) can be used.

^b But using a brush to obtain reproducible results.

^c For ultra-fine and surface-treated types, higher values are possible. The requirements for these types shall therefore be agreed between the interested parties.

^d By agreement between the interested parties, test portions other than 10 g may be used.

Table 2 — Conditional requirements

Characteristic	Unit	Requirement	Test method
Particle size distribution (instrumental method)	% mass fraction	To be agreed between the interested parties ^a	
Colour		To be agreed between the interested parties	ISO 3262-1
Lightness			To be agreed between the interested parties
Oil absorption value	g/100 g		ISO 787-5
Resistivity of aqueous extract	Ω m		ISO 787-14

^a A general description of a sedimentation method using X-ray absorption is given in EN 725-5.

5 Sampling

Take a representative sample of the product to be tested, as specified in ISO 15528.

6 Determination of BaSO₄ content (gravimetric)¹⁾

6.1 General

For precipitated barium sulfate, the acid-insoluble barium compounds, calculated as barium sulfate, are taken as the BaSO₄ content. Strontium sulfate, which is precipitated similar and might be present as well, can be subtracted using additional e.g. inductively coupled plasma optical emission spectrometry (ICP-OES) analysis. Alternatively, X-ray fluorescent analysis can be used to determine the BaSO₄ content (see [Clause 7](#)) instead of the gravimetric determination.

1) This determination includes strontium sulfate.

6.2 Reagents

Use only reagents of recognized analytical grade and only water of at least grade 3 purity as specified in ISO 3696.

6.2.1 Hydrochloric acid, CAS²⁾ No. 7647-01-0, concentrated, approximately 37 % mass fraction, $\rho \approx 1,19$ g/ml.

6.2.2 Hydrochloric acid, CAS No. 7647-01-0, diluted 1 + 3.

Add 1 part by volume of concentrated hydrochloric acid ([6.2.1](#)) to 3 parts by volume of water.

6.2.3 Sulfuric acid, CAS No. 7664-93-9, diluted 1 + 9.

Add 1 part by volume of concentrated sulfuric acid [approximately 96 % mass fraction, $\rho \approx 1,84$ g/ml] slowly to 9 parts by volume of water.

6.2.4 Ammonium carbamate solution, CAS No. 1111-78-0, 10 %.

Dissolve 10 g of ammonium carbamate in 90 ml of water.

6.2.5 Fusion mixture.

Mix equal parts by mass of sodium carbonate, CAS No. 497-91-8, and potassium carbonate, CAS No. 584-08-7.

6.2.6 Ammonia solution, CAS No. 1336-21-6, approximately 25 % mass fraction, $\rho \approx 0.903$ g/ml.

6.2.7 Ammonium sulfate solution, CAS No. 7783-20-2, 10 %.

Dissolve 10 g of ammonium sulfate in 90 ml of water.

6.3 Apparatus

Use ordinary laboratory apparatus and glassware, together with the following:

6.3.1 Platinum crucible, with lid, 40 ml.

6.3.2 Sintered-silica crucible.

6.3.3 Air oven, capable of being maintained at (105 ± 2) °C.

6.3.4 Muffle furnace.

6.3.5 Balance, with an accuracy of 0,0001 g.

6.3.6 Desiccator, containing a suitable desiccant, for example dried silica gel.

6.4 Procedure

Weigh 19 g of the fusion mixture ([6.2.5](#)) into the platinum crucible ([6.3.1](#)). Add approximately 1 g (m_0), weighed to the nearest 0.1 mg, of the test sample, previously dried in accordance with ISO 787-2. Mix well and place a further 1 g of the fusion mixture on top of the mixture in the crucible.

2) Chemistry Abstracts Service Registry Number

ISO/DIS 3262-3:2022(E)

Heat the crucible, fitted with its lid, at bright-red heat (800 °C to 900 °C) for minimum 15 min. Then allow the crucible and lid to cool.

Measure 250 ml of hot water into a 500 ml beaker (A) and place into it the crucible and lid. Heat gently for at least 15 min to extract the melt until it is disintegrated, then, using clean nickel or other suitable tongs, remove the crucible and lid. Rinse the crucible and lid and tongs with a small amount of hot water into the beaker. Remove any white residue from the crucible with a rubber-tipped glass stirring rod and rinse again with a small amount of hot water. Let the solution in the beaker completely cool down for at least 4 h or over night.

Measure 95 ml of water and 5 ml of concentrated hydrochloric acid (6.2.1) into a second 500 ml beaker (B) and put the crucible and lid into it.

Allow the aqueous fusion extract in beaker A to settle and decant the solution through a 125 mm fine-textured ashless filter paper. Wash the precipitate three times by decantation, using 10 ml portions of ammonium carbamate solution (6.2.4) and transfer to the filter paper. Repeat the washing three times with 5 ml portions of ammonium carbamate solution and discard the washings.

Remove the crucible and lid from the acid solution in beaker B and wash down with water into the beaker. Transfer this solution to beaker A, in which the melt was extracted, and add to it the filter paper and residue. Cover the beaker with a watch glass, boil for 5 min and after that allow the solution to cool down.

Transfer the solution into a 250 ml volumetric flask (C). 200 ml of this solution are transferred to a 1000 ml Erlenmeyer flask and diluted with water to 600 ml. Use ammonia solution (6.2.6) and hydrochloric acid (6.2.1) to adjust the pH to slightly acidic conditions. Heat the solution and add 40 ml ammonium sulfate solution (6.2.7), then stir the solution boiling for 30 min. Let the solution and precipitation in the flask completely cool down for at least 4 h or over night. Then filter through a 125 mm filter paper into a beaker, wash the filter paper thoroughly six times with 10 ml portions of hot water.

Transfer the filter paper to a sintered-silica crucible (6.3.2) which has been previously dried in the air oven (6.3.3) at (105 ± 2) °C, cooled in a desiccator (6.3.6) and weighed. Heat it in the muffle furnace (6.3.4) at a temperature of 800 °C to constant mass (approx. 4 h). Allow to cool in a desiccator. Add few drops of sulfuric acid (6.2.3) to oxidize potentially developed BaS to BaSO₄. Dry and heat in the muffle furnace at a temperature of 800 °C to constant mass (approx. 4 h) again. Allow to cool in a desiccator and weigh the precipitate to the nearest 0,1 mg (m_1).

If applicable determine strontium content of remaining solution in volumetric flask (C) with e.g. inductively coupled plasma optical emission spectrometry (ICP-OES). Subtract calculated SrSO₄ content from total result.

6.5 Expression of results

Calculate the BaSO₄ content $w(\text{BaSO}_4)$ (which here includes potential SrSO₄), expressed as a percentage by mass of barium sulfate, using [formula \(1\)](#)

$$w(\text{BaSO}_4) = \frac{m_1}{m_0} \times 100 \quad (1)$$

where

m_0 is the mass, in grams, of the test portion;

m_1 is the mass, in grams, of the precipitate.