



SLOVENSKI STANDARD
oSIST prEN ISO 3262-10:2023

01-maj-2023

Polnila - Specifikacije in preskusne metode - 10. del: Naravni talk/klorit v obliki lamel (ISO/DIS 3262-10:2023)

Extenders - Specifications and methods of test - Part 10: Natural talc/chlorite in lamellar form (ISO/DIS 3262-10:2023)

Füllstoffe - Anforderungen und Prüfverfahren - Teil 10: Verwachsungen von natürlichem plättchenförmigen Talk und Chlorit (ISO/DIS 3262-10:2023)

Matières de charge - Spécifications et méthodes d'essai - Partie 10: Mélange talc/chlorite naturel sous forme lamellaire (ISO/DIS 3262-10:2023)

Ta slovenski standard je istoveten z: prEN ISO 3262-10

ICS:

87.060.10 Pigmenti in polnila Pigments and extenders

oSIST prEN ISO 3262-10:2023 en,fr,de

DRAFT INTERNATIONAL STANDARD

ISO/DIS 3262-10

ISO/TC 256

Secretariat: DIN

Voting begins on:
2023-03-09

Voting terminates on:
2023-06-01

Extenders — Specifications and methods of test —

Part 10: Natural talc/chlorite in lamellar form

ICS: 87.060.10

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 3262-10:2023](https://standards.iteh.ai/catalog/standards/sist/6429d5d0-7a24-4591-a25f-b4928a0e29d5/osist-pren-iso-3262-10-2023)

<https://standards.iteh.ai/catalog/standards/sist/6429d5d0-7a24-4591-a25f-b4928a0e29d5/osist-pren-iso-3262-10-2023>

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 3262-10:2023(E)

© ISO 2023

iTeh STANDARD PREVIEW (standards.iteh.ai)

oSIST prEN ISO 3262-10:2023

<https://standards.iteh.ai/catalog/standards/sist/6429d5d0-7a24-4591-a25f-b4928a0e29d5/osist-pren-iso-3262-10-2023>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Requirements and test methods.....	2
5 Test report.....	3
Annex A (informative) Ternary diagram illustrating the mineralogical grades (A, B, C and D) of natural talc/chlorite in lamellar form.....	4

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 3262-10:2023](https://standards.iteh.ai/catalog/standards/sist/6429d5d0-7a24-4591-a25f-b4928a0e29d5/osist-pren-iso-3262-10-2023)

<https://standards.iteh.ai/catalog/standards/sist/6429d5d0-7a24-4591-a25f-b4928a0e29d5/osist-pren-iso-3262-10-2023>

ISO/DIS 3262-10:2023(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 256, *Pigments, dyestuffs and extenders* in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 298, *Pigments and extenders*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 3262-10:2000), which has been technically revised.

The main changes are as follows:

- the first part of the title has been changed to "Extenders";
- the determination of quartz and asbestos have been added to the essential requirements in [Table 1](#);
- the test method for particle size distribution in [Table 2](#) has been changed to ISO 8130-13;
- the normative references have been updated and the text has been editorially revised.

A list of all parts in the ISO 3262 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Extenders — Specifications and methods of test —

Part 10: Natural talc/chlorite in lamellar form

1 Scope

This document specifies requirements and corresponding methods of test for products made from naturally occurring talc/chlorite in lamellar form.

Note The mineralogical classes have been designated in accordance with products existing on the market (see [Annex A](#)).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 787-2, *General methods of test for pigments and extenders — Part 2: Determination of matter volatile at 105 °C*

ISO 787-3, *General methods of test for pigments and extenders — Part 3: Determination of matter soluble in water — Hot extraction method*

ISO 787-7, *General methods of test for pigments and extenders — Part 7: Determination of residue on sieve — Water method — Manual procedure*

ISO 787-9, *General methods of test for pigments and extenders — Part 9: Determination of pH value of an aqueous suspension*

ISO 787-14, *General methods of test for pigments and extenders — Part 14: Determination of resistivity of aqueous extract*

ISO 787-18, *General methods of test for pigments and extenders — Part 18: Determination of residue on sieve — Mechanical flushing procedure*

ISO 3262-1, *Extenders — Specifications and methods of test — Part 1: Introduction and general test methods*

ISO 3262-2, *Extenders — Specifications and methods of test — Part 2: Barytes (natural barium sulfate)*

ISO 8130-13, *Coating powders — Part 13: Particle size analysis by laser diffraction*

ISO 14966, *Ambient air — Determination of numerical concentration of inorganic fibrous particles — Scanning electron microscopy method*

ISO 18451-1, *Pigments, dyestuffs and extenders — Terminology — Part 1: General terms*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 18451-1 and the following apply.

ISO/DIS 3262-10:2023(E)

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1 natural talc/chlorite
 natural association of hydrated magnesium silicate $3\text{MgO}\cdot 4\text{SiO}_2\cdot \text{H}_2\text{O}$ | $\text{Mg}_3[(\text{OH})_2/\text{Si}_4\text{O}_{10}]$ and hydrated magnesium aluminium silicate $\text{MgAl}_2[(\text{OH})_2/\text{Al}_2\text{Si}_2\text{O}_{10}]\cdot \text{Mg}_3(\text{OH})_6$ in lamellar form

4 Requirements and test methods

For natural talc/chlorite in lamellar form complying with document, the essential requirements are specified in [Table 1](#) and the conditional requirements are listed in [Table 2](#). The test method in [Tables 1](#) and [2](#) shall be in accordance with the standards listed.

Table 1 — Essential requirements

Characteristic	Unit	Requirement				Test method
		Grade A	Grade B	Grade C	Grade D	
Talc content	% mass fraction	100 to 85	85 to 70	70 to 30	30 to 0	X-ray diffraction or as agreed between the interested parties
Chlorite content		0 to 15	5 to 30	20 to 70	60 to 100	
Total talc/chlorite content, min.		90				
Loss on ignition	% mass fraction	4,7 to 9,5	5,9 to 11,1	7,0 to 13,9	9,8 to 16,0	ISO 3262-1
Matter volatile at 105 °C, max.	% mass fraction	0,5				ISO 787-2 ^a
Matter soluble in water, max.	% mass fraction	0,2				ISO 787-3
pH value of aqueous suspension	—	8 to 10 ^b				ISO 787-9
Quartz content, max.	% mass fraction	0,5				X-ray diffraction
Asbestos	—	Non asbestos fibres detectable using SEM/ED				ISO 14966
^a By agreement between the interested parties, test portions other than 10 g may be used.						
^b These values do not take account of the effect on the result of any surface treatment.						

Table 2 — Conditional requirements

Characteristic	Unit	Requirement				Test method
		Grade A	Grade B	Grade C	Grade D	
Residue on 45 µm sieve	% mass fraction	To be agreed between the interested parties				ISO 787-7 or ISO 787-18
Particle size distribution (instrumental method)	% mass fraction					ISO 8130-13
Matter soluble in hydrochloric acid	% mass fraction					ISO 3262-2:—, Clause 8
Colour	—					ISO 3262-1
Lightness (tristimulus value Y)	—					To be agreed between the interested parties
Resistivity of aqueous extract	Ω·m					ISO 787-14

5 Test report

The test report shall contain at least the following information:

- a) all details necessary to identify the product tested;
- b) a reference to this document, i.e. ISO 3262-10:—;
- c) the results of the test, the method used, and whether or not the product complies with the relevant specification limits;
- d) any deviation from the method of test specified;
- e) any unusual features (anomalies) observed during the test;
- f) the date of the test.

Annex A (informative)

Ternary diagram illustrating the mineralogical grades (A, B, C and D) of natural talc/chlorite in lamellar form

