



## **Standard Test Methods for Determining Bulk Density of Granular Carriers and Granular Pesticides<sup>1</sup>**

This standard is issued under the fixed designation E 727; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### **1. Scope**

1.1 These test methods are used to determine bulk density of granular carriers and granular pesticides by measuring either free-fall bulk density (Test Method A) or loose-fill bulk density (Test Method B).

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific hazard statements see Section 4.

### **2. Referenced Documents**

#### **2.1 ASTM Standards:**

E 725 Test Method for Sampling Granular Carriers and Granular Pesticides<sup>2</sup>

### **3. Significance and Use**

3.1 These test methods were designed principally with clay, corncob, nut shell, or sand granular carriers, and granular pesticide products, but need not be limited to these materials. There may be more appropriate test methods for other types of granular carriers or pesticide products. The differences in the following test methods are slight, but they offer a choice of a recognized test procedure.

### **4. Hazards**

4.1 Before testing granular pesticides, read the precautionary statements on the product label. Take proper precautions to prevent skin contact and inhalation of the fines and vapors. Take care to prevent contamination of the surrounding area. Always wear the appropriate safety equipment and, where indicated, wear respiratory devices approved by NIOSH for the product being tested.

### **5. Summary of Test Method A—Free-Fall Bulk Density**

5.1 A tared 500-mL cylinder is filled with the granular carrier or granular pesticide. The weight of the sample is

measured and the bulk density calculated in pounds per cubic foot.

### **6. Apparatus**

6.1 *Balance*, sensitivity of 1 g.

6.2 *Cylinder*, graduated, capacity 500 mL. The cylinder should be calibrated at the 500-mL mark by using 500 g water at 20°C. The cylinder is cut off at the 500-mL mark and ground smooth.

6.3 *Funnel*, powder, 6 in. (152 mm) in diameter at the top, bottom stem opening of 1-in. (25-mm) diameter, and sides having a slope of approximately 60°.

6.4 *Spatula*, large with 2-in. (51-mm) wide blade.

6.5 *Beaker*, glass, metal, or plastic, 600-mL capacity.

6.6 *Pan*, metal or plastic, 8 in. (203 mm) in diameter with 2-in. (51-mm) sides to collect overflow of cylinder.

6.7 *Ring Stand and Ring Clamp*.

### **7. Procedure**

7.1 Weigh the 500-mL graduated cylinder and place it in the overflow pan.

7.2 Support the funnel on a ring which is then affixed to a ring stand such that the top of the funnel is horizontal and rigidly in position. Adjust the height of the funnel so that its bottom position is 1.5 in. (38 mm) above the top center of the 500-mL graduated cylinder.

7.3 Hold a piece of flat metal (such as a wide spatula or similar tool) against the bottom of the funnel stem. Fill a 600-mL beaker with a representative sample of the granular carrier as defined in Test Method E 725 and pour into the funnel. Quickly remove the metal plate, allowing the granules to fall into the graduate of their own accord.

7.4 Hold the graduate firmly and level off the granules to the top of the graduate with the straight edge of the spatula. Avoid jiggling or vibrating the cylinder.

7.5 Tap the cylinder to tamp the particles into the cylinder away from the top, to avoid spillage losses during handling.

7.6 Reweigh the cylinder and determine the weight of the sample to the nearest 1 g.

7.7 Determine the weight on duplicate samples.

### **8. Calculation**

8.1 For the granular carrier or granular pesticide, calculate the free-fall density as follows:

<sup>1</sup> These test methods are under the jurisdiction of ASTM Committee E-35 on Pesticides and are the direct responsibility of Subcommittee E35.22 on Pesticide Equipment.

Current edition approved March 15, 1991. Published May 1991. Originally published as E 727 – 80. Last previous edition E 727 – 86.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 11.05.