



**SLOVENSKI STANDARD**  
**oSIST prEN ISO 3262-14:2022**

**01-december-2022**

---

**Polnila za barve - Specifikacije in metode preskušanja - 14. del: Kristobalit  
(ISO/DIS 3262-14:2022)**

Extenders - Specifications and methods of test - Part 14: Cristobalite (ISO/DIS 3262-14:2022)

Füllstoffe - Anforderungen und Prüfverfahren - Teil 14: Cristobalit (ISO/DIS 3262-14:2022)

Matières de charge - Spécifications et méthodes d'essai - Partie 14: Cristobalite  
(ISO/DIS 3262-14:2022)

**Ta slovenski standard je istoveten z: prEN ISO 3262-14**

---

**ICS:**

87.060.10      Pigmenti in polnila                      Pigments and extenders

**oSIST prEN ISO 3262-14:2022                      en,fr,de**



# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 3262-14

ISO/TC 256

Secretariat: DIN

Voting begins on:  
2022-10-04

Voting terminates on:  
2022-12-27

---

---

### Extenders — Specifications and methods of test —

#### Part 14: Cristobalite

ICS: 87.060.10

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

[oSIST prEN ISO 3262-14:2022](https://standards.iteh.ai/catalog/standards/sist/e9cb0bf7-2353-4b6d-b7ac-abe14d55ed04/osist-pren-iso-3262-14-2022)

<https://standards.iteh.ai/catalog/standards/sist/e9cb0bf7-2353-4b6d-b7ac-abe14d55ed04/osist-pren-iso-3262-14-2022>

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

**ISO/CEN PARALLEL PROCESSING**



Reference number  
ISO/DIS 3262-14:2022(E)

© ISO 2022

# iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 3262-14:2022](https://standards.iteh.ai/catalog/standards/sist/e9cb0bf7-2353-4b6d-b7ac-abe14d55ed04/osist-pren-iso-3262-14-2022)

<https://standards.iteh.ai/catalog/standards/sist/e9cb0bf7-2353-4b6d-b7ac-abe14d55ed04/osist-pren-iso-3262-14-2022>



## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword.....	iv
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>1</b>
<b>4 Requirements and test methods.....</b>	<b>2</b>
<b>5 Sampling.....</b>	<b>2</b>
<b>6 Determination of silica content.....</b>	<b>2</b>
6.1 Reagents.....	2
6.2 Apparatus.....	3
6.3 Procedure.....	3
6.4 Expression of results.....	3
<b>7 Test report.....</b>	<b>4</b>
<b>Bibliography.....</b>	<b>5</b>

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 3262-14:2022](https://standards.iteh.ai/catalog/standards/sist/e9cb0bf7-2353-4b6d-b7ac-abe14d55ed04/osist-pren-iso-3262-14-2022)

<https://standards.iteh.ai/catalog/standards/sist/e9cb0bf7-2353-4b6d-b7ac-abe14d55ed04/osist-pren-iso-3262-14-2022>

## ISO/DIS 3262-14:2022(E)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 256, *Pigments, dyestuffs and extenders*.

This second edition cancels and replaces the first edition (ISO 3262-14:2000), which has been technically revised.

The main changes are as follows:

- the first part of the title has been changed to "Extenders";
- the test method for particle size distribution in [Table 2](#) has been changed to ISO 8130-13;
- the normative references have been updated and the text has been editorially revised.

A list of all parts in the ISO 3262 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Extenders — Specifications and methods of test —

## Part 14: Cristobalite

### 1 Scope

This document specifies requirements and corresponding methods of test for cristobalite.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 787-2, *General methods of test for pigments and extenders — Part 2: Determination of matter volatile at 105 °C*

ISO 787-3, *General methods of test for pigments and extenders — Part 3: Determination of matter soluble in water — Hot extraction method*

ISO 787-5, *General methods of test for pigments and extenders — Part 5: Determination of oil absorption value*

ISO 787-7, *General methods of test for pigments and extenders — Part 7: Determination of residue on sieve — Water method — Manual procedure*

ISO 787-9, *General methods of test for pigments and extenders — Part 9: Determination of pH value of an aqueous suspension*

ISO 787-14, *General methods of test for pigments and extenders — Part 14: Determination of resistivity of aqueous extract*

ISO 3262-1, *Extenders — Specifications and methods of test — Part 1: Introduction and general test methods*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 8130-13, *Coating powders — Part 13: Particle size analysis by laser diffraction*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

ISO 18451-1, *Pigments, dyestuffs and extenders — Terminology — Part 1: General terms*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 18451-1 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

## ISO/DIS 3262-14:2022(E)

**3.1 cristobalite**  
low-temperature modification of crystalline silicon dioxide with theoretical density of 2,35 g/cm<sup>3</sup>

## 4 Requirements and test methods

For cristobalite complying with this document, the essential requirements are specified in [Table 1](#) and the conditional requirements are listed in [Table 2](#). The test method in [Tables 1](#) and [2](#) shall be in accordance with the standards listed.

**Table 1 — Essential requirements**

Characteristic	Unit	Requirement	Test method
Cristobalite content, min.	% mass fraction	60	X-ray diffraction
Silicia content, min.	% mass fraction	98	See <a href="#">clause 6</a>
Matter volatile at 105 °C, max.	% mass fraction	0,2	ISO 787-2 <sup>a</sup>
Loss on ignition, max.	% mass fraction	0,2 0,5 <sup>b</sup>	ISO 3262-1
Matter soluble in water, max.	% mass fraction	0,2	ISO 787-3
pH value of aqueous suspension	—	6 to 9 6 to 10 <sup>b</sup>	ISO 787-9

<sup>a</sup> Another method may be agreed between the interested parties provided it gives the same results.  
<sup>b</sup> These values take into account the effect on the result if the product has undergone surface treatment.

**Table 2 — Conditional requirements**

Characteristic	Unit	Requirement	Test method
Residue on 45 µm sieve	% mass fraction	To be agreed between the interested parties	ISO 787-7
Particle size distribution (instrumental method)	% mass fraction	To be agreed between the interested parties	ISO 8130-13
Colour	—	To be agreed between the interested parties	ISO 3262-1
Lightness	—		To be agreed between the interested parties
Resistivity of aqueous extract	Ω · m		ISO 787-14
Oil absorption value	g/100 g		ISO 787-5

## 5 Sampling

Take a representative sample of the product to be tested, in accordance with ISO 15528.

## 6 Determination of silica content<sup>1)</sup>

### 6.1 Reagents

Use only reagents of recognized analytical grade and only water of a least grade 3 purity as specified in ISO 3696.

1) This determination includes strontium sulfate.



**6.1.1 Sulfuric acid**, CAS<sup>2)</sup> No. 7664-93-9, diluted 1 + 1.

Add 1 part by volume of concentrated sulfuric acid [approximately 96 % mass fraction,  $\rho \approx 1,84$  g/ml] slowly to 1 part by volume of water.

**6.1.2 Hydrofluoric acid**, CAS No. 7664-39-3, [approximately 40 % mass fraction,  $\rho \approx 1,13$  g/ml].**6.2 Apparatus**

Use ordinary laboratory apparatus and glassware, together with the following:

**6.2.1 Platinum dish.****6.2.2 Muffle furnace.****6.2.3 Balance**, with an accuracy of 0,0001 g.**6.2.4 Desiccator.****6.3 Procedure**

Weigh, to the nearest 1 mg, approximately 2 g of the test sample, previously dried at 105 °C in accordance with ISO 787-2, into the tared platinum dish (6.2.1), ignite in the muffle furnace (6.2.2) at  $1\ 000\ \text{°C} \pm 25\ \text{°C}$  to constant mass ( $m_1$ ) and allow to cool in a desiccator (6.2.4) containing phosphorus pentoxide.

Add approximately 1 ml of sulfuric acid (6.1.1). Heat the platinum dish gently until fuming ceases and then continue the heating at 900 °C for 15 min in the muffle furnace. Remove from the furnace, allow to cool in a desiccator and weigh to the nearest 0,1 mg ( $m_2$ ).

Add to the residue in the platinum dish 15 ml of the hydrofluoric acid (6.1.2) and 1 ml of the sulfuric acid (6.1.1) and evaporate to a syrup, taking care to avoid loss by spitting. Cool the dish and wash the sides down with small quantities of water. Then add a further 10 ml of hydrofluoric acid and evaporate to dryness, Heat the residue on a hot-plate until white fumes are no longer evolved, then ignite in the muffle furnace at 900 °C for 15 min. Remove the dish from the furnace, cool in the desiccator and weigh to the nearest 0,1 mg ( $m_3$ ).

**6.4 Expression of results**

Calculate the silica content  $w(\text{SiO}_2)$ , expressed as a percentage by mass of barium sulfate, using the [Formula \(1\)](#)

$$w(\text{SiO}_2) = \frac{m_2 - m_3}{m_1} \times 100 \quad (1)$$

where

$m_1$  is the mass, in grams, of the ignited residue;

$m_2$  is the mass, in grams, after treatment with sulfuric acid and igniting;

$m_3$  is the mass, in grams, after treatment with hydrofluoric acid and igniting.

2) Chemistry Abstracts Service Registry Number.

**ISO/DIS 3262-14:2022(E)****7 Test report**

The test report shall contain at least the following information:

- a) all details necessary to identify the product tested;
- b) a reference to this document, i. e. ISO 3262-14:—;
- c) the results of the test, the method used, and whether or not the product complies with the relevant specification limits;
- d) any deviation from the method of test specified;
- e) any unusual features (anomalies) observed during the test;
- f) the date of the test.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[oSIST prEN ISO 3262-14:2022](https://standards.iteh.ai/catalog/standards/sist/e9cb0bf7-2353-4b6d-b7ac-abe14d55ed04/osist-pren-iso-3262-14-2022)

<https://standards.iteh.ai/catalog/standards/sist/e9cb0bf7-2353-4b6d-b7ac-abe14d55ed04/osist-pren-iso-3262-14-2022>