



Designation: B564 – 10

Standard Specification for Nickel Alloy Forgings¹

This standard is issued under the fixed designation B564; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification² covers forgings of nickel alloy UNS N02200, Ni-Cu alloy UNS N04400, Ni-Cr-Fe alloys UNS N06600, UNS N06603, and UNS N06690, Ni-Cr-Mo-Nb alloy UNS N06625, Ni-Cr-Mo-Si alloy UNS N06219, low-carbon Ni-Mo-Cr alloys UNS N10276 and UNS N06022, Ni-Cr-Mo-W alloy UNS N06110, low-carbon Ni-Cr-Mo-W alloy UNS N06686, Ni-Fe-Cr-Mo-Cu alloy UNS N08825, Fe-Ni-Cr-Mo-N alloy UNS N08367, low-carbon Ni-Cr-Mo alloys UNS N06035, UNS N06058, and UNS N06059, low carbon Ni-Cr-Mo-Cu alloy UNS N06200, low-carbon Ni-Mo-Cr alloy UNS N10362, Ni-Mo-Cr-Fe alloy UNS N10242, Ni-Mo alloys UNS N10665 and UNS N10675, low-carbon Ni-Fe-Cr-Mo-Cu alloy UNS N08031, Ni-Cr-W-Mo alloy UNS N06230, Ni-Cr-Co-Mo alloy UNS N06617, Ni-Co-Cr-Si alloy UNS N12160, Ni-Fe-Cr alloys, Ni-Mo alloy UNS N10629, Ni-Cr-Fe-Al alloy UNS N06025, Ni-Cr-Fe-Si alloy UNS N06045, Low-Carbon Ni-Mo-Cr-Ta alloy UNS N06210, Ni-Mo-Cr-Fe alloy UNS N10624, and low-carbon Cr-Ni-Fe-N alloy UNS R20033*.

1.1.1 The nickel-iron-chromium alloys are UNS N08120, UNS N08800, UNS N08810, and UNS N08811. Alloy UNS N08800 is normally employed in service temperatures up to and including 1100°F (593°C). Alloys UNS N08810, N08120, and UNS N08811 are normally employed in service temperatures above 1100°F where resistance to creep and rupture is required, and are annealed to develop controlled grain size for optimum properties in this temperature range.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the*

responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer; to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:³

B880 Specification for General Requirements for Chemical Check Analysis Limits for Nickel, Nickel Alloys and Cobalt Alloys

E8 Test Methods for Tension Testing of Metallic Materials

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E76 Test Methods for Chemical Analysis of Nickel-Copper Alloys⁴

E112 Test Methods for Determining Average Grain Size

E350 Test Methods for Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

E1473 Test Methods for Chemical Analysis of Nickel, Cobalt, and High-Temperature Alloys

2.2 Military Standards:⁵

MIL-STD-129 Marking for Shipment and Storage

MIL-STD-271 Nondestructive Testing Requirements for Metals

3. Ordering Information

3.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered under this specification. Examples of such requirements include, but are not limited to, the following:

3.1.1 Alloy (**Table 1**).

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved Oct. 1, 2010. Published October 2010. Originally approved in 1972. Last previous edition approved in 2006 as B564 – 06A. DOI: 10.1520/B0564-10.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SB-564 in Section II of that Code.

* New designations established in accordance with ASTM E527 and SAE J1086, Practice for Numbering Metals and Alloys (UNS).

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Withdrawn. The last approved version of this historical standard is referenced on www.astm.org.

⁵ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, http://www.dodssp.daps.mil.

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Chemical Requirements

Composition, %

Element	Nickel-Copper Alloy	Nickel-Chromium-Iron Alloy	Nickel-Chromium-Iron Alloy	Nickel-Iron Chromium Alloy	Nickel-Iron-Chromium Alloy	Nickel-Iron-Chromium Alloy	Nickel-Chromium-Iron-Aluminum Alloy	Nickel-Chromium-Iron-Aluminum Alloy	Nickel-Chromium-Iron-Silicon Alloy	Low-Carbon Nickel-Molybdenum-Chromium-Tantalum Alloy
	UNS N04400	UNS N06600	UNS N06690	UNS N08120	UNS N08800	UNS N08810	UNS N06603	UNS N06025	UNS N06045	UNS N06210
Nickel	63.0 ^A min	72.0 ^A min	58.0 min ^A	35.0–39.0	30.0–35.0	30.0–35.0	balance ^A	balance	45 min	remainder ^A
Copper	28.0–34.0	0.5 max	0.5 max	0.50 max	0.75 max	0.75 max	0.5 max	0.10 max	0.3 max	...
Iron	2.5 max	6.0–10.0	7.0–11.0	remainder	39.5 min ^A	39.5 min ^A	8.0–11.0	8.0–11.0	21.0–25.0	1.0 max
Manganese	2.0 max	1.0 max	0.5 max	1.5	1.5 max	1.5 max	0.15 max	0.15	1.0	0.5 max
Carbon	0.3 max	0.15 max	0.05 max	0.02–0.10	0.10 max	0.05–0.10	0.20–0.40	0.15–0.25	0.05–0.12	0.015 max
Silicon	0.5 max	0.5 max	0.5 max	1.0	1.0 max	1.0 max	0.5 max	0.5	2.5–3.0	0.08 max
Sulfur, max	0.024	0.015	0.015	0.03	0.015	0.015	0.010	0.01	0.010	0.02
Chromium	...	14.0–17.0	27.0–31.0	23.0–27.0	19.0–23.0	19.0–23.0	24.0–26.0	24.0–26.0	26.0–29.0	18.0–20.0
Aluminum	0.40 max	0.15–0.60	0.15–0.60	2.4–3.0	1.8–2.4
Titanium	0.20 max	0.15–0.60	0.15–0.60	0.01–0.25	0.1–0.2
Columbium (Nb) + tantalum	0.4–0.9
Molybdenum	2.50 max	18.0–20.0
Phosphorus	0.040 max	0.02 max	0.02 max	0.02 max	0.02 max
Tungsten	2.50 max
Cobalt, max	3.0	1.0
Vanadium, max	0.35
Nitrogen	0.15–0.30
Boron	0.010 max
Lanthanum
Aluminum + Titanium
Nickel + Molybdenum
Columbium (Nb) max
Tantalum	1.5–2.2
Zirconium, max	0.01–0.10	0.01–0.10
Cerium	0.03–0.09	...
Yttrium	0.01–0.15	0.05–0.12

^A Element shall be determined arithmetically by difference.

TABLE 1 Chemical Requirements (continued)

Element	Composition, %								
	Nickel-Iron-Chromium Alloy	Nickel-Chromium-Molybdenum-Columbium Alloy	Nickel-Chromium-Molybdenum-Tungsten Alloy	Nickel-Iron-Chromium-Molybdenum-Copper Alloy	Low-Carbon Nickel-Molybdenum-Chromium Alloy	Low-Carbon Nickel-Molybdenum-Chromium Alloy	Iron-Nickel-Chromium-Molybdenum-Nitrogen Alloy	Low-Carbon Nickel-Chromium-Molybdenum Alloy	Low-Carbon Nickel-Chromium-Molybdenum Alloy
	UNS N08811	UNS N06625	UNS N06110	UNS N08825	UNS N10276	UNS N06022	UNS N08367	UNS N06059	UNS N06058
Nickel	30.0–35.0	58.0 min ^A	51.0 min ^A	38.0–46.0	remainder ^A	remainder ^A	23.50–25.50	balance ^A	balance
Copper	0.75 max	...	0.50 max	1.5–3.0	0.75 max	0.50 max	0.50 max
Iron	39.5 min ^A	5.0 max	1.0 max	22.0 min ^A	4.0–7.0	2.0–6.0	remainder ^A	1.5 max	1.5 max
Manganese	1.5 max	0.5 max	1.0 max	1.0 max	1.0 max	0.50 max	2.00 max	0.5 max	0.50 max
Carbon	0.06–0.10	0.10 max	0.15 max	0.05 max	0.010 max	0.015 max	0.030 max	0.010 max	0.010 max
Silicon	1.0 max	0.5 max	1.0 max	0.5 max	0.08 max	0.08 max	1.00 max	0.10 max	0.10 max
Sulfur, max	0.015	0.015	0.015	0.03	0.03	0.02	0.030	0.010	0.010
Chromium	19.0–23.0	20.0–23.0	28.0–33.0	19.5–23.5	14.5–16.5	20.0–22.5	20.0–22.0	22.0–24.0	20.0–23.0
Aluminum	0.15–0.60	0.4 max	1.0 max	0.2 max	0.1–0.4	0.40 max
Titanium	0.15–0.60	0.4 max	1.0 max	0.6–1.2
Columbium (Nb) + tantalum	...	3.15–4.15	1.0 max
Molybdenum	...	8.0–10.0	9.0–12.0	2.5–3.5	15.0–17.0	12.5–14.5	6.00–7.00	15.0–16.5	19.0 - 21.0
Phosphorus	...	0.015 max	0.50 max	...	0.04 max	0.02 max	0.040 max	0.015 max	0.015 max
Tungsten	1.0-4.0	...	3.0–4.5	2.5–3.5	0.3 max
Cobalt	2.5 max	2.5 max	...	0.3 max	0.3 max
Vanadium, max	0.35	0.35
Nitrogen	0.18–0.25	...	0.02 - 0.15
Boron
Lanthanum
Aluminum + Titanium	0.85–1.20
Nickel + Molybdenum
Columbium (Nb), max
Tantalum
Zirconium, max
Cerium
Yttrium

^A Element shall be determined arithmetically by difference.

TABLE 1 Chemical Requirements (continued)

Composition, %

Element	Low-Carbon Nickel-Chromium-Molybdenum Alloy UNS N06035	Low-Carbon Nickel-Chromium-Molybdenum-Copper Alloy UNS N06200	Low-Carbon Nickel-Molybdenum-Chromium UNS N10362	Nickel-Chromium-Molybdenum-Silicon Alloy UNS N06219	Low-Carbon Nickel-Iron Chromium-Molybdenum-Copper Alloy UNS N08031	Nickel Chromium-Tungsten-Molybdenum Alloy UNS N06230	Nickel Chromium-Cobalt-Molybdenum Alloy UNS N06617	Nickel-Molybdenum Alloy UNS N10629
Nickel	remainder ^A	remainder ^B	remainder ^B	balance ^B	30.0–32.0	remainder ^A	44.5 min	balance
Copper	0.30 max	1.3–1.9	...	0.50 max	1.0–1.4	...	0.5 max	0.5 max
Iron	2.00 max	3.0 max	1.25 max	2.0–4.0	balance ^B	3.0 max	3.0 max	1.0–6.0
Manganese	0.50 max	0.50 max	0.60 max	0.50 max	2.0 max	0.30–1.00	1.0 max	1.5
Carbon	0.050 max	0.010 max	0.010 max	0.05 max	0.015 max	0.05–0.15	0.05–0.15	0.010 max
Silicon	0.60 max	0.08 max	0.08 max	0.70–1.10	0.3 max	0.25–0.75	1.0 max	0.05
Sulfur, max	0.015	0.010	0.010	0.010	0.010	0.015	0.015	0.01
Chromium	32.25–34.25	22.0–24.0	13.8–15.6	18.0–22.0	26.0–28.0	20.0–24.0	20.0–24.0	0.5–1.5
Aluminum	0.40 max	0.50 max	0.50 max	0.50 max	...	0.50 max	0.8–1.5	0.1–0.5
Titanium	0.50 max	0.6 max	...
Columbium (Nb) + tantalum
Molybdenum	7.60–9.00	15.0–17.0	21.5–23.0	7.0–9.0	6.0–7.0	1.0–3.0	8.0–10.0	26.0–30.0
Phosphorus	0.030 max	0.025 max	0.025 max	0.020 max	0.020 max	0.030 max	...	0.04 max
Tungsten	0.60 max	13.0–15.0
Cobalt	1.00 max	2.0 max	...	1.0 max	...	5.0 max	10.0 min–15.0 max	2.5
Vanadium, max	0.20
Nitrogen	0.15–0.25
Boron	0.015 max	0.006 max	...
Lanthanum	0.005–0.050
Aluminum + Titanium
Nickel + Molybdenum
Columbium (Nb), max
Tantalum
Zirconium, max
Cerium
Yttrium

^B Element shall be determined arithmetically by difference.

TABLE 1 Chemical Requirements (continued)

Composition, %

Element	Nickel-Molybdenum Alloy	Nickel-Molybdenum Alloy	Nickel-Molybdenum-Chromium-Iron Alloy	Low-Carbon Nickel-Chromium-Molybdenum-Tungsten Alloy	Nickel-Cobalt-Chromium-Silicon Alloy	Nickel Alloy	Nickel-Molybdenum-Chromium-Iron Alloy	Chromium-Nickel-Iron-Nitrogen Alloy
	UNS N10665	UNS N10675	UNS N10242	UNS N06686	UNS N12160	UNS N02200	UNS N10624	UNS R00033
Nickel	remainder ^A	65.0 min	remainder ^A	remainder	remainder ^A	99.0 ^A min	remainder ^A	30.0–33.0
Copper	...	0.20 max	0.25 max	0.5 max	0.30–1.20
Iron	2.0 max	1.0–3.0	2.0 max	5.0 max	3.5 max	0.40 max	5.0–8.0	balance ^A
Manganese	1.0 max	3.0 max	0.80 max	0.75 max	1.5 max	0.35 max	1.0 max	2.0
Carbon	0.02 max	0.01 max	0.03	0.010 max	0.15 max	0.15 max	0.01 max	0.015 max
Silicon	0.10 max	0.10 max	0.80 max	0.08 max	2.4–3.0	0.35 max	0.10 max	0.50
Sulfur, max	0.03	0.010	0.015	0.02	0.015	0.01	0.01 max	0.01
Chromium	1.0 max	1.0–3.0	7.0–9.0	19.0–23.0	26.0–30.0	...	6.0–10.0	31.0–35.0
Aluminum	...	0.50 max	0.50 max	0.5 max	...
Titanium	...	0.20 max	...	0.02–0.25	0.20–0.80
Columbium (Nb) + tantalum
Molybdenum	26.0–30.0	27.0–32.0	24.0–26.0	15.0–17.0	1.0 max	...	21.0–25.0	0.50–2.0
Phosphorus	0.04 max	0.030 max	0.030 max	0.04 max	0.030 max	...	0.025 max	0.02 max
Tungsten	...	3.0 max	...	3.0–4.4	1.0 max
Cobalt	1.00 max	3.0 max [†]	1.00 max	...	27.0–33.0 [†]	...	1.0 max	...
Vanadium, max	...	0.20
Nitrogen	0.35–0.60
Boron	0.006 max
Lanthanum
Aluminum + Titanium
Nickel + Molybdenum	...	94.0–98.0
Columbium (Nb), max	...	0.20	1.0
Tantalum	...	0.20 max
Zirconium, max	...	0.10
Cerium
Yttrium

^A Element shall be determined arithmetically by difference.

3.1.2 Condition (**Table 2**).

3.1.3 Quantity (mass or number of pieces).

3.1.4 Forging, sketch or drawing.

3.1.5 *Certification*—State if certification or a report of test results is required (**14.1**).

3.1.6 *Samples for Product (Check) Analysis*—Whether samples for product (check) analysis should be furnished (see **4.2**).

3.1.7 *Purchaser Inspection*—If the purchaser wishes to witness tests or inspection of material at the place of manufacture, the purchase order must so state indicating which tests or inspections are to be witnessed (**12.1**).

4. Chemical Composition

4.1 The material shall conform to the composition limits specified in **Table 1**.

4.2 If a product (check) analysis is performed by the purchaser, the material shall conform to the product (check) analysis variations in accordance with Specification **B880**.

5. Mechanical Properties and Other Requirements

5.1 *Mechanical Properties*—The material shall conform to the mechanical properties specified in **Table 2**.

5.2 *Grain Size*—Annealed alloys (UNS N08810, N08120, and UNS N08811) shall conform to an average grain size of ASTM No. 5 or coarser.

6. Dimensions and Permissible Variations

6.1 Dimensions and tolerances shall be as specified on the applicable forging sketch or drawing.

7. Workmanship, Finish and Appearance

7.1 The material shall be uniform in quality and condition, sound, and free of injurious imperfections.

8. Sampling

8.1 *Lot Definition*:

8.1.1 A lot for chemical analysis shall consist of one heat.

8.1.2 A lot for mechanical properties and grain size testing shall consist of all material from the same heat, size, finish, condition, and processed at one time.

8.2 *Test Material Selection*:

8.2.1 *Chemical Analysis*—Representative samples shall be taken during pouring or subsequent processing.

8.2.1.1 Product (check) analysis shall be wholly the responsibility of the purchaser.

8.2.2 *Mechanical Properties and Grain Size*—Samples of the material to provide test specimens for mechanical properties and grain size shall be taken from such locations in each lot as to be representative of that lot.

9. Number of Tests

9.1 *Chemical Analysis*—One test per lot.

9.2 *Mechanical Properties*—One test per lot.

9.3 *Grain Size*—For alloys N08810, N08120, and UNS N08811, one test per lot.

10. Specimen Preparation

10.1 The tension test specimen representing each lot shall be taken from a forging or from a test prolongation.

10.2 The axis of the specimen shall be located at any point midway between the center and the surface of solid forgings and at any point midway between the inner and outer surfaces of the wall of hollow forgings, and shall be parallel to the direction of greatest metal flow.

10.3 The specimens shall be the largest possible round type shown in Test Methods **E8**.

11. Test Methods

11.1 The chemical composition, mechanical, and other properties of the material as enumerated in this specification shall be determined, in case of disagreement, in accordance with the following methods:

Test	ASTM Designation
Chemical Analysis	E76, E350, E1473
Tension	E8
Rounding Procedure	E29
Grain Size	E112

11.2 The measurement of average grain size may be carried out by the planimetric method, the comparison method, or the intercept method described in Test Methods **E112**. In case of dispute, the “referee” method for determining average grain size shall be the planimetric method.

11.3 For purposes of determining compliance with the specified limits for requirements of the properties listed in the following table, an observed value, or a calculated value, shall be rounded as indicated as follows, in accordance with the rounding method of Practice **E29**:

Test	Rounded Unit for Observed or Calculated Value
Chemical composition	nearest unit in the last right-hand place of figures of the specified limit
Tensile strength, yield strength	nearest 1000 psi (6.9 MPa)
Elongation	nearest 1 %
Grain size:	
0.0024 in. (0.060 mm) or larger	nearest multiple of 0.0002 in. (0.005 mm)
less than 0.0024 in. (0.060 mm)	nearest multiple of 0.0001 in. (0.002 mm)

12. Inspection

12.1 Inspection of the material by the purchaser shall be made as agreed upon between the purchaser and the seller as part of the purchase contract.

13. Rejection and Rehearing

13.1 Material, tested by the purchaser, that fails to conform to the requirements of this specification may be rejected. Rejection should be reported to the producer or supplier promptly and in writing. In case of dissatisfaction with the results of the test, the producer or supplier may make claim for a rehearing.

14. Certification

14.1 When specified in the purchase order or contract, a manufacturer’s certification shall be furnished to the purchaser stating that material has been manufactured, tested, and inspected in accordance with this specification, and that the test results on representative samples meet specification requirements. When specified in the purchase order or contract, a report of the test results shall be furnished.