



SLOVENSKI STANDARD
oSIST prEN ISO 3262-16:2022

01-december-2022

Polnila za barve - Specifikacije in metode preskušanja - 16. del: Aluminijevi hidroksidi (ISO/DIS 3262-16:2022)

Extenders - Specifications and methods of test - Part 16: Aluminium hydroxides (ISO/DIS 3262-16:2022)

Füllstoffe - Anforderungen und Prüfverfahren - Teil 16: Aluminiumhydroxide (ISO/DIS 3262-16:2022)

Matières de charge - Spécifications et méthodes d'essai - Partie 16: Alumines hydratées (ISO/DIS 3262-16:2022)

Ta slovenski standard je istoveten z: prEN ISO 3262-16

ICS:

87.060.10 Pigmenti in polnila Pigments and extenders

oSIST prEN ISO 3262-16:2022 en,fr,de

DRAFT INTERNATIONAL STANDARD

ISO/DIS 3262-16

ISO/TC 256

Secretariat: DIN

Voting begins on:
2022-10-04

Voting terminates on:
2022-12-27

Extenders — Specifications and methods of test —

Part 16: Aluminium hydroxides

ICS: 87.060.10

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 3262-16:2022](https://standards.iteh.ai/catalog/standards/sist/86427e9e-ed37-4b01-b396-ba868dcc30b0/osist-pren-iso-3262-16-2022)

<https://standards.iteh.ai/catalog/standards/sist/86427e9e-ed37-4b01-b396-ba868dcc30b0/osist-pren-iso-3262-16-2022>

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 3262-16:2022(E)

© ISO 2022

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 3262-16:2022](https://standards.iteh.ai/catalog/standards/sist/86427e9e-ed37-4b01-b396-ba868dcc30b0/osist-pren-iso-3262-16-2022)
[https://standards.iteh.ai/catalog/standards/sist/86427e9e-ed37-4b01-b396-
ba868dcc30b0/osist-pren-iso-3262-16-2022](https://standards.iteh.ai/catalog/standards/sist/86427e9e-ed37-4b01-b396-ba868dcc30b0/osist-pren-iso-3262-16-2022)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Requirements and test methods.....	2
4.1 Essential requirements.....	2
4.2 Conditional requirements.....	4
5 Sampling.....	4
6 Test report.....	4

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 3262-16:2022](https://standards.iteh.ai/catalog/standards/sist/86427e9e-ed37-4b01-b396-ba868dcc30b0/osist-pren-iso-3262-16-2022)

<https://standards.iteh.ai/catalog/standards/sist/86427e9e-ed37-4b01-b396-ba868dcc30b0/osist-pren-iso-3262-16-2022>

ISO/DIS 3262-16:2022(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 256, *Pigments, dyestuffs and extenders*.

This second edition cancels and replaces the first edition (ISO 3262-16:2000), which has been technically revised.

The main changes are as follows:

- the first part of the title has been changed to "Extenders";
- the normative references have been updated and the text has been editorially revised.

A list of all parts in the ISO 3262 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Extenders — Specifications and methods of test —

Part 16: Aluminium hydroxides

1 Scope

This document specifies requirements and corresponding methods of test for aluminium hydroxides.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 787-2, *General methods of test for pigments and extenders — Part 2: Determination of matter volatile at 105 °C*

ISO 787-7, *General methods of test for pigments and extenders — Part 7: Determination of residue on sieve — Water method — Manual procedure*

ISO 787-9, *General methods of test for pigments and extenders — Part 9: Determination of pH value of an aqueous suspension*

ISO 787-11, *General methods of test for pigments and extenders — Part 11: Determination of tamped volume and apparent density after tamping*

ISO 787-14, *General methods of test for pigments and extenders — Part 14: Determination of resistivity of aqueous extract*

ISO 5794-1, *Rubber compounding ingredients — Silica, precipitated, hydrated — Part 1: Non-rubber tests*

ISO 3262-1, *Extenders — Specifications and methods of test — Part 1: Introduction and general test methods*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

ISO 18451-1, *Pigments, dyestuffs and extenders — Terminology — Part 1: General terms*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 18451-1 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

ISO/DIS 3262-16:2022(E)

3.1 aluminium hydroxide

material crystallized by the Bayer process, for instance, the main constituent of which is gibbsite, $\text{Al}(\text{OH})_3$

Note 1 to entry: Other constituents may be bayerite, $\text{Al}(\text{OH})_3$, and boehmite, $\text{AlO}(\text{OH})$, both of which are also regarded as aluminium hydroxide.

3.2 crystallized aluminium hydroxides

aluminium hydroxides crystallized directly with the particle size distribution required for the application

3.3 ground aluminium hydroxides

aluminium hydroxides ground to the particle size distribution required and containing not only single crystals and agglomerates, but also the fragments of such crystals and agglomerates

4 Requirements and test methods

4.1 Essential requirements

For aluminium hydroxides complying with this document, the essential requirements are specified in [Table 1](#). The test method in [Table 1](#) shall be in accordance with the standards listed.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 3262-16:2022](#)

<https://standards.iteh.ai/catalog/standards/sist/86427e9e-ed37-4b01-b396-ba868dcc30b0/osist-pren-iso-3262-16-2022>

Table 1 — Essential requirements

Characteristic	Unit	Requirement												Test method			
		Low-electrolyte-content material, crystallized			Low-electrolyte-content material, ground			Standard material, crystallized							Standard material, ground		
		Grade A1	Grade A2	Grade A3	Grade B	Grade C1	Grade C2	Grade C3	Grade C4	Grade D1	Grade D2	Grade D3	Grade D3				
Residue on 63 µm sieve, max.	% mass fraction	To be agreed between the interested parties	To be agreed between the interested parties	0,1	To be agreed between the interested parties	To be agreed between the interested parties	To be agreed between the interested parties	0,1	To be agreed between the interested parties	To be agreed between the interested parties	To be agreed between the interested parties	To be agreed between the interested parties	0,5	ISO 787-7			
45 µm sieve, max.			0,2		0,2			0,2					0,5				
Median particle size ^a	µm	> 40	10 to 40	—	< 10	> 40	10 to 40	< 10	—	10 to 40	< 10	—	10 to 40	< 10	ISO 787-7 ^b		
Specific surface area, min.	m ² /g	—	—	3,0	—	—	—	—	—	—	—	—	—	—	ISO 5794-1		
Resistivity of aqueous extract, min.	Ω·m	100	100	—	66	50	40	30	10	40	30	10	40	10	ISO 787-14		
pH value of aqueous suspension		7 to 9	7 to 9	7 to 9	7 to 10	7 to 10	7 to 10	7 to 10	7 to 10	7 to 9	7 to 10	7 to 10	7 to 9	7 to 10	ISO 787-9		
Matter volatile at 105 °C, max.	% mass fraction	0,2	0,3	0,5	0,4	0,2	0,3	0,4	1,0	0,3	0,4	1,0	0,3	0,4	ISO 787-2		
Apparent density after tamping	g/ml	> 1,2	> 0,6	0,4 to 0,7	0,6 to 1,2	> 1,2	0,9 to 1,2	0,6 to 1,0	< 0,6	> 0,9	0,6 to 1,0	< 0,6	> 0,9	0,6 to 1,0	ISO 787-11		

^a The median particle size is defined as the mesh aperture in µm of sieve through which 50 % of the product will pass.

^b Or any other test method giving the same results.

ISO/DIS 3262-16:2022(E)

4.2 Conditional requirements

Requirements for the lightness of aluminium hydroxides shall be agreed between the interested parties. The test method used to determine the lightness shall also be agreed.

5 Sampling

Take a representative sample of the product to be tested, in accordance with ISO 15528.

6 Test report

The test report shall contain at least the following information:

- a) all details necessary to identify the product tested;
- b) a reference to this document, i. e. ISO 3262-16:—;
- c) the results of the test, the method used, and whether or not the product complies with the relevant specification limits;
- d) any deviation from the method of test specified;
- e) any unusual features (anomalies) observed during the test;
- f) the date of the test.

ITeh STANDARD PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/86427e9e-ed37-4b01-b396-ba868dcc30b0/osist-pren-iso-3262-16-2022>