



**SLOVENSKI STANDARD**  
**oSIST prEN ISO 5774:2022**  
**01-april-2022**

---

**Polimerne cevi - S tekstilom ojačene cevi za zrak pod tlakom - Specifikacija  
(ISO/DIS 5774:2022)**

Plastics hoses - Textile-reinforced types for compressed-air applications - Specification  
(ISO/DIS 5774:2022)

Kunststoffschläuche - Textilverstärkte Typen für Druckluftanwendungen – Anforderung  
(ISO/DIS 5774:2022)

Tuyaux en plastique - Types armés de textile pour applications avec de l'air comprimé -  
Spécifications (ISO/DIS 5774:2022)

Ta slovenski standard je istoveten z: [oSIST prEN ISO 5774:2022](https://standards.iteh.ai/catalog/standards/sist/a6c79d1c-5927-4924-a5c0-e6a7029cf3af/osist-pren-iso-5774-2022)  
**prEN ISO 5774**

**ICS:**

83.140.40      Gumene cevi      Hoses

**oSIST prEN ISO 5774:2022**      **en,fr,de**

**iTeh STANDARD  
PREVIEW  
(standards.iteh.ai)**

[oSIST prEN ISO 5774:2022](https://standards.iteh.ai/catalog/standards/sist/a6c79d1c-5927-4924-a5c0-e6a7029cf3af/osist-pren-iso-5774-2022)

<https://standards.iteh.ai/catalog/standards/sist/a6c79d1c-5927-4924-a5c0-e6a7029cf3af/osist-pren-iso-5774-2022>

# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 5774

ISO/TC 45/SC 1

Secretariat: DIN

Voting begins on:  
2022-02-16Voting terminates on:  
2022-05-11

---

---

## Plastics hoses — Textile-reinforced types for compressed-air applications — Specification

*Tuyaux en plastique — Types armés de textile pour applications avec de l'air comprimé — Spécifications*

ICS: 23.040.70

### iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 5774:2022](https://standards.iteh.ai/catalog/standards/sist/a6c79d1c-5927-4924-a5c0-e6a7029cf3af/osist-pren-iso-5774-2022)

<https://standards.iteh.ai/catalog/standards/sist/a6c79d1c-5927-4924-a5c0-e6a7029cf3af/osist-pren-iso-5774-2022>

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

### ISO/CEN PARALLEL PROCESSING



Reference number  
ISO/DIS 5774:2022(E)

© ISO 2022

**iTeh STANDARD  
PREVIEW  
(standards.iteh.ai)**

[oSIST prEN ISO 5774:2022](https://standards.iteh.ai/catalog/standards/sist/a6c79d1c-5927-4924-a5c0-e6a7029cf3af/osist-pren-iso-5774-2022)

<https://standards.iteh.ai/catalog/standards/sist/a6c79d1c-5927-4924-a5c0-e6a7029cf3af/osist-pren-iso-5774-2022>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword.....	iv
Introduction.....	v
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>2</b>
<b>4 Classification.....</b>	<b>2</b>
<b>5 Couplings and end fittings.....</b>	<b>2</b>
<b>6 Materials and construction.....</b>	<b>2</b>
<b>7 Dimensions and tolerances.....</b>	<b>2</b>
7.1 Inside diameter, tolerances and minimum wall thickness.....	2
7.2 Concentricity.....	3
7.3 Tolerances on length.....	3
<b>8 Physical properties.....</b>	<b>3</b>
8.1 Plastic compounds.....	3
8.1.1 Tensile strength and elongation at break of lining and cover.....	3
8.1.2 Resistance to ageing.....	4
8.1.3 Loss in mass on heating.....	4
8.1.4 Resistance to liquids.....	4
8.1.5 Hydrolysis test.....	4
8.2 Performance requirements on finished hoses.....	4
8.2.1 Hydrostatic requirements.....	4
8.2.2 Exposure to a xenon arc lamp.....	5
8.2.3 Bending test.....	5
8.2.4 Low-temperature flexibility.....	6
<b>9 Frequency of testing.....</b>	<b>6</b>
<b>10 Marking.....</b>	<b>6</b>
<b>11 Recommendations for packaging and storage.....</b>	<b>6</b>
<b>12 Test report.....</b>	<b>7</b>
<b>Annex A (normative) Hydrolysis test.....</b>	<b>8</b>
<b>Annex B (normative) Type and routine tests.....</b>	<b>10</b>
<b>Annex C (informative) Production acceptance tests.....</b>	<b>11</b>
<b>Annex D (informative) Couplings and end fittings.....</b>	<b>12</b>
<b>Bibliography.....</b>	<b>13</b>

## ISO/DIS 5774:2022(E)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Rubber and plastics hoses and hose assemblies*.

This fifth edition cancels and replaces the fourth edition (ISO 5774:2016), of which it constitutes a minor revision.

The minor changes are as follows:

- Update the normative references;
- Revise and add the unit of pressure; i.e. Mpa (bar);
- Update the marking clauses.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

This International Standard has been prepared to provide minimum acceptable requirements for the satisfactory performance of flexible thermoplastics hoses, textile reinforced, for compressed-air applications.

Maximum working pressures of each hose type are specified with two operating temperatures.

Some hose materials will require a hydrolysis test (given in [Annex A](#))

# iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 5774:2022](#)

<https://standards.iteh.ai/catalog/standards/sist/a6c79d1c-5927-4924-a5c0-e6a7029cf3af/osist-pren-iso-5774-2022>

**iTeh STANDARD  
PREVIEW  
(standards.iteh.ai)**

[oSIST prEN ISO 5774:2022](https://standards.iteh.ai/catalog/standards/sist/a6c79d1c-5927-4924-a5c0-e6a7029cf3af/osist-pren-iso-5774-2022)

<https://standards.iteh.ai/catalog/standards/sist/a6c79d1c-5927-4924-a5c0-e6a7029cf3af/osist-pren-iso-5774-2022>



# Plastics hoses — Textile-reinforced types for compressed-air applications — Specification

## 1 Scope

This International Standard specifies the requirements for four types of flexible thermoplastic hose, textile reinforced, for compressed-air applications in the temperature range from  $-10\text{ °C}$  to  $+60\text{ °C}$ .

The four types are classified as light service for a maximum working pressure of 0,7 MPa (7 bar) at  $23\text{ °C}$  and 0,45 MPa (4,5 bar) at  $60\text{ °C}$ , medium service for a maximum working pressure of 1,0 MPa (10 bar) at  $23\text{ °C}$  and 0,65 MPa (6,5 bar) at  $60\text{ °C}$ , heavy service for a maximum working pressure of 1,6 MPa (16 bar) at  $23\text{ °C}$  and 1,1 MPa (11 bar) at  $60\text{ °C}$ , and heavy service for use in mining for a maximum working pressure of 2,5 MPa (25 bar) at  $23\text{ °C}$  and 1,3 MPa (13 bar) at  $60\text{ °C}$ .

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 105-A02, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*

ISO 176:2005, *Plastics — Determination of loss of plasticizers — Activated carbon method*

ISO 188, *Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests*

ISO 1307, *Rubber and plastics hoses — Hose sizes, minimum and maximum inside diameters, and tolerances on cut-to-length hoses*

ISO 1402, *Rubber and plastics hoses and hose assemblies — Hydrostatic testing*

ISO 1817, *Rubber, vulcanized or thermoplastic — Determination of the effect of liquids*

ISO 4671, *Rubber and plastics hoses and hose assemblies — Methods of measurement of the dimensions of hoses and the lengths of hose assemblies*

ISO 8033, *Rubber and plastics hoses — Determination of adhesion between components*

ISO 8330, *Rubber and plastics hoses and hose assemblies — Vocabulary*

ISO 8331, *Rubber and plastics hoses and hose assemblies — Guidelines for selection, storage, use and maintenance*

ISO 10619-1, *Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 1: Bending tests at ambient temperature*

ISO 10619-2:2021, *Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 2: Bending tests at sub-ambient temperatures*

ISO 30013, *Rubber and plastics hoses — Methods of exposure to laboratory light sources — Determination of changes in colour, appearance and other physical properties*

## ISO/DIS 5774:2022(E)

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8330 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

### 4 Classification

Hoses are designated as one of the following four types depending on their pressure rating at the specified temperature:

- Type A: General industrial use — light service — for a maximum working pressure of 0,7 MPa (7 bar) at 23 °C and 0,45 MPa (4, 5 bar) at 60 °C.
- Type B: General industrial use — medium service — for a maximum working pressure of 1 MPa (10 bar) at 23 °C and 0,65 MPa (6,5 bar) at 60 °C.
- Type C: Heavy service — for a maximum working pressure of 1,6 MPa (16 bar) at 23 °C and 1,1 MPa (11 bar) at 60 °C.
- Type D: Heavy service — for use in mining and outdoor work — for a maximum working pressure of 2,5 MPa (25 bar) at 23 °C and 1,3 MPa (13 bar) at 60 °C.

The hoses are not intended for the transport of oil. However, compressed air coming from a compressor may contain some oil in suspension.

### 5 Couplings and end fittings

Hoses may be fitted with the appropriate coupling type and end fitting to form hose assemblies.

NOTE Guidance on coupling type is given in [Annex D](#) and ISO/TR 17784.

### 6 Materials and construction

The hoses shall consist of:

- a) a lining made of a flexible thermoplastics material;
- b) a reinforcement made of a natural or synthetic textile material applied by any suitable technique;
- c) a cover made of a flexible thermoplastics material.

The lining and the cover shall be of uniform thickness, concentric, fully gelled and free from visible cracks, porosity, foreign inclusions and any other defects which could cause the hose to be unserviceable.

### 7 Dimensions and tolerances

#### 7.1 Inside diameter, tolerances and minimum wall thickness

When measured in accordance with ISO 4671, the inside diameter of hoses shall lie within the tolerance limits given in [Table 1](#) and the wall thickness shall meet the minimum requirement given in [Table 1](#).

**Table 1 — Nominal bores, inside diameters, tolerances and minimum wall thicknesses**

Nominal bore	Inside diameter mm	Tolerance mm	Minimum wall thickness mm			
			Type A	Type B	Type C	Type D
			4	4	±0,25	1,5
5	5	±0,25	1,5	1,5	1,5	2,0
6,3	6,3	±0,25	1,5	1,5	1,5	2,3
8	8	±0,25	1,5	1,5	1,5	2,3
9	8,5	±0,25	1,5	1,5	1,5	2,3
10	9,5	±0,35	1,5	1,5	1,8	2,3
12,5	12,5	±0,35	2,0	2,0	2,3	2,8
16	16	±0,5	2,4	2,4	2,8	3,0
19	19	±0,7	2,4	2,4	2,8	3,5
25	25	±1,2	2,7	3,0	3,3	4,0
31,5	31,5	±1,2	3,0	3,3	3,5	4,5
38	38	±1,2	3,0	3,5	3,8	4,5
40	40	±1,5	3,3	3,5	4,1	5,0
50	50	±1,5	3,5	3,8	4,5	5,0

## 7.2 Concentricity

When determined in accordance with ISO 4671, the concentricity, based on the difference in indicator reading between the inside surface of the lining and the outside surface of the cover, shall be no greater than 0,3 mm for hoses of minimum wall thickness from 1,5 mm up to and including 3,0 mm, no greater than 10 % of the wall thickness for hoses of minimum wall thickness over 3,0 mm and up to and including 5,0 mm, and no greater than 15 % of the wall thickness for hoses of minimum wall thickness over 5,0 mm as given in [Table 2](#).

**Table 2 — Concentricity**

Minimum wall thickness mm	Concentricity
1,5 to 3,0	≤ 0,3 mm
over 3,0 to 5,0	≤ 10 % of wall thickness
over 5,0	≤ 15 % of wall thickness

## 7.3 Tolerances on length

The tolerances on cut lengths of hose shall be in accordance with ISO 1307.

## 8 Physical properties

### 8.1 Plastic compounds

#### 8.1.1 Tensile strength and elongation at break of lining and cover

When determined in accordance with ISO 37, the tensile strength and elongation at break shall not be less than the values given in [Table 3](#).