

INTERNATIONAL STANDARD

ISO
2559

Third edition
1991-07-01

**Textile glass — Mats (made from chopped or
continuous strands) — Basis for a specification**

iTeh Standards
*Verre textile — Mats (constitués de fils de base, coupés ou non) — Base
de spécification*
[\(<https://standards.iteh.ai>\)](https://standards.iteh.ai)
Document Preview

[ISO 2559:1991](#)

<https://standards.iteh.ai/catalog/standards/iso/52119601-58b5-4cc4-bdac-11d5837ef40d/iso-2559-1991>



Reference number
ISO 2559:1991(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 2559 was prepared by Technical Committee ISO/TC 61, *Plastics*.

This third edition cancels and replaces the second edition (ISO 2559:1980), of which it constitutes a technical revision.

Annex A of this International Standard is for information only.

[ISO 2559:1991](https://standards.iteh.ai/catalog/standards/iso/52119601-58b5-4cc4-bdac-11d5837ef40d/iso-2559-1991)

<https://standards.iteh.ai/catalog/standards/iso/52119601-58b5-4cc4-bdac-11d5837ef40d/iso-2559-1991>

© ISO 1991

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Introduction

A basis for a specification is intended to serve as a guide for the establishment of technical specifications for products of a given type. It should enumerate as completely as possible the points that should be considered at the time of writing of the specifications that will apply to a particular product or family of products whose characteristics are closely related. These specifications may be established by a producer, a supplier, a user or a standards organization.

iTeh Standards (<https://standards.iteh.ai>) Document Preview

[ISO 2559:1991](#)

<https://standards.iteh.ai/catalog/standards/iso/52119601-58b5-4cc4-bdac-11d5837ef40d/iso-2559-1991>

iTeh Standards
(<https://standards.iteh.ai>)
This page intentionally left blank
Document Preview

[ISO 2559:1991](#)

<https://standards.iteh.ai/catalog/standards/iso/52119601-58b5-4cc4-bdac-11d5837ef40d/iso-2559-1991>

Textile glass — Mats (made from chopped or continuous strands) — Basis for a specification

1 Scope

This International Standard provides a basis for specifications which is applicable only to textile glass mats that are made from chopped or continuous strands and used for the reinforcement of plastics.

It is not applicable to surfacing mats, staple fibre mats or glass mats (or bats) of the type used for thermal and acoustic insulation.

ISO 1888:1979, *Textile glass — Determination of the average diameter of staple fibres or continuous filaments constituting a textile glass yarn — Cross-section method*.

ISO 2078:1985, *Textile glass — Yarns — Designation*.

ISO 2558:1974, *Textile glass chopped-strand mats for reinforcement of plastics — Determination of time of dissolution of the binder in styrene*.

ISO 3342:1987, *Textile glass — Mats — Determination of tensile breaking force*.

ISO 3374:1990, *Textile glass mats — Determination of mass per unit area*.

ISO 3616:1977, *Textile glass — Mats — Determination of average thickness, thickness under load and recovery after compression*.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 139:1973, *Textiles — Standard atmospheres for conditioning and testing*.

ISO 291:1977, *Plastics — Standard atmospheres for conditioning and testing*.

ISO 472:1988, *Plastics — Vocabulary*.

ISO 1144:1973, *Textiles — Universal system for designating linear density (Tex System)*.

ISO 1886:1990, *Reinforcement fibres — Sampling plans applicable to received batches*.

ISO 1887:1980, *Textile glass — Determination of combustible matter content*.

3 Technical description

A complete and accurate technical description of a textile glass mat (see ISO 472) shall be given in the manufacturer's catalogue. It shall include those properties that are mandatory, as indicated by (m), and may include some or all of the optional properties, indicated by (o), as listed in this clause.

3.1 Type of mat

3.1.1 Whether the strands are chopped or not (m).

3.1.2 In the case of chopped strands, whether the mat consists of strands of similar or dissimilar nominal lengths (m).

3.1.3 The code number or designation of the plastic (or coupling) size deposited on the strand (o).

3.1.4 Whether the strands are bound together mechanically or chemically (m).

3.1.4.1 If a chemical binder is used:

- whether the binder is solid or liquid-based (m);
- the degree of solubility of the binder in styrene or other monomers (high, medium or low — see 5.3) (m);
- the percentage of combustible matter (m);
- the code number of each binder (o).

3.1.4.2 In the case of mechanical binding (needled mat):

- whether the mat has a carrier or not (m);
- if it has, the nature of the carrier (m).

3.2 Designation of strands (see ISO 2078)

3.2.1 One or more initial capital letters indicating the type of glass used in the production (m).

3.2.2 A capital letter indicating the strand type: C for continuous, D for discontinuous (m).

3.2.3 The linear density (tex) (see ISO 1144) of the basic strand(s) in the mat (o).

3.3 Mass per unit area of mat

The mass per unit area of the mat, in grams per square metre (m).

3.4 Width of mat

The width of the mat, in centimetres (m).

The specification of the width of the mat shall also include whether one or both edges are trimmed or untrimmed (m).

4 Labelling code

The labelling code shall comprise the following elements:

- a) an identification code specific to the manufacturer and the type of mat (with this information, the user can find in the manufacturer's catalogue the technical description of the type of mat as indicated in clause 3);
- b) a double space;

c) the mass per unit area of the mat, in grams per square metre;

d) a hyphen;

e) the width of the mat, in centimetres.

For example:

M.XY9 450-125

where

M.XY9 is the code name chosen by the manufacturer for this type of mat;

450 is the mass per unit area, in grams per square metre;

125 is the width, in centimetres.

5 Technical requirements

The specification shall define, for each particular type of mat, the appropriate characteristics (physical, mechanical, visual and/or resin compatibility) including tolerances where appropriate.

For each of the characteristics used in the specification, the criteria for acceptance or rejection of a lot shall be stated.

5.1 General

Depending on the type of mat and the intended end use, textile glass mats shall satisfy some or all of the following technical requirements.

5.2 Strands used in the manufacture of the mat

5.2.1 Type of glass

At the purchaser's request, the textile glass producer shall state the mean content of the essential chemical elements in the type of glass supplied.

5.2.2 Average diameter of the filaments constituting the strand

The average diameter of the filaments constituting the strands shall be determined in accordance with ISO 1888¹⁾.

5.2.3 Plastic size (coupling size)

For the manufacture of textile glass mats used in the reinforcement of plastics, only those strands shall be used that have plastic size.

1) ISO 1888:1979 is currently being revised. The new edition will also include the longitudinal-section method.