
**Glass in building — Forced-entry
security glazing —**

**Part 1:
Test and classification by repetitive
ball drop**

iTeh STANDARD PREVIEW
*Verre dans la construction — Vitrages de sécurité contre
infractions —
(standards.iteh.ai)
Partie 1: Essai et classification par balle lancée répétée*

[ISO 16936-1:2020](https://standards.iteh.ai/catalog/standards/sist/352f7831-3bfd-468a-ae11-cdb31a9eb556/iso-16936-1-2020)

[https://standards.iteh.ai/catalog/standards/sist/352f7831-3bfd-468a-ae11-
cdb31a9eb556/iso-16936-1-2020](https://standards.iteh.ai/catalog/standards/sist/352f7831-3bfd-468a-ae11-cdb31a9eb556/iso-16936-1-2020)



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 16936-1:2020

<https://standards.iteh.ai/catalog/standards/sist/352f7831-3bfd-468a-ae11-cdb31a9eb556/iso-16936-1-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Sampling	2
5 Apparatus	2
6 Required characteristics	3
7 Test method	3
7.1 Room temperature test	3
7.2 Installation of the test piece	4
7.3 Test procedure	4
7.4 Evaluation of the test results	6
8 Classification and designation	6
9 Test report	6
10 Marking	7
Annex A (normative) Testing by repetitive ball drop at extreme temperatures	8
Bibliography	9

<https://standards.iteh.ai/catalog/standards/sist/352f7831-3bfd-468a-ae11-cdb31a9eb556/iso-16936-1-2020>
 ISO 16936-1:2020

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 160, *Glass in building*, Subcommittee SC 2, *Use considerations*.

This second edition cancels and replaces the first edition (ISO 16936-1:2005), which has been technically revised. The main changes compared to the previous edition are as follows:

- addition of [Figure 2](#);
- [Annex A](#) status has been changed to normative due to reference in [7.1](#).

A list of all parts in the ISO 16936 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document assesses security-glazing products that are more familiarly known as “anti-vandal”, “anti-bandit” and “detention” glazing products. Because there is no single test that will cover the wide range of resistances to attack, four separate test methods are provided to assess the forced entry resistant properties of security glazing. It is not intended that any particular test method be associated with the terms “anti-vandal” or “anti-bandit”, since these terms can be only loosely defined and there is considerable overlap in their definition.

It is important that security-glazing products be installed in a frame which can give appropriate resistance to impact and which also provides a suitable support for the security-glazing product. It is important that cut-outs and holes in security-glazing products be avoided where possible, as these can affect the resistance of the product.

The test method specified in this document does not reproduce the conditions of a real human attack but is intended to give a classification of comparative resistance.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 16936-1:2020](https://standards.iteh.ai/catalog/standards/sist/352f7831-3bfd-468a-ae11-cdb31a9eb556/iso-16936-1-2020)

<https://standards.iteh.ai/catalog/standards/sist/352f7831-3bfd-468a-ae11-cdb31a9eb556/iso-16936-1-2020>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 16936-1:2020

<https://standards.iteh.ai/catalog/standards/sist/352f7831-3bfd-468a-ae11-cdb31a9eb556/iso-16936-1-2020>

Glass in building — Forced-entry security glazing —

Part 1: Test and classification by repetitive ball drop

1 Scope

This document specifies requirements and a test method for security glazing designed to resist impacts of a hard body by delaying access of objects and/or persons to a protected space for a short period of time. It also classifies security-glazing products into categories of resistance to repetitive impacts of a steel sphere.

In this document, the categories of resistance have not been assigned to special applications. It is intended that the glazing classification be specified on an individual basis for every application and anticipated action of force upon the glazing.

This document deals with mechanical resistance to impact only.

NOTE Other properties can also be important.

iTeh STANDARD PREVIEW

2 Normative references (standards.iteh.ai)

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 48-2:2018, *Rubber, vulcanized or thermoplastic — Determination of hardness — Part 2: Hardness between 10 IRHD and 100 IRHD*

ISO 6508-1, *Metallic materials — Rockwell hardness test — Part 1: Test method*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <http://www.electropedia.org/>

3.1

action of force

deliberate attempt on the part of a person made with the intention of creating a hole in the *security-glazing product* (3.6), by the use of manually held implements or thrown objects

3.2

asymmetric construction

product in which, from both outer surfaces, the sequence of glass panes, plastic glazing sheet material and interlayer(s) by type, thickness, finish and/or general characteristics is different

3.3

category of resistance

classification of the capability of a security-glazing product to resist *actions of force* (3.1)

**3.4
protected space**

area the access to which is prevented by the completed installation

**3.5
sample**

specified number of test pieces which together are representative of the *security-glazing product* (3.6) intended to comply with a particular *category of resistance* (3.3)

**3.6
security-glazing product**

product based on glass with or without plastics with a single or multiple ply construction, where the individual plies are of uniform thickness over the whole area of the product

Note 1 to entry: A security-glazing product is usually transparent or translucent and provides a specific resistance to the actions of force.

4 Sampling

The sample submitted for testing shall consist of three test pieces for each category for which testing is required.

To ensure against invalid test results because of errors during the test, it is advisable to submit at least one extra test piece.

If the test pieces are of an asymmetric material, their number shall be doubled.

Each test piece shall be $(1\ 100 \pm 5)$ mm long \times (900 ± 5) mm wide. The edges shall be free from visible chips, cracks and flaws. Glass samples should be lightly abraded for ease of handling.

Each test piece shall be stored vertically and self-supporting at (18 ± 3) °C for at least 12 h immediately prior to the test.

For exterior uses under extreme conditions, the influence of the outside temperature should be considered.

5 Apparatus

5.1 Impactor, consisting of a steel sphere with a diameter of $(100 \pm 0,2)$ mm and a mass of $(4,11 \pm 0,06)$ kg. The sphere shall be manufactured from polished steel with a hardness of 60 HRC to 65 HRC on the Rockwell C scale, in accordance with ISO 6508-1.

5.2 Impactor-holding equipment, with a drop height adjustable to the required tolerance (see [Table 1](#)).

The equipment for holding the impactor and the mechanism for releasing the impactor shall not induce any momentum or rotation in the impactor, so that the impactor is accelerated only by gravitational forces and falls vertically.

Table 1 — Drop heights

Category of resistance	Drop height mm
P1A	1 500 ± 50
P2A	3 000 ± 50
P3A	6 000 ± 50
P4A	9 000 ± 50
P5A	9 000 ± 50

5.3 Test piece support apparatus, consisting of a steel frame to clamp the edge of the test piece and a receiving box to collect fragments and the impactor (see [Figure 1](#)).

The support apparatus shall:

- be inherently rigid;
- have an unyielding connection to a solid base;
- ensure plane and parallel clamping of the test piece in a horizontal position;
- be designed in such a way that the test piece touches only the clamping frame during the test;
- ensure clamping of the test piece on all four edges with an edge cover of (30 ± 5) mm;
- have the clamping frame covered on the contact area of the test piece with rubber strips 30 mm wide and 4 mm thick of hardness 40 HRD to 60 HRD, according to method N of ISO 48-2:2018;
- ensure that the edges of the test piece are clamped with a uniform pressure of (140 ± 20) kN/m²;
- ensure that the impactor is not damaged and does not rebound when hitting the bottom of the receiving box;
- ensure that air cannot be trapped in the support apparatus in such a way that it can cushion the effects of the impact.

6 Required characteristics

The security-glazing product shall be submitted to testing for a particular category of resistance.

The security-glazing product shall be classified in that particular category of resistance if all three test pieces (or all six test pieces in the case of an asymmetric material) prevent penetration by the impacting body when tested by the method described in [Clause 7](#).

7 Test method

7.1 Room temperature test

The test room temperature shall be (18 ± 5) °C.

If the glass is tested at extreme temperatures, i.e. at -20 °C or at $+40$ °C, it shall be tested according to the specifications given in [Annex A](#).