



Designation: B135M – 10

Standard Specification for Seamless Brass Tube [Metric]¹

This standard is issued under the fixed designation B135M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers seamless round and rectangular including square copper alloy tube in straight lengths. Ten alloys are specified having the following nominal compositions:

Copper Alloy UNS No.	Previously Used Designation ^A	Nominal Composition, %			
		Copper	Zinc	Lead	Tin
C22000	7	90.0	10.0
C23000	1	85.0	15.0
C26000	2	70.0	30.0
C27000	9	65.0	35.0
C27200	8	63.0	37.0
C27400	...	62.5	37.5
C28000	5	60.0	40.0
C33000	3	66.0	33.5	0.5	...
C33200	4	66.0	32.4	1.6	...
C37000	6	60.0	39.0	1.0	...
C44300	...	71	27.5	...	1.00

^A Alloy Designations of ASTM Specification B135 – 63 which was published in the 1966 Book of ASTM Standards, Part 5.

1.2 This specification is the SI companion to Specification B135.

1.3 **Warning**—Mercury has been designated by EPA and many state agencies as a hazardous material that can cause central nervous system, kidney, and liver damage. Mercury, or its vapor, may be hazardous to health and corrosive to materials. Caution should be taken when handling mercury and mercury-containing products. See the applicable product Material Safety Data Sheet (MSDS) for details and EPA's website (<http://www.epa.gov/mercury/faq.htm>) for additional information. Users should be aware that selling mercury or mercury-containing products, or both, in your state may be prohibited by state law. (See 10.1.)

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate*

¹ This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.04 on Pipe and Tube.

Current edition approved Oct. 1, 2010. Published November 2010. Originally approved in 1984. Last previous edition approved in 2008 as B135M – 08a. DOI: 10.1520/B0135M-10.

appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 *ASTM Standards:*²

B153 Test Method for Expansion (Pin Test) of Copper and Copper-Alloy Pipe and Tubing

B154 Test Method for Mercurous Nitrate Test for Copper Alloys

B251M Specification for General Requirements for Wrought Seamless Copper and Copper-Alloy Tube (Metric)

B601 Classification for Temper Designations for Copper and Copper Alloys—Wrought and Cast

E243 Practice for Electromagnetic (Eddy Current) Examination of Copper and Copper-Alloy Tubes

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *capable of*—as used in this specification, the test need not be performed by the producer of the material. However, should subsequent testing by the purchaser establish that the material does not meet these requirements the material shall be subject to rejection.

4. Ordering Information

4.1 Orders for material under this specification shall include the following information:

4.1.1 Alloy (Section 1),

4.1.2 Temper (Section 7),

4.1.3 Whether tension tests are required (for drawn tempers only (see 8.1)),

4.1.4 Dimensions, the diameter or distance between parallel surfaces and wall thickness (see 11.2 and 11.3),

4.1.5 Length (see 12.4),

4.1.6 Mercurous nitrate test, if required (Section 10),

4.1.7 Total length of each size,

4.1.8 Hydrostatic pressure test, when specified, and

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

4.1.9 Pneumatic test, when specified.

5. General Requirements

5.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification **B251M**.

6. Chemical Composition

6.1 The material shall conform to the chemical requirements specified in **Table 1**.

6.2 These specification limits do not preclude the presence of other elements. Limits for unnamed elements are to be established by agreement between manufacturer or supplier and purchaser.

6.2.1 For copper alloys in which zinc is specified as the remainder, either copper or zinc shall be taken as the difference between the sum of all the elements analyzed and 100 %.

6.2.1.1 When all the elements in **Table 1** are analyzed, their sum shall be as shown in the following table.

Copper Alloy UNS No.	Copper Plus Named Elements, % min
C22000	99.8
C23000	99.8
C26000	99.7
C27000	99.7
C27200	99.7
C27400	99.7
C28000	99.7
C33000	99.6
C33200	99.6
C37000	99.6
C44300	99.6

7. Temper

7.1 *Drawn Tempers, H*—The tempers of drawn tube shall be designated as light-drawn (H55), drawn (H58), and hard-drawn (H80) (see **Table 2**). Light-drawn (bending) temper is used only when a tube of some stiffness but yet capable of being bent is needed. Drawn temper is for general purposes and is most commonly used where there is no specific requirement for high strength on the one hand or for bending qualities on the other. Hard-drawn temper is used only where there is need for a tube as strong as is commercially feasible for the sizes indicated. For any combination of diameter and wall thickness not covered under hard-drawn temper, the values given for

drawn temper shall be used. Rectangular including square tubes shall normally be supplied only in drawn (general purpose) temper. When there is a need for light-drawn or hard-drawn tempers these are to be supplied as agreed upon between the manufacturer and the purchaser.

7.2 *Annealed Tempers, O*—The tempers of annealed tube shall be designated as light anneal (O50) and soft anneal (O60) (**Table 3**).

NOTE 1—Tube of Copper Alloy UNS No. C23000, when specified to meet the requirements of the *ASME Boiler and Pressure Vessel Code*, shall have in the annealed condition a minimum tensile strength of 275 MPa and a minimum yield strength of 80 MPa at 0.5 % extension under load, in which case the provisions for grain size and Rockwell hardness in 8.2 do not apply.

8. Mechanical Properties

8.1 *Drawn Temper*—Tube shall conform to the mechanical properties prescribed in **Table 2**. Tension tests are required for tubes with a wall thickness under (0.508 mm) and for round tubes having an inside diameter under 8.0 mm and for rectangular including square tubes having a major distance between inside parallel surfaces under 5.0 mm. The tension test for other sizes of tubes need not be made except when indicated by the purchaser at the time of placing the order. A convenient method of indicating that the tension test is required is to specify that “Test procedure ‘T’ is required” (see 4.1.3). When agreement on the Rockwell hardness tests cannot be reached, the tensile strength requirements of **Table 2** shall be the basis for acceptance or rejection.

8.2 *Annealed Temper*—Tube shall conform to the grain size and Rockwell hardness limits prescribed in **Table 3**.

9. Expansion Test for Round Tube

9.1 Tube ordered in the annealed (O) condition, selected for test, shall be capable of withstanding in accordance with Test Method **B153** an expansion of the outside diameter by the following amount:

Outside Diameter, mm	Expansion of Outside Diameter, %
19.0 and under	20
Over 19.0	15

TABLE 1 Chemical Requirements

Copper Alloy UNS No.	Composition, %					
	Copper	Lead	Arsenic	Tin	Iron, max	Zinc
C22000	89.0–91.0	0.05 max	0.05	remainder
C23000	84.0–86.0	0.05 max	0.05	remainder
C26000	68.5–71.5	0.07 max	0.05	remainder
C27000	63.0–68.5	0.09 max	0.07	remainder
C27200	62.0–65.0	0.07 max	0.07	remainder
C27400	61.0–64.0	0.09 max	0.05	remainder
C28000	59.0–63.0	0.09 max	0.07	remainder
C33000	65.0–68.0	0.25 ^A –0.7	0.07	remainder
C33200	65.0–68.0	1.5–2.5	0.07	remainder
C37000	59.0–62.0	0.9–1.4	0.15	remainder
C44300	70.0–73.0	0.07 max	0.02–0.06	0.9–1.2	0.06	remainder

^A In the case of Copper Alloy UNS No. C33000 or tube sizes greater than 127 mm in outside diameter, or distance between outside parallel surfaces, the lead content shall be 0.7 % maximum, no minimum is specified.

TABLE 2 Mechanical Property Requirements of Drawn Temper Tube

Copper Alloy UNS No.	Temper Designation ^A		Outside Diameter, in. or Major Distance Between Outside Parallel Surfaces, mm	Wall Thickness, mm	Tensile Strength, MPa	Rockwell Hardness ^B 30T
	Standard	Former				
C22000	H58	drawn (general purpose)	all	all	275 min	38 min
C22000	H80	hard drawn ^C	up to 25, incl	0.050 to 3.0, incl	360 min	55 min
C22000	H80	hard drawn ^C	over 25 to 40, incl	0.090 to 5.50, incl	360 min	55 min
C22000	H80	hard drawn ^C	over 50 to 100, incl	1.5 to 6.0, incl	360 min	55 min
C23000	H55	light drawn ^C	all	all	305–400	43–75
C23000	H58	drawn (general purpose)	all	all	305 min	43 min
C23000	H80	hard drawn ^C	up to 25, incl	0.050 to 3.0, incl	395 min	65 min
C23000	H80	hard drawn ^C	over 25 to 50, incl	0.090 to 5.0, incl	395 min	65 min
C23000	H80	hard drawn ^C	over 50 to 100, incl	1.5 to 6.0, incl	395 min	65 min
C26000, C27000, C27200, C27400, C33000, and C33200	H58	drawn (general purpose)	all	all	370 min	53 min
C26000, C27000, C27200, C27400, C33000, and C33200	H80	hard drawn ^C	up to 25, incl	0.050 to 3.0, incl	455 min	70 min
C26000, C27000, C27200, C27400, C33000, and C33200	H80	hard drawn ^C	over 25 to 50, incl	0.090 to 5.0, incl	455 min	70 min
C26000, C27000, C27200, C27400, C33000, and C33200	H80	hard drawn ^C	over 50 to 100, incl	1.5 to 6.0, incl	455 min	70 min
C28000 and C37000	H58	drawn (general purpose)	all	all	370 min	55 min
C44300	H58	drawn (general purpose)	all	all	370 min	53 min
C44300	H80	hard drawn ^C	all	all	455 min	70 min

^A Standard designations defined in Classification **B601**.

^B Rockwell hardness values shall apply only to tubes having a wall thickness of 0.30 mm or over and to round tubes having an inside diameter of 8.0 mm or over and to rectangular including square tubes having an inside major distance between parallel surfaces of 5.0 mm or over. Rockwell hardness shall be made on the inside surface of the tube. When suitable equipment is not available for determining the specified Rockwell hardness, other Rockwell scales and values shall be specified subject to agreement between the manufacturer and the purchaser.

^C Light-drawn and hard-drawn tempers are available in round tube only.

The expanded tube shall show no cracking or rupture visible to the unaided eye. Tube ordered in the drawn (H) condition is not subject to this test.

NOTE 2—The term “unaided eye,” as used herein, permits the use of corrective spectacles necessary to obtain normal vision.

9.2 As an alternative to the expansion test for tube over 102 mm in diameter in the annealed condition, a section 102 mm in length shall be cut from the end of one of the lengths for a flattening test. This 102-mm test specimen shall be flattened so that a gage set at three times the wall thickness will pass over the tube freely throughout the flattened part. The tube so tested shall develop no cracks or flaws visible to the unaided eye (Note 2) as a result of this test. In making the flattening test, the elements shall be slowly flattened by one stroke of the press.

9.3 Drawn temper tube shall not be required to withstand these tests.

10. Mercurous Nitrate Test

10.1 **Warning**—Mercury is a definite health hazard. Use equipment for the detection and removal of mercury vapor. Wear rubber gloves when conducting the test.

10.2 When specifically required, test specimens 152 mm in length of both annealed and drawn tempers shall withstand, after proper cleaning, an immersion for 30 min without

cracking in the standard mercurous nitrate solution prescribed in Test Method **B154**. Immediately after removal from the solution, the specimen shall be wiped free of excess mercury and examined for cracks.

11. Nondestructive Testing

11.1 Unless nondestructive testing has been waived, tubes shall be subjected to a nondestructive test. The manufacturer shall select the nondestructive test that is most suitable for the tube size and the application.

11.1.1 Eddy-current testing is the standard nondestructive test, and all tubes of appropriate size shall be eddy-current tested in accordance with **11.2**.

11.1.2 Tubes that are not of a size suitable for eddy-current test capabilities shall be tested by the hydrostatic test as described in **11.3.1**, or by the pneumatic test as described in **11.3.2**.

11.2 *Eddy-Current Test*—Each tube up to 79 mm in outside diameter shall be subjected to an eddy-current test. Testing shall follow the procedure of Practice **E243**, except the determination of “end effect” is not required. Tubes shall be passed through an eddy-current test unit adjusted to provide information on the suitability of the tube for the intended application.