

---

---

**Plastics — Fire tests — Standard  
ignition sources**

*Plastiques — Essais au feu — Sources d'allumage normalisées*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO/TR 10093:2018](https://standards.iteh.ai/catalog/standards/sist/8f7f80a6-1690-4dd3-aeb9-a9cdf4e19782/iso-tr-10093-2018)

<https://standards.iteh.ai/catalog/standards/sist/8f7f80a6-1690-4dd3-aeb9-a9cdf4e19782/iso-tr-10093-2018>



**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO/TR 10093:2018

<https://standards.iteh.ai/catalog/standards/sist/8f7f80a6-1690-4dd3-aeb9-a9cdf4e19782/iso-tr-10093-2018>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword .....	v
Introduction .....	vi
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Ignition processes</b> .....	<b>4</b>
<b>5 Characteristics of ignition sources</b> .....	<b>4</b>
<b>6 General principles</b> .....	<b>5</b>
6.1 Flaming ignition sources .....	5
6.1.1 Diffusion flame ignition source .....	5
6.1.2 Premixed flame source .....	5
6.1.3 Issues associated with flaming ignition sources .....	5
6.2 Non-flaming ignition sources .....	6
<b>7 Smouldering (cigarette) ignition sources</b> .....	<b>7</b>
7.1 Traditional cigarettes .....	7
7.2 Non-reduced ignition propensity cigarettes .....	8
<b>8 Non-flaming electrical ignition sources</b> .....	<b>8</b>
8.1 Glow-wire ignition .....	8
8.2 Hot-wire ignition .....	9
<b>9 Radiant ignition sources</b> .....	<b>10</b>
9.1 Conical radiant ignition sources .....	10
9.1.1 General .....	10
9.1.2 Cone calorimeter ignition source .....	11
9.1.3 Smoke chamber conical heater .....	14
9.1.4 Ignition source from periodic flaming ignition test .....	17
9.2 Other radiant ignition sources .....	18
9.2.1 Glowbars ignition source .....	18
9.2.2 Lateral ignition and flame spread test (LIFT) radiant panel heater .....	19
9.2.3 Setchkin ignition .....	20
<b>10 Infrared heating system</b> .....	<b>21</b>
<b>11 Diffusion flame ignition</b> .....	<b>22</b>
11.1 Needle flame ignition .....	22
11.2 Burning match .....	23
11.3 Burners generating 50 W or 500 W flames .....	25
<b>12 Premixed burners</b> .....	<b>28</b>
12.1 Premixed burner for 1 kW flame .....	28
12.2 Burners for vertical cable tray tests .....	29
12.2.1 Venturi burners for 20 kW vertical cable tray tests .....	29
12.2.2 Burner for vertical riser cable tests .....	31
12.3 Burner for large scale horizontal tests .....	31
12.4 Burners for room corner tests .....	32
12.4.1 Burner for ISO 9705-1 .....	32
12.4.2 Alternate burner for room corner test .....	33
12.5 Burners for individual product heat release tests .....	34
12.5.1 Burner for single fuel package calorimeter .....	34
12.5.2 Square tube propane burner .....	34
12.5.3 T-shaped propane burner .....	35
12.5.4 Dual T-shaped propane burner .....	35
<b>13 Other ignition sources</b> .....	<b>36</b>

13.1	Wood cribs.....	36
13.2	Paper bags.....	37
<b>Bibliography</b>	.....	<b>38</b>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO/TR 10093:2018](https://standards.iteh.ai/catalog/standards/sist/8f7f80a6-1690-4dd3-aeb9-a9cdf4e19782/iso-tr-10093-2018)

<https://standards.iteh.ai/catalog/standards/sist/8f7f80a6-1690-4dd3-aeb9-a9cdf4e19782/iso-tr-10093-2018>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 4, *Burning behaviour*.

<https://standards.iteh.ai/catalog/standards/sist/8f7f80a6-1690-4dd3-aeb9-a021b1d97810-iso-10093:2018>

This second edition cancels and replaces the first edition (ISO/TR 10093:2017), which has been technically revised. The main changes compared to the previous edition are as follows:

- general changes and updates have been made following early publication of the previous edition;
- **Clause 3**: terms and definitions have been updated to align and with the definitions in ISO 13943:2017;
- **Table 1** has been corrected: Column 2 for “Premixed burner for 1 kW flame” has been corrected to show IEC 60332-1-1 and IEC 60332-1-2;
- **Figure 9**: reference in note has been corrected to IEC 60695-11-5:2016, Figure 1;
- **11.3.1** has been updated with correct references to IEC standards;
- **12.1.1**: “Premixed burner for 1 kW flame” has been corrected to show IEC 60332-1-1 and IEC 60332-1-2;
- **12.1.2** has been updated to state that the flow rates are for the preferred “Method A”;
- **12.1.2** has been updated to change “greater than 98%” to “not less than 95%”.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

Fires are caused by a wide range of possible ignition sources. Statistical analysis of fires has identified the main primary and secondary sources, especially for fires in buildings. The most frequent sources of fires have been found to be as follows:

- a) cooking appliances;
- b) space-heating appliances;
- c) electric wiring, connectors and terminations;
- d) other electrical appliances (such as washing machines, bedwarmers, televisions, water heaters);
- e) cigarettes;
- f) matches and smokers' gas lighters;
- g) blow-lamps, blow-torches and welding torches;
- h) rubbish burning; and
- i) candles.

The above list covers the major primary ignition sources for accidental fires. Other sources can be involved in fires raised maliciously. Research into causes of fires has shown that primary ignition sources (e.g. glowing cigarettes or dropped flaming matches) can set fire to waste paper, which then acts as a secondary ignition source of greater intensity.

When analysing and evaluating the various ignition sources for applications involving plastics materials, it is important to answer the following questions on the basis of detailed fire statistics.

- 1) What is the significance of the individual ignition sources in various fire risk situations?
- 2) What proportion is attributable to secondary ignition sources?
- 3) Where does particular attention have to be paid to secondary ignition sources?
- 4) To what extent are different ignition sources responsible for fatal fire accidents?

The following laboratory ignition sources are intended to simulate actual ignition sources that have been shown to be the cause of real fires involving plastics. Laboratory ignition sources are preferred over actual ignition sources due to their consistency, which results in greater data repeatability within a laboratory and greater reproducibility between laboratories.

These laboratory ignition sources can be used to develop new test procedures.

# Plastics — Fire tests — Standard ignition sources

## 1 Scope

This document describes and classifies a range of laboratory ignition sources for use in fire tests on plastics and products consisting substantially of plastics. These sources vary in intensity and area of impingement. They are suitable for use to simulate the initial thermal abuse to which plastics are potentially exposed in certain actual fire risk scenarios.

Different standards developing organizations have issued many standard test methods, specifications and regulations to assess fire properties of plastics or of products containing plastic materials. Many of those standards contain ignition sources associated with flaming and non-flaming ignition. This document describes the ignition sources and references the associated standard.

This compilation of ignition sources does not discuss the application of the standard where the ignition source is described and is likely not to be a fully comprehensive list of ignition sources.

This document does not address detailed test procedures.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 13943, *Fire safety — Vocabulary* ISO/TR 10093:2018  
<https://standards.iteh.ai/catalog/standards/sist/8f7f80a6-1690-4dd3-aeb9-a9cd4e19782/iso-tr-10093-2018>

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 13943 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 3.1

#### **afterflame**

*flame* (3.8) that persists after the ignition source has been removed

[SOURCE: ISO 13943:2017, 3.11]

### 3.2

#### **afterflame time**

length of time for which an *afterflame* (3.1) persists under specified conditions

[SOURCE: ISO 13943:2017, 3.12]

### 3.3

#### **afterglow**

persistence of glowing combustion after both removal of the ignition source and the cessation of any flaming combustion

[SOURCE: ISO 13943:2017, 3.13]

3.4

**afterglow time**

length of time for which an *afterglow* (3.3) persists under specified conditions

[SOURCE: ISO 13943:2017, 3.14]

3.5

**combustion**

exothermic reaction of a substance with an oxidizing agent

[SOURCE: ISO 13943:2017, 3.55, modified — note has been omitted.]

3.6

**ease of ignition**

measure of the ease with which a test specimen can be ignited, under specified conditions

[SOURCE: ISO 13943:2017, 3.212]

3.7

**exposed surface**

surface of a test specimen subjected to the heating conditions of a fire test

[SOURCE: ISO 13943:2017, 3.106]

3.8

**flame**, noun

rapid, self-sustaining, sub-sonic propagation of *combustion* (3.5) in a gaseous medium, usually with emission of light

[SOURCE: ISO 13943:2017, 3.159]

3.9

**flame**, verb

produce *flame* (3.8)

[SOURCE: ISO 13943:2017, 3.160]

ITeH STANDARD PREVIEW  
(standards.iteh.ai)  
ISO/TR 10093:2018  
<https://standards.iteh.ai/catalog/standards/sist/8f7f80a6-1690-4dd3-aeb9-a9cd4e19782/iso-tr-10093-2018>

3.10

**flaming debris**

burning material separating from a burning item and continuing to *flame* (3.9) on the floor, during a fire or fire test

Note 1 to entry: Alternatively, flaming debris can be burning material, other than drops, which has detached from a test specimen during a fire or fire test and continues to burn.

Note 2 to entry: Compare with the terms *flaming droplets* (3.11).

[SOURCE: ISO 13943:2017, 3.176]

3.11

**flaming droplets**

flaming molten or flaming liquefied drops which fall from the test specimen during the fire test and continue to burn on the floor

Note 1 to entry: Compare with the term *flaming debris* (3.10).

[SOURCE: ISO 13943:2017, 3.177]



**3.12****glowing combustion**

*combustion* (3.5) of a material in the solid phase without *flame* (3.8) but with emission of light from the combustion zone

[SOURCE: ISO 13943:2017, 3.197]

**3.13****ignitability**

measure of the ease with which a specimen can be *ignited* (3.14), under specified conditions

[SOURCE: ISO 13943:2017, 3.212]

**3.14****ignite**, transitive verb

initiate *combustion* (3.5)

[SOURCE: ISO 13943:2017, 3.215]

**3.15****ignite**, intransitive verb

catch fire with or without the application of an external heat source

[SOURCE: ISO 13943:2017, 3.214]

**3.16****ignition**

initiation of *combustion* (3.5)

[SOURCE: ISO 13943:2017, 3.217]

**3.17****ignition source**

source of energy that initiates *combustion* (3.5)

[SOURCE: ISO 13943:2017, 3.219]

**3.18****ignition time**

duration of exposure of a test specimen to a defined *ignition source* (3.17) required for the initiation of sustained *combustion* (3.5) under specified conditions

[SOURCE: ISO 13943:2017, 3.220]

**3.19****irradiance**

ratio of the radiant flux incident on a small but measurable element of surface containing the point, by the area of that element

[SOURCE: ISO 13943:2017, 3.236]

**3.20****minimum ignition temperature**

minimum temperature of a material at which sustained *combustion* (3.5) can be initiated under specified test conditions

[SOURCE: ISO 13943:2017, 3.327]

**3.21****primary ignition source**

first applied *ignition source* (3.17)

### 3.22

#### **punking**

propagation of a smouldering *combustion* (3.5) front after removal of the *ignition source* (3.17)

### 3.23

#### **secondary ignition source**

heat source which is activated following *ignition* (3.16) from a primary source

### 3.24

#### **sustained flaming**

*flame* (3.8), on or over the surface of a test specimen, which persists for longer than a defined period of time

Note 1 to entry: Compare with the term *transitory flaming* (3.25).

[SOURCE: ISO 13943:2017, 3.380]

### 3.25

#### **transitory flaming**

*flame* (3.8), on or over the surface of a test specimen, which persists for a defined short period of time

Note 1 to entry: Compare with the term *sustained flaming* (3.24).

[SOURCE: ISO 13943:2017, 3.408]

## 4 Ignition processes iTeh STANDARD PREVIEW

(standards.iteh.ai)

4.1 When plastics are exposed to thermal energy, flammable vapours are often generated from their surface. Under suitable conditions (especially high temperatures), it is possible that a critical concentration of flammable vapour will form and spontaneous ignition will result. If a flame is present as the sole energy source, or as a supplementary source, the ignition process will be assisted; this mechanism is sometimes known as piloted ignition.

4.2 A specimen of plastic is regarded as ignited when flames appear on the surface of the plastic or when glowing combustion is evident.

4.3 After ignition has occurred, some burning plastics create additional fire hazards by forming flaming debris or drips. If this flaming debris falls on to combustible material, it is possible that secondary ignition will occur and the fire will spread more rapidly.

4.4 The localized application of a heat source to some plastics results in glowing combustion. With some thermoplastic foams and foams from thermosetting materials, the localized application of a heat source results in punking which produces a carbonaceous char.

## 5 Characteristics of ignition sources

5.1 The following factors are the main characteristics describing ignition sources and their relation to the test specimen:

- a) intensity of the ignition source, which is a measure of the thermal load on the specimen resulting from the combined conduction, convection and radiation effects caused by the ignition source;
- b) area of impingement of the ignition source on the specimen;
- c) duration of exposure of the specimen and whether it is continuous or intermittent;
- d) presentation of the ignition source to the specimen and whether or not it impinges;

- e) orientation of the specimen in relation to the ignition source;
- f) ventilation conditions in the vicinity of the ignition source and exposed surface of the specimen.

NOTE Factors c) to f) are often a function of the specific fire test conditions.

**5.2** Several of the ignition sources provide a range of intensities and areas of impingement to be considered for use in fire tests of plastics.

**5.3** IEC 60695-1-21 provides guidance on ignition sources relevant to the fire testing of electrotechnical products.

## 6 General principles

### 6.1 Flaming ignition sources

#### 6.1.1 Diffusion flame ignition source

To form a diffusion flame ignition source, a gas (usually propane, methane or butane) flows through metallic tubes without ingress of air prior to the base of the flame. These flames simulate natural flames well but they often fluctuate and are not convenient to direct if it is necessary to point any angular presentation toward the specimen.

#### 6.1.2 Premixed flame source

To form a premixed flame source, a gas burner (usually using propane, methane or butane) fitted with air inlet ports or an air intake manifold is used. Premixed flame sources are typically more directional than diffusion flame sources and are generally hotter than diffusion flame sources.

#### 6.1.3 Issues associated with flaming ignition sources

Gas burners are always set up to conform to precise gas flow rates and/or flame heights. Periodic checks of flame temperature or heat flux precede the setup, but criteria on these parameters are not necessarily an essential part of the laboratory procedure. After setting up the burner for a particular test (i.e. often at an acute angle to the test specimen), it is desirable to leave the burner in this orientation throughout a series of experiments. This objective is conveniently satisfied if the operator simply maintains the gas flow constant to the burner.

The gas burners are connected to the gas supply by flexible tubing via a cylinder regulator providing an outlet pressure, on-off valve, fine-control valve and flowmeter.

Difficulties sometimes occur with the supply and measurement of butane or propane when the cylinders have been stored in an environment cooler than the defined test conditions and/or some distance from the test rig. When difficulties occur, a sufficient length of tubing is used inside the controlled environment (15 °C to 30 °C) to ensure that the gas equilibrates to the appropriate temperature before flow measurement.

NOTE 1 One way to facilitate this equilibration is to pass the gas (before flow measurement) through a metal tube immersed in water maintained at 25 °C.

It is important to exercise great care with the measurement and setting of the flow rate of the gas and to check direct-reading flowmeters, even those obtained with a direct calibration for the gas used initially,

at regular intervals during testing, with a method capable of measuring accurately the absolute gas flow at the burner tube.

NOTE 2 One way of doing this is to connect the burner tube with a short length of tubing (about 7 mm internal diameter) to a soap bubble flowmeter. Passage of a soap film meniscus in a glass tube (e.g. a calibrated burette) over a known period of time gives an absolute measurement of the flow. Also, fine-control valves that can each be pre-set to one of the desired gas flow rates, with simple means for switching from one to the other, have proved helpful.

## 6.2 Non-flaming ignition sources

The following clauses/subclauses describe ignition sources as follows (see [Table 1](#)):

- [Clause 7](#): smouldering (cigarette);
- [Clause 8](#): Non-flaming electrical ignition sources;
  - [8.1](#) Glow-wire ignition;
  - [8.2](#) Hot-wire ignition;
- [Clause 9](#): Radiant ignition sources;
  - [9.1](#) Conical radiant ignition;
  - [9.2](#) Other radiant ignition;
- [Clause 10](#): Infrared heating ignition;
- [Clause 11](#): Diffusion flame ignition;
  - [11.1](#) Needle flame ignition; [ISO/TR 10093:2018](#)
  - [11.2](#) Burning match; <https://standards.iteh.ai/catalog/standards/sist/8f7f80a6-1690-4dd3-aeb9-a9cdf4e19782/iso-tr-10093-2018>
  - [11.3](#) Burners generating 50 W or 500 W flames;
- [Clause 12](#): Premixed flame ignition;
  - [12.1](#) Premixed burner for 1 kW flame;
  - [12.2](#) Vertical cable tray burners;
  - [12.3](#) Burners for large scale horizontal tests;
  - [12.4](#) Burners for room corner tests;
  - [12.5](#) Burners for individual product heat release tests;
- [Clause 13](#): Other ignition sources;
  - [13.1](#) Wood cribs;
  - [13.2](#) Paper bags.

Table 1 — Classification of ignition sources

Type of ignition source	Standard(s) using ignition source	Clause/subclause
Smouldering (cigarette)	ISO 8191-1, NFPA 260, NFPA 261	<a href="#">Clause 7</a>
Non flaming electrical ignition sources		<a href="#">Clause 8</a>
Glow-wire ignition	IEC 60695-2-10, IEC 60695-2-11, IEC 60695-2-12, IEC 60695-2-13, ASTM D6194	<a href="#">8.1</a>
Hot-wire ignition	IEC/TS 60695-2-20, ASTM D3874	<a href="#">8.2</a>
Radiant ignition sources		<a href="#">Clause 9</a>
Conical radiant ignition	ISO 5657, ISO 5659-2, ISO 5660-1, ASTM E1354, ASTM E1995, NFPA 270	<a href="#">9.1</a>
Other radiant ignition	ISO 871, ASTM D1929, ASTM E906, ISO 5658-2, ASTM E1321	<a href="#">9.2</a>
Infrared heating ignition sources	ISO 12136, ASTM E2058, NFPA 287	<a href="#">Clause 10</a>
+		
Diffusion flame ignition sources		<a href="#">Clause 11</a>
Needle flame ignition	IEC 60695-11-5	<a href="#">11.1</a>
Burning match	ISO 8191-2, ISO 11925-2	<a href="#">11.2</a>
Burners generating 50 W or 500 W flames	IEC 60695-11-3, IEC 60695-11-4, ASTM D635, ASTM D5025, UL 94	<a href="#">11.3</a>
Premixed flame ignition sources		<a href="#">Clause 12</a>
Premixed burner for 1 kW flame	IEC 60695-11-2, IEC 60332-1-1, IEC 60332-1-2	<a href="#">12.1</a>
Vertical cable tray burners	IEC 60332-3-10, ASTM D5424, ASTM D5537, UL 1666, UL 1685, UL 2556	<a href="#">12.2</a>
Burners for large scale horizontal tests	ASTM E84, NFPA 262	<a href="#">12.3</a>
Burners for room corner tests	ISO 9705,-1 ASTM E2257, NFPA 265, NFPA 286	<a href="#">12.4</a>
Burners for individual product heat release tests	ASTM E1537, ASTM E1590, ASTM E1822, NFPA 289	<a href="#">12.5</a>
Other ignition sources		<a href="#">Clause 13</a>
Wood cribs		<a href="#">13.1</a>
Paper bags		<a href="#">13.2</a>

## 7 Smouldering (cigarette) ignition sources

### 7.1 Traditional cigarettes

**7.1.1** This source is typical of a common commercial cigarette, which is known to cause many fires involving upholstered furniture and bedding as discussed in ISO 8191-1. The untipped (unfiltered) cigarette meets the following:

- length: (70 ± 4) mm;
- diameter: (8,0 ± 0,5) mm;
- mass: (1,0 ± 0,1) g;
- smouldering rate: (12,0 ± 3,0) min to reach from 5 mm to 50 mm mark.