NOTICE: This standard has either been superseded and replaced by a new version or withdrawn. Contact ASTM International (www.astm.org) for the latest information



Designation: E 760 – 92 (Reapproved 2000)

Standard Test Method for Effect of Impact on Bonding of Sprayed Fire-Resistive Material Applied to Structural Members¹

This standard is issued under the fixed designation E 760; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers a procedure for determining the effect of impact loading on the bonding of sprayed fire-resistive material (SFRM) applied to the underside of steel floor deck. These materials include sprayed fibrous and cementitious materials applied directly in contact with the structural members. The test method is applicable only to laboratory procedures.

1.2 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

- 2.1 ASTM Standards:
- E 84 Test Method for Surface Burning Characteristics of Building Materials²
- E 119 Test Methods for Fire Tests of Building Construction and Materials²

E 605 Test Methods for Thickness and Density of Sprayed 6

Fire-Resistive Material (SFRM) Applied to Structural Members³

E 695 Method for Measuring Relative Resistance of Wall, Floor, and Roof Constructions to Impact Loading³

3. Summary of Test Method

3.1 In this test method, a cellular steel deck with a concrete topping sprayed with fire-resistive material is subjected to a leather bag drop impact while supported horizontally at its ends.

4. Significance and Use

4.1 The intent of this test method is to determine a property of SFRM that may be used to provide an indication of its

² Annual Book of ASTM Standards, Vol 04.07.

in-place serviceability. Satisfactory performance of SFRM applied to structural members and assemblies depends upon its ability to withstand the various influences that may occur during construction and during the life of the structure, as well as upon its satisfactory performance under fire conditions.

4.2 The test method measures the behavior of SFRM when the floor construction to which it is applied is subjected to shock loading and evaluates adhesion and resistance to spalling, cracking, and delamination. It is an indication of the ability of SFRM to remain in place and resist removal during anticipated service conditions.

5. Apparatus

5.1 *Supports*—Rigid base to provide at least 50 mm (2 in.) bearing and a clear span between supports of at least 3 m (10 ft).

5.2 *Impact Instrument*—A lead shot- or steel shot-filled leather bag weighing 27.2 kg (60 lb) and equipped with a leather hoisting strap, both as described in Method E 695.

5.3 *Rule*—To measure the height of drop (1.2 m (4 ft)) with an accuracy of 12.8 mm ($\frac{1}{2}$ in.).

6. Materials afa6-68d346b665bd/astm-e760-922000

6.1 The test specimen shall be a deck assembly consisting of cellular steel deck and a concrete topping. The cellular steel deck shall be of the noncomposite type, nominal 40 mm ($1\frac{1}{2}$ in.) deep, 600 mm (24 in.) wide, by 3600 mm (12 ft) long, consisting of a 1.5-mm (0.060-in.) thick galvanized or painted steel fluted top section and 1.2-mm (0.048-in.) galvanized steel flat bottom section welded together to form four cells 150 mm (6 in.) on center.

6.2 The concrete shall be nominal 20 MPa (3000 psi), and 64 mm ($2\frac{1}{2}$ in.) deep as measured from the top plane to the steel decking.

6.3 This test method requires the application of SFRM in accordance with manufacturers' published instructions. The apparatus, materials, and procedures used to apply the SFRM for this test shall be representative of application in the field.

6.4 The density of the prepared sample shall be similar to the density tested and reported during the Test Methods E 119 and Test Method E 84 fire exposure tests or as required by the sponsor of the test.

¹This test method is under the jurisdiction of ASTM Committee E06 on Performance of Buildings and is the direct responsibility of Subcommittee E06.21 on Serviceability.

Current edition approved Sept. 22, 1992. Published November 1992. Originally published as E 760 – 80. Last previous edition E 760 – 86 (1991).

³ Annual Book of ASTM Standards, Vol 04.11.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.