
**Nanotechnologies — Characterization
of volatile components in single-
wall carbon nanotube samples
using evolved gas analysis/gas
chromatograph-mass spectrometry**

Nanotechnologies — Caractérisation des composés volatils dans les nanotubes de carbone à simple paroi (SWCNT) utilisant l'analyse des gaz émis par chromatographie en phase gazeuse couplée à la spectrométrie de masse

[ISO/TS 11251:2019](https://standards.iteh.ai/catalog/standards/sist/945fa8bb-016e-48c8-84fd-deb0b246af61/iso-ts-11251-2019)

<https://standards.iteh.ai/catalog/standards/sist/945fa8bb-016e-48c8-84fd-deb0b246af61/iso-ts-11251-2019>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/TS 11251:2019

<https://standards.iteh.ai/catalog/standards/sist/945fa8bb-016e-48c8-84fd-deb0b246af61/iso-ts-11251-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus	2
6 Sample preparation	4
7 Measurement procedures for EGA/MS and EGA/GCMS	4
7.1 General	4
7.2 Measurement procedure of EGA/MS	4
7.3 Measurement procedure of EGA/GCMS	4
8 Data analysis and interpretations of results	5
8.1 Qualitative analysis	5
8.2 Mass loss analysis	5
9 Accuracy and uncertainties	5
10 Test report	5
Annex A (informative) Case study	7
Bibliography	12

ITeH STANDARD PREVIEW
(standards.iteh.ai)

[ISO/TS 11251:2019](https://standards.iteh.ai/catalog/standards/sist/945fa8bb-016e-48c8-84fd-deb0b246af61/iso-ts-11251-2019)

<https://standards.iteh.ai/catalog/standards/sist/945fa8bb-016e-48c8-84fd-deb0b246af61/iso-ts-11251-2019>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 229, *Nanotechnologies*.

This second edition cancels and replaces the first edition (ISO/TS 11251:2010), which has been technically revised.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Nanotechnologies — Characterization of volatile components in single-wall carbon nanotube samples using evolved gas analysis/gas chromatograph-mass spectrometry

1 Scope

This document specifies a method for the characterization of evolved gas components in single-wall carbon nanotube (SWCNT) samples using evolved gas analysis/gas chromatograph mass spectrometry (EGA/GCMS).

NOTE Some difference could appear between qualitative and quantitative results of emitted gas and gas content in the sample due to the heating and the possible presence of catalysts.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/TS 80004-3, *Nanotechnologies — Vocabulary — Part 3: Carbon nano-objects*

3 Terms and definitions

ISO/TS 11251:2019

<https://standards.iteh.ai/catalog/standards/sist/945fa8bb-016e-48c8-84fd->

For the purposes of this document, the terms and definitions given in ISO/TS 80004-3 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

single-wall carbon nanotube SWCNT

carbon nanotube consisting of cylindrical graphene layer

3.2

evolved gas analysis

EGA

technique in which the nature and/or amount of evolved gas product(s) released by a sample subjected to a controlled temperature program is(are) determined

Note 1 to entry: The method of analysis should always be clearly stated (Reference [1] in the Bibliography).

3.3

EGA/MS

evolved gas analysis/mass spectrometry

technique using mass spectrometry to analyse gaseous components evolved from a sample as a function of temperature

Note 1 to entry: Although the gases evolved at any particular temperature are detected simultaneously, it might not be possible to uniquely identify the different components using MS alone.

3.4

EGA/GCMS

evolved gas analysis/gas chromatography coupled to mass spectrometry

technique combining a gas chromatograph and a mass spectrometer to identify the chemical composition of gases evolved from a sample as a function of temperature

Note 1 to entry: The evolved gases are passed through a gas chromatograph (GC) to separate each component so that it can be identified in the MS unit.

3.5

volatile compounds

compounds that are evolved from a sample at the temperature under consideration

4 Principle

EGA/MS and EGA/GCMS are used to characterize evolved gas impurities in samples of SWCNT. Evolved gas compounds are identified by measuring the mass spectra of the gaseous component evolved from the heated samples in a furnace or other suitable heating device, such as that used for programmed temperature pyrolysis or thermogravimetric analysis. EGA/MS is used to determine the temperature range over which the release of evolved gas components occurs. EGA/GCMS analysis is used to identify each component separately by the use of a GC capillary column. Quantitative information can additionally be obtained by the sample mass loss in thermogravimetric analysis (TGA) and the peak area in EGA/MS.

NOTE Some details of the technique are described in References [2] to [6] in the Bibliography. EGA/GCMS plays a complementary role to TGA, which is mainly devoted to quantifying the mass of the evolved gas components.

ITEH STANDARD PREVIEW
(standards.iteh.ai)


5 Apparatus

ISO/TS 11251:2019

<https://standards.iteh.ai/catalog/standards/sist/945fa8bb-016e-48c8-84fd->

[Figure 1](#) shows a schematic diagram of EGA/MS which is composed of a furnace, a heating unit without a GC capillary column and a MS unit. In the EGA/MS, evolved gas from the furnace is led to the MS unit directly through a capillary tube without a separation process.


[Figure 2](#) shows a schematic diagram of an EGA/GCMS which is composed of a furnace, a GC with a capillary column and an MS unit. In the EGA/GCMS, all compounds evolved from the sample within the furnace are captured by the cooling trap and are then introduced to the GC capillary column unit by heating the trap. The compounds are separated by the column in the GC unit.



Key

- 1 furnace
- 2 heating unit
- 3 MS unit
- 4 temperature controller of furnace

Figure 1 — Schematic diagram of EGA/MS
iTeh STANDARD PREVIEW
(standards.iteh.ai)



Key

- 1 furnace
- 2 cooling trap
- 3 capillary column
- 4 GC unit
- 5 MS unit
- 6 temperature controller of furnace

Figure 2 — Schematic diagram of EGA/GCMS

6 Sample preparation

Sample preparation, such as dissolution or dispersion, is not required. For a qualitative analysis, the sample shall be introduced into the EGA/MS or EGA/GCMS as it is. In order to avoid the vaporization of any evolved gas that might be present, samples shall not be exposed to temperature above 30 °C before analysis.

7 Measurement procedures for EGA/MS and EGA/GCMS

7.1 General

Load the SWCNT sample into the furnace and heat it up to identify the temperature range of gasification using EGA/MS measurement, and use the EGA/GCMS to identify each component at the designated temperature range.

7.2 Measurement procedure of EGA/MS

Weigh between 0,5 mg and 2 mg of the SWCNT sample, to the nearest 0,01 mg, using a calibrated mass balance.

Load the weighed sample into the furnace, including the sample cup used when weighing.

Heat the sample at a constant rate until gas evolution stops. Measure the total ions from evolved gas components. Determine the start temperature and the end-point of gasification using the EGA curve.

Compare the observed mass spectrum with the mass spectral database and determine each component in the evolved gas species. For appropriate comparison of mass spectra, ionization energy and tuning conditions used for the analysis shall match those in the spectral database.

Perform EGA/GCMS if the measured spectrum cannot be identified using the MS spectral database due to the mixture of components (see 7.3).

Weigh the sample after EGA/MS measurement, to the nearest 0,01 mg.

NOTE The rate of heating depends on the calorific capacity of the sample. Generally, a range of 10 to 25 °C/min is used for EGA/MS.

7.3 Measurement procedure of EGA/GCMS

Weigh between 0,5 mg and 2 mg of SWCNT from the same sample as that used in 7.2, to the nearest 0,01 mg.

Load the sample into the furnace.

Heat the sample at a constant rate to the lower temperature of either the end-point of the gasification or upper limit of the instrument.

Compare the electron ionization (EI) mass spectrum for each of the GC peaks with the mass spectral database and determine each component of the evolved gas species. For appropriate comparison of mass spectra, ionization energy and tuning conditions used for the analysis shall match those in the spectral database (typically 70 electron volts).

The mass analyser shall be calibrated manually or via the instrument's tuning algorithm by using a calibration reference material.

The rate of heating depends on the sample. Generally, a range of 45 to 65 °C/min is used for EGA/GCMS to shorten the analytical time. The temperature of the trap should be less than about -150 °C.

8 Data analysis and interpretations of results

8.1 Qualitative analysis

The qualitative analysis shall be based upon the standard spectral information of compounds. Components from evolved gas shall be determined by comparing the measured MS spectra with a mass spectral database.

- a) Choose the component that needs to be identified.
- b) Subtract the background from the analyte's mass spectra.
- c) Search for similar spectra from within the spectral database.
- d) Select the possible components in the sample from the candidates identified using the standard spectra.

NOTE 1 Many kinds of software for similarity searching and a mass spectral database are available, as an example, NIST/EPA/NIH Mass Spectral database with Similarity Search Program.

NOTE 2 Using this method, *n*-hexane, benzene and toluene were identified in the example shown in [Annex A](#) and [Figure A.4](#).

8.2 Mass loss analysis

The evolved gas components in SWCNT samples are determined using the following formula:

$$P = \frac{W_0 - W_t}{W_0} \times 100$$

where

P is the evolved gas impurity content, expressed as a percentage;

W_0 is the sample mass, in milligrams, before heating;

W_t is the sample mass, in milligrams, after heating.

NOTE Normally, quantitative analysis by GC/MS needs calibration curves, which show the relationship of the signal intensity and the concentration of each component. It is impossible to prepare the calibration curves for all components of interest. For this reason, only mass loss by the EGA process is used.

9 Accuracy and uncertainties

Currently, the uncertainties in the evolved gas components characterizations for SWCNTs by EGA/GCMS come from

- a) fluctuation of temperature in the oven or detector,
- b) mis-calibration and/or drifting of the mass analyser, or
- c) fluctuation of ionization energy.

10 Test report

The test report shall include the following information:

- a) a reference to this document and its year of publication;
- b) Identified components including gas chromatograph-mass spectrometry;