



Designation: C1240 – 10

Standard Specification for Silica Fume Used in Cementitious Mixtures¹

This standard is issued under the fixed designation C1240; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This specification covers silica fume for use in concrete and other systems containing hydraulic cement.

1.2 In the cases of slurried or densified silica fume, perform the tests on the raw silica fume from which these products have been made.

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 The following safety hazards caveat pertains only to the test methods portions, Sections 10-19, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Read the material safety data sheets for materials used.

1.5 The text of this standard references notes and footnotes that provide explanatory information. These notes and footnotes (excluding those in tables) shall not be considered as requirements of this standard.

2. Referenced Documents

2.1 ASTM Standards:²

C109/C109M Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or [50-mm] Cube Specimens)

C114 Test Methods for Chemical Analysis of Hydraulic Cement

C125 Terminology Relating to Concrete and Concrete Aggregates

C135 Test Method for True Specific Gravity of Refractory Materials by Water Immersion

C183 Practice for Sampling and the Amount of Testing of Hydraulic Cement

C185 Test Method for Air Content of Hydraulic Cement Mortar

C219 Terminology Relating to Hydraulic Cement

C311 Test Methods for Sampling and Testing Fly Ash or Natural Pozzolans for Use in Portland-Cement Concrete

C430 Test Method for Fineness of Hydraulic Cement by the 45- μ m (No. 325) Sieve

C441 Test Method for Effectiveness of Pozzolans or Ground Blast-Furnace Slag in Preventing Excessive Expansion of Concrete Due to the Alkali-Silica Reaction

C494/C494M Specification for Chemical Admixtures for Concrete

C604 Test Method for True Specific Gravity of Refractory Materials by Gas-Comparison Pycnometer

C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials

C1005 Specification for Reference Masses and Devices for Determining Mass and Volume for Use in the Physical Testing of Hydraulic Cements

C1012 Test Method for Length Change of Hydraulic-Cement Mortars Exposed to a Sulfate Solution

C1069 Test Method for Specific Surface Area of Alumina or Quartz by Nitrogen Adsorption

C1157 Performance Specification for Hydraulic Cement

C1437 Test Method for Flow of Hydraulic Cement Mortar

3. Terminology

3.1 Definitions:

3.1.1 *silica fume*—very fine pozzolanic material, composed mostly of amorphous silica produced by electric arc furnaces as a by-product of the production of elemental silicon or ferro-silicon alloys (also known as condensed silica fume and microsilica).

3.1.2 Other terms in this specification are defined in Terminologies C125 and C219.

¹ This specification is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.24 on Supplementary Cementitious Materials.

Current edition approved Oct. 15, 2010. Published November 2010. Originally approved in 1993. Last previous edition approved in 2005 as C1240-05. DOI: 10.1520/C1240-10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

4. Ordering Information

4.1 The purchaser shall specify any optional chemical or physical requirements.

5. Chemical Composition

5.1 Silica fume shall conform to the requirements for chemical composition prescribed in Table 1.

6. Physical Requirements

6.1 Silica fume shall conform to the physical requirements prescribed in Table 2. Optional physical requirements are given in Table 3.

7. Sampling

7.1 When the purchaser desires that the silica fume be sampled and tested to verify compliance with this specification, perform the sampling and testing in accordance with Practice C183, modified as described in 7.3.

NOTE 1—Exercise caution in the interpretation of Practice C183, since there is a difference between the continuous manufacture of hydraulic cement and the generation and collection of silica fume. To a great extent, storage is dictated by the design of the silica-fume collection system. The design of silica-fume collection systems may not have provided for sampling points and practices.

7.2 Practice C183, as modified, is not designed for manufacturing quality control and is not required for manufacturer's certification.

7.3 The following modification of Practice C183 is necessary to render it applicable to silica fume.

7.3.1 Replace the words "hydraulic cement" and "cement" with the words "silica fume" every time that they appear in the text.

7.3.2 All samples, whether grab or composite, shall have a mass of at least 1 kg (2 lb).

7.3.3 When compliance verification tests of silica fume are required to be made at a laboratory other than that of the silica-fume manufacturer or marketer, coordinate the silica-fume sampling schedule, sample transportation time, and sample testing schedule among the purchaser, manufacturer, and testing laboratory so that the test results will be available when the decision to accept or reject the silica fume must be made.

7.3.4 The section entitled "Sampling" is modified as follows:

7.3.4.1 Take two grab samples or two composite samples for the first 100 Mg (110 tons) of silica fume. Take a grab sample or a composite sample for each subsequent 100 Mg (110 tons) of silica fume, but not less than two samples shall be taken in any sampling program.

7.3.4.2 *From Bulk Storage at Points of Discharge*—Withdraw silica fume from the discharge openings in a steady stream until sampling is completed. In sampling bulk storage at points of discharge, while the silica fume is flowing through the openings, take samples at such intervals so that, at a minimum, the sampling requirements of 7.3.4.1 are met.

7.3.5 The section entitled "Amount of Testing" is modified by deleting the first paragraph, "General."

8. Frequency of Tests

8.1 Except for the tests listed in 8.2, make all chemical determinations and physical tests on composite samples representing no more than 400 Mg (440 tons) each. Prepare each composite sample by combining portions from the samples representing each 100 Mg (110 tons), so that each 100 Mg is represented equally.

8.2 Test for specific surface, density, and accelerated pozzolanic strength activity index using composite samples that represent 3200 Mg (3520 tons) or 3 months of production, whichever gives the highest frequency. Prepare each composite sample by combining portions from the samples representing each 400 Mg (440 tons) or 1 month, whichever gives the highest frequency, so that each sample is represented equally.

9. Preparation of Sample

9.1 Prepare composite samples for tests, as required in Section 8, by arranging all test samples in groups, with each group representing the number of megagrams required by the test or tests for which the composite sample is intended. From each of the samples in a group, take equal portions, sufficient in amount to form a composite sample large enough to permit making the required physical or chemical determinations.

9.2 Prior to testing, mix grab samples and composite samples thoroughly. A clean and dry laboratory concrete drum mixer provides adequate mixing for this purpose. Take care to limit the volume of silica fume in the drum mixer to the range of 10 to 50 % of the drum's total capacity. If necessary, secure a sheet of polyethylene film on the drum with an elastic tiedown to keep the material in the drum. Limit the mixing action to 5 ± 1 min.

TABLE 1 Chemical Requirements

SiO ₂ , min, %	85.0
Moisture content, max, %	3.0
Loss on ignition, max, %	6.0

TABLE 2 Physical Requirements

Oversize:	
Percent retained on 45- μm (No. 325), max, % ^A	10
Percent retained on 45- μm (No. 325), max variation from average, percentage points ^B	5
Accelerated pozzolanic strength activity index: ^C	
With portland cement at 7 days, min percent of control	105
Specific surface, min, m ² /g	15

^A Exercise care to avoid retaining agglomerations of extremely fine material.

^B The average shall consist of the ten preceding tests or all of the preceding tests if the number is less than ten.

^C Accelerated pozzolanic strength activity index is not to be considered a measure of the compressive strength of concrete containing the silica fume. This is a measure of the reactivity of a given silica fume with a given cement and may vary with the source of both the silica fume and the cement.

TABLE 3 Optional Physical Requirements^A

Uniformity requirements:	
When air-entraining concrete is specified, the quantity of air-entraining agent required to produce air content of 18.0 vol % of mortar shall not vary from the average established by the ten preceding tests or by all preceding tests if less than ten, by more than, %	20
Reactivity with cement alkalis: ^B	
Reduction of mortar expansion at 14 days, min, %	80
Sulfate resistance expansion, ^C	
(moderate resistance) 6 months, max, %	0.10
(high resistance) 6 months, max, %	0.05
(very high resistance) 1 year, max, %	0.05

^A Will be made only at the request of the purchaser.

^B The indicated tests for reactivity with cement alkalis shall not be requested unless the material is to be used with an aggregate that is regarded as deleteriously reactive with alkalis in hydraulic cement. The test for reduction of mortar expansion may be made using any high-alkali cement in accordance with Test Methods C311, if the cement to be used in the work is not known or is not available at the time of the test. The test for mortar expansion should be performed by each of the high-alkali cements to be used in the work.

^C Only one limit shall be specified.

9.2.1 When a small sample size precludes the use of a concrete mixer, use a heavy plastic bag, of a capacity at least five times larger than the sample volume, to mix the sample thoroughly. After placing the sample in the bag, close the bag by tying the bag opening tightly, and mix the material by rolling the bag around for 5 ± 1 min.

9.3 Take material for specific tests from a thoroughly mixed sample by using a sampling device (sampling tube, scoop, etc.) of appropriate size to make a test specimen. Make this test specimen from at least six random subsamples.

TEST METHODS—CHEMICAL ANALYSIS

10. Silicon Dioxide and Total Alkalies

10.1 *Reference Method*—Use the reference method in Test Methods C114 for cements with insoluble residue greater than 1 %. Analysts performing sodium oxide and potassium oxide determinations shall observe the precautions outlined in the applicable section of Performance Specification C1157 (refer to the section on Test Methods). Most pozzolans dissolve completely in lithium borate fluxes.

11. Moisture Content and Loss on Ignition

11.1 Follow the applicable provisions of Test Methods C311.

TEST METHODS—PHYSICAL TESTS

12. Density

12.1 Test Method C135 has been adapted for determining the density of silica fume. Test Method C604, which utilizes a helium pycnometer is quick, precise, and is an alternative method that is acceptable for density determinations.

12.1.1 Test Method C135 adapted as follows:

12.2 *Equipment:*

12.2.1 *Two 500-mL Volumetric Flasks*, Class A.

12.2.2 *Balance*, with an accuracy of at least 0.01 g.

12.2.3 *Constant Temperature Bath*, capable of being regulated within ± 0.5 °C (1.0 °F).

12.3 *Deionized Water*.