

---

---

## Welding — Grouping systems for materials — European materials

*Soudage — Systèmes de groupement des matériaux — Matériaux  
européens*

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

[ISO/PRE TR 20172](https://standards.iteh.ai/catalog/standards/sist/8500f346-705f-408b-a742-32fce8607614/iso-prf-tr-20172)

<https://standards.iteh.ai/catalog/standards/sist/8500f346-705f-408b-a742-32fce8607614/iso-prf-tr-20172>

# PROOF / ÉPREUVE

---

---



## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/PRE TR 20172

<https://standards.iteh.ai/catalog/standards/sist/8500f346-705f-408b-a742-32fce8607614/iso-prf-tr-20172>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

|   | Page     |
|---|----------|
| Foreword .....  | iv       |
| Introduction .....  | v        |
| <b>1 Scope .....</b>  | <b>1</b> |
| <b>2 Normative references .....</b>   | <b>1</b> |
| <b>3 Terms and definitions .....</b>  | <b>1</b> |
| <b>4 International grouping system for European materials .....</b>   | <b>1</b> |
| 4.1 Types of steel in accordance with the grouping system of ISO/TR 15608:2017, Table 1.....                          | 1        |
| 4.2 Types of aluminium and aluminium alloy in accordance with the grouping system of ISO/TR 15608:2017, Table 2 ..... | 21       |
| 4.3 Types of copper and copper alloy in accordance with the grouping system of ISO/TR 15608:2017, Table 3 .....       | 23       |
| 4.4 Types of cast iron in accordance with the grouping system of ISO/TR 15608:2017, Table 7 .....                     | 25       |
| 4.5 Types of cast iron in accordance with the grouping system of ISO/TR 15608:2017, Table 7 .....                     | 26       |
| 4.6 Types of nickel and nickel alloy in accordance with the grouping system of ISO/TR 15608:2017, Table 4 .....       | 28       |
| Bibliography .....  | 31       |

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO/PRF TR 20172](https://standards.iteh.ai/catalog/standards/sist/8500f346-705f-408b-a742-32fce8607614/iso-prf-tr-20172)

<https://standards.iteh.ai/catalog/standards/sist/8500f346-705f-408b-a742-32fce8607614/iso-prf-tr-20172>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 10, *Quality management in the field of welding*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 121, *Welding*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 20172:2009), which has been technically revised.

The main changes compared to the previous edition are as follows:

- [Tables 1](#) to [5](#) have been revised;
- new [Table 6](#) has been added for nickel and nickel alloys.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

This document reflects the situation at the time of publication.

Lists of former designations can be found in the relevant European materials standards.

For the materials not listed in this document, ISO/TR 20173:2018 and ISO/TR 20174:2020 are applicable.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO/PRE TR 20172](https://standards.iteh.ai/catalog/standards/sist/8500f346-705f-408b-a742-32fce8607614/iso-prf-tr-20172)

<https://standards.iteh.ai/catalog/standards/sist/8500f346-705f-408b-a742-32fce8607614/iso-prf-tr-20172>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO/PRE TR 20172

<https://standards.iteh.ai/catalog/standards/sist/8500f346-705f-408b-a742-32fce8607614/iso-prf-tr-20172>

# Welding — Grouping systems for materials — European materials

## 1 Scope

This document establishes a European grouping system for materials for welding purposes, classified in accordance with the grouping system of ISO/TR 15608.

It is also applicable for other purposes such as heat treatment, forming and non-destructive testing.

This document covers grouping systems for the following standardized materials:

- a) steel;
- b) aluminium and its alloys;
- c) copper and its alloys;
- d) cast irons;
- e) nickel and nickel alloys.

In case of dispute, for example where variations in properties such as thickness and yield strength occur, ISO/TR 15608 applies.

## 2 Normative references

[ISO/PREF TR 20172](#)

<https://standards.iteh.ai/catalog/standards/sist/8500f346-705f-408b-a742->

There are no normative references in this document.

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

## 4 International grouping system for European materials

### 4.1 Types of steel in accordance with the grouping system of ISO/TR 15608:2017, Table 1

See [Table 1](#).

Materials grouped according to this document based on chemical composition and mechanical properties but with specific delivering conditions outside ISO/TR 15608:2017 are qualified separately.

Table 1 — Steel materials, classification according to the grouping of material

| Designation     |        | Group            | Standard(s)  |
|-----------------|--------|------------------|--|
| Name            | Number |                  |  |
| 10CrMo5-5       | 1.7338 | 5.1              | EN 10216-2   |
| 10CrMo9-10      | 1.7380 | 5.2              | EN 10028-2, EN 10216-2, EN 10273                                     |
| 11CrMo9-10      | 1.7383 | 5.2              | EN 10028-2, EN 10216-2, EN 10222-2, EN 10273                         |
| 11MnNi5-3       | 1.6212 | 9.1              | EN 10028-4, EN 10216-4   |
| 12Ni14          | 1.5637 | 9.2              | EN 10028-4, EN 10216-4, EN 10222-3                                   |
| 12Ni19          | 1.5680 | 9.2              | EN 10028-4   |
| 13CrMo4-5       | 1.7335 | 5.1              | EN 10028-2, EN 10216-2, EN 10222-2, EN 10273                         |
| 13MnNi6-3       | 1.6217 | 9.1              | EN 10028-4, EN 10216-4, EN 10222-3                                   |
| 14MoV6-3        | 1.7715 | 6.1              | EN 10216-2, EN 10222-2   |
| 15MnCrMoNiV5-3  | 1.6920 | 4.1              | EN 10222-2   |
| 15MnMoV4-5      | 1.5402 | 1.2              | EN 10222-2   |
| 15NiCuMoNb5-6-4 | 1.6368 | 3.1              | EN 10216-2   |
| 15NiMn6         | 1.6228 | 9.1              | EN 10028-4, EN 10222-3   |
| 16Mo3           | 1.5415 | 1.2              | EN 10222-2, EN 10216-2, EN 10217-2, EN 10217-5, EN 10273, EN 10028-2 |
| 18MnMoNi5-5     | 1.6308 | 3.1              | EN 10222-2   |
| 20CrMoV13-5-5   | 1.7779 | 6.3              | EN 10216-2   |
| 20Mn5           | 1.1133 | 1.4              | EN 10250-2   |
| 20MnB5          | 1.5353 | 3.2              | EN ISO 683-2, EN ISO 683-3   |
| 20MnNb6         | 1.0471 | 1.2              | EN 10216-2   |
| 20NiCrMo2-2     | 1.6523 | 3.1              | EN 10297-1   |
| 20NiCrMoS2-2    | 1.6526 | 3.1              | EN 10297-1   |
| 24CrMo13-6      | 1.8516 | 5.2              | EN 10085   |
| 25CrMo4         | 1.7218 | 5.1              | EN ISO 683-2, EN ISO 683-3, EN 10132-2, EN 10216-2, EN 10297-1       |
| 25CrMoS4        | 1.7213 | 5.1              | EN ISO 683-2, EN ISO 683-3, EN 10277                                 |
| 25Mn4           | 1.1177 | 1.3              | EN 10132-2   |
| 26CrMo4-2       | 1.7219 | 5.1              | EN 10216-4   |
| 27MnCrB5-2      | 1.7182 | 11.1             | EN ISO 683-2, EN ISO 683-3   |
| 28Mn6           | 1.1170 | 1.4 <sup>a</sup> | EN 10083-2, EN 10250-2   |
| 30CrMo4         | 1.7216 | 5.1 <sup>a</sup> | EN 10297-1   |
| 30MnB5          | 1.5531 | 11.1             | EN ISO 683-2, EN ISO 683-3   |
| 30NiCrMo16-6    | 1.6747 | 9.2 <sup>a</sup> | EN ISO 683-2, EN ISO 683-3   |
| 31CrMo12        | 1.8515 | 5.2 <sup>a</sup> | EN 10085   |
| 31CrMoV9        | 1.8519 | 6.2 <sup>a</sup> | EN 10085   |
| 32CrAlMo7-10    | 1.8505 | 5.1 <sup>a</sup> | EN 10085   |
| 33CrMoV12-9     | 1.8522 | 6.2 <sup>a</sup> | EN 10085   |

<sup>a</sup> The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.



Table 1 (continued)

| Designation  |        | Group             | Standard(s)   |
|--------------|--------|-------------------|---|
| Name         | Number |                   |   |
| 34Cr4        | 1.7033 | 5.1 <sup>a</sup>  | EN ISO 683-2, EN ISO 683-3                            |
| 34CrAlMo5-10 | 1.8507 | 5.1 <sup>a</sup>  | EN 10085  |
| 34CrAlNi7-10 | 1.8550 | 5.1 <sup>a</sup>  | EN 10085  |
| 34CrMo4      | 1.7220 | 11.2 <sup>a</sup> | EN ISO 683-2, EN ISO 683-3,<br>EN 10297-1             |
| 34CrMoS4     | 1.7226 | 11.2 <sup>a</sup> | EN ISO 683-2, EN ISO 683-3                            |
| 34CrNiMo6    | 1.6582 | 5.2 <sup>a</sup>  | EN 10277  |
| 34CrS4       | 1.7037 | 5.1 <sup>a</sup>  | EN ISO 683-2, EN ISO 683-3                            |
| 35NiCr6      | 1.5815 | 9.1 <sup>a</sup>  | EN ISO 683-2, EN ISO 683-3                            |
| 36NiCrMo16   | 1.6773 | 9.2 <sup>a</sup>  | EN ISO 683-2, EN ISO 683-3                            |
| 37Cr4        | 1.7034 | 5.1 <sup>a</sup>  | EN ISO 683-2, EN ISO 683-3                            |
| 37CrS4       | 1.7038 | 5.1 <sup>a</sup>  | EN ISO 683-2, EN ISO 683-3                            |
| 38Cr2        | 1.7003 | 5.1 <sup>a</sup>  | EN ISO 683-2, EN ISO 683-3                            |
| 38Mn6        | 1.1127 | 11.2 <sup>a</sup> | EN 10297-1  |
| 39MnCrB6-2   | 1.7189 | 5.1 <sup>a</sup>  | EN ISO 683-2, EN ISO 683-3                            |
| 39NiCrMo3    | 1.6510 | 9.2 <sup>a</sup>  | EN ISO 683-2, EN ISO 683-3                            |
| 40CrMoV13-9  | 1.8523 | 6.2 <sup>a</sup>  | EN 10085  |
| 41Cr4        | 1.7035 | 11.2 <sup>a</sup> | EN ISO 683-2, EN ISO 683-3                            |
| 41CrAlMo7-10 | 1.8509 | 5.1 <sup>a</sup>  | EN 10085  |
| 41CrS4       | 1.7039 | 11.2 <sup>a</sup> | EN ISO 683-2, EN ISO 683-3                            |
| 42CrMo4      | 1.7225 | 5.1 <sup>a</sup>  | EN ISO 683-2, EN ISO 683-3, EN<br>10132-2, EN 10297-1 |
| 42CrMoS4     | 1.7227 | 5.1 <sup>a</sup>  | EN ISO 683-2, EN ISO 683-3, EN<br>10277               |
| 46Cr2        | 1.7006 | 11.2 <sup>a</sup> | EN ISO 683-2, EN ISO 683-3                            |
| 50CrMo4      | 1.7228 | 5.1 <sup>a</sup>  | EN ISO 683-2, EN ISO 683-3                            |
| 51CrV4       | 1.8159 | 6.1 <sup>a</sup>  | EN ISO 683-2, EN ISO 683-3                            |
| 8MoB5-4      | 1.5450 | 1.3               | EN 10216-2  |
| C10          | 1.0301 | 1.1               | EN 10277  |
| C10E         | 1.1121 | 1.1               | EN 10132-2, EN 10297-1                                |
| C15          | 1.0401 | 1.1               | EN 10277  |
| C15E         | 1.1141 | 1.1               | EN 10132-2, EN 10297-1                                |
| C15R         | 1.1114 | 1.1               | EN 10297-1  |
| C16          | 1.0407 | 1.1               | EN 10277  |
| C22          | 1.0402 | 1.1               | EN 10250-2  |
| C22E         | 1.1151 | 1.1               | EN 10132-2, EN 10083-2,<br>EN 10297-1                 |
| C22R         | 1.1149 | 1.1               | EN 10083-2  |
| C25          | 1.0406 | 1.1               | EN 10250-2  |
| C25E         | 1.1158 | 1.1               | EN 10250-2  |
| C30          | 1.0528 | 11.1              | EN 10250-2  |
| C30E         | 1.1178 | 11.1              | EN 10132-2  |

<sup>a</sup> The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

| Designation |        | Group             | Standard(s)  |
|-------------|--------|-------------------|--|
| Name        | Number |                   |  |
| C35         | 1.0501 | 11.1              | EN 10083-2, EN 10250-2, EN 10277   |
| C35E        | 1.1181 | 11.1              | EN 10083-2, EN 10250-2,<br>EN 10297-1, EN 10132-2, EN 10277                              |
| C35R        | 1.1180 | 11.1              | EN 10277   |
| C35R        | 1.1180 | 11.2              | EN 10083-2   |
| C40         | 1.0511 | 11.2              | EN 10083-2, EN 10250-2, EN 10277   |
| C40E        | 1.1186 | 11.2              | EN 10083-2, EN 10132-2, EN 10277   |
| C40R        | 1.1189 | 11.2              | EN 10083-2, EN 10277   |
| C45         | 1.0503 | 11.2 <sup>a</sup> | EN 10083-2, EN 10250-2, EN 10277   |
| C45E        | 1.1191 | 11.2 <sup>a</sup> | EN 10083-2, EN 10250-2,<br>EN 10297-1, EN 10132-2  |
| C45R        | 1.1201 | 11.2 <sup>a</sup> | EN 10083-2, EN 10277   |
| C50         | 1.0540 | 11.2              | EN 10250-2, EN 10277   |
| C50E        | 1.1206 | 11.3 <sup>a</sup> | EN 10277, EN 10083-2   |
| C50R        | 1.1241 | 11.3              | EN 10083-2, EN 10277   |
| C55         | 1.0535 | 11.3              | EN 10250-2, EN 10083-2   |
| C55E        | 1.1203 | 11.3              | EN 10083-2, EN 10250-2,<br>EN 10132-2  |
| C55R        | 1.1209 | 11.3              | EN 10083-2   |
| C60         | 1.0601 | 11.3              | EN 10083-2, EN 10277, EN 10250-2   |
| C60E        | 1.1221 | 11.3              | EN 10083-2, EN 10132-2,<br>EN 10250-2, EN 10297-1, EN 10277                              |
| C60R        | 1.1223 | 11.3              | EN 10083-2, EN 10277   |
| E155        | 1.0033 | 1.1               | EN 10296-1, EN 10305-2,<br>EN 10305-3, EN 10305-6  |
| E190        | 1.0031 | 1.1               | EN 10296-1, EN 10305-3   |
| E195        | 1.0034 | 1.1               | EN 10296-1, EN 10305-3,<br>EN 10305-6, EN 10305-2  |
| E215        | 1.0212 | 1.1               | EN 10305-1, EN 10305-4   |
| E220        | 1.0215 | 1.1               | EN 10296-1, EN 10305-3,<br>EN 10305-5  |
| E235        | 1.0308 | 1.1               | EN 10296-1, EN 10297-1, EN 10305-1,<br>EN 10305-2, EN 10305-3,<br>EN 10305-4, EN 10305-6 |
| E260        | 1.0220 | 1.1               | EN 10296-1, EN 10305-3   |
| E260        | 1.0221 | 1.1               | EN 10305-3   |
| E275        | 1.0225 | 1.1               | EN 10296-1, EN 10297-1,<br>EN 10305-2, EN 10305-3,<br>EN 10305-5, EN 10305-6             |
| E275K2      | 1.0456 | 1.1               | EN 10296-1, EN 10297-1   |
| E275M       | 1.8895 | 1.1               | EN 10296-1   |
| E295GC      | 1.0533 | 1.2               | EN 10277   |
| E315        | 1.0236 | 1.2               | EN 10297-1   |

<sup>a</sup> The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

| Designation          |        | Group            | Standard(s)  |
|----------------------|--------|------------------|--|
| Name                 | Number |                  |  |
| E320                 | 1.0237 | 1.2              | EN 10296-1, EN 10305-3, EN 10305-5   |
| E335GC               | 1.0543 | 1.2              | EN 10277   |
| E355                 | 1.0580 | 1.2 <sup>a</sup> | EN 10296-1, EN 10305-2, EN 10305-3, EN 10305-4, EN 10305-6, EN 10305-1, EN 10297-1 |
| E355K2               | 1.0599 | 1.2              | EN 10297-1   |
| E355K2               | 1.0920 | 1.2              | EN 10296-1   |
| E355M                | 1.8896 | 1.2              | EN 10296-1   |
| E370                 | 1.0261 | 1.3              | EN 10296-1, EN 10305-3, EN 10305-5   |
| E420                 | 1.0575 | 1.3              | EN 10305-3, EN 10305-5   |
| E420J2               | 1.0920 | 1.3              | EN 10297-1   |
| E420M                | 1.8897 | 2.1              | EN 10296-1   |
| E460K2               | 1.8891 | 1.3              | EN 10296-1, EN 10297-1   |
| E460M                | 1.8898 | 2.1              | EN 10296-1   |
| E470                 | 1.0536 | 1.3              | EN 10297-1   |
| E590K2               | 1.0644 | 1.3              | EN 10297-1   |
| E730K2               | 1.8893 | 1.3              | EN 10297-1   |
| G12MoCrV5-2          | 1.7720 | 6.1              | EN 10213   |
| G17CrMo5-5           | 1.7357 | 5.1              | EN 10213   |
| G17CrMo9-10          | 1.7379 | 5.2              | EN 10213   |
| G17CrMoV5-10         | 1.7706 | 6.2              | EN 10213   |
| G17Mn5               | 1.1131 | 1.1              | EN 10213   |
| G17NiCrMo13-6        | 1.6781 | 9.2              | EN 10213   |
| G18Mo5               | 1.5422 | 1.2              | EN 10213   |
| G20Mn5               | 1.6220 | 1.2              | EN 10213   |
| G20Mo5               | 1.5419 | 1.2              | EN 10213   |
| G9Ni10               | 1.5636 | 9.1              | EN 10213   |
| G9Ni14               | 1.5638 | 9.2              | EN 10213   |
| GP240GH              | 1.0619 | 1.1              | EN 10213   |
| GP240GR              | 1.0621 | 1.1              | EN 10213   |
| GP280GH              | 1.0625 | 1.2              | EN 10213   |
| GX15CrMo5            | 1.7365 | 5.3              | EN 10213   |
| GX23CrMoV12-1        | 1.4931 | 6.4              | EN 10213   |
| GX2CrNi19-11         | 1.4309 | 8.1              | EN 10213   |
| GX2CrNiMo19-11-2     | 1.4409 | 8.1              | EN 10213   |
| GX2CrNiMoCuN25-6-3-3 | 1.4517 | 10.2             | EN 10213   |
| GX2CrNiMoN22-5-3     | 1.4470 | 10.1             | EN 10213   |
| GX2CrNiMoN26-7-4     | 1.4469 | 10.2             | EN 10213   |
| GX2NiCrMo28-20-2     | 1.4458 | 8.2              | EN 10213   |
| GX3CrNi13-4          | 1.6982 | 7.2              | EN 10213   |

<sup>a</sup> The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

| Designation        |        | Group | Standard(s) |
|--------------------|--------|-------|-------------|
| Name               | Number |       |             |
| GX4CrNi13-4        | 1.4317 | 7.2   | EN 10213    |
| GX4CrNiMo16-5-1    | 1.4405 | 7.2   | EN 10132-2  |
| GX5CrNi19-10       | 1.4308 | 8.1   | EN 10213    |
| GX5CrNiMo19-11-2   | 1.4408 | 8.1   | EN 10213    |
| GX5CrNiMoNb19-11-2 | 1.4581 | 8.1   | EN 10213    |
| GX5CrNiNb19-11     | 1.4552 | 8.1   | EN 10213    |
| GX8CrNi12          | 1.4107 | 7.2   | EN 10213    |
| HC180B             | 1.0395 | 1.1   | EN 10268    |
| HC180P             | 1.0342 | 1.1   | EN 10268    |
| HC180Y             | 1.0922 | 1.1   | EN 10268    |
| HC220B             | 1.0396 | 1.1   | EN 10268    |
| HC220I             | 1.0346 | 1.1   | EN 10268    |
| HC220P             | 1.0397 | 1.1   | EN 10268    |
| HC220Y             | 1.0925 | 1.1   | EN 10268    |
| HC260B             | 1.0400 | 1.1   | EN 10268    |
| HC260I             | 1.0349 | 1.1   | EN 10268    |
| HC260LA            | 1.0480 | 1.1   | EN 10268    |
| HC260P             | 1.0417 | 1.1   | EN 10268    |
| HC260Y             | 1.0928 | 1.1   | EN 10268    |
| HC300B             | 1.0444 | 1.2   | EN 10268    |
| HC300I             | 1.0447 | 1.2   | EN 10268    |
| HC300LA            | 1.0489 | 1.2   | EN 10268    |
| HC300P             | 1.0448 | 1.2   | EN 10268    |
| HC340LA            | 1.0548 | 1.2   | EN 10268    |
| HC380LA            | 1.0550 | 1.3   | EN 10268    |
| HC420LA            | 1.0556 | 1.3   | EN 10268    |
| L210GA             | 1.0319 | 1.1   | EN ISO 3183 |
| L235               | 1.0252 | 1.1   | EN 10224    |
| L235GA             | 1.0458 | 1.1   | EN ISO 3183 |
| L245GA             | 1.0459 | 1.1   | EN ISO 3183 |
| L245MB             | 1.0418 | 1.1   | EN ISO 3183 |
| L245NB             | 1.0457 | 1.1   | EN ISO 3183 |
| L275               | 1.0260 | 1.1   | EN 10224    |
| L290GA             | 1.0483 | 1.2   | EN ISO 3183 |
| L290MB             | 1.0429 | 1.2   | EN ISO 3183 |
| L290NB             | 1.0484 | 1.2   | EN ISO 3183 |
| L355               | 1.0419 | 1.2   | EN 10224    |
| L360GA             | 1.0499 | 1.2   | EN ISO 3183 |
| L360MB             | 1.0578 | 1.2   | EN ISO 3183 |
| L360NB             | 1.0582 | 1.2   | EN ISO 3183 |

<sup>a</sup> The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

| Designation |        | Group | Standard(s)   |
|-------------|--------|-------|---|
| Name        | Number |       |   |
| L360QB      | 1.8948 | 1.2   | EN ISO 3183   |
| L415MB      | 1.8973 | 2.1   | EN ISO 3183   |
| L415NB      | 1.8972 | 1.3   | EN ISO 3183   |
| L415QB      | 1.8947 | 3.1   | EN ISO 3183   |
| L450MB      | 1.8975 | 2.1   | EN ISO 3183   |
| L450QB      | 1.8952 | 3.1   | EN ISO 3183   |
| L485MB      | 1.8977 | 2.2   | EN ISO 3183   |
| L485QB      | 1.8955 | 3.1   | EN ISO 3183   |
| L550QB      | 1.8957 | 3.1   | EN ISO 3183   |
| L555MB      | 1.8978 | 2.2   | EN ISO 3183   |
| P195GH      | 1.0348 | 1.1   | EN 10216-2, EN 10217-2                                      |
| P195TR1     | 1.0107 | 1.1   | EN 10216-1, EN 10217-1                                      |
| P195TR2     | 1.0108 | 1.1   | EN 10216-1, EN 10217-1                                      |
| P215NL      | 1.0451 | 1.1   | EN 10216-4, EN 10217-4,<br>EN 10217-6                       |
| P235GH      | 1.0345 | 1.1   | EN 10216-2, EN 10217-2, EN 10217-5,<br>EN 10273, EN 10028-2 |
| P235S       | 1.0112 | 1.1   | EN 10207  |
| P235TR1     | 1.0254 | 1.1   | EN 10216-1, EN 10217-1                                      |
| P235TR2     | 1.0255 | 1.1   | EN 10216-1, EN 10217-1                                      |
| P245GH      | 1.0352 | 1.1   | EN 10222-2  |
| P245NB      | 1.0111 | 1.1   | EN 10120  |
| P250GH      | 1.0460 | 1.1   | EN 10273  |
| P255QL      | 1.0452 | 1.1   | EN 10216-4  |
| P265GH      | 1.0425 | 1.1   | EN 10216-2, EN 10217-2, EN 10217-5,<br>EN 10273, EN 10028-2 |
| P265NB      | 1.0423 | 1.1   | EN 10120, EN 10149-3  |
| P265NL      | 1.0453 | 1.1   | EN 10216-4, EN 10217-4,<br>EN 10217-6                       |
| P265S       | 1.0130 | 1.1   | EN 10207  |
| P265TR1     | 1.0258 | 1.1   | EN 10216-1, EN 10217-1                                      |
| P265TR2     | 1.0259 | 1.1   | EN 10216-1, EN 10217-1                                      |
| P275N       | 1.0486 | 1.1   | EN 10028-3  |
| P275NH      | 1.0487 | 1.1   | EN 10273, EN 10028-3  |
| P275NL1     | 1.0488 | 1.1   | EN 10216-3, EN 10217-3,<br>EN 10028-3                       |
| P275NL2     | 1.1104 | 1.1   | EN 10216-3, EN 10217-3,<br>EN 10028-3                       |
| P275S       | 1.1100 | 1.1   | EN 10207  |
| P280GH      | 1.0426 | 1.2   | EN 10222-2  |
| P285NH      | 1.0477 | 1.2   | EN 10222-4  |
| P285QH      | 1.0478 | 1.2   | EN 10222-4  |

<sup>a</sup> The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.