
**Petrokemična industrija ter industrija za predelavo nafte in zemeljskega plina -
Notranji premazi in obloge jeklenih rezervoarjev za shranjevanje (ISO/DIS
16961:2022)**

Petroleum, petrochemical and natural gas industries - Internal coating and lining of steel storage tanks (ISO/DIS 16961:2022)

Erdöl-, petrochemische und Erdgasindustrie – Innere Schutzbeschichtungen und Auskleidungen für überirdische Stahltanklager (ISO/DIS 16961:2022)

Industries du pétrole, de la pétrochimie et du gaz naturel - Revêtement intérieur et doublage interne des réservoirs de stockage en acier (ISO/DIS 16961:2022)

[oSIST prEN ISO 16961:2022](https://standards.iteh.ai/catalog/standards/sist/118fa49b-8602-4636-8620-37ad4adb319d/osist-pr-en-iso-16961-2022)

Ta slovenski standard je istoveten z: prEN ISO 16961

ICS:

25.220.99	Druge obdelave in prevleke	Other treatments and coatings
75.200	Oprema za skladiščenje nafte, naftnih proizvodov in zemeljskega plina	Petroleum products and natural gas handling equipment

oSIST prEN ISO 16961:2022**en,fr,de**

**iTeh STANDARD
PREVIEW
(standards.iteh.ai)**

oSIST prEN ISO 16961:2022

<https://standards.iteh.ai/catalog/standards/sist/118fa49b-b60c-4b3b-8b20-37ad4adb319d/osist-pren-iso-16961-2022>

DRAFT INTERNATIONAL STANDARD

ISO/DIS 16961

ISO/TC 67

Secretariat: NEN

Voting begins on:
2022-03-15Voting terminates on:
2022-06-07

Petroleum, petrochemical and natural gas industries — Internal coating and lining of steel storage tanks

Industries du pétrole, de la pétrochimie et du gaz naturel — Revêtement intérieur et doublage interne des réservoirs de stockage en acier

ICS: 75.200

**iTeh STANDARD
PREVIEW
(standards.iteh.ai)**

[oSIST prEN ISO 16961:2022](https://standards.iteh.ai/catalog/standards/sist/118fa49b-b60c-4b3b-8b20-37ad4adb319d/osist-pren-iso-16961-2022)

<https://standards.iteh.ai/catalog/standards/sist/118fa49b-b60c-4b3b-8b20-37ad4adb319d/osist-pren-iso-16961-2022>

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 16961:2022(E)

© ISO 2022

iTeh STANDARD PREVIEW (standards.iteh.ai)

oSIST prEN ISO 16961:2022
<https://standards.iteh.ai/catalog/standards/sist/118fa49b-b60c-4b3b-8b20-37ad4adb319d/osist-pren-iso-16961-2022>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	v
Introduction.....	vi
1 Scope.....	1
2 Normative references.....	1
3 Terms, definitions and abbreviated terms.....	3
3.1 Terms and definitions.....	3
3.2 Abbreviated terms.....	5
4 Conformance.....	6
4.1 Rounding.....	6
4.2 Conformance to this document.....	6
5 Pre-work requirements.....	7
5.1 General.....	7
5.2 Safety precautions in flammable atmosphere.....	7
5.3 Safety precautions in confined space.....	7
5.4 Qualification of coating/lining application and inspection personnel.....	7
5.5 Positive isolation and ventilation.....	8
6 Coating/lining materials.....	8
6.1 General.....	8
6.2 Approvals.....	9
6.3 Prequalification of coating/lining system.....	9
6.4 Holding (blast) primer.....	9
6.5 Caulking (putty) and filler compounds.....	10
6.6 Fibreglass lining materials.....	10
6.6.1 Fibreglass resin compound.....	10
6.6.2 Glass fibre reinforcement.....	10
6.7 Glass flake filled coating/lining system.....	11
6.8 Epoxy coating/lining systems.....	11
6.9 Material approvals — Fibreglass lining system.....	11
6.10 Material approvals — Glass flake filled coating/lining system.....	14
6.11 Material approvals — Thin film epoxy coating/lining systems.....	15
6.12 Pre-production trial.....	15
7 Surface preparation.....	16
7.1 General.....	16
7.2 Tank pre-cleaning and residue removal (for rehabilitation work).....	16
7.3 Preparatory patching and grinding (for new and rehabilitation work).....	16
7.4 Dry abrasive blasting cleaning.....	17
7.5 Humidity control.....	18
7.6 After blast cleaning.....	18
7.7 Removal of existing laminate linings prior to abrasive blasting.....	19
7.8 Striker plates, steel legs, risers, down comers and supports.....	19
7.9 Safety precautions.....	19
8 Coating/lining application.....	20
8.1 General requirements.....	20
8.2 Safety precautions.....	21
8.3 Areas to be lined (fibreglass lining).....	21
8.4 Weather conditions.....	21
8.5 Primer application.....	22
8.6 Caulking (putty) application.....	22
8.7 Fibreglass laminate application.....	22
8.8 Coating/lining thickness.....	23
8.9 Glass flake filled coating application.....	23

ISO/DIS 16961:2022(E)

8.10	Thin film coating application.....	25
9	Inspection and testing.....	26
9.1	General requirements.....	26
9.2	Environmental conditions testing.....	27
9.3	Materials and equipment inspection.....	27
9.4	Compressed air and abrasive.....	27
9.5	Surface preparation inspection.....	28
9.6	Coating/lining inspection and testing.....	28
9.7	Coating/lining film thickness.....	28
9.8	Holiday detection test.....	28
9.9	Curing hardness test.....	29
9.10	Defects and pinhole repair.....	29
9.11	Adhesion test.....	29
10	Quality requirements.....	29
11	Documentation.....	30
11.1	General.....	30
11.2	Work proposal.....	30
11.3	Work records/reports.....	30
11.4	Inspection and testing reports and certificates of conformance.....	30
11.5	Final report.....	31
Annex A (informative)	Dew point calculation chart.....	32
Annex B (informative)	Caulking (putty) application.....	33
Annex C (informative)	Example of coating/lining work record/data sheet.....	34
Annex D (informative)	Example of coating/lining inspection and testing data sheet.....	35
Bibliography		36

oSIST prEN ISO 16961:2022

<https://standards.iteh.ai/catalog/standards/sist/118fa49b-b60c-4b3b-8b20-37ad4adb319d/osist-pren-iso-16961-2022>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical, and natural gas industries*.

This second edition cancels and replaces the first edition (ISO 16961:2015), which has been technically revised.

The main changes compared to the previous edition are as follows:

- inclusion of lining selection criteria ([Clause 6](#));
- update of minimum requirements for non-exposure and exposure tests ([Clause 6](#));
- clarification of the requirements in a pre-production trial ([Clause 6](#));
- update of the typical thicknesses based on industry standards ([Clause 8](#));
- update of references throughout the document.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The objectives of this document are to define minimum technical requirements for the corrosion protection by coating and lining of internal surfaces of steel storage tanks, to provide technical guidance for developing local standards and specifications, and to ensure conformance in coating and lining material selection and performance with contract requirements.

Users of this document need to be aware that further or differing requirements can be needed for individual applications. This document is not limiting the contractor and/or manufacturer from proposing or the company from accepting alternative engineering solutions for the individual application. This can be particularly applicable where there is innovative or developing technology. Where an alternative is proposed, the specification issuer will need to identify any deviations from this document and provide details.

[Annexes A, B, C](#) and [D](#) of this document are informative only.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 16961:2022](#)

<https://standards.iteh.ai/catalog/standards/sist/118fa49b-b60c-4b3b-8b20-37ad4adb319d/osist-pren-iso-16961-2022>

Petroleum, petrochemical and natural gas industries — Internal coating and lining of steel storage tanks

1 Scope

This document specifies the minimum requirements for surface preparation, materials, application, inspection and testing of internal coating lining systems that are intended to be applied on internal surfaces of steel storage tanks of crude oil, hydrocarbons and water for corrosion protection.

It covers both new construction and maintenance works of tank internal coating and lining as well as the repair of defective and deteriorated coating/lining.

This document also provides the minimum requirements for shop performance testing of the coated/lined samples and the criteria for their approval.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2808, *Paints and varnishes — Determination of film thickness*

ISO 2812-1, *Paints and varnishes — Determination of resistance to liquids — Part 1: Immersion in liquids other than water*

ISO 4624, *Paints and varnishes — Pull-off test for adhesion*

<https://standards.iteh.ai/catalog/standards/sist/118fa49b-400v4b1e620-5744a0399e9a4f0c-coating>

ISO 4628-2, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 2: Assessment of degree of blistering*

ISO 4628-3, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 3: Assessment of degree of rusting*

ISO 4628-4, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 4: Assessment of degree of cracking*

ISO 4628-5, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 5: Assessment of degree of flaking*

ISO 7027 (all parts), *Water quality — Determination of turbidity*

ISO 8501-1, *Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 1: Rust grades and preparation grades of uncoated steel substrates and of steel substrates after overall removal of previous coatings*

ISO 8501-3, *Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 3: Preparation grades of welds, edges and other areas with surface imperfections*

ISO 8502-3, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 3: Assessment of dust on steel surfaces prepared for painting (pressure-sensitive tape method)*

ISO/DIS 16961:2022(E)

ISO 8502-6, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 6: Extraction of water soluble contaminants for analysis (Bresle method)*

ISO 8502-9, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 9: Field method for the conductometric determination of water-soluble salts*

ISO 8502-11, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 11: Field method for the turbidimetric determination of water-soluble sulfate*

ISO 8503-2, *Preparation of steel substrates before application of paints and related products — Surface roughness characteristics of blast-cleaned steel substrates — Part 2: Method for the grading of surface profile of abrasive blast-cleaned steel — Comparator procedure*

ISO 8503-5, *Preparation of steel substrates before application of paints and related products — Surface roughness characteristics of blast-cleaned steel substrates — Part 5: Replica tape method for the determination of the surface profile*

ISO 8573-1, *Compressed air — Part 1: Contaminants and purity classes*

ISO 11124 (all parts), *Preparation of steel substrates before application of paints and related products — Specifications for metallic blast-cleaning abrasives*

ISO 11126 (all parts), *Preparation of steel substrates before application of paints and related products — Specifications for non-metallic blast-cleaning abrasives*

ISO 11127 (all parts), *Preparation of steel substrates before application of paints and related products — Test methods for non-metallic blast-cleaning abrasives*

ISO 12944-3, *Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Part 3: Design considerations*

ISO 12944-9:2018, *Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Part 9: Protective paint systems and laboratory performance test methods for offshore and related structures*

ISO 15234:1999, *Paints and varnishes — Testing of formaldehyde-emitting coatings and melamine foams — Determination of the steady-state concentration of formaldehyde in a small test chamber*

ISO 15711, *Paints and varnishes — Determination of resistance to cathodic disbonding of coatings exposed to sea water*

ISO 19840, *Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Measurement of, and acceptance criteria for, the thickness of dry films on rough surfaces*

ISO 29601, *Paints and varnishes — Corrosion protection by protective paint systems — Assessment of porosity in a dry film*

ISO 80000-1:2009, *Quantities and units — Part 1: General*

API RP 652, *Lining of Aboveground Petroleum Storage Tank Bottoms*

API Std 653, *Tank Inspection, Repair, Alteration and Reconstruction*

STD API 2015, *Requirements for Safe Entry and Cleaning of Petroleum Storage Tanks*

ASTM A380, *Standard Practice for Cleaning, Descaling, and Passivation of Stainless Steel Parts, Equipment, and Systems*

ASTM D522, *Standard Test Methods for Mandrel Bend Test of Attached Organic Coatings*

ASTM D570, *Standard Test Method for Water Absorption of Plastics*

ASTM D790, *Standard Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials*

ASTM D2240-05, *Standard Test Method for Rubber Property—Durometer Hardness*

ASTM D2583, *Standard Test Method for Indentation Hardness of Rigid Plastics by Means of a Barcol Impressor*

ASTM D4060, *Standard Test Method for Abrasion Resistance of Organic Coatings by the Taber Abrader*

ASTM D4285, *Standard Test Method for Indicating Oil or Water in Compressed Air*

ASTM D5402, *Standard Practice for Assessing the Solvent Resistance of Organic Coatings Using Solvent Rubs*

ASTM D6943, *Standard Practice for Immersion Testing of Industrial Protective Coatings and Linings*

ASTM F21, *Standard Test Method for Hydrophobic Surface Films by the Atomizer Test*

ASTM G42, *Standard Test Method for Cathodic Disbonding of Pipeline Coatings Subjected to Elevated Temperatures*

EN 14020 (all parts), *Reinforcements — Specification for textile glass roving's*

NACE TM0304, *Offshore Platform Atmospheric and Splash Zone Maintenance Coating System Evaluation*

NACE TM0404, *Offshore Platform Atmospheric and Splash Zone New C*

OSHA 1910.146, *Permit-required confined spaces*

SSPC Guide 12, *Guide for Illumination of Industrial Painting Projects*

PAINTING MANUAL VOL. SSPC, 1

SSPC-SP 1, *Steel Structure Painting Council Surface Preparation Specifications — Solvent Cleaning*

SSPC-SP 11, *Surface Preparation Standard, Power-Tool Cleaning to Bare Metal*

3 Terms, definitions and abbreviated terms

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1 Terms and definitions

3.1.1

application procedure specification

document describing procedures, methods, equipment and tools used for coating application

3.1.2

applicator

contractor or subcontractor having the technical capability, knowledge, equipment and qualified personnel that is approved by the client for the coating processes as required by this document

ISO/DIS 16961:2022(E)

3.1.3

C glass

glass fibre that provides greater resistance to chemicals and is used in advanced composites

Note 1 to entry: C glass is mainly used in the form of surface tissue in the outer layer of laminates used in chemical and water pipes and tanks.

3.1.4

caulking

process of applying a 98 % to 100 % solid catalysed epoxy material (caulking compound) on tank internal surfaces to fill pores/pits or to cover weld seams, lap joints, large projections, connections, etc.

Note 1 to entry: This is to provide a uniform gradual transition and smooth surfaces.

3.1.5

client

party or organization for which professional services are rendered or person that receives a product

3.1.6

coat

paint, varnish or lacquer applied to surface in a single application (one layer) to form an evenly distributed film when dry

3.1.7

coating/lining

material applied to the internal surfaces of a tank to serve as a barrier to corrosion and/or product contamination

3.1.8

contractor

vendor company or business that agrees to furnish materials and/or perform specific project/services to client

3.1.9

curing

chemical process of developing the intended properties of a coating/polymerized product in the lining system,

Note 1 to entry: Chemical process is generally due to a reaction between two or more chemicals (e.g. resin and curing compound).

3.1.10

dew point

temperature of a given air/water vapour mixture at which condensation starts, since its maximum water content saturation is reached at that temperature

3.1.11

dry abrasive blasting

surface preparation method that uses an abrasive propelled by air pressure, centrifugal force, to clean and provide a surface profile

3.1.12

dry film thickness

thickness of a coat or coating system in its fully cured and dry condition

3.1.13

E glass

glass containing not more than 1 % by mass of alkali (calculated as Na₂O) and used for the manufacture of glass fibre

iTeh STANDARD
PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/118fa49b-b60c-4b3b-8b20-37ad4adb319d/osist-pren-iso-16961-2022>

3.1.14**epoxy**

resin containing epoxide functional groups that allow for curing by polymerization with a variety of curing agents

3.1.15**fibreglass reinforced lining**

resin linings, usually polyester, vinyl ester or epoxies, into which layers of fibreglass are incorporated to enhance the lining's structural capability, corrosion and chemical resistance performance

3.1.16**fibre mat**

woven glass fibre that is used as reinforcement of the thermosetting resin (e.g. epoxy) lining to repair and/or add strength to tank bottoms

3.1.17**gel coat**

final coat applied over the fibreglass lining laminate to seal the laminate surface and enhance water and hydrocarbon resistance

3.1.18**holiday**

discontinuity in a lining or contamination in the coating film that significantly lowers the dielectric strength of the coating

Note 1 to entry: Examples of a discontinuity in a lining are a pinhole, void, crack, thin spot, and inclusion of foreign material.

3.1.19**manufacturer**

company responsible for the manufacture of coating material(s)

3.1.20**pinhole**

small film defect characterized by small pore-like flaws in the lining that will permit corrosion of the substrate under the conditions for which the lining is designed

Note 1 to entry: A pinhole can extend entirely through the film to the substrate and lead to a holiday.

3.1.21**pre-production trial**

application of coating and inspection/testing of its properties, to confirm that the application procedure specification is able to produce a coating with the specified properties

3.1.22**surface profile**

micro-roughness of a surface

Note 1 to entry: Surface profile is generally expressed as the average height of the major peaks relative to the major valleys, and sometimes referred to as amplitude.

3.2 Abbreviated terms

ANSI	American National Standardization Institute
API	American Petroleum Institute
APS	application procedure specification
ASTM	American Society for Testing and Materials