



SLOVENSKI STANDARD

SIST ISO 13794:2019

01-december-2019

Nadomešča:
SIST ISO 13794:2002

Zunanji zrak - Določevanje azbestnih vlaken - Metoda transmisijske elektronske mikroskopije s posrednim prenosom

Ambient air - Determination of asbestos fibres - Indirect-transfer transmission electron microscopy method

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Air ambient - Dosage des fibres d'amiante - Méthode par microscopie électronique à transmission par transfert indirect

[SIST ISO 13794:2019](https://standards.iteh.ai/catalog/standards/sist/735984c4-204f-4c6c-b33b-ad73280404ad/sist-iso-13794-2019)
<https://standards.iteh.ai/catalog/standards/sist/735984c4-204f-4c6c-b33b-ad73280404ad/sist-iso-13794-2019>

Ta slovenski standard je istoveten z: ISO 13794:2019

ICS:

13.040.20 Kakovost okoljskega zraka Ambient atmospheres

SIST ISO 13794:2019

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 13794:2019

<https://standards.iteh.ai/catalog/standards/sist/735984c4-204f-4c6c-b33b-ad73280404ad/sist-iso-13794-2019>

INTERNATIONAL STANDARD

ISO
13794

Second edition
2019-10

Ambient air — Determination of asbestos fibres — Indirect-transfer transmission electron microscopy method

*Air ambiant — Dosage des fibres d'amiante — Méthode par
microscopie électronique à transmission par transfert indirect*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 13794:2019](https://standards.iteh.ai/catalog/standards/sist/735984c4-204f-4c6c-b33b-ad73280404ad/sist-iso-13794-2019)

[https://standards.iteh.ai/catalog/standards/sist/735984c4-204f-4c6c-b33b-
ad73280404ad/sist-iso-13794-2019](https://standards.iteh.ai/catalog/standards/sist/735984c4-204f-4c6c-b33b-ad73280404ad/sist-iso-13794-2019)



Reference number
ISO 13794:2019(E)

© ISO 2019

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST ISO 13794:2019

<https://standards.iteh.ai/catalog/standards/sist/735984c4-204f-4c6c-b33b-ad73280404ad/sist-iso-13794-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	vi
Introduction.....	vii
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Symbols and abbreviated terms.....	7
5 Type of sample.....	8
6 Range.....	8
7 Limit of detection.....	8
8 Principle.....	8
9 Reagents.....	9
10 Apparatus.....	10
10.1 Air sampling.....	10
10.1.1 Filter cassette.....	10
10.1.2 Sampling pump.....	10
10.1.3 Stand.....	10
10.1.4 Personal sampling.....	10
10.1.5 Flowmeter.....	10
10.2 Specimen preparation laboratory.....	11
10.3 Equipment for analysis.....	11
10.3.1 Transmission electron microscope.....	11
10.3.2 Energy dispersive X-ray analyser.....	13
10.3.3 Plasma asher.....	13
10.3.4 Vacuum coating unit.....	13
10.3.5 Sputter coater.....	13
10.3.6 Beakers.....	13
10.3.7 Vacuum source.....	13
10.3.8 Glass filtration apparatus.....	14
10.3.9 Solvent washer (Jaffe washer).....	14
10.3.10 Condensation washer.....	15
10.3.11 Slide warmer or oven.....	16
10.3.12 Ultrasonic bath.....	16
10.3.13 Carbon grating replica.....	16
10.3.14 Calibration specimen grids for EDXA.....	16
10.3.15 Carbon rod sharpener.....	17
10.3.16 Disposable tip micropipettes.....	17
10.3.17 Thermometer.....	17
10.3.18 Stopwatch.....	17
10.4 Consumable supplies.....	17
10.4.1 Copper or nickel electron microscope grids.....	17
10.4.2 Gold or nickel electron microscope grids.....	17
10.4.3 Aluminium foil.....	17
10.4.4 Carbon rod electrodes.....	17
10.4.5 Routine electron microscopy tools and supplies.....	18
10.4.6 Reference asbestos samples.....	18
10.4.7 Reference samples of mineral fibres other than asbestos.....	18
11 Air sample collection.....	18
11.1 Calculation of analytical sensitivity.....	18
11.2 Sample collection procedure.....	19

ISO 13794:2019(E)

12	Procedure for analysis	20
12.1	General	20
12.2	Cleaning of sample cassettes	20
12.3	Preparation of analytical filters	20
12.3.1	Selection of filter area for ashing	20
12.3.2	Ashing of sample collection filters	20
12.3.3	Aqueous dispersal of residual ash from sample collection filters	21
12.3.4	Assembly of system for filtration of aqueous dispersions	21
12.3.5	Filtration of aqueous dispersions	21
12.4	Preparation of TEM specimens from PC analytical filters	22
12.4.1	Selection of filter area for carbon-coating	22
12.4.2	Carbon-coating of filter portions	22
12.4.3	Preparation of the Jaffe washer	23
12.4.4	Placing of specimens into the Jaffe washer	23
12.5	Preparation of TEM specimens from cellulose ester analytical filters	23
12.5.1	Selection of area of filter for preparation	23
12.5.2	Preparation of solution for collapsing cellulose ester filters	23
12.5.3	Filter-collapsing procedure	23
12.5.4	Plasma etching of the filter surface	23
12.5.5	Carbon-coating	24
12.5.6	Preparation of the Jaffe washer	24
12.5.7	Placing of specimens in the Jaffe washer	24
12.6	Criteria for acceptable TEM specimen grids	24
12.7	Procedure for structure counting by TEM	25
12.7.1	General	25
12.7.2	Measurement of mean grid opening area	25
12.7.3	TEM alignment and calibration procedures	26
12.7.4	Determination of criterion for termination of TEM examination	26
12.7.5	General procedure for structure counting and size analysis	26
12.7.6	Estimation of mass concentration of asbestos fibres and bundles	27
12.7.7	Magnification requirements	27
12.8	Blank and quality control determinations	29
12.9	Calculation of results	30
13	Performance characteristics	30
13.1	General	30
13.2	Interferences and limitations of fibre identification	30
13.3	Precision and accuracy	31
13.3.1	Precision	31
13.3.2	Accuracy	31
13.3.3	Inter- and intra-laboratory analyses	31
13.4	Limit of detection	32
14	Test report	32
Annex A (normative)	Determination of operating conditions for plasma asher	36
Annex B (normative)	Determination and standardization of operating conditions for ultrasonic bath	37
Annex C (normative)	Calibration procedures	39
Annex D (normative)	Structure counting criteria	42
Annex E (normative)	Fibre identification procedure	52
Annex F (normative)	Determination of the concentration of asbestos fibres and bundles longer than 5 µm and PCM equivalent asbestos fibres	68
Annex G (normative)	Calculation of results	69
Annex H (normative)	Test procedure to determine suitability of cellulose ester sample collection filters	76

Annex I (informative) Strategies for collection of air samples	77
Bibliography	78

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST ISO 13794:2019

<https://standards.iteh.ai/catalog/standards/sist/735984c4-204f-4c6c-b33b-ad73280404ad/sist-iso-13794-2019>

ISO 13794:2019(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.itech.ai)

This document was prepared by Technical Committee ISO/TC 146, *Air quality*, Subcommittee SC 3, *Ambient atmospheres*.
SIST ISO 13794:2019

<https://standards.itech.ai/catalog/standards/sist/735984c4-204f-4c6c-b33b-4737f9f06e1d/iso-13794>

This second edition cancels and replaces the first edition (ISO 13794:1999), which has been technically revised. The main changes compared to the previous edition are as follows:

- the use of electronic display systems with measurement software is permitted;
- the maximum particulate loading for TEM specimens is increased from 10 % to 25 %;
- a simplified fibre identification procedure for investigation of known sources of the regulated asbestos varieties and richterite/winchite asbestos is permitted;
- the reporting requirements have been changed to permit reporting of the concentrations of fibres and bundles longer than 5 µm and/or the concentrations of PCM equivalent fibres without the requirement to report the concentrations of structures equal to or greater than 0,5 µm;
- there is no requirement to report the 95 % confidence intervals of the fibre concentrations.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document is applicable to the measurement of airborne asbestos in a wide range of ambient air situations, including the interior atmospheres of buildings, and for a detailed evaluation of any atmosphere. Because the best available medical evidence indicates that the numerical fibre concentration and the fibre size and type are the relevant parameters for evaluation of the inhalation hazards, a fibre counting and measuring technique is the only logical approach. Most fibres in ambient atmospheres are not asbestos, and therefore there is a requirement for fibres to be identified. Many airborne asbestos fibres in ambient atmospheres have diameters below the resolution limit of the optical microscope. This document is based on transmission electron microscopy, which has adequate resolution to allow for the detection of small fibres and is currently the only technique capable of unequivocal identification of the majority of individual fibres of asbestos. The fibres found suspended in an ambient atmosphere can often be identified unequivocally, if sufficient measurement effort is expended. However, if each fibre were to be identified in this way, the analysis becomes prohibitively expensive. Because of instrumental deficiencies or because of the nature of the particulate, some fibres cannot be positively identified as asbestos, even though the measurements all indicate that they could be asbestos. Subjective and instrumental factors therefore contribute to this measurement, and consequently a very precise definition of the procedure for identification and enumeration of asbestos fibres is required.

In addition to single fibres and bundles, asbestos is often found in air samples as very complex, aggregated structures, which may or may not be also aggregated with other particles. The number of asbestos fibres and bundles incorporated in these complex structures often exceeds the number of isolated fibres and bundles observed, and many of them may be completely obscured in direct-transfer transmission electron microscope (TEM) preparations. The method defined in this document incorporates specimen preparation procedures that result in the selective concentration of asbestos fibres and the removal of organic, water-soluble and acid-soluble materials. These procedures have the effect of dispersing the majority of the complex clusters and aggregates of fibres into their component fibres and bundles so that the asbestos in the air sample can be more accurately quantified. All of the feasible specimen preparation techniques result in some modification of the airborne particulate. Even the collection of particles from a three-dimensional airborne dispersion on to a two-dimensional filter surface can be considered a modification of the particulate, and some of the particles in most samples are modified by the specimen preparation procedures. Although this method results in dispersal of complex clusters and aggregates, it minimizes other effects on the size distribution of fibres and fibre bundles.

This document requires a very detailed and logical procedure is used to reduce the subjective aspects of the measurement. The method of data recording specified in the document is designed to allow re-evaluation of the fibre counting data as new medical evidence becomes available.

This document describes the method of analysis for a single air filter. However, one of the largest potential errors in characterizing asbestos in ambient atmospheres is associated with the variability between filter samples. For this reason, it is necessary to design a replicate sampling scheme in order to determine the standard's accuracy and precision.

Comparison of results obtained using this indirect-transfer procedure with those from the direct-transfer procedure cannot be done a priori. This can only be achieved by a site-specific inter-comparison study that takes into account the fibre size and type of asbestos, and also the nature of the source of the airborne asbestos.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 13794:2019

<https://standards.iteh.ai/catalog/standards/sist/735984c4-204f-4c6c-b33b-ad73280404ad/sist-iso-13794-2019>

Ambient air — Determination of asbestos fibres — Indirect-transfer transmission electron microscopy method

1 Scope

This document specifies a reference method using transmission electron microscopy for the determination of airborne asbestos fibres and structures in a wide range of ambient air situations, including the interior atmospheres of buildings, and for a detailed evaluation for asbestos structures in any atmosphere. The specimen preparation procedure incorporates ashing and dispersion of the collected particulate, so that all asbestos is measured, including the asbestos originally incorporated in particle aggregates or particles of composite materials. The lengths, widths and aspect ratios of the asbestos fibres and bundles are measured, and these, together with the density of the type of asbestos, also allow the total mass concentration of airborne asbestos to be calculated. The method allows determination of the type(s) of asbestos fibres present. The method cannot discriminate between individual fibres of the asbestos and elongate fragments (cleavage fragments and acicular particles) from non-asbestos analogues of the same amphibole mineral^[12].

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4225, *Air quality — General aspects — Vocabulary*

<https://standards.iteh.ai/catalog/standards/sist/735984c4-204f-4c6c-b33b-ad73280404ad/sist-iso-13794-2019>

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4225 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

acicular


shape shown by an extremely slender crystal with cross-sectional dimensions which are small relative to its length, i.e. needle-like

[SOURCE: ISO 10312:1995, 3.1]

3.2

amphibole

group of rock-forming ferromagnesium silicate minerals, closely related in crystal form and composition, and having the nominal formula:



where

ISO 13794:2019(E)

A is K, Na;

B is Fe²⁺, Mn, Mg, Ca, Na;

C is Al, Cr, Ti, Fe³⁺, Mg, Fe²⁺;

T is Si, Al, Cr, Fe³⁺, Ti.

Note 1 to entry: In some varieties of amphibole, these elements can be partially substituted by Li, Pb, or Zn. Amphibole is characterized by a cross-linked double chain of Si-O tetrahedra with a silicon:oxygen ratio of 4:11, by columnar or fibrous prismatic crystals and by good prismatic cleavage in two directions parallel to the crystal faces and intersecting at angles of about 56° and 124°.

[SOURCE: ISO 10312:1995, 3.2]

3.3**amphibole asbestos**

amphibole in an asbestiform habit

[SOURCE: ISO 10312:1995, 3.3]

3.4**analytical filter**

filter through which an aqueous dispersion of ash from the sample collection filter is passed, and from which transmission electron microscope specimen grids are prepared

[SOURCE: ISO 13794:1999, 2.4]

3.5**analytical sensitivity**

calculated airborne asbestos structure concentration in structures/litre, equivalent to counting of one asbestos structure in the analysis

Note 1 to entry: It is expressed in structures/litre.

Note 2 to entry: This method does not specify a unique analytical sensitivity. The analytical sensitivity is determined by the needs of the measurement and the conditions found on the prepared sample.

[SOURCE: ISO 10312:1995, 3.4]

3.6**asbestiform**

specific type of mineral fibrosity in which the fibres and fibrils possess high tensile strength and flexibility

[SOURCE: ISO 10312:1995, 3.5]

3.7**asbestos**

group of silicate minerals belonging to the serpentine and amphibole groups which have crystallized in the asbestiform habit, causing them to be easily separated into long, thin, flexible, strong fibres when crushed or processed

Note 1 to entry: The Chemical Abstracts Service Registry Numbers of the most common asbestos varieties are: chrysotile (12001-29-5), crocidolite (12001-28-4), grunerite asbestos (Amosite) (12172-73-5), anthophyllite asbestos (77536-67-5), tremolite asbestos (77536-68-6) and actinolite asbestos (77536-66-4). Other varieties of asbestiform amphibole, such as richterite asbestos and winchite asbestos^[18], are also found in some products such as vermiculite and talc.

[SOURCE: ISO 10312:1995, 3.6]

3.8**asbestos structure**

individual fibre, or any connected or overlapping grouping of asbestos fibres or bundles, with or without other particles

[SOURCE: ISO 10312:1995, 3.7]

3.9**ashed filter blank**

fibre count made on transmission electron microscope specimens prepared by the indirect procedure from a blank membrane filter of the type used for collection of air samples

[SOURCE: ISO 13794:1999, 2.9]

3.10**aspect ratio**

ratio of length to width of a particle

[SOURCE: ISO 10312:1995, 3.8]

3.11**blank**

structure count made on transmission electron microscope specimens prepared from an unused filter, to determine the background measurement

[SOURCE: ISO 10312:1995, 3.9]


3.12**camera length**

equivalent projection length between the specimen and its electron diffraction pattern, in the absence of lens action

[SOURCE: ISO 10312:1995, 3.10] <https://standards.iteh.ai/catalog/standards/sist/735984c4-204f-4c6c-b33b-ad73280404ad/sist-iso-13794-2019>

3.13**chrysotile**

fibrous mineral of the serpentine group, which has the nominal composition:



Note 1 to entry: Most natural chrysotile deviates little from this nominal composition. In some varieties of chrysotile, minor substitution of silicon by Al^{3+} may occur. Minor substitution of magnesium by Al^{3+} , Fe^{2+} , Fe^{3+} , Ni^{2+} , Mn^{2+} and Co^{2+} may also be present. Chrysotile is the most prevalent type of asbestos.

[SOURCE: ISO 10312:1995, 3.11]

3.14**cleavage**

breaking of a mineral along one of its crystallographic directions

[SOURCE: ISO 10312:1995, 3.12]

3.15**cleavage fragment**

fragment of a crystal that is bounded by cleavage faces

Note 1 to entry: Crushing of non-asbestiform amphibole generally yields elongated fragments that conform to the definition of a fibre, but rarely have aspect ratios exceeding 30:1.

[SOURCE: ISO 10312:1995, 3.13, modified — Note 1 to entry added.]

ISO 13794:2019(E)**3.16****cluster**

structure in which two or more fibres, or fibre bundles, are randomly oriented in a connected grouping

[SOURCE: ISO 10312:1995, 3.14]

3.17**direct-transfer blank**

structure count made on transmission electron microscope specimens prepared by the direct-transfer procedure from a blank filter of the type used for filtration of aqueous dispersions of ash

[SOURCE: ISO 13794:1999, 2.17]

3.18**d-spacing**

distance between identical adjacent and parallel planes of atoms in a crystal

[SOURCE: ISO 10312:1995, 3.15]

3.19**electron diffraction**

technique in electron microscopy by which the crystal structure of a specimen is examined

[SOURCE: ISO 10312:1995, 3.16]

3.20**electron scattering power**

extent to which a thin layer of substance scatters electrons from their original directions

[SOURCE: ISO 10312:1995, 3.17]

3.21**empty beaker blank**

fibre count made on transmission electron microscope specimens prepared by the indirect procedure using an empty beaker as the initial sample

[SOURCE: ISO 13794:1999, 2.21]

3.22**energy dispersive X-ray analysis**

measurement of the energies and intensities of X-rays by use of a solid state detector and multi-channel analyser system

[SOURCE: ISO 10312:1995, 3.18]

3.23**eucentric**

condition when the area of interest of an object is placed on a tilting axis at the intersection of the electron beam with that axis and is in the plane of focus

[SOURCE: ISO 10312:1995, 3.19]

3.24**field blank**

filter cassette that has been taken to the sampling site, opened and then closed and which is used to determine the background structure count for the measurement

[SOURCE: ISO 10312:1995, 3.20]

STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 13794:2019](https://standards.iteh.ai/catalog/standards/sist/735984c4-204f-4c6c-b33b-ad73280404ad/sist-iso-13794-2019)

[https://standards.iteh.ai/catalog/standards/sist/735984c4-204f-4c6c-b33b-](https://standards.iteh.ai/catalog/standards/sist/735984c4-204f-4c6c-b33b-ad73280404ad/sist-iso-13794-2019)

[ad73280404ad/sist-iso-13794-2019](https://standards.iteh.ai/catalog/standards/sist/735984c4-204f-4c6c-b33b-ad73280404ad/sist-iso-13794-2019)

3.25**fibril**

single fibre of asbestos, which cannot be further separated longitudinally into smaller components without losing its fibrous properties or appearances

[SOURCE: ISO 10312:1995, 3.21]

3.26**fibre**

elongated particle which has parallel or stepped sides

Note 1 to entry: For the purposes of this document, a fibre is defined to have an aspect ratio equal to or greater than 5:1 and a minimum length of 0,5 µm.

[SOURCE: ISO 10312:1995, 3.22]

3.27**fibre bundle**

structure composed of parallel, smaller diameter fibres attached along their lengths

Note 1 to entry: A fibre bundle may exhibit diverging fibres at one or both ends.

[SOURCE: ISO 10312:1995, 3.23]

3.28**fibrous structure**

fibre, or connected grouping of fibres, with or without other particles

[SOURCE: ISO 10312:1995, 3.24]

3.29**funnel blank**

structure count made on transmission electron microscope specimens prepared by the direct-transfer method from a filter used for filtration of a sample of distilled water

[SOURCE: ISO 13794:1999, 2.29]

3.30**habit**

characteristic crystal growth form or combination of these forms of a mineral, including characteristic irregularities

[SOURCE: ISO 10312:1995, 3.25]

3.31**limit of detection**

calculated airborne fibre concentration in structures/l, equivalent to the upper 95 % confidence limit of 2,99 structures predicted by the Poisson distribution for a count of zero structures

[SOURCE: ISO 10312:1995, 3.26]

3.32**matrix**

structure in which one or more fibres, or fibre bundles, touch, are attached to, or partially concealed by, a single particle or connected group of non-fibrous particles

[SOURCE: ISO 10312:1995, 3.27]